



(11)

EP 2 332 945 B9

(12)

CORRECTED EUROPEAN PATENT SPECIFICATION

(15) Correction information:

Corrected version no 1 (W1 B1)**Corrections, see****Description Paragraph(s) 8, 13, 17, 29, 80,
87, 115, 121, 146**

(51) Int Cl.:

C07F 7/18 (2006.01)**C08G 77/28 (2006.01)**

(48) Corrigendum issued on:

29.05.2013 Bulletin 2013/22

(45) Date of publication and mention

of the grant of the patent:

19.12.2012 Bulletin 2012/51(21) Application number: **11000224.3**(22) Date of filing: **16.02.2007**(54) **Organofunctional silanes and their mixtures**

Organfunktionelle Silane und deren Mischungen

Polysiloxanes à organofonction et leur melanges

(84) Designated Contracting States:

**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IS IT LI LT LU LV MC NL PL PT RO SE SI
SK TR**(30) Priority: **21.02.2006 US 358550**

(43) Date of publication of application:

15.06.2011 Bulletin 2011/24

(62) Document number(s) of the earlier application(s) in accordance with Art. 76 EPC:

07751084.0 / 1 994 039(73) Proprietor: **Momentive Performance Materials Inc.
Albany, NY 12211 (US)**

(72) Inventors:

- **Chaves, Antonio
Chappaqua
NY 10514 (US)**

- **Pohl, Eric, R.
Mount Kisco
NY 10549 (US)**

- **Vecere, Linda
Fischkill
NY 12524 (US)**
- **Hwang, Lesley
Chappaqua
NY 10514 (US)**

(74) Representative: **Herrmann, Uwe et al
Lorenz - Seidler - Gossel
Widenmayerstrasse 23
80538 München (DE)**

(56) References cited:
US-A1- 2003 199 619 US-B2- 6 635 700

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

DescriptionFIELD OF THE INVENTION

5 [0001] The present invention relates to organofunctional silanes and mixtures of organofunctional silanes possessing mercaptan and blocked mercaptan functionality.

DESCRIPTION OF THE RELATED ART

10 [0002] Glycol derivatives of organosilanes are known in the art. However, these silane derivatives suffer from a tendency to yield bridged structures in favor of cyclic structures exclusively or primarily, leading to high viscosities and gellation, which limits their usefulness in elastomer manufacture.

[0003] Polyether-based monol derivatives of sulfur silanes are also known. Their use suffers from the hazards associated with the use of ethers, which have a tendency to spontaneously form peroxides thus presenting a substantial 15 flammability risk, as well as the possibility of interfering with the usefulness of the silanes as coupling agents in elastomers.

[0004] Blocked mercaptosilanes, such as thiocarboxylate-functional silanes, are described, e.g., in U.S. Patent Nos. 6,127,468, 6,414,061 and 6,528,673. A presentation on the subject of blocked mercaptosilanes was also given at the 2002 International Tire Exposition and Conference (ITEC) in Akron, Ohio. The blocked mercaptosilanes of these patents possess hydrolyzable groups which are derived from simple monofunctional alcohols. When employed as coupling 20 agents for rubber compositions used in the manufacture of tires, the thiocarboxylate-functional silanes of U.S. Patent Nos. 6,127,468, 6,414,061 and 6,528,673 allow tires to be manufactured with fewer steps. However, during the rubber compounding operation, these blocked mercaptosilanes generate volatile organic compound (VOC) emissions.

[0005] This concern regarding VOC emissions, which represents a growing environmental problem in the use of silane coupling agents is addressed, by the cyclic diol-derived blocked organofunctional dimeric and oligomeric silanes described in published U.S. Patent Application 2005/0245753 and U.S. patent application Serial Nos. 11/104,103, filed April 12, 2005, and 11/208,367, filed August 19, 2005. Another approach to the issue of VOC emissions is the use of 25 high boiling monofunctional alcohol-derived silanes as disclosed in U.S. Patent No. 6,849,754.

[0006] In addition to the need to reduce VOC's during the preparation of inorganic filled elastomers, there is also a 30 need to improve the coupling efficiency between the inorganic filler and organic polymer while maintaining processability of the elastomeric compositions. Better coupling improves the performance of cured articles, such as tires, by reducing rolling resistance, heat build-up and wear. U.S. Patent No. 6,635,700 describes the use of a mixture of free and blocked mercaptosilanes to achieve better coupling. However, these mixtures emit VOC's upon use. The level of mercaptosilane in these mixtures is limited because this additive reduces the scorch time of the uncured filled elastomer. In an attempt 35 to lengthen the scorch time of uncured filled elastomers containing mercaptosilanes, published U.S. Patent Application 2004/0014840 discloses the use of thiuram disulfide accelerators in combination with functionalized organosilane.

[0007] US 2003/0199619 A1 is directed to blocked mercaptosilane condensates that are useful as coupling agents in 40 mineral filled elastomer compositions. Among the advantages and the use of these blocked mercaptosilane condensates over the use of previously described blocked mercaptosilanes are the release of less volatile organic compounds during the elastomer compounding process and the lower coupling agent loading requirements. The blocked mercaptosilane condensate according to US 2003/0199619 A1 comprises at least one component whose chemical structure is represented by: $(W1)_1(W2)_m(W3)_y(W4)_0(W5)_b(W6)_b$ wherein W1 is a hydrolysable blocked mercaptosilane fragment, W2 is a hydrolysable mercaptosilane fragment, W3 is a hydrolysable polysulfide silane fragment, W4 is a hydrolysable alkyl silane fragment, W5 is a hydrolysable bis silyl alkane fragment and W6 is a hydrolysable tris silyl alkane fragment.

SUMMARY OF THE INVENTION

[0008] The present invention is directed to an organo functional silane composition according to claim 1. Preferred embodiments are the subject matter of the subclaims.

[0009] Organofunctional silanes and/or their mixtures can be prepared by the transesterification of at least one mercaptosilane, blocked mercaptosilane or mixture of mercaptosilane(s) and blocked mercaptosilane(s) with at least one 50 polyhydroxy-containing compound, part or all of the transesterified reaction product(s) thereafter being optionally treated, e.g., in a deblocking operation to convert blocked mercaptan functionality if present to free mercaptan functionality or in an esterification operation to convert free mercaptan functionality if present to blocked mercaptan functionality.




[0010] As will be appreciated from the foregoing, the composition of this invention can include one or more silane 55 dimers and/or oligomers in which adjacent silane units are bonded to each other through bridged dialkoxy silane structures derived from polyhydroxy-containing compounds, e.g., diols (glycols), triols, tetrols, etc., all of which are low volatile organic compounds (VOCs) relative to simple monohydroxy-containing compounds such as methanol and ethanol which are released by known mercaptosilanes, blocked mercaptosilanes and/or polysulfide silanes.

[0011] It will also be appreciated that all of the compositions within the scope of the invention contain both mercapto- and blocked mercapto- functionalities, either present in the same silane or in mixtures of individual silanes. While it is known that silanes possessing exclusively mercaptan functionality are prone to scorchiness, it has come as a surprise that the compositions of this invention which possess both mercaptan and blocked mercaptan functionalities possess long scorch times, e.g., approaching those of silanes possessing exclusively blocked mercaptan, but with significantly better performance than the latter.

DETAILED DESCRIPTION OF THE INVENTION

[0012] The expression "organofunctional silane" as used herein shall be understood to mean a non-polymeric, dimeric or oligomeric silane possessing mercaptan and/or blocked mercaptan functionality and at least one hydroxyalkoxysilyl and/or cyclic dialkoxy silyl group; and, in the case of the dimeric and oligomeric organofunctional silanes, possessing dialkoxy bridging groups linking adjacent silane units.

[0013] Organofunctional silanes of the present invention and their mixtures can be obtained, *inter alia*, from one or more silanes of the general formulae:



wherein:

each occurrence of Y is independently selected from a polyvalent species (Q), A(=E), wherein the atom (A) attached to an unsaturated heteroatom (E) is attached to a sulfur, which in turn is linked by means of a group G² to a silicon atom; each occurrence of R is independently selected from the group consisting of hydrogen, straight, cyclic or branched alkyl that may or may not contain unsaturation, alkenyl groups, aryl groups, and aralkyl groups, wherein each R, other than hydrogen, contains from 1 to 18 carbone atoms;

each occurrence of G¹ is independently selected from the group consisting of monovalent and polyvalent groups derived by substitution of alkyl, alkenyl, aryl, or aralkyl wherein G¹ can have from 1 to 30 carbon atoms, with the proviso that if G¹ is univalent, G¹ can be hydrogen;

each occurrence of G² is independently selected from the group consisting of divalent or polyvalent group derived by substitution of alkyl, alkenyl, aryl, or aralkyl wherein G² can have from 1 to 30 carbon atoms;

each occurrence of X is independently selected from the group consisting of -Cl, -Br, RO-, RC(=O)O-, R₂C=NO-, R₂NO-, R₂N-, -R, wherein each R is as above;


each occurrence of Q is independently selected from the group consisting of oxygen, sulfur, and (-NR-);

each occurrence of A is independently selected from the group consisting of carbon, sulfur, phosphorus, and sulfonyl;

each occurrence of E is independently selected from the group consisting of oxygen, sulfur, and (-NR-);

each occurrence of the subscripts, a, b, c, j, k, p, q, r, s, and z are independently given by a is 0 to 7; b is 1 to 3; c is 1 to 6; j is 0 to 1, but j may be 0 only if p is 1; k is 1 to 2, with the provisos that if A is carbon, sulfur, or sulfonyl, then (i) a + b = 2 and (ii) k = 1; if A is phosphorus, then a + b = 3 unless both (i) c > 1 and (ii) b = 1, in which case a = c + 1; and if A is phosphorus, then k is 2; p is 0 to 5, q is 0 to 6; r is 1 to 3; s is 1 to 3; z is 0 to 3 and with the proviso that each of the above structures contains at least one hydrolysable X group.

[0014] In one particular embodiment of the invention, the silane reactants are trialkoxysilanes represented by at least one of the general formula:



wherein each R independently has one of the aforestated meanings and, advantageously, is a methyl, ethyl, propyl, isopropyl, n-butyl, or sec-butyl group; G² is an alkylene group of from 1 to 12 carbon atoms; and, G¹ is an alkyl group of from 3 to 12 carbon atoms.

[0015] Mixtures of different silane monomers (1, 2 and/or 3) can be used, e.g., two or more mercaptotrialkoxysilanes of Formula (5), two or more thiocarboxylate trialkoxysilanes of Formula (4) and mixtures of one or more mercaptotri-


alkoxysilanes (5) and one or more thiocarboxylate trialkoxysilanes (4) with R, G¹ and G² in these silanes being defined as in silanes (1) and (3).

[0016] In a silane dimer or oligomer of this invention, each silane unit of the dimer or oligomer is bonded to an adjacent silane unit through a bridging group resulting from the reaction of the selected silane monomer(s) with one or more polyhydroxy-containing compounds of the general formula:



wherein G³ is a hydrocarbon group of from 1 to 15 carbon atoms or a heterocarbon group of from 4 to 15 carbon atoms containing one or more etheric oxygen atoms and d is an integer of from 2 to 8.

[0017] In one embodiment of the invention, polyhydroxy-containing compound (6) is a diol (glycol) of at least one of the general formulae:



wherein R⁰ is independently given by one of the members listed above for R, f is 2 to about 15 and e is 2 to 7. Representative examples of such diols are HOCH₂CH₂OH, HOCH₂CH₂CH₂OH, HOCH₂CH₂CH₂CH₂OH, HOCH₂CH(CH₃)CH₂OH, etc., a diol possessing an etheric oxygen-containing group such as HOCH₂CH₂OCH₂CH₂OH, HOCH₂CH₂OCH₂CH₂OCH₂CH₂OH; HOCH₂CH₂CH₂OCH₂CH₂OH, and a diol possessing a polyether backbone such as a diol of Formula (8) in which R⁰ is hydrogen or methyl and e is 3 to 7.




[0018] In another embodiment of the invention, polyhydroxy-containing compound (6) possesses higher hydroxyl functionality, e.g., a triol or tetrol, of the general formula:



wherein G³ is a substituted hydrocarbon group from 2 to 15 carbon atoms or a substituted heterocarbon from 4 to 15 carbon atoms and contains one or more etheric oxygen atoms; and d is an integer of from 3 to 8. Examples of higher hydroxyl functionality compounds (9) include glycerol, trimethylethane, trimethylolpropane, 1,2,4-butanetriol, 1,2,6-hexanetriol, pentaerythritol, dipentaerythritol, tripentaerythritol, mannitol, galactitol, sorbitol, etc.

[0019] Mixtures of polyhydroxy-containing compounds (6) can also be used herein.

[0020] Organofunctional silanes (i)-(viii) and mixtures thereof can be prepared by the process which comprises reacting at least one silane of one or more of general formulae (1), (2), and/or (3) *supra*:



with at least one polyhydroxy-containing compound of the general formula (6):



wherein each occurrence of G¹, G², G³, R, Y, X, a,b,c,d, j, k, p, r, and s are defined *supra* and with the proviso that at least one of the X is a hydrolyzable group, each of the aforesaid having the meanings previously stated, under transesterification reaction conditions, part or all of the product(s) of the reaction being optionally treated to convert blocked mercaptan functionality, if present, to mercaptan functionality, or to convert' mercaptan functionality, if present, to blocked mercaptan functionality.

[0021] In a first embodiment of the foregoing process, at least one blocked mercaptosilane (1) or (2) is transesterified with at least one polyhydroxy-containing compound (6), optionally, in the presence of catalyst, e.g., transesterification catalyst, to provide one or more organofunctional blocked mercaptosilanes (ii), (iv) and (vii), part or all of the blocked mercaptosilane(s) thereafter being subjected to partial or complete deblocking to provide one or more organofunctional silanes (i), (iii), (iv), (vi) and (viii), any of which may be in admixture with one or more of (ii), (iv), and (vii) depending on the extent of deblocking.

[0022] In one application of this first embodiment of the general preparative process herein, at least one thiocarboxylate trialkoxysilane (4) is transesterified with at least one diol (7) or (8), optionally, in the presence of a transesterification

catalyst such as *para*-toluenesulfonic acid, to provide organofunctional silane (vii), i.e., blocked mercaptosilane oligomer, which can thereafter be subjected to partial deblocking employing a suitable base such as alkali metal alkoxide, e.g., sodium ethoxide in ethanol, to yield one or more organofunctional silanes (viii), i.e., silane oligomer containing one or more mercaptosilanes and one or more blocked mercaptosilanes, alone or in combination with one or more other organofunctional silanes (i) - (vi).

[0023] In a second embodiment of the general preparative procedure herein, at least one mercaptosilane (3) in admixture with at least one blocked mercaptosilane (1) or (2) are transesterified with at least one polyhydroxy-containing compound (6), optionally, in the presence transesterification catalyst, to provide, *inter alia*, one or more organofunctional silanes (v) and/or (viii), and/or other mixtures of organofunctional silanes, e.g., a mixture of silanes (i) and (ii), (i) and (v), (i), (ii) and (v), (i), (ii) and (v), (ii) and (viii), (i), (ii), (v) and (viii), etc.

[0024] In one application of the foregoing second embodiment of the general preparative process, at least one mercaptotrialkoxysilane (5) and at least one thiocarboxylate trialkoxysilane (4) are transesterified together with at least one diol (7), optionally, in the presence of transesterification catalyst, to provide one or more silanes (v) and/or (viii) which, if desired, can be subjected to deblocking to increase the amounts of mercaptosilane relative to blocked mercaptosilane in a particular silane product or mixture of silane products.


[0025] In a third embodiment of the general preparative process, at least one mercaptosilane (3) is transesterified with at least one polyhydroxy-containing compound (6), optionally, in the presence of transesterification catalyst, to provide at least one dimer (iii) and/or oligomer (vi), or mercaptosilane (i) alone or in admixture with dimer (iii) and/or oligomer (iv). Optionally, any of these transesterification products or their mixtures can be subjected to esterification with a carboxylic acid or acid halide to block mercapto groups therein.

[0026] In one application of the foregoing third embodiment of the general preparative process, at least one mercaptotrialkoxysilane (5) is transesterified with at least one diol (7), optionally, in the presence of transesterification catalyst, to provide mercaptosilane dimer (iii) and/or oligomer (vi).

[0027] It is also within the scope of the invention to combine part or all of the esterification product(s) obtained from one of the aforescribed process embodiments with part or all of the product(s) obtained from one of the other process embodiments. Thus, e.g., blocked mercaptosilane dimer (iv) and/or blocked mercaptosilane oligomer (vii) resulting from the first preparative procedure can be admixed with mercaptosilane dimer (iii) and/or mercaptosilane oligomer (vi) to provide a mixture of organofunctional silanes possessing both mercapto and blocked mercapto functionalities. In a similar manner, simple mixing of the esterified product(s) of one particular embodiment of the general preparative process can be admixed with the esterified product(s) of another embodiment of the general preparative process to provide still other compositions within the scope of the invention possessing both mercapto and blocked mercapto functionality.

[0028] Reaction conditions for the process of preparing organofunctional silanes (i)-(viii) and their mixtures include molar ratios of silane(s), determined by adding the individual molar contribution of silanes (1), (2) and (3), and polyhydroxy-containing compound(s) (6) of from about 0.1 to 3 moles of (6) per mole of silyl group, determined by adding the individual contribution of silanes (1), (2) and (3), a temperature of from 0°C to 150°C, a pressure of from about 0.1 to 2,000 mmHg, and in the optional presence of catalyst, solvent, etc.

[0029] According to the present invention, an organofunctional and cyclic and/or bridging dialkoxy silane composition is provided comprising at least one silane selected from the group consisting of:



and



wherein:

each occurrence of Y is independently selected from a polyvalent species (Q)_ZA(=E), wherein the atom (A) attached to an unsaturated heteroatom (E) is attached to a sulfur, which in turn is linked by means of a group G² to a silicon atom;

each occurrence of R is independently selected from the group consisting of hydrogen, straight, cyclic or branched alkyl that may or may not contain unsaturation, alkenyl groups, aryl groups, and aralkyl groups, wherein each R, other than hydrogen, contains from 1 to 18 carbon atoms;


each occurrence of G¹ is independently selected from the group consisting of monovalent and polyvalent groups derived by substitution of alkyl, alkenyl, aryl, or aralkyl wherein G¹ can have from 1 to 30 carbon atoms, with the proviso that if G¹ is univalent, G¹ can be hydrogen;

each occurrence of G² is independently selected from the group consisting of divalent or polyvalent group derived by substitution of alkyl, alkenyl, aryl, or aralkyl wherein G² can have from 1 to 30 carbon atoms;


each occurrence of X is independently selected from the group consisting of -Cl, -Br, RO-, RC(=O)O-, R₂C=NO-,

R₂NO-, R₂N-, -R, HO(R⁰CR⁰)_fO-, wherein each R is as above and each occurrence of R⁰ is independently given by one of the members listed above for R;
 5 each occurrence of Z^b, which forms a bridging structure between two silicon atoms, is independently selected from the group consisting of (-O-)_{0.5}, and [-O(R⁰CR⁰)_fO-]_{0.5}, wherein each occurrence of R⁰ is independently given by one of the members listed above for R;
 each occurrence of Z^c, which forms a cyclic structure with a silicon atom, is independently given by -O(R⁰CR⁰)_fO-
 10 wherein each occurrence of R⁰ is independently given by one of the members listed above for R;
 each occurrence of Q is independently selected from the group consisting of oxygen, sulfur, and (-NR-);
 each occurrence of A is independently selected from the group consisting of carbon, sulfur, phosphorus, and sulfonyl;
 15 each occurrence of E is independently selected from the group consisting of oxygen, sulfur, and (-NR-);
 each occurrence of the subscripts, a, b, c, f, j, k, m, n, p, q, r, s, u, v, w, and z is independently given by a is 0 to 7; b is 1 to 3; c is 1 to 6; f is 2 to 15, j is 0 to 1, but j may be 0 only if p is 1; k is 1 to 2, with the provisos that if A is carbon, sulfur, or sulfonyl, then (i) a + b = 2 and (ii) k = 1;
 if A is phosphorus, then a + b = 3 unless both (i) c > 1 and (ii) b = 1, in which case a = c + 1; and if A is phosphorus, then k is 2; m is 1 to 20, n is 1 to 20, p is 0 to 5, q is 0 to 6; r is 1 to 3; s is 1 to 3; u is 0 to 3; v is 0 to 3; w is 0 to 1 with the proviso that u+v+2w=3; z is 0 to 3; and with the proviso that the each of the above structures contains at least one hydrolysable group, Z^b or Z^c, that is a difunctional alkoxy group.


[0030] In accordance with another embodiment of the present invention, a process for the preparation of an organo-functional silane containing cyclic hydroxyalkyloxysilyl groups, and/or bridging dialkoxy silyl groups and both free and blocked mercaptan functionality groups is provided which comprises blending at least one blocked mercaptofunctional silane of the formula:



and/or of the formula:




30 with at least one mercaptofunctional silane of the formula:



35 wherein each occurrence of G¹, G², R, Y, X, a, b, c, j, k, p, q, r, and s have one of the aforestated meanings and with the proviso that at least one of X is a hydrolyzable group, and transesterifying the mixture with a diol HO(R⁰CR⁰)_fOH, advantageously in the presence of a transesterification catalyst wherein R⁰ and f have one of the aforestated meanings.


[0031] In still another embodiment of the invention, a process for the preparation of an organofunctional silane containing cyclic and/or bridging dialkoxy silyl groups and both free and blocked mercaptan functionality is provided which comprises reacting a cyclic and/or bridging dialkoxy silane with a metal alkoxide.

[0032] As used herein in connection with silanes (10) and (11), the terms "diol" and "difunctional alcohol" refer to any structure of the general Formula (7):



45 wherein f and R⁰ are as defined above. These structures represent hydrocarbons in which two hydrogen atoms are replaced with -OH in accordance with compounds (7), *supra*.

[0033] As used herein in connection with silanes (10) and (11), "dialkoxy" and "difunctional alkoxy" refer to hydrocarbon-based diols in which the two OH hydrogen atoms have been removed to give divalent radicals; and whose structures are represented by the general formula:



wherein f and R⁰ are as defined above.

[0034] As used herein in connection with silanes (10) and (11), "cyclic dialkoxy" refers to a silane or group in which cyclization is about a silicon atom by two oxygen atoms each of which is attached to a common divalent hydrocarbon group such as is commonly the case with diols. Cyclic dialkoxy groups herein are represented by Z^c. The structure of Z^c is important in the formation of the cyclic structure. R⁰ groups that are more sterically hindered than hydrogen promote the formation of cyclic structures. The formation of cyclic structures is also promoted when the value of f in diol (7) is 2

or 3, and more preferably 3..

[0035] As used herein in connection with silanes (10) and (11), "bridging dialkoxy" refers to a silane or group in which two different silicon atoms are each bound to one oxygen atom, which in turn is bound to a common divalent hydrocarbon group such as is commonly found in diols. Bridging dialkoxy groups herein are represented by Z^b .

[0036] As used herein in connection with silanes (10) and (11), "hydroxyalkoxy" refers to a silane or group in which one OH hydrogen atom has been removed to provide a monovalent radical, and whose structures are represented by the general formula:



wherein f and R^0 are defined above. Hydroxyalkoxy groups herein are represented by X .

[0037] As used herein in connection with silanes (10) and (11), the term "hydrocarbon based diols" refers to diols that contain two OH groups as part of a hydrocarbon structure. Absent from these hydrocarbon based diols are heteroatoms (other than, of course, the oxygens in the OH groups), in particular ether groups, which are deliberately avoided due to problems associated with their tendency to spontaneously form peroxides which may lead to flammability hazards and free radical formation.

[0038] The structure (7) will be referred to herein as the appropriate diol (in a few specific cases, glycol is the more commonly used term), prefixed by the particular hydrocarbon group associated with the two OH-groups, Examples include neopentylglycol, 1,3-butanediol, and 2-methyl-2,4-pentanediol.

[0039] The structure (12) will be referred to herein as the appropriate dialkoxy, prefixed by the particular hydrocarbon group associated with the two OH groups. Thus, for example, the diols, neopentylglycol, 1,3-butanediol, and 2-methyl-2,4-pentanediol correspond herein to the dialkoxy groups, neopentylglycoxy, 1,3-butanedialkoxy, and 2-methyl-2,4-pentanedialkoxy, respectively.

[0040] The silanes herein that contain both a free and blocked mercaptofunctional group, in which the diol from which such silanes are derived is commonly referred to as a glycol, are named as the corresponding glycoxysilane. Cyclic dialkoxy silanes herein, in which the diol from which the silane is derived is commonly referred to as a diol, are named as the corresponding dialkoxy silane.

[0041] As used herein for Z^b , the notations, $(-\text{O}-)_{0.5}$ and $[-\text{O}(\text{R}^0\text{CR}^0)_f\text{O-}]_{0.5}$, refer to one-half of a siloxane bond, and one-half of a bridging dialkoxy group, respectively. These notations are used in conjunction with a silicon atom and they are taken herein to mean one-half of an oxygen atom, namely, the half bound to the particular silicon atom, or to one-half of a dialkoxy group, namely, the half bound to the particular silicon atom, respectively. It is understood that the other half of the oxygen atom or dialkoxy group and its bond to silicon occurs somewhere else in the overall molecular structure being described. Thus, the $(-\text{O}-)_{0.5}$ siloxane groups and the $[-\text{O}(\text{R}^0\text{CR}^0)_f\text{O-}]_{0.5}$ dialkoxy groups mediate the chemical bonds that hold two separate silicon atoms together, whether these two silicon atoms occur intermolecularly or intramolecularly. In the case of $[-\text{O}(\text{R}^0\text{CR}^0)_f\text{O-}]_{0.5}$, if the hydrocarbon group $(\text{R}^0\text{CR}^0)_f$ is unsymmetrical, either end of $[-\text{O}(\text{R}^0\text{CR}^0)_f\text{O-}]_{0.5}$ may be bound to either of the two silicon atoms required to complete the structures of silanes (10) and (11).

[0042] As used herein in connection with silanes (1), (2), (3), (10) and (11), "alkyl" includes straight, branched and cyclic alkyl groups; "alkenyl" includes any straight, branched, or cyclic alkenyl group containing one or more carbon-carbon double bond, where the point of substitution can be either at a carbon-carbon double bond or elsewhere in the group; and "alkynyl" includes any straight, branched, or cyclic alkynyl group containing one or more carbon-carbon triple bonds and, optionally, one or more carbon-carbon double bonds as well, where the point of substitution can be either at a carbon-carbon triple bond, a carbon-carbon double bond, or elsewhere in the group. Specific examples of alkyls include, but are not limited to, methyl, ethyl, propyl and isobutyl. Specific examples of alkenyls include, but are not limited to, vinyl, propenyl, allyl, methallyl, ethylidene norbornane, ethylidene norbornyl, ethylidene norbornene and ethylidene norbomanyl. Specific examples of alkynyls include, but are not limited to, acetylenyl, propargyl and methylacetylenyl.

[0043] As used herein in connection with silanes (1), (2), (3), (10) and (11), "aryl" includes any aromatic hydrocarbon from which one hydrogen atom has been removed; "aralkyl" includes, but is not limited to, any of the aforementioned alkyl groups in which one or more hydrogen atoms have been substituted by the same number of like and/or different aryl (as defined herein) substituents; and "arenyl" includes any of the aforementioned aryl groups in which one or more hydrogen atoms have been substituted by the same number of like and/or different alkyl (as defined herein) substituents. Specific examples of aryls include, but are not limited to, phenyl and naphthalenyl. Specific examples of aralkyls include, but are not limited to, benzyl and phenethyl. Specific examples of arenyls include, but are not limited to, tolyl and xylyl.

[0044] As used herein in connection with silanes (1), (2), (3), (10) and (11), "cyclic alkyl", "cyclic alkenyl", and "cyclic alkynyl" also include bicyclic, tricyclic, and higher cyclic structures, as well as the aforementioned cyclic structures further substituted with alkyl, alkenyl, and/or alkynyl groups. Representative examples include, but are not limited to, norbornyl, norbornenyl, ethylnorbornyl, ethylnorbornenyl, ethylcyclohexyl, ethylcyclohexenyl, cyclohexylcyclohexyl and cyclododecatrienyl.

[0045] Representative examples of the functional groups (-YS-) present in the silanes of the present invention include,

but are not limited to, thiocarboxylate ester, $-C(=O)-S-$ (any silane with this functional group is a "thiocarboxylate ester silane"); dithiocarboxylate, $-C(=S)-S-$ (any silane with this functional group is a "dithiocarboxylate ester silane"); thiocarbonate ester, $-O-C(=O)-S-$ (any silane with this functional group is a "thiocarbonate ester silane"); dithiocarbonate ester, $-S-C(=O)-S-$ and $-O-C(=S)-S-$ (any silane with this functional group is a "dithiocarbonate ester silane"); trithiocarbonate ester, $-S-C(=S)-S-$ (any silane with this functional group is a "trithiocarbonate ester silane"); dithiocarbamate ester, $N-C(=S)-S-$ (any silane with this functional group is a "dithiocarbamate ester silane"); thiosulfonate ester, $-S(=O)_2-S-$ (any silane with this functional group is a "thiosulfonate ester silane"); thiosulfate ester, $-O-S(=O)_2-S-$ (any silane with this functional group is a "thiosulfate ester silane"); thiosulfamate ester, $(-N)S(=O)_2-S-$ (any silane with this functional group is a "thiosulfamate ester silane"), thiosulfinate ester, $C-S(=O)-S-$ (any silane with this functional group is a "thiosulfinate ester silane"); thiosulfite ester, $-O-S(=O)-S-$ (any silane with this functional group is a "thiosulfite ester silane"); thiosulfimate ester, $N-S(=O)-S-$ (any silane with this functional group is a "thiosulfimate ester silane"); thiophosphate ester, $P(=O)(O-)_2(S-)$ (any silane with this functional group is a "thiophosphate ester silane"); dithiophosphate ester, $P(=O)(O-)(S-)_2$ or $P(=S)(O-)(S-)$ (any silane with this functional group is a "dithiophosphate ester silane"); trithiophosphate ester, $P(=O)(S-)_3$ or $P(=S)(O-)(S-)_2$ (any silane with this functional group is a "trithiophosphate ester silane"); tetrathiophosphate ester $P(=S)(S-)_3$ (any silane with this functional group is a "tetrathiophosphate ester silane"); thiophosphamate ester, $-P(=O)(-N-)(S-)$ (any silane with this functional group is a "thiophosphamate ester silane"); dithiophosphamate ester, $-P(=S)(-N-)(S-)$ (any silane with this functional group is a "dithiophosphamate ester silane"); thiophosphoramidate ester, $(-N)P(=O)(O-)(S-)$ (any silane with this functional group is a "thiophosphoramidate ester silane"); dithiophosphoramidate ester, $(-N)P(=O)(S-)_2$ or $(-N)P(=S)(O-)(S-)$ (any silane with this functional group is a "dithiophosphoramidate ester silanes"); and trithiophosphoramidate ester, silane".

[0046] In another embodiment, each occurrence of Y is selected independently from the group consisting of $-C(=NR)-$; $-SC(=NR)-$; $-SC(=O)-$; $(-NR)C(=O)-$; $(-NR)C(=S)-$; $-OC(=O)-$; $-OC(=S)-$; $-C(=O)-$; $-SC(=S)-$; $-C(=S)-$; $-S(=O)-$; $-S(=O)_2-$; $OS(=O)_2-$; $(-NR)S(=O)_2-$; $-SS(=O)-$; $-OS(=O)-$; $(-NR)S(=O)-$; $-SS(=O)_2-$; $(-S)_2P(=O)-$; $(-S)P(=O)-$; $-P(=O)(-)_2$; $(-S)_2P(=S)-$; $(-S)P(=S)-$; $-P(=S)(-)_2$; $(-NR)_2P(=O)-$; $(-NR)(-S)P(=O)-$; $(-O)(-NR)P(=O)-$; $(-O)(-S)P(=O)-$; $(-O)_2P(=O)-$; $(-O)P(=O)-$; $(-NR)P(=O)-$; $(-NR)_2P(=S)-$; $(-NR)(-S)P(=S)-$; $(-O)(-NR)P(=S)-$; $(-O)(-S)P(=S)-$; $(-O)_2P(=S)-$; $(-O)P(=S)-$; and, $(-NR)P(=S)-$.

[0047] In still another embodiment, Y is $-C(=O)-$.

[0048] In another embodiment of the present invention, the novel silane is one in which Y is $-C(=O)-$, G¹ has a primary carbon atom attached to the carbonyl and is a C₁-C₁₈ alkyl, and G² is a divalent or polyvalent group derived by substitution of C₁-C₁₂ alkyl.

[0049] In still another embodiment of the present invention, the novel silane is one in which Y is $-C(=O)-$, G¹ is a monovalent straight chain group derived from a C₃-C₁₀ alkyl, and G² is a divalent or polyvalent group derived by substitution of a C₃-C₁₀ alkyl, p is 0, j is 1 and k is 1 and the ratio of m to n is in the range of 20:1 to 3:1. In yet another embodiment of the present invention, the novel silane is one in which Y is $-C(=O)-$, G¹ is a monovalent straight chain group derived from a C₆-C₈ alkyl, G² is a divalent or polyvalent group derived by substitution of a C₃-C₆ alkyl, p is 0, j is 1 and k is 1 and the ratio of m to n is in the range of 10:1 to about 4:1.

[0050] Representative examples of G¹ include, but are not limited to, $CH_3(CH_2)_g-$, wherein g is 1 to 29; benzyl; 2-phenylethyl; diethylene cyclohexane; 1,2,4-triethylene cyclohexane; diethylene benzene; phenylene; $-(CH_2)_g-$ wherein g is preferably 1 to 29, which represent the terminal straight-chain alkyl further substituted terminally at the other end, such as $-CH_2-$, $-CH_2CH_2-$, $-CH_2CH_2CH_2-$, and $-CH_2CH_2CH_2CH_2CH_2CH_2CH_2-$, and their beta-substituted analogs, such as $CH_2(CH_2)_iCH(CH_3)-$, where i is preferably 0 to 16; $-CH_2CH_2C(CH_3)_2CH_2-$; the structure derivable from methylallyl chloride, $-CH_2CH(CH_3)CH_2-$; any of the structures derivable from divinylbenzene, such as $-CH_2CH_2(C_6H_4)CH_2CH_2-$ and $-CH_2CH_2(C_6H_4)CH(CH_3)-$, where the notation C₆H₄ denotes a disubstituted benzene ring; any of the structures derivable from dipropenylbenzene, such as $-CH_2CH(CH_3)(C_6H_4)CH(CH_3)CH_2-$, where the notation C₆H₄ denotes a disubstituted benzene ring; any of the structures derivable from butadiene, such as $-CH_2CH_2CH_2CH_2-$, $-CH_2CH_2CH(CH_3)-$, and $-CH_2CH(CH_2CH_3)-$; any of the structures derivable from piperylene, such as $-CH_2CH_2CH_2CH(CH_3)-$, $-CH_2CH_2CH(CH_2CH_3)-$, and $-CH_2CH(CH_2CH_2CH_3)-$; any of the structures derivable from isoprene, such as $-CH_2CH(CH_3)CH_2CH_2-$, $-CH_2CH(CH_3)CH(CH_3)-$; $-CH_2C(CH_3)(CH_2CH_3)-$, $-CH_2CH_2CH(CH_3)CH_2-$, $-CH_2CH_2C(CH_3)_2-$ and $-CH_2CH[CH(CH_3)]_2-$; any of the isomers of $-CH_2CH_2$ -norbornyl-, $-CH_2CH_2$ -cyclohexyl-; any of the diradicals obtainable from norbornane, cyclohexane cyclopentane, tetrahydronyclopentadiene, or cyclododecene by loss of two hydrogen atoms; the structures derivable from limonene, $-CH_2CH(4-CH_3-1-C_6H_9)CH_3$, where the notation C₆H₉ denotes isomers of the trisubstituted cyclohexane ring lacking substitution in the 2 position; any of the monovinyl-containing structures derivable from trivinylcyclohexane, such as $-CH_2CH_2(vinylC_6H_9)CH_2CH_2-$ and $-CH_2CH_2(vinylC_6H_9)CH(CH_3)-$, where the notation C₆H₉ denotes any isomer of the trisubstituted cyclohexane ring; any of the monounsaturated structures derivable from myrcene containing a trisubstituted C=C, such as $-CH_2CH[CH_2CH_2CH=C(CH_3)_2]CH_2CH_2-$, $-CH_2CH[CH_2CH_2CH=C(CH_3)_2]CH(CH_3)-$, $-CH_2C[CH_2CH_2CH=C(CH_3)_2](CH_2CH_3)-$, $-CH_2CH_2CH[CH_2CH_2CH=C(CH_3)_2]CH_2-$, $-CH_2CH_2(C-)(CH_3)[CH_2CH_2CH=C(CH_3)_2]-$, and $-CH_2CH[CH(CH_3)[CH_2CH_2CH=C(CH_3)_2]]-$; and, any of the monounsaturated structures derivable from myrcene lacking a trisubstituted C=C, such as $-CH_2CH(CH=CCH_2)CH_2CH_2CH_2C(CH_3)_2-$, $-CH_2CH$

$(CH=CH_2)CH_2CH_2CH[CH(CH_3)_2]-$, $-CH_2C(=CH-CH_3)CH_2CH_2CH_2C(CH_3)_2-$, $-CH_2C(=CH-CH_3)CH_2CH_2CH(CH(CH_3)_2)-CH_2CH_2C(=CH_2)CH_2CH_2CH_2C(CH_3)_2-$, $-CH_2CH_2C(=CH_2)CH_2CH_2CH[CH(CH_3)_2]-$, $-CH_2CH=C(CH_3)_2CH_2CH_2CH_2C(CH_3)_2-$, and $-CH_2CH=C(CH_3)_2CH_2CH_2CH[CH(CH_3)_2]$.

[0051] Representative examples of G^2 include, but are not limited to, diethylene cyclohexane; 1,2,4-triethylene cyclohexane; diethylene benzene; phenylene; $-(CH_2)_g$ -wherein g is preferably 1 to 29, which represent terminal straight-chain alkyls further substituted terminally at the other end, such as $-CH_2-$, $-CH_2CH_2-$, $-CH_2CH_2CH_2-$, and $-CH_2CH_2CH_2CH_2CH_2CH_2CH_2-$, and their beta-substituted analogs, such as $-CH_2(CH_2)_iCH(CH_3)-$, where i is preferably 0 to 16; $-CH_2CH_2C(CH_3)_2CH_2-$; the structure derivable from methallyl chloride, $-CH_2CH(CH_3)CH_2-$; any of the structures derivable from divinylbenzene, such as $-CH_2CH_2(C_6H_4)CH_2CH_2-$ and $-CH_2CH_2(C_6H_4)CH(CH_3)-$, where the notation C_6H_4 denotes a disubstituted benzene ring; any of the structures derivable from dipropenylbenzene, such as $-CH_2CH(CH_3)(C_6H_4)CH(CH_3)CH_2-$, where the notation C_6H_4 denotes a disubstituted benzene ring; any of the structures derivable from butadiene, such as $-CH_2CH_2CH_2CH_2CH_2-$, $-CH_2CH_2CH(CH_3)-$, and $-CH_2CH(CH_2CH_3)-$; any of the structures derivable from piperylene, such as $-CH_2CH_2CH_2CH(CH_3)_2-$, $CH_2CH_2CH(CH_2CH_3)-$, and $-CH_2CH(CH_2CH_2CH_3)-$; any of the structures derivable from isoprene, such as $-CH_2CH(CH_3)CH_2CH_2-$, $-CH_2CH(CH_3)CH(CH_3)-$, $-CH_2C(CH_3)(CH_2CH_3)-$, $-CH_2CH_2CH(CH_3)CH_2-$, $-CH_2CH_2C(CH_3)_2-$ and $-CH_2CH_2CH[CH(CH_3)_2]-$; any of the isomers of $-CH_2CH_2$ -norbornyl-, $-CH_2CH_2$ -cyclohexyl-; any of the diradicals obtainable from norbornane, cyclohexane, cyclopentane, tetrahydrodicyclopentadiene, or cyclododecene by loss of two hydrogen atoms; the structures derivable from limonene, $-CH_2CH(4-CH_3-1-C_6H_9)-CH_3$, where the notation C_6H_9 denotes isomers of the trisubstituted cyclohexane ring lacking substitution in the 2 position; any of the monovinyl-containing structures derivable from trivinylcyclohexane, such as $-CH_2CH_2(vinylC_6H_9)CH_2CH_2-$ and $-CH_2CH_2(vinylC_6H_9)CH(CH_3)-$, where the notation C_6H_9 denotes any isomer of the trisubstituted cyclohexane ring; any of the monounsaturated structures derivable from myrcene containing a trisubstituted $C=C$, such as $-CH_2CH[CH_2CH_2CH=C(CH_3)_2]CH_2CH_2-$, $-CH_2CH[CH_2CH_2CH=C(CH_3)_2]CH(CH_3)-$, $-CH_2C[CH_2CH_2CH=C(CH_3)_2](CH_2CH_3)-$, $-CH_2CH_2CH[CH_2CH_2CH=C(CH_3)_2]CH_2-CH_2CH_2(C-)(CH_3)[CH_2CH_2CH=C(CH_3)_2]$, and $-CH_2CH[CH(CH_3)[CH_2CH_2CH=-C(CH_3)_2]]-$ and any of the monounsaturated structures derivable from myrcene lacking a trisubstituted $C=C$, such as $-CH_2CH(CH=CH_2)CH_2CH_2CH_2C(CH_3)_2-$, $-CH_2CH(CH=CH_2)CH_2CH_2CH_2CH[CH(CH_3)_2]-$, $-CH_2C(=CH-CH_3)CH_2CH_2CH_2C(CH_3)_2-$, $-CH_2C(=CH-CH)CH_2CH_2CH[CH(CH_3)_2]-$, $-CH_2CH_2C(=CH_2)CH_2CH_2CH_2C(CH_3)_2-$, $-CH_2CH_2C(=CH_2)CH_2CH_2CH[CH(CH_3)_2]-$, $-CH_2CH=C(CH_3)_2CH_2CH_2CH_2C(CH_3)_2-$ and $-CH_2CH=C(CH_3)_2CH_2CH_2CH[CH(CH_3)_2]$.

[0052] In another embodiment of the present invention, the silane (10) has a structure in which the sum of the carbon atoms in its G^1 and G^2 groups is from 3 to 18 and, advantageously, is from 6 to 14. The amount of carbon in the blocked mercapto fragment facilitates the dispersion of the inorganic filler into the organic polymers, thereby improving the balance of properties in the cured filled rubber.

[0053] In yet another embodiment of the present invention, G^1 is $CH_3CH_2CH_2CH_2CH_2CH_2CH_2-$ and G^2 is $-CH_2CH_2CH_2-$, r is 1 and s is 1.

[0054] Representative examples of R and R^0 groups are hydrogen, branched and straight chain alkyls of 1 to 18 carbon atoms or more, such as methyl, ethyl, propyl, isopropyl, butyl, octenyl, cyclohexyl, phenyl, benzyl, tolyl and allyl.

[0055] In one embodiment, R groups are selected from C_1 to C_4 alkyls and hydrogen and R^0 groups are selected from hydrogen, methyl, ethyl and propyl.

[0056] Specific examples of X are methoxy, ethoxy, isobutoxy, propoxy, isopropoxy, acetoxy, oximato and monovalent hydroxyalkoxy groups derived from diols, $-O(R^0CR^0)_fOH$ where f is defined above, such as 2-hydroxyethoxy; 2-hydroxypropoxy, 3-hydroxy-2,2-dimethylpropoxy, 3-hydroxypropoxy, 3-hydroxy-2-methylpropoxy, 3-hydroxybutoxy, 4-hydroxy-2-methylpent-2-oxy, and 4-hydroxybut-1-oxy. X may also be a monovalent alkyl group, such as methyl and ethyl.

[0057] In a specific embodiment, X is one of methoxy, ethoxy, acetoxy, methyl, ethyl, 2-hydroxyethoxy, 2-hydroxypropoxy, 3-hydroxy-2,2-dimethylpropoxy, 3-hydroxypropoxy, 3-hydroxy-2-methylpropoxy, 3-hydroxybutoxy, 4-hydroxy-2-methylpent-2-oxy, and 4-hydroxybut-1-oxy.

[0058] Specific examples of Z^b and Z^c are the divalent alkoxy groups derived from diols such as ethylene glycol, propylene glycol, neopentyl glycol, 1,3-propanediol, 2-ethyl-1,3-propanediol, 1,3-butanediol, 2-methyl-2,4-pentanediol, 1,4-butanediol, cyclohexane dimethanol and pinacol. The divalent alkoxy groups derived from ethylene glycol, propylene glycol, neopentyl glycol, 1,3-propanediol, 2-methyl-1,3-propanediol, 1,3-butanediol and 2-methyl-2,4-pentanediol are preferred.

[0059] In an embodiment of the present invention, the Z^b and Z^c are divalent alkoxy groups derived from 1,3-propanediol, 2-methyl-1,3-propanediol, 1,3-butanediol, and 2-methyl-2,4-pentanediol.

[0060] The cyclic dialkoxy content of the silanes herein should be kept sufficiently high relative to the total dialkoxy content present to prevent excessive crosslinking, which would lead to gellation. Excessive crosslinking can also be avoided if X in the structure, as indicated by the coefficient u , is large. In one embodiment, the v and w in Formulae (10) and (11) are such that the ratio v/w is between 0 and 10. In another embodiment, u is from 1 to 2 with the proviso that $u + v + 2w = 3$.

[0061] Representative examples of the organofunctional silanes of the present invention that contain cyclic and/or

bridging dialkoxysilyl groups and free and blocked mercapto groups include, but are not limited to, thioacetic acid 2-(2-[3-[2-(3-mercaptopropyl)-5-methyl-[1,3,2]dioxasilinan-2-yloxy]-2-methyl-propoxy]-5-methyl-[1,3,2]dioxasilinan-2-yloxy)-ethyl ester; thioacetic acid 3-(2-[3-[2-(3-mercaptopropyl)-5-methyl-[1,3,2]dioxasilinan-2-yloxy]-2-methyl-propoxy]-5-methyl-[1,3,2]dioxasilinan-2-yloxy)-propyl ester; thiobutyric acid 3-(2-[3-[2-(3-mercaptopropyl)-5-methyl-[1,3,2]dioxasilinan-2-yloxy]-2-methyl-propoxy]-5-methyl-[1,3,2]dioxasilinan-2-yloxy)-propyl ester, octanethioic acid 3-(2-[3-[2-(3-mercaptopropyl)-5-methyl-[1,3,2]dioxasilinan-2-yloxy]-2-methyl-propoxy]-5-methyl-[1,3,2]dioxasilinan-2-yloxy)-propyl ester; octanethioic acid S-[3-(2-[3-[2-(3-mercaptopropyl)-4,4,6-trimethyl-[1,3,2]dioxasilinan-2-yloxy]-1,1-dimethyl-butoxy]-4,4,6-trimethyl-[1,3,2]dioxasilinan-2-yloxy)-propyl] ester; octanethioic acid S-[3-(2-[3-[2-(3-mercaptopropyl)-4-methyl-[1,3,2]dioxasilinan-2-yloxy]-butoxy]-4-methyl-[1,3,2]dioxasilinan-2-yloxy)-propyl] ester; undecanethioic acid S-[3-(2-[3-[2-(3-mercaptopropyl)-4-methyl-[1,3,2]dioxasilinan-2-yloxy]-butoxy]-4-methyl-[1,3,2]dioxasilinan-2-yloxy)-propyl] ester; heptanethioic acid S-[3-(3-hydroxy-2-methyl-propoxy)-{3-[3-hydroxy-2-methyl-propoxy)-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl] ester; heptanethioic acid S-[3-(2-[3-[3-hydroxy-2-methyl-propoxy)-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy]-5-methyl-[1,3,2]dioxasilepan-2-yloxy)-propyl] ester; thiopropionic acid 3-{2-[3-[3-mercaptopropyl)-methyl-[2-methyl-3-[5-methyl-2-(3-propionylsulfanyl-propyl)-[1,3,2]dioxasilinan-2-yloxy]-propoxy]-silanyloxy)-2-methyl-propoxy]-5-methyl-[1,3,2]dioxasilepan-2-yloxy)-propyl ester; octanethioic acid 3-{2-[3-[3-mercaptopropyl)-methyl-[2-methyl-3-[5-methyl-2-(3-octanoylsulfanyl-propyl)-[1,3,2]dioxasilinan-2-yloxy]-propoxy]-silanyloxy)-2-methyl-propoxy]-5-methyl-[1,3,2]dioxasilepan-2-yloxy)-propyl ester; octanethioic acid S-[3-(3-hydroxy-2-methyl-propoxy)-{3-[3-hydroxy-2-methyl-propoxy)-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy}-methyl-(3-octanoylsulfanyl-propyl)-silanyloxy]-2-methyl-propoxy)-methyl-silanyl)-propyl] ester; octanethioic acid S-[3-(3-hydroxy-2-methyl-propoxy)-{3-[3-[3-hydroxy-2-methyl-propoxy)-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl] ester, octanethioic acid S-[3-(3-hydroxy-2-methyl-propoxy)-{3-[3-[bis-(3-hydroxy-2-methyl-propoxy)-(3-mercaptopropyl)-silanyloxy]-2-methyl-propoxy)-(3-mercaptopropyl)-3-hydroxy-2-methyl-propoxy)-silanyloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl] ester; dimethyl-thiocarbamic acid S-[3-(3-hydroxy-2-methyl-propoxy)-{3-[3-hydroxy-2-methyl-propoxy)-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl] ester, dimethyl-dithiocarbamic acid 3-[3-hydroxy-2-methyl-propoxy)-{3-[3-hydroxy-2-methyl-propoxy)-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl ester; dimethyl-dithiocarbamic acid 3-[3-hydroxy-2-methyl-propoxy)-{3-[2-(3-mercaptopropyl)-5-methyl-[1,3,2]dioxasilinan-2-yloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl ester, thiocarbonic acid O-ethyl ester S-[3-(3-hydroxy-2-methyl-propoxy)-{3-[3-hydroxy-2-methyl-propoxy)-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl] ester; trithiocarbonic acid ethyl ester 3-[3-hydroxy-2-methyl-propoxy)-{3-[3-hydroxy-2-methyl-propoxy)-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl ester; trithiocarbonic acid ethyl ester 3-[3-hydroxy-2-methyl-propoxy)-{3-[2-(3-mercaptopropyl)-5-methyl-[1,3,2]dioxasilinan-2-yloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl ester, dithiobutyric acid 3-[3-hydroxy-2-methyl-propoxy)-{3-[3-hydroxy-2-methyl-propoxy)-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl ester, dithiobutyric acid 3-[3-hydroxy-2-methyl-propoxy)-{3-[2-(3-mercaptopropyl)-5-methyl-[1,3,2]dioxasilinan-2-yloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl ester; diethyl-dithiocarbamic acid 3-[3-hydroxy-2-methyl-propoxy)-{3-[2-(3-mercaptopropyl)-5-methyl-[1,3,2]dioxasilinan-2-yloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl ester; N-methyl-thiobutyrimidic acid 3-[3-hydroxy-2-methyl-propoxy)-{3-[2-(3-mercaptopropyl)-5-methyl-[1,3,2]dioxasilinan-2-yloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl ester; N-methyl-thiobutyrimidic acid 3-[3-hydroxy-2-methyl-propoxy)-{3-[3-hydroxy-2-methyl-propoxy)-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl ester; thiophosphoric acid O,O'-diethyl ester S-[3-(3-hydroxy-2-methyl-propoxy)-{3-[3-hydroxy-2-methyl-propoxy)-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl] ester; thiophosphoric acid O-ethyl ester S-[3-(3-hydroxy-2-methyl-propoxy)-{3-[2-(3-mercaptopropyl)-5-methyl-[1,3,2]dioxasilinan-2-yloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl] ester O'-propyl ester; thiophosphoric acid O-ethyl ester S-[3-(3-hydroxy-2-methyl-propoxy)-{3-[2-(3-mercaptopropyl)-5-methyl-[1,3,2]dioxasilinan-2-yloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl] ester O'-propyl ester; trithiophosphoric acid S,S'-diethyl ester S-[3-(3-hydroxy-2-methyl-propoxy)-{3-[3-hydroxy-2-methyl-propoxy)-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl] ester; tetrathiophosphoric acid diethyl ester 3-[3-hydroxy-2-methyl-propoxy)-{3-[3-hydroxy-2-methyl-propoxy)-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl ester, tetrathiophosphoric acid diethyl ester 3-[3-hydroxy-2-methyl-propoxy)-{3-[3-hydroxy-2-methyl-propoxy)-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl ester; tetrathiophosphoric acid ethyl ester 3-[3-hydroxy-2-methyl-propoxy)-{3-[2-(3-mercaptopropyl)-5-methyl-[1,3,2]dioxasilinan-2-yloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl ester propyl ester, methyl-phosphonodithioic acid S-ethyl ester S-[3-(3-hydroxy-2-methyl-propoxy)-{3-[3-hydroxy-2-methyl-propoxy)-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl ester; dimethyl-phosphinothioic acid S-[3-(3-hydroxy-2-methyl-propoxy)-{3-[3-hydroxy-2-methyl-propoxy)-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl] ester, and the like.

[0062] In another embodiment, the cyclic and bridging dialkoxy free and blocked mercaptofunctional silanes of the

present invention include, but are not limited to, octanethioic acid S-[3-((3-hydroxy-2-methyl-propoxy)-{3-[3-[bis-(3-hydroxy-2-methyl-propoxy)-(3-mercaptopropyl)-silanyloxy]-2-methyl-propoxy)-(3-mercaptopropyl)-(3-hydroxy-2-methyl-propoxy)-silanyloxy]-2-methyl-propoxy)-(3-hydroxy-2-methyl-propoxy)-silanyl)-propyl] ester; octanethioic acid S-[3-((3-hydroxy-2-methyl-propoxy)-{3-[3-[(3-hydroxy-2-methyl-propoxy)-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy)-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy)-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy)-methyl-silanyl)-propyl] ester; octanethioic acid S-[3-(2-{3-[2-(3-mercaptopropyl)-5-methyl-[1,3,2]dioxasilinan-2-yloxy]-2-methyl-propoxy)-5-methyl-[1,3,2]dioxasilinan-2-yl)-propyl ester; octanethioic acid S-[3-(2-{3-[2-(3-mercaptopropyl)-4,4,6-trimethyl-[1,3,2]dioxasilinan-2-yloxy]-1,1-dimethyl-butoxyl-4,4,6-trimethyl-[1,3,2]dioxasilinan-2-yl)-propyl]ester; octanethioic acid S-[3-(2-{3-[2-(3-mercaptopropyl)-4-methyl-[1,3,2]dioxasilinan-2-yloxy]-butoxy)-4-methyl-[1,3,2]dioxasilinan-2-yl)-propyl] ester; undecanethioic acid S-[3-(2-{3-[2-(3-mercaptopropyl)-4-methyl-[1,3,2]dioxasilinan-2-yloxy]-butoxy)-4-methyl-[1,3,2]dioxasilinan-2-yl)-propyl] ester; heptanethioic acid S-[3-((3-hydroxy-2-methyl-propoxy)-{3-[(3-hydroxy-2-methyl-propoxy)-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl] ester; heptanethioic acid S-[3-(2-{3-[(3-hydroxy-2-methyl-propoxy)-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy}-5-methyl-[1,3,2]dioxasilepan-2-yl)-propyl] ester; thiopropionic acid 3-{2-[3-((3-mercaptopropyl)-methyl-{2-methyl-3-[5-methyl-2-(3-propionylsulfanyl-propyl)-[1,3,2]dioxasilinan-2-yloxy]-propoxy)-silanyloxy]-2-methyl-propoxy]-5-methyl-[1,3,2]dioxasilepan-2-yl}-propyl ester; and octanethioic acid 3-{2-[3-((3-mercaptopropyl)-methyl-{2-methyl-3-[5-methyl-2-(3-octanoylsulfanyl-propyl)-[1,3,2]dioxasilinan-2-yloxy]-propoxy)-silanyloxy]-2-methyl-propoxy]-5-methyl-[1,3,2]dioxasilepan-2-yl}-propyl ester.

[0063] The organofunctional silane compositions of this invention that contain cyclic and/or bridging silyl groups and both free and blocked mercaptan groups normally have a random distribution of free and blocked mercapto groups within the individual silane. However, silanes in accordance with the invention can be prepared in which the free and blocked mercaptan groups are segregated. This segregation will result in compositions where the nearest neighbors to a free mercaptan group are other free mercaptan groups or the nearest neighbors to a blocked mercaptan group are other blocked mercaptan groups. The segregation of the free and blocked mercaptan groups can occur when blocked mercaptofunctional cyclic and bridged silanes are physically mixed with free mercaptofunctional cyclic and bridged silanes.

[0064] Moreover, it is understood that these novel silane compositions can also contain free and blocked mercaptofunctional silane components that contain only monofunctional alkoxy groups. These free and blocked mercaptofunctional silanes containing only monofunctional alkoxy groups may be used as reagents in the preparation of the novel silanes of the present invention. However, it is understood that these monofunctional alkoxy groups may contribute to VOC emissions during use. Moreover, it is understood that the partial hydrolyzates and/or condensates of these cyclic and bridging dialkoxy blocked mercaptofunctional silanes (i.e., cyclic and bridging dialkoxy blocked mercaptofunctional siloxanes and/or silanols) may also be encompassed by the silanes herein, in that these partial hydrolyzates and/or condensates will be a side product of most methods of manufacture of the novel silanes of the present invention or can occur upon storage, especially in humid conditions, or under conditions in which residual water remaining from their preparation is not completely removed subsequent to their preparation.


[0065] Furthermore, partial to substantial hydrolysis of silanes (10) and (11) will form novel silanes that contain siloxane bonds, i.e., $Z^b = (-O-)_0.5$, and are encompassed by the silanes described herein. They can be deliberately prepared by incorporating the appropriate stoichiometry or an excess of water into the methods of preparation described herein for the silanes. Silane structures herein encompassing hydrolyzates and siloxanes are described in the structures represented by Formulae (10) and (11) wherein the subscripts, v , of $Z^b = (-O-)_0.5$ and/or u of $X = OH$ are substantive (i.e., substantially larger than zero). In one embodiment of the present invention, the ratio of siloxane bridging group, $(-O-)_0.5$, to dioxy bridging group, $[-O(R^0CR^0)O]_0.5$, is within a range of from 0 to 1. In another embodiment, the ratio is within a range of from 0 to 0.2.

[0066] In another embodiment of the present invention, the organofunctional silanes herein, including their mixtures, can be loaded on a particulate carrier such as a porous polymer, carbon black, a siliceous material such as or silica, etc., so that they are in solid form for addition to rubber in a rubber compounding operation.


[0067] Organofunctional silanes (10) and (11) herein and mixtures thereof can be prepared by the general preparative process described above of which there are numerous specific embodiments. Generally, the process embodiments for making one or a mixture of silanes (10) and (11) involve a transesterification reaction between one or more alkoxy silane formulae (1), (2) and (3) and one or more polyhydroxy-containing compounds of formula (6).

[0068] In one embodiment, the process for preparing the organofunctional silanes (10) and/or (11) comprises:

a.) transesterifying at least one blocked mercaptofunctional silane:



or



wherein each occurrence of G¹, G², R, Y, X, a, b, c, j, k, p, q, r, and s are defined *supra*, and with the proviso that at least one of X is a hydrolyzable group, with at least one diol having the structure. HO(R⁰CR⁰)_jOH; optionally in the presence of a transesterification catalyst; and,

5 b) partially removing blocking groups, e.g., by the addition of a strong base, to provide free mercaptan groups.

10 [0069] The first reaction can be carried out by reacting a mixture of blocked mercaptofunctional alkoxy silane and a diol at a molar ratio of 0.1 mole to 3.0 moles of diol per 1 mole of silyl group to be transesterified. In another embodiment, the ratio can range from 1.0 to 2.5 for a trialkoxysilyl group. The reaction can be carried out at a temperature ranging from about 0 to about 150°C and all subranges therebetween while maintaining a pressure in the range of from 0.1 to 2000 mm Hg absolute. In one embodiment, the temperature can range from 30°C to 90°C and all subranges therebetween. In another embodiment, the pressure can range from 1 to 80 mm Hg absolute. As those skilled in the art will recognize, excess diol can be utilized to increase reaction rate, but it is not necessary under these conditions as it may increase 15 the cost. The reaction can be carried out by slowly adding diol to the blocked mercaptofunctional alkoxy silane at the desired reaction temperature and vacuum. As the lower boiling mono alcohol is formed, it can be removed from the reaction mixture by a distillation cycle. Removal of the mono alcohol helps drive the reaction to completion. The reactions 20 optionally can be catalyzed using a transesterification catalyst. Suitable transesterification catalysts are strong protic acids whose pK_a are below 5.0, transition metal complexes such as complexes of tin, iron, titanium and other metal catalysts. Catalysts suitable for these reaction are disclosed in, "The Siloxane Bond, Physical Properties and Chemical 25 Transformations", M. G. Voronkov, V. P. Mileshevich and Yu. A. Yuzhelevskii, Consultants Bureau, a division of Plenum Publishing Company, New York (1978); Chapter 5 and are included by reference herein. Strong bases are generally unsuitable as transesterification catalysts since they promote the reaction of the blocked mercaptofunctional group with the diol and result in removal of the blocking group. The acid or metal catalysts can be used at a range of about 10 ppm to about 2 weight percent.

30 [0070] After the transesterification reaction has reached completion, a strong base may be added to partially remove blocking groups. In one embodiment, suitable bases are those with a pK_b below 5.0 including, but not limited to, metal alkoxides, amides (-NR₂), mercaptides and carbonates wherein the metal ion is lithium; sodium or potassium. The amount of blocking group that is removed is dependent upon the amount of base added. It is understood that the strong 35 base will first neutralize any protic acids that were used in the transesterification reaction of the alkoxy silyl groups. Therefore, additional base in excess of that amount needed to remove the desired amount of blocking group will be required to first complete this neutralization and then remove the blocking group to the desired level. In one embodiment, the amount of additional base added is in a range of from 0.0005 to 0.05 molar equivalents to the blocked mercapto group. In another embodiment, 0.001 to 0.01 molar equivalents of base are added.

35 [0071] After the blocking group has been partially removed, the final mixture can optionally be buffered. Buffering the mixture will inhibit further removal of blocking groups and will thus add to long-term product stability.

40 [0072] The products of the transesterification of blocked mercaptofunctional silane can comprise a considerable fraction of monomeric material in addition to the formation of dimers and other cyclic and bridged oligomers as illustrated by low viscosity reaction products.

45 [0073] The process for making the organofunctional silane compositions of the invention can optionally employ an inert solvent. The solvent may serve as a diluent; carrier, stabilizer, refluxing aid or heating agent. Generally, any inert solvent that does not enter into the reaction or adversely affect the preparative process can be used. In one embodiment, the solvents are liquid under normal conditions and have a boiling point below about 150°C. Examples of suitable solvents include aromatic, hydrocarbon, ether, aprotic, or chlorinated hydrocarbon solvents such as toluene, xylene, hexane, butane, diethyl ether, dimethylformamide, dimethyl sulfoxide, carbon tetrachloride, methylene chloride, and the like.

50 [0074] In one embodiment of the present invention, the process of transesterifying the alkoxy silane with diol can be conducted continuously. In the case of a continuous operation, the process comprises:

- 55 a) reacting, in a thin film reactor, a thin film reaction medium comprising at least one silane of Formula 5, at least one diol and, optionally, transesterification catalyst, to provide blocked mercaptosilane that contains a cyclic and/or bridged dialkoxy group, and by-product mono alcohol;
- b) vaporizing by-product mono alcohol from the thin film to drive the reaction;
- c) optionally, recovering by-product mono alcohol by condensation;
- d) partially removing blocking groups by the addition of base;
- e) optionally; removing by-products of the deblocking step;
- f) recovering the organofunctional silane reaction product(s); and,
- 55 g) optionally, neutralizing the reaction medium to improve the storage stability of the organofunctional silane product(s) therein.

[0075] The molar ratio of diol to blocked mercaptofunctional alkoxy silane used in the continuous thin film process will depend upon the number of alkoxy groups that are desired to be replaced with a diol group. Theoretically, a molar ratio of 0.5 moles of diol is required per alkoxy-silyl group to be transesterified. For a trialkoxy silane; the stoichiometric equivalent molar ratio is 1, wherein one diol replaces two alkoxy groups. However, in many cases, only one of the hydroxyl groups of the diol reacts with the alkoxy-silyl group. These diols are defined as X in Formulae (10) and (11). The diols, referred to herein as "hydroxyalkoxy", reduce the viscosity and inhibit the gelation of the silane. As one skilled in the art will readily recognize, excess diol can be utilized to increase reaction rates.

[0076] The method of forming the film can be any of those known in the art. Typical known devices include but are not limited to, falling film or wiped film evaporators. Minimum film thickness and flow rates will depend on the minimum wetting rate for the film forming surface. Maximum film thickness and flow rates will depend on the flooding point for the film and device. The alcohol is vaporized from the film by heating the film, by reducing pressure over the film, or by a combination of both. In one embodiment, mild heating and reduced pressure are utilized to form the structures of this invention. Optimal temperatures and pressures (partial vacuum) for running this process will depend upon the specific blocked mercaptofunctional silane's alkoxy groups and the diol used in the process. Additionally if an optional inert solvent is used in the process, that choice will affect the optimal temperatures and pressures (partial vacuum) utilized. Examples of such solvents include those listed above.


[0077] The by-product alcohol vaporized from the film is removed from the reactive distillation device by a standard partial vacuum-forming device and can be condensed, collected, and recycled as feed to other processes. The silane product is recovered by standard means from the reactive distillation device as a liquid phase. If an inert solvent has been used or if additional purification is necessary, the silane product may be fed to another similar distillation device or distillation column to effect that separation.

[0078] The addition of the base should occur after the transesterification reaction between the diol and silane is complete. In one embodiment, this reaction can occur in a separate reaction vessel, so that the base does not neutralize the transesterification - catalyst or catalyze the removal of the blocking group. The transesterified intermediate product can be continuous by transferred to a second reaction vessel, e.g., by use of a transfer line and gravity, reduced or elevated pressure, or mechanical pump, to facilitate the process. In the second vessel, the deblocking reaction can occur by the addition of base.


[0079] Optionally the transesterified reaction products can be neutralized to improve product storage.

[0080] In another embodiment of the present invention, a process for preparing the organofunctional silanes containing both free and blocked mercaptan groups comprises:


a) mixing at least one blocked mercaptofunctional silane of chemical structure:



and/or



with a mercaptofunctional silane of chemical formula



wherein each occurrence of G¹, G², R, Y, X, a, b, c, j, k, p, q, r, and s is as defined above and with the proviso that at least one of X is a hydrolyzable group;

b) reacting the silane mixture from step (a) with a diol HO(R⁰CR⁰)_fOH wherein f and R⁰ are as defined above;


optionally in the presence of transesterification catalyst;

c) removing by-product mono alcohol; and,


d) optionally, neutralizing protonic transesterification catalyst, if utilized, with a base.

[0081] The reaction conditions for transesterification of the mixture of free and blocked mercaptofunctional silanes are described above for the blocked mercaptofunctional silane. However, after the transesterification reaction is complete, the reaction mixture can be neutralized if a protic catalyst is used. Neutralization of the catalyst will improve the shelf-stability of the reaction products.


[0082] In one embodiment of the present invention, the amount of blocked mercaptofunctional silane of:



or



5 and the amount of free mercaptofunctional silane of:




10 wherein each occurrence of G¹, G², R, Y, X, a, b, c, j, k, p, q, r, and s is as defined above and with the proviso that at least one of the X is a hydrolyzable group, are mixed in a molar ratio of silanes (1) and/or (2) to silane (3) in a range of from 100:1 to 0.2:1.


15 [0083] In another embodiment, the molar ratios of silane (1) and/or (2) to silane (3) are in a range of from 10:1 to 1:1. If a protic catalyst is used to promote the transesterification of the alkoxy silane with diol, it may be useful to neutralize the catalyst with a base to inhibit the reaction of diol with blocked mercaptan groups. However, only a stoichiometric amount of base is required to neutralize the protic catalyst. Larger amounts of base will promote the removal of blocking group.

20 [0084] In yet another embodiment of the present invention, the process for preparing the organofunctional silane containing both free and blocked mercaptan groups comprises:

20 a) transesterifying at least one blocked mercaptofunctional silane of :




and/or



25 wherein each occurrence of G¹, G², R, Y, X, a, b, c, j, k, p, q, r, and s is as defined above, and with the proviso that at least one of X is a hydrolyzable group, with at least one diol HO(R⁰CR⁰)_fOH wherein f and R⁰ are as defined above, optionally, in the presence of transesterification catalyst;

30 b) optionally, removing by-product mono alcohol from the reaction mixture resulting from step (a);
c) transesterifying at least one mercaptofunctional silane of :



35 wherein each occurrence of G², X, r, and s is as defined above, and with the proviso that at least one of X is a hydrolyzable group, with at least one diol of structure HO(R⁰CR⁰)_fOH wherein f and R⁰ are as defined above, optionally, in the presence of transesterification catalyst;

40 d) optionally, removing by-product mono alcohol from the reaction mixture resulting from step (c);
e) mixing product silane(s) from step (a) with product silane(s) from step (c) to provide a mixture possessing a predetermined amount of mercaptan and blocked mercaptan groups;
f) optionally, neutralizing the product mixture from step (e) with a base if a protic catalyst was utilized.

45 [0085] In one embodiment of the present invention, the molar ratios of the silane prepared in step a and the silane prepared in step d to form silane f are in the range of 100:1 to 0.2:1. In another embodiment, the molar ratios of silane from step a and silane from step d to form silane f are in a range from 10:1 to 1:1. It is understood that the desired ratio of blocked to free mercapto groups is determined by the mix ratio. The structure of the silane prepared may be bimodal in distribution of the free and blocked mercapto groups. The oligomers and polymers formed may have segments where the nearest neighbors of the free mercapto group are other free mercapto groups and likewise the nearest neighbors of the blocked mercapto group are other blocked mercapto groups. The distribution of free and blocked mercapto groups is therefore not random. The reaction conditions and processes for transesterifying the free and blocked mercaptofunctional silanes are given above.


50 [0086] Further in accordance with the invention, a filled elastomer composition is provided which comprises:

55 a) at least one elastomer containing carbon-carbon double bonds;
b) at least one inorganic particulate filler; and,
c) an organofunctional silane composition comprising at least one organofunctional silane selected from the group consisting of:

- (i) mercaptosilane possessing at least one hydroxyalkoxysilyl group and/or a cyclic dialkoxy silyl group,
 (ii) blocked mercaptosilane possessing at least one hydroxyalkoxysilyl group and/or a cyclic dialkoxy silyl group,
 (iii) mercaptosilane dimer in which the silicon atoms of the mercaptosilane units are bonded to each other through a bridging dialkoxy group, each silane unit optionally possessing at least one hydroxyalkoxysilyl group or a cyclic dialkoxy silyl group,
 (iv) blocked mercaptosilane dimer in which the silicon atoms of the blocked mercaptosilane units are bonded to each other through a bridging dialkoxy group, each silane unit optionally possessing at least one hydroxyalkoxysilyl group or a cyclic dialkoxy silyl group,
 (v) silane dimer possessing a mercaptosilane unit the silicon atom of which is bonded to the silicon atom of a blocked mercaptosilane unit through a bridging dialkoxy group, each silane unit optionally possessing at least one hydroxyalkoxysilyl group or a cyclic dialkoxy silyl group,
 (vi) mercaptosilane oligomer in which the silicon atoms of adjacent mercaptosilane units are bonded to each other through a bridging dialkoxy group, the terminal mercaptosilane units possessing at least one hydroxyalkoxysilyl group or a cyclic dialkoxy silyl group,
 (vii) blocked mercaptosilane oligomer in which the silicon atoms of adjacent blocked mercaptosilane units are bonded to each other through a bridging dialkoxy group, the terminal mercaptosilane units possessing at least one hydroxyalkoxysilyl group or a cyclic dialkoxy silyl group, and (viii) silane oligomer possessing at least one mercaptosilane unit and at least one blocked mercaptosilane unit, the silicon atoms of adjacent silane units being bonded to each other through a bridging dialkoxy group, the terminal silane units possessing at least one hydroxyalkoxysilyl group or a cyclic dialkoxy silyl group, with the proviso that,

where the composition contains one or more of (i), (iii) and (vi), the composition additionally contains one or more of (ii), (iv), (v), (vii) and (viii), and where the composition contains one or more of (ii), (iv) and (vii), the composition additionally contains one or more of (i), (iii), (v), (vi) and (viii).

[0087] In one embodiment of the foregoing filled elastomer composition, the organofunctional silane composition comprises at least one of :



and/or



wherein:

- each occurrence of Y is independently a polyvalent species $(Q)_zA(=E)$, each wherein an atom (A) attached to an unsaturated heteroatom (E) is attached to a sulfur, which in turn is linked by means of a group G^2 to a silicon atom; each occurrence of R is independently selected from the group consisting of hydrogen, straight, cyclic or branched alkyl that may or may not contain unsaturation, alkenyl groups, aryl groups, and aralkyl groups, wherein each R, other than hydrogen, preferably contains from 1 to 18 carbon atoms;
 each occurrence of G^1 is independently selected from the group consisting of monovalent and polyvalent groups derived by substitution of alkyl, alkenyl, aryl, or alkyl wherein G^1 contains from 1 to 30 carbon atoms, with the proviso that if G^1 is univalent, G^1 can be hydrogen;
 each occurrence of G^2 is independently selected from the group consisting of monovalent and polyvalent groups derived by substitution of alkyl, alkenyl, aryl, or aralkyl wherein G^1 contains from 1 to 30 carbon atoms;
 each occurrence of X is independently selected from the group consisting of -Cl, -Br, RO-, RC(=O)O-, $R_2C=NO-$, R_2NO- , R_2N- , =R, HO(R^0CR^0)₂O, wherein each R is as above and each occurrence of R^0 is independently given by one of the members listed above for R;
 each occurrence of Z^b , which forms a bridging structure between two silicon atoms, is independently selected from the group consisting of $(-O-)_0.5$, and $[-O(R^0CR^0)_2O]_{0.5}$, wherein each occurrence of R^0 is independently given by one of the members listed above for R;
 each occurrence of Z^c , which forms a cyclic structure with a silicon atom, is independently given by $-O(R^0CR^0)_2O-$ wherein each occurrence of R^0 is independently given by one of the members listed above for R;
 each occurrence of Q is independently selected from the group consisting of oxygen, sulfur, and (-NR-);
 each occurrence of A is independently selected from the group consisting of carbon, sulfur, phosphorus, and sulfonyl;
 each occurrence of E is independently selected from the group consisting of oxygen, sulfur, and (-NR-);
 each occurrence of the subscripts, a, b, c, f, j, k, m, n, p, q, r, s, u, v, w, and z is independently given by a is 0 to 7;

b is 1 to 3; *c* is 1 to 6; *f* is 1 to 15, *j* is 0 to 1, but *j* may be 0 only if *p* is 1; *k* is 1 to 2, with the provisos that if *A* is carbon, sulfur, or sulfonyl, then (i) *a* + *b* = 2 and (ii) *k* = 1;
 if *A* is phosphorus, then *a* + *b* = 3 unless both (i) *c* > 1 and (ii) *b* = 1, in which case *a* = *c* + 1; and
 if *A* is phosphorus, then *k* is 2;
 5 *m* is 1 to about 20, *n* is 1 to 20, *p* is 0 to 5, *q* is 0 to 6; *r* is 1 to 3; *s* is 1 to 3; *u* is 0 to 3; *v* is 0 to 3; *w* is 0 to 1 with the proviso that *u* + *v* + 2*w* = 3; *z* is 0 to 3; and with the proviso that the each of the above structures contains at least one hydrolysable group, *Z*^b or *Z*^c, that is a difunctional alkoxy group.

10 [0088] Also within the scope of the invention are articles of manufacture, particularly tires, made from the foregoing filled elastomer compositions. The invention offers a means for significantly reducing volatile organic compound (VOC) emissions during rubber manufacture and improving the coupling between the organic polymers and inorganic fillers.

15 [0089] The novel organofunctional silane-based compositions described herein are useful as coupling agents between elastomeric resins (i.e., rubbers) and inorganic fillers. The organofunctional silane compositions are unique in that the high efficiency of the mercaptan group can be utilized without the detrimental side effects typically associated with the use of mercaptosilanes, such as high processing viscosity, less than desirable filler dispersion, premature curing (scorch), and odor. These benefits are obtained because the mercaptan group is part of a high boiling compound that liberates diol or higher polyhydroxy-containing compound upon use. The combination of free and blocked mercapto groups in this silane-based composition allow for a controlled amount of coupling to the organic polymer during the compounding of the rubber. During this non-productive mixing step, the cyclic and/or bridged alkoxy-silyl groups may react with the 20 filler and essentially only the free mercaptan groups may react with the rubber. The blocked mercaptan groups remain essentially inactive and are available to help disperse the inorganic filler during the rubber compounding operation. Thus, a controlled amount of coupling of the filler to the polymer occurs during mixing thereby minimizing the undesirable premature curing (scorch) and the associated undesirable increase in viscosity, while promoting the end-use properties such as reinforcing index, which is an indicator of wear. Thus, one can achieve better cured filled rubber properties such as a balance of high modulus and abrasion resistance, resulting from the avoidance or lessening of premature curing.

25 [0090] The organofunctional silane-based compositions herein provide significant advantages over traditional coupling agents that have found extensive use in the rubber and tire industries. These silanes usually contain in their molecular structures three alkoxy groups, e.g., ethoxy groups, on each silicon atom, which results in the release of up to three moles of simple monohydroxy alcohol, e.g., ethanol for each silane equivalent during the rubber manufacturing process 30 in which the silane couples to the filler. The release of simple mono alcohols is a great disadvantage because they are flammable and therefore pose a threat of fire, and because they contribute so greatly to volatile organic compound (VOC) emissions and are therefore potentially harmful to the environment.

35 [0091] The organofunctional silane-based compositions described herein eliminate or greatly mitigate the foregoing problems by reducing volatile mono alcohol emissions to only one, less than one, and even essentially zero, moles of mono alcohol per silane equivalent. They accomplish this because the silane alkoxy groups are replaced with polyhydroxy alcohols, e.g., diol derived bridging groups, and thus such polyhydroxy alcohols are released during the rubber manufacture process in place of much, or nearly all, of the mono alcohol released. Describing the advantages of the 40 organofunctional silanes herein width specific reference to those silanes that are prepared with diols (such advantages being realizable with polyhydroxy-containing compounds of higher hydroxyl functionality), diols, e.g., having boiling points well in excess of rubber processing temperatures, are not vaporized out of the rubber during the rubber manufacture process, as is the case, e.g., with ethanol, but are retained by the rubber where they migrate to the silica surface due to their high polarity and become hydrogen bonded to the surfaces of siliceous fillers such as silicas. The presence of diols on silica surfaces leads to further advantages not obtainable with ethanol (due to its volatility and ejection during the rubber compounding process) in the subsequent cure process, in which such presence prevents the silica surface 45 from binding the curatives and thereby interfering with the cure. Traditional silanes not based on diols require more curatives to counter losses due to silica binding.'

50 [0092] The addition of hydrocarbon-based diols to the rubber compounding formulation prior to and/or concurrent with the addition of curatives is of advantage for the efficient utilization of the curatives, in particular, and polar substances, such as, but not limited to, amines, amides, sulfenamides, thiurams, and guanidines. Whether diols are exclusively added in the form of diol-derived silanes or as free diols in combination with the silanes coupling agents, the polarity of the diols is of advantage to the rubber compounding process. These polar substances tend to migrate to the filler surface due to dipole interaction with the filler. This tends to make them unavailable within the organic : polymer matrix, where their functions include plasticization of the filled elastomer and acceleration, or retardation, of the curing reactions. The hydrocarbon-based diols enhance the function of the curatives by interfering with their tendency to bind to the silica surface 55 thereby forcing them into the rubber matrix to perform their function. The hydrocarbon-based diols accomplish this by themselves being very polar, and thereby by themselves binding to the filler surface, leaving less room for the curatives to bind to filler. The hydrocarbon-based diols thus act as curative displacing agents from the filler.

55 [0093] The short chain of the hydrocarbon-based diols further enhances their function by a chelate effect. In one

embodiment, the number of carbon atoms between the hydroxide groups of Z^c and/or Z^b herein are important and are defined by the divalent radical $-O(R^0CR^0)O-$; wherein each occurrence of f is 2 or 3. These chains of two or three carbon atoms between the two OH groups of the diol promote the formation of 5- or 6-membered rings when both oxygen atoms bind to a common silicon atom of the silanes of Formulae (10) and (11). This dual binding to a common center, known, and referred to herein as the-chelate effect, increases the amount of cyclic dialkoxysilyl group and inhibits the formation of gel. After reactions with the silica in the rubber compounding step, the diols that have been released have a high affinity to the filler because they can chelate with the metal or silicon atom on the filler surface thereby enhancing their ability to prevent the binding of the curatives to the filler.

[0094] The hydrocarbon-based diols used herein are superior to ether- and/or polyether-based monofunctional alcohols or difunctional alcohols (diols) because the lack of the ether functionality of the hydrocarbon based diols avoids the problems typically encountered with ethers. These problems include high toxicity, their tendency for spontaneous peroxide formation, and high chain lengths between OH groups. Spontaneous peroxide formation is a problem because it is difficult to prevent and ; because the peroxides represent flammability hazards. Furthermore, peroxides will decompose when heated to provide free radicals which can initiate unwanted side reactions in the rubber polymers. These side reactions include peroxide-induced cure in which polymer chains are crosslinked. This can lead to premature, excess, and variable crosslinking during or prior to cure. The excess crosslinking can lead to inferior properties in the rubber, premature crosslinking can lead to scorch, and the variability makes it hard to fabricate a reproducible rubber composition and any articles of manufacture derived thereof.

[0095] The excess chain lengths of the ether-containing diols forces chelation by the two OH groups to involve ring sizes of at least about 8 atoms, which is well beyond the optimum 5 or 6, accessible to hydrocarbon based diols. Chelation involving an OH group and an ether, which would give the optimum 5 or 6 membered rings, is not as strong as chelation with the two OH groups accessible to the hydrocarbon based diols because the OH groups are less sterically hindered and because the OH groups are more active at forming hydrogen bond interactions, which are key to binding the diols to the filler surface.

[0096] An important advantage of the silanes herein is that the by-products of the silane coupling process are themselves of utility in enhancing the rubber compounding process; the value of the resulting rubber compositions, and/or any articles of manufacture employing the rubber compositions. Thus, the blocked mercaptan groups of the silanes of the present invention not only retards coupling of silane to polymer during mixing but also assists in the dispersion of the filler into the polymer during mixing by reducing the ability of the surface hydroxyl or metal oxides to form hydrogen bonds between filler particles, thereby enhancing the ease and completeness of filler dispersion and retarding the reversal of this process, namely, filler reagglomeration. In addition, the diols released from the silane's silicon atoms during the process of coupling to the filler are not just shed as a waste product, but perform an important follow-up function, specifically, enhancing the efficiency of the curatives, as previously described.

[0097] An unexpected result of the organofunctional silanes of the present invention is the long scorch times for uncured filled elastomers containing silanes (10) and (11). The high levels of mercapto-functional groups that are present in these silanes would normally produce very short scorch times. Long scorch times are desirable because they allow the uncured rubber to be mixed with the fillers and other ingredients in a single pass and at higher temperatures, which facilitate filler dispersion and uniform composition, without generating high and variable viscosities or partially cured compounds. Uncured filled elastomers with high viscosities are undesirable because they slow down the extrusion rates and fabrication of the articles. If the uncured rubber compound is partially cured before the molding process begins, then the gel particles resulting from premature crosslinking may generate defects and negatively affect one or more of the physical properties of the cured elastomer.

[0098] In use, at least one of the organofunctional silane compositions that contain cyclic and/or bridging dialkoxysilyl groups and free and blocked mercapto groups is mixed with the organic polymer before, during, or after the compounding of the filler into the organic polymer. In one embodiment, the silanes are added before or during the compounding of the filler into the organic polymer because these silanes facilitate and improve the dispersion of the filler. The total amount of silane present in the resulting rubber composition should be 0.05 to 25 parts by weight per hundred parts by weight of organic polymer (phr). In another embodiment, the amount of silane present in the rubber is from 1 to 10 phr. Fillers can be used in quantities ranging from 5 to 100 phr, more preferably from 25 to 80 phr.

[0099] When reaction of the mixture to couple the filler to the polymer is desired, a deblocking agent is added to the mixture to deblock the organofunctional silane compositions that contain cyclic and/or bridging dialkoxysilyl groups and free and blocked mercapto groups. The deblocking agent may be added at quantities ranging from 0.1 to 5 phr; more preferably in the range of from 0.5 to 3 phr. If alcohol or water are present in the mixture (as is common), a catalyst (e.g., tertiary amines, or Lewis acids) may be used to initiate and promote the loss of the blocking group by hydrolysis or alcoholysis to liberate the corresponding mercaptosilane. Alternatively, the deblocking agent may be a nucleophile containing a hydrogen atom sufficiently labile such that hydrogen atom could be transferred to the site of the original blocking group to form the mercaptosilane. Thus, with a blocking group acceptor molecule, an exchange of hydrogen from the nucleophile would occur with the blocking group of the blocked mercaptosilane to form the mercaptosilane and

the corresponding derivative of the nucleophile containing the original blocking group. This transfer of the blocking group from the silane to the nucleophile could be driven, for example, by a greater thermodynamic stability of the products (mercaptosilane and nucleophile containing the blocking group) relative to the initial reactants (organofunctional silane compositions that contain cyclic and/or bridging dialkoxyisilyl groups and free and blocked mercapto groups and the nucleophile). For example, if the nucleophile were an amine containing an N-H bond, transfer of the blocking group from the organofunctional silane compositions that contain cyclic and/or bridging dialkoxyisilyl groups and free and blocked mercapto groups would yield the mercaptosilane and one of several classes of amides corresponding to the type of blocking group used. For example, carboxyl blocking groups deblocked by amines would yield amides, sulfonyl blocking groups deblocked by amines would yield sulfonamides, sulfinyl blocking groups deblocked by amines would yield sulfonamides, phosphonyl blocking groups deblocked by amines would yield phosphonamides, and phosphinyl blocking groups deblocked by amines would yield phosphinamides. What is important is that regardless of the blocking group initially present on the cyclic and bridging dialkoxy blocked mercaptofunctional silane and regardless of the deblocking agent used, the initially substantially inactive (from the standpoint of coupling to the organic polymer) organofunctional silane compositions that contain cyclic and/or bridging dialkoxyisilyl groups and free and blocked mercapto groups is substantially converted at the desired point in the rubber compounding procedure to the active mercaptosilane. It is noted that partial amounts of the nucleophile may be used (i.e., a stoichiometric deficiency), if one were to only deblock part of the organofunctional silane compositions that contain cyclic and/or bridging dialkoxyisilyl groups and free and blocked mercapto groups to control the degree of vulcanization of a specific formulation.

[0100] Water typically is present on the inorganic filler as a hydrate or bound to the filler in the form of a hydroxyl group. The deblocking agent can be added in the curative package or, alternatively, at any other stage in the compounding process as a single component. Examples of nucleophiles would include any primary or secondary amines, or amines containing C=N double bonds, such as imines or guanidines; with the proviso that said amine contains at least one N-H (nitrogen-hydrogen) bond. Numerous specific examples of guanidines, amines, and imines well known in the art, which are useful as components in curatives for rubber, are cited in Rubber Chemicals; J. Van Alphen; Plastics and Rubber Research Institute TNO, Delft, Holland; 1973. Some examples include: N,N'-diphenylguanidine, N,N',N"-triphenylguanidine, N,N'-di-ortho-tolylguanidine, ortho-biguanide, hexamethylenetetramine, cyclohexylethylamine, dibutylamine, and 4,4'-diaminodiphenylmethane. Any general acid catalysts used to transesterify esters, such as Bronsted or Lewis acids, could be used as catalysts.

[0101] The rubber composition need not be, but preferably is, substantially free of functionalized siloxanes, especially those of the type disclosed in Australian Patent AU-A-10082/97. Most preferably, the rubber composition is free of functionalized siloxanes.

[0102] In practice, sulfur vulcanized rubber products typically are prepared by thermomechanically mixing rubber and various ingredients in a sequentially step-wise manner followed by shaping and curing the compounded rubber to form a vulcanized product. First, for the aforesaid mixing of the rubber and various ingredients, typically exclusive of sulfur and sulfur vulcanization accelerators (collectively "curing agents"), the rubber(s) and various rubber compounding ingredients are usually blended in at least one, and often (in the case of silica filled low rolling resistance tires) two, preparatory thermomechanical mixing stage(s) in suitable mixers. Such preparatory mixing is referred to as non-productive mixing or non-productive mixing steps or stages. Such preparatory mixing usually is conducted at temperatures in the range of from 140 °C to 200 °C and often in the range of from 150 °C to 180 °C.

[0103] Subsequent to such preparatory mix stages, in a final mixing stage, sometimes referred to as a productive mix stage, deblocking agent (in the case of this invention), curing agents, and possibly one or more additional ingredients, are mixed with the rubber compound or compositions, typically at a temperature in a range of 50 °C to 130 °C, which is a lower temperature than those utilized in the preparatory mix stages to prevent or retard premature curing of the sulfur curable rubber, which is sometimes referred to as scorching of the rubber composition.

[0104] The rubber mixture, sometimes referred to as a rubber compound or composition, typically is allowed to cool, sometimes after or during a process intermediate mill mixing, between the aforesaid various mixing steps, for example, to a temperature of 50 °C or lower.

[0105] When it is desired to mold and to cure the rubber, the rubber is placed into the appropriate mold at at least 130 °C and up to 200 °C, which will cause the vulcanization of the rubber by the mercapto groups on the mercaptosilane and any other free sulfur sources in the rubber mixture.

[0106] By thermomechanical mixing, it is meant that the rubber compound, or composition of rubber and rubber compounding ingredients, is mixed in a rubber mixture under high shear conditions where it autogenously heats up as a result of the mixing, primarily due to shear and associated friction within the rubber mixture in the rubber mixer. Several chemical reactions may occur at various steps in the mixing and curing processes.

[0107] The first reaction is a relatively fast reaction and is considered herein to take place between the filler and the alkoxyisilane group of the cyclic and/or bridging dialkoxy blocked mercaptofunctional silanes. Such reaction may occur at a relatively low temperature, such as, for example, 120 °C. The second and third reactions are considered herein to be the deblocking of the cyclic and/or bridging dialkoxy blocked mercaptofunctional silanes and the reaction which takes

place between the sulfur-containing portion of the silane (after deblocking), and the sulfur vulcanizable rubber at a higher temperature; for example, above 140 °C.

[0108] Another sulfur source may be used, for example, in the form of elemental sulfur as S₈. A sulfur donor is considered herein as a sulfur-containing compound that liberates free, or elemental sulfur, at a temperature in a range of 140 °C to 190 °C. Such sulfur donors may be, for example, although are not limited to, polysulfide vulcanization accelerators and organosilane polysulfides with at least two connecting sulfur atoms in their polysulfide bridge. The amount of free sulfur source addition to the mixture can be controlled or manipulated as a matter of choice relatively independently from the addition of the aforesaid cyclic and bridging dialkoxy blocked mercaptofunctional silane composition.

[0109] Thus, for example, the independent addition of a sulfur source may be manipulated by the amount of addition thereof and by sequence of addition relative to addition of other ingredients to the rubber mixture.

[0110] In an embodiment of the present invention, a rubber composition is prepared by a process comprising the sequential steps of:

(a) thermomechanically mixing, in at least one preparatory mixing step, to a temperature of 140 °C to 200 °C, alternatively to -140 °C to 190 °C, for a total mixing time of 2 to 20, alternatively 4 to 15, minutes for such mixing step(s):

- i) 100 parts by weight of at least one sulfur vulcanizable rubber selected from conjugated diene homopolymers and copolymers, and copolymers of at least one conjugated diene and aromatic vinyl compound,
- ii) 5 to 100, preferably 25 to 80, phr of particulate filler, wherein the filler preferably contains from 1 to 85 weight percent carbon black, and
- iii) 0.05 to 20 parts by weight filler of at least one cyclic and/or bridging dialkoxy silane of the present invention composition;

b) subsequently blending therewith, in a final thermomechanical mixing step at a temperature to 50 °C to 130 °C for a time sufficient to blend the rubber, preferably between 1 to 30 minutes, more preferably 1 to 3 minutes, at least one deblocking agent at 0.05 to 20 parts by weight of the filler and a curing agent at 0 to 5 phr; and, optionally; and,

c) curing said mixture at a temperature in the range of from 130 to 200 °C for about 5 to 60 minutes.

[0111] The process may also comprise the additional steps of preparing an assembly of a tire or sulfur vulcanizable rubber with a tread comprised of the rubber composition prepared according to this invention and vulcanizing the assembly at a temperature in a range of 130°C to 200°C.

[0112] Suitable organic polymers and fillers are well known in the art and are described in numerous texts, of which two examples include The Vanderbilt Rubber Handbook, R.F. Ohm, ed.; RT. Vanderbilt Company, Inc., Norwalk, CT; 1990 and Manual For The Rubber Industry; T. Kempermann, S. Koch, J. Sumner, eds.; Bayer AG, Leverkusen, Germany; 1993. Representative examples of suitable polymers include solution styrene-butadiene rubber (SSBR), styrene-butadiene rubber (SBR), natural rubber (NR), polybutadiene (BR), ethylene-propylene co- and ter-polymers (EP, EPDM), and acrylonitrile-butadiene rubber (NBR).

[0113] The rubber composition is comprised of at least one diene-based elastomer, or rubber. Suitable conjugated dienes are isoprene and 1,3-butadiene, and suitable vinyl aromatic compounds are styrene and alpha methyl styrene. Thus, the rubber is a sulfur - curable rubber. Such diene based elastomer, or rubber, may be selected, for example, from at least one of cis-1,4-polyisoprene rubber (natural and/or synthetic), and preferably natural rubber), emulsion polymerization prepared styrene-butadiene copolymer rubber, organic solution polymerization prepared styrene-butadiene rubber, 3,4-polyisoprene rubber, isoprene-butadiene rubber, styrene/isoprene/butadiene terpolymer rubber, cis-1,4-polybutadiene, medium vinyl polybutadiene rubber (35-50 percent vinyl), high vinyl polybutadiene rubber (50-75 percent vinyl), styrene/isoprene copolymers, emulsion polymerization prepared styrene/butadiene/acrylonitrile terpolymer rubber and butadiene/acrylonitrile copolymer rubber. An emulsion polymerization derived styrene/butadiene (ESBR) may be used having a relatively conventional styrene content of 20 to 28 percent bound styrene or, for some applications, an BSBR having a medium to relatively high bound styrene content, namely, a bound styrene content of 30 to 45 percent. Emulsion polymerization prepared styrene/butadiene/acrylonitrile terpolymer-rubbers containing 2 to 40 weight percent bound acrylonitrile in the terpolymer are also contemplated as diene based rubbers for use in this invention.

[0114] The solution polymerisation prepared SBR (SSBR) typically has a bound styrene content in a range of 5 to 50, preferably 9 to 36, percent. Polybutadiene elastomer may be conveniently characterized, for example, by having at least a 90 weight percent cis-1,4-content.

[0115] Representative examples of suitable filler materials include include metal oxides, such as silica (pyrogenic and precipitated), titanium dioxide, aluminosilicate, and alumina, siliceous materials, including clays and talc, and carbon black. Particulate, precipitated silica is also sometimes used for such purpose, particularly in connection with a silane. In some cases, a combination of silica and carbon black is utilized for reinforcing fillers for various rubber products,

including treads for tires. Alumina can be used either alone or in combination with silica. The term "alumina" can be described herein as aluminum oxide, or Al_2O_3 . The fillers may be hydrated or in anhydrous form. Use of alumina in rubber compositions is known, see, for example, U.S. Patent No. 5,116,886 and EP 631 982.

[0116] The organofunctional silane compositions that contain cyclic and/or bridging dialkoxysilyl groups and free and blocked mercapto groups may be premixed, or pre-reacted, with the filler particles or added to the rubber mix during the rubber and filler processing, or mixing stage. If the silane and filler are added separately to the rubber mix during the rubber and filler mixing, or processing stage, it is considered that the organofunctional silane compositions that contain cyclic and/or bridging dialkoxysilyl groups and free and blocked mercapto groups then couple in situ to the filler.

[0117] The vulcanized rubber composition should contain a sufficient amount of filler to contribute a reasonably high modulus and high resistance to tear. The combined weight of the filler may be as low as 5 to 100 phr, but is more preferably from 25 to 85 phr.

[0118] In one embodiment of the present invention, precipitated silica is utilized as filler. The silica filler herein may be characterized by having a BET surface area, as measured using nitrogen gas, preferably in the range of from 40 to $600m^2/g$, and more preferably in a range of from 50 to $300m^2/g$. The BET method of measuring surface area is described in the Journal of the American Chemical Society, Volume 60, page 304 (1930). The silica typically may also be characterized by having a dibutylphthalate (DBP) absorption value in a range of from 100 to 350, and more usually from 150 to 300. Further, useful silica fillers, as well as the aforesaid alumina and aluminosilicate fillers, may be expected to have a CTAB surface area in a range of from 100 to $220m^2/g$. The CTAB surface area is the external surface area as evaluated by cetyl trimethylammonium bromide with a pH of 9. The method is described in ASTM D 3849.

[0119] Mercury porosity surface area is the specific surface area determined by mercury porosimetry. For such technique, mercury is penetrated into the pores of the sample after a thermal treatment to remove volatiles. Set-up conditions may be suitably described as using a 100 mg sample; removing volatiles during 2 hours at $105^\circ C$ and ambient atmospheric pressure; and ambient to 2000 bars pressure measuring range. Such evaluation may be performed according to the method described in Winslow, et al. in ASTM bulletin, p.39 (1959) or according to DIN 66133. For such an evaluation, a CARLO-ERBA Porosimeter 2000 may be used. The average mercury porosity specific surface area for the selected silica filler should be in a range of 100 to $300m^2/g$.

[0120] In one embodiment, a suitable pore size distribution for the silica, alumina and aluminosilicate according to such mercury porosity evaluation is considered herein to be: five percent or less of its pores having a diameter of less than 10 nm; from 60 to 90 percent of its pores have a diameter of from 0 to 100 nm; from 10 to 30 percent of its pores having a diameter of from 100 to 1,000 nm; and from 5 to 20 percent of its pores have a diameter of greater than 1,000 nm. In a second embodiment, the silica may be expected to have an average ultimate particle size, for example, in the range of from 0.01 to $(0.05\mu m$ as determined by electron microscopy, although the silica particles may be even smaller, or possibly larger, in size. Various commercially available silicas may be considered for use herein such as, those available from PPG Industries under the HI-SIL trademark, in particular, HI-SIL 210, 243, etc.; silicas available from Rhone-Poulenc, e.g., ZEOSIL 1165MP; silicas available from Degussa, e.g., VN2 and VN3, etc. and silicas available from Huber, e.g., HUBERSIL 8745.

[0121] Where, it is desired for the rubber composition, which contains both a siliceous filler such as silica, alumina and/or aluminosilicates and also carbon black reinforcing pigments, to be primarily reinforced with silica as the reinforcing pigment, it is often preferable that the weight ratio of such siliceous fillers to carbon black is at least 3/1 and preferably at least 10/1 and, thus, in a range of 3/1 to 30/1. The filler may comprise from 15 to 95 weight percent precipitated silica, alumina and/or aluminosilicate and, correspondingly from 5 to 85 weight percent carbon black, wherein the said carbon black has a CTAB value in a range of from 80 to 150. Alternatively, the filler may comprise from 60 to 95 weight percent of said silica, alumina and/or aluminosilicate and, correspondingly, from 40 to 5 weight percent of carbon black. The siliceous filler and carbon black may be pre-blended or blended together in the manufacture of the vulcanized rubber.

[0122] The rubber composition can be compounded by methods known in the rubber compounding art, such as mixing the various sulfur-vulcanizable constituent rubbers with various commonly used additive materials as, for example, curing aids such as sulfur, activators, retarders and accelerators, processing additives such as oils, resins e.g., tackifying resins, silicas, plasticizers, fillers, pigments, fatty acid, zinc oxide, waxes, antioxidants and antiozonants, peptizing agents, and reinforcing materials such as, for example, carbon black, and the like. Depending on the intended use of the sulfur vulcanizable and sulfur vulcanized material (rubbers), the additives mentioned above are selected and commonly used in conventional amounts.

[0123] The vulcanization can be conducted in the presence of an additional sulfur vulcanizing agent. Examples of suitable sulfur vulcanizing agents include, e.g., elemental sulfur (free sulfur) or sulfur donating vulcanizing agents, for example, an amino disulfide, polymeric polysulfide or sulfur olefin adducts, which are conventionally added in the final, productive, rubber composition mixing step. The sulfur vulcanizing agents (which are common in the art) are used, or added in the productive mixing stage, in an amount ranging from 0.4 to 3 phr, or even in some circumstances, up to 8 phr, with a range of from 1.5 to 5 phr, and in some cases from 2 to 2.5 phr, being preferred.

[0124] Vulcanization accelerators, i.e., additional sulfur donors, may also be used. It will be appreciated that they may

be, for example, of the type, such as, for example, benzothiazole, alkyl thiuram disulfide, guanidine derivatives, and thiocarbamates. Representative of such accelerators are, e.g., but not limited to, mercapto benzothiazole, tetramethyl thiuram disulfide, benzothiazole disulfide, diphenylguanidine, zinc dithiocarbamate, alkylphenoldisulfide, zinc butyl xanthate, N-dicyclohexyl-2-benzothiazolesulfenamide, N-cyclohexyl-2-benzothiazolesulfenamide, N-oxydiethylenebenzothiazole-2-sulfenamide, N,N-diphenylthiourea, dithiocarbamylsulfenamide, N,N-diisopropylbenzothiazole-2-sulfenamide, zinc-2-mercaptopotoluimidazole, dithiobis(N-methyl piperazine), dithiobis(N-beta-hydroxy ethyl piperazine) and dithiobis(dibenzyl amine). Other additional sulfur donors, include, e.g., thiuram and morpholine derivatives. Representative of such donors include, e.g., but are not limited to, dimorpholine disulfide, dimorpholine tetrasulfide, tetramethyl thiuram tetrasulfide, benzothiazyl-2,N-dithiomorpholide, thioplasts, dipentamethylenethiuram hexasulfide and disulfide-caprolactam.

[0125] Accelerators are used to control the time and/or temperature required for vulcanization and to improve the properties of the vulcanizate. In one embodiment, a single accelerator system can be used, i.e., a primary accelerator. Conventionally and preferably, a primary accelerator(s) is used in total amounts ranging from 0.5 to 4, preferably from 0.8 to 1.5, phr. Combinations of a primary and a secondary accelerator might be used with the secondary accelerator being used in smaller amounts (e.g., from 0.05 to 3 phr) in order to activate and to improve the properties of the vulcanizate. Delayed action accelerators may be used. Vulcanization retarders can also be used. Suitable types of accelerators are amines, disulfides, guanidines, thioureas, thiazoles, thiurams, sulfenamides, dithiocarbamates and xanthates. Preferably, the primary accelerator is a sulfenamide. If a second accelerator is used, the secondary accelerator is preferably a guanidine, dithiocarbamate or thiuram compound.

[0126] Typical amounts of tackifier resins, if used, can be from 0.5 to 10 phr, usually from 1 to 5 phr. Typical amounts of processing aids comprise from 1 to 50 phr. Such processing aids can include, e.g., aromatic, naphthenic and/or paraffinic processing oils. Typical amounts of antioxidants are from 1 to 5 phr. Representative antioxidants include, e.g., diphenyl-p-phenylenediamine and others, e.g., those disclosed in the Vanderbilt Rubber Handbook (1978), pages 344-346. Typical amounts of antiozonants, are from 1 to 5 phr. Typical amounts of fatty acids, if used, which can include stearic acid, are from 0.5 to 3 phr. Typical amounts of zinc oxide are from 2 to 5 phr. Typical amounts of waxes are from 1 to 5 phr. Often microcrystalline waxes are used. Typical amounts of peptizers are from 0.1 to 1 phr. Typical peptizers include, e.g., pentachlorothiophenol and dibenzamidodiphenyl disulfide.

[0127] The rubber compositions of this invention can be used for various purposes. For example, they can be used for various tire compounds, shoe soles and other industrial goods. Such articles can be built, shaped, molded and cured by various known and conventional methods as is readily apparent to those skilled in the art. One particularly useful application of the rubber compositions herein is for the manufacture of tire treads. An advantage of tires, tire treads, or other articles of manufacture derived from the rubber compositions herein is that they suffer from less VOC emissions during their lifetime and use as a result of having been manufactured from a rubber compound that contains less residual silane ethoxy groups than do rubber compounds of the known and currently practiced art. This is a direct result of having used dialkoxy-functional silane coupling agents in their manufacture, which contain fewer or essentially no ethoxy groups on silicon, relative to the silane coupling agents of the currently known and practiced art. The lack or reduction of ethoxysilane groups in the coupling agents used results in fewer residual ethoxy groups on silicon after the article of manufacture is produced, from which less or no ethanol can be released by hydrolysis of the residual ethoxysilane groups by exposure of the article of manufacture to water during use.

[0128] The rubber compositions herein and the articles of manufacture derivable therefrom as described herein are novel in that both contain non-silicon-containing ethoxy esters and esters of hydrocarbon-based diols, as well as the hydrocarbon based diols. Typical examples of such species contained in the rubber compositions and articles of manufacture described herein include octanoate, hexanoate, decanoate, and/or dodecanoate esters of diols such as propanediols, pentane diols, ethylene glycol, and propylene glycol. Additional species would include ethyl octanoate, ethyl hexanoate, ethyl decanoate, and/or ethyl dodecanoate. These species possess polarities intermediate between those of the rubber polymers and the filler, thereby helping to stabilize the compositions and articles of manufacture from filler reagglomeration and the resulting degradation of the properties and performance parameters thereof.

[0129] All references cited herein are incorporated herein as they are relevant to the present invention.

[0130] The invention may be better understood by reference to the following examples in which the parts and percentages are by weight unless otherwise indicated.

COMPARATIVE EXAMPLES 1-3

[0131] Comparative Examples 1-3 were prepared by mixing 3-thiooctanoylpropyltriethoxysilane and 3-mercaptopropyltriethoxysilane in the ratio indicated in Table 1.

TABLE 1

Silane	Comparative Example 1	Comparative Example 2	Comparative Example 3
3-thiooctanoylpropyltriethoxysilane	100	92.7	85.4
1-mercaptopropyltriethoxysilane	0	7.3	14.6

EXAMPLE 1

[0132] 3-thiooctanoylpropyltriethoxysilane (1101 g; 3.03 moles) was added to a round-bottomed flask. Sulfuric acid (0.98 g) was added to the reaction flask and 2-methylpropane-1,3-diol (816.6 g; 9.06 moles) was added via addition funnel. The flask was heated to 50° C under a vacuum of 50 torr. Ethanol (367 g) was collected. A 21% ethanolic solution of sodium ethoxide (9.53 g) was added and the mixture was heated to 100-120°C under atmospheric pressure for several hours.

EXAMPLE 2

[0133] 3-thiooctanoylpropyltriethoxysilane (1101 g; 3.03 moles) was added to a round-bottomed flask. Sulfuric acid (0.98 g) was added to the reaction flask and 2-methylpropane-1,3-diol (816.6 g; 9.06 moles) was added via addition funnel. The flask was heated to 50° C under a vacuum of 50 torr. Ethanol (367 g) was collected. A 21% ethanolic solution of sodium ethoxide (10.7 g) was added and the mixture was heated to 100-120°C under atmospheric pressure for several hours.

EXAMPLE 3

[0134] 3-thiooctanoylpropyltriethoxysilane (1101 g; 3.03 moles) was added to a round-bottomed flask. Sulfuric acid (0.98 g) was added to the reaction flask and 2-methylpropane-1,3-diol (816.6 g; 9.06 moles) was added via addition funnel. The flask was heated to 50° C under a vacuum of 50 torr. Ethanol (367 g) was collected. A 21% ethanolic solution of sodium ethoxide (11.3 g) was added and the mixture was heated to 100-120°C under atmospheric pressure for several hours.

EXAMPLE 4

[0135] 3-thiooctanoylpropyltriethoxysilane (293.5 g; 0.81 mole) and 3-mercaptopropyltriethoxysilane (32.6 g, 0.12 mole) were added to a round-bottomed flask. Sulfuric acid (0.29 g) was added to the reaction flask and 2-methylpropane-1,3-diol (254.6 g; 4.04 moles) was added via addition funnel. The flask was heated to 50° C under a vacuum of 50 torr. Ethanol (112.7 g) was collected. A 21% ethanolic solution of sodium ethoxide (0.73 g) was added. 439.8 grams of product were recovered.

EXAMPLE 5

[0136] 3-thiooctanoylpropyltriethoxysilane (276.6 g; 0.76 moles) and 3-mercaptopropyltriethoxysilane (69.2 g; 0.25 moles) were added to a round-bottomed flask. Sulfuric acid (0.31 g) was added to the reaction flask and 2-methylpropane-1,3-diol (238.5 g; 2.65 moles) was added via addition funnel. The flask was heated to 50° C under a vacuum of 50 torr. Ethanol (137.9 g) was collected. A 21% ethanolic solution of sodium ethoxide (1.13 g) was added.

EXAMPLE 6

[0137] Component I was prepared by adding 3-thiooctanoylpropyltriethoxysilane (541.1 g; 1.49 moles) to a round-bottomed flask. Sulfuric acid (0.47 g) was added to the reaction flask and 2-methylpropane-1,3-diol (401.4 g; 4.45 moles) was added via addition funnel. The flask was heated to 50° C under a vacuum of 50 torr. Ethanol (185.9 g) was collected. A 21% ethanolic solution of sodium ethoxide (3.5 g) was added. Component II was prepared by adding 3-mercaptopropyltriethoxysilane (250 g; 0.91 mole) to a round-bottomed flask. Sulfuric acid (0.26 g) was added to the reaction flask and 2-methylpropane-1,3-diol (283 g; 3.14 moles) was added via addition funnel. The flask was heated to 50° C under a vacuum of 50 torr. Ethanol (126.7 g) was collected. A 21% ethanolic solution of sodium ethoxide (1.24 g) was added. In a round-bottomed flask were combined Component I (145.2 g) and Component II (54.8 g). The mixture was stirred under nitrogen.

COMPARATIVE EXAMPLES 4-6; EXAMPLES 7-12

[0138] Cured rubber compositions in the form of plaques (Comparative Examples 4-6 employing the silanes of Comparative Examples 1-3, respectively; and Examples 7-12 employing the silanes of Examples 1-6, respectively) were prepared and their physical and dynamic properties measured.

[0139] A typical silica-rubber SBR formulation was used as described below in Table 2. Mixing was carried out in a 1550 ml Krupp intermeshing mixer. The silane loadings were 8.2 phr.

TABLE 2: Silica-Silane/Rubber Formulation

PHR	Components
103.2	sSBR(Buna VSL 5525-1) - (BayerAG)
25	BR (Budene 1207) - (Goodyear)
80	silica - Zeosil 1165MP, (Rhodia)
8.2	Silane from Comparative Examples 1-3 and Examples 1-6
4.5	oil - Sundex 8125 (Sun Oil)
2.5	zinc oxide - Kadox 720C (ZincCorp.)
1.0	stearic acid - Industrene R (Witco, Crompton)
2.0	6 PPD - Flexzone 7P (Uniroyal, Crompton)
1.5	Wax - Sunproof Improved (Uniroyal, Crompton)
	Final Mix Ingredients
1.4	Rubbermakers Sulfur 104, Harwick
1.7	CBS - Delac S (Uniroyal, Crompton)
2.0	DPG - (Uniroyal, Crompton)

[0140] The procedure for preparing a single non-productive mix is presented in Table 3 below.

TABLE 3: One Pass Procedure; Cooling with water @ 25°C, 68% fill factor:

Step	Procedure
1	Add polymers, RDM (ram down mix) 60 seconds
2	Add 50% silica, all silane, oil, RDM 60 seconds
3	Add remaining 50% silica, wax, RDM 90 seconds
4	Dust down, RDM 30 seconds
5	Add remainder of ingredients, RDM 60 seconds
6	Dust down, RDM to 160-170 °C (in approx. 2 minutes) by increasing rotor speed
7	Hold at 170 °C (or higher temperature) for 8 minutes by changing speeds on the mixer.
8	Dump, sheet off roll mill @ 65-70 °C to cool

[0141] The procedure for preparing a single productive mix involved adding sulfur and accelerators (primary and secondary) into a masterbatch prepared as described in Table 3 on a two-roll mill at 65-70°C. After all the silica filler, silane and oil were incorporated into a given mix, the rpm of the rotors was raised so as to achieve the desired silanization temperature. The mix was then held at that temperature for 8 minutes. The mix procedures are shown in Table 3, above.

[0142] Curing and testing of the cured rubber compositions in the form of plaques were carried out according to ASTM standards. In addition, small strain dynamic tests were carried out on a Rheometrics Dynamic Analyzer (ARES - Rheometrics Inc.). The specific curing procedure, measurements and measuring procedures were as follows:

Curing Procedure/Measurement	Testing Standard
Mooney viscosity and scorch	ASTM D1646
Oscillating disc rheometry	ASTM D2084
Curing of test plaques	ASTM D3182
Stress-strain properties	ASTM D412
Heat build-up	ASTM D623

Dynamic Mechanical properties:

[0143] Payne effect strain sweeps were carried out from dynamic strain amplitudes of 0.01 % to about 25% shear strain amplitude at 10 Hz and 60°C. The dynamic parameters, G' _{initial}, $\Delta G'$, G''_{max} , $\tan \delta_{max}$ were extracted from the non-linear responses of the rubber compounds at small strains. In some cases, steady state values of $\tan \delta$ were measured after 15 minutes of dynamic oscillations at strain amplitudes of 35% (at 60 °C). Temperature dependence of dynamic properties were also measured from about -80 °C to +80 °C at small strain amplitudes (1 or 2%) at a frequency of 10 Hz.

[0144] The results for the test plaques of Comparative Examples 4-6 and Examples 7-12 are presented in Table 4.

10 TABLE 4: Physical and Dynamic Properties of Cured Rubber Compositions: of Comparative Examples 4-6 and
Examples 7-12

Examples	Comp Ex.4	Comp Ex. 5	Comp Ex.6	Ex. 7	Ex. 8	Ex. 9	Ex. 10	Ex. 11	Ex. 12
Silane used:	Comp. Ex. 1	Comp. Ex. 2	Comp. Ex. 3	Ex.1	Ex. 2	Ex. 3	Ex. 4	Ex. 5	Ex. 6
%SH Titration				1.43	2.41	3.09	1.03	2.24	2.31
Mooney Viscosity @ 100°C									
ML1+4	59	62	64	64.38	64.52	65.36	62	64	65.22
Mooney Scorch @135°C									
M_v	24	29	31	30.16	32.40	34.49	29	31.0	32.12
MS1+, t_3 , minutes	8.5	6.1	5.0	7.4	7.3	7.0	7.3	6.0	6.3
MS1+, t_{18} , minutes	13.2	10.0	7.5	9.48	9.13	8.25	9.4	7.5	8.05
Oscillating Disc Rheometer @ 149°C, 1° arc, 30 minute timer									
M_L , dNm	8.3	9.5	10.3	8.92	9.42	10.16	8.6	8.8	9.57
M_H , dNm	27.7	28.2	28.5	31.20	30.36	30.18	31.2	30.4	31.38
t_{s1} , minutes	4.6	4.3	3.5	4.68	4.54	4.25	4.3	3.5	4.04
t_{90} , minutes	15.4	14.2	11.1	9.69	9.39	8.76	8.7	7.3	7.98
M_H , dNm- M_L	19.4	18.7	18.2	22.28	20.94	20.02	22.6	21.6	21.80
Physical Properties, cured t_{90} @ 149°C									
Hardness, Shore A	54	53	53	58	58	57	58	56	58
25% Modulus, MPa	0.68	0.68	0.73	0.923	0.866	0.819	0.77	0.80	0.879
100% Modulus, MPa	1.53	1.65	1.76	2.42	2.29	2.15	2.10	2.20	2.35

(continued)

5	Physical Properties, cured t ₉₀ @ 149°C									
10	300% Modulus, MPa	7.30	8.78	9.82	13.32	13.98	14.20	12.02	13.36	14.03
15	Tensile, MPa	22.2	22.6	23.1	21.78	20.36	19.03	22.0	21.7	19.98
20	RI 300/25	10.74	12.91	13.45	14.43	16.14	17.34	15.6	16.7	15.96
25	RI 300/100	4.78	5.32	5.58	5.50	6.10	6.60	5.7	6.1	5.97
30	Dynamic Properties in the Cured State									
35	Non-linearity (0-10%) @ 60°C									
40	G', initial, MPa				2.51	2.67	2.23	2.15	2.02	2.87
45	Delta G', MPa				1.06	1.19	0.84	0.79	0.69	1.35
50	G ["] _{max} , MPa				0.29	0.33	0.25	0.233	0.205	0.32
55	tan delta _{max}				0.14	0.14	0.13	0.126	0.121	0.14
60	Low Temperature Viscoelasticity									
65	tan delta, 0°C				0.54	0.55	0.54	0.568	0.560	0.55
70	tan delta, 60°C				0.13	0.13	0.12	0.119	0.113	0.12
75	G', 0°C, MPa				5.50	5.42	4.65	5.20	4.77	5.54
80	G', 60°C, MPa				1.92	1.92	1.72	1.72	1.69	1.96

[0145] As shown by the data presented in Table 4, the organofunctional and cyclic and/or bridging dialkoxy silane compositions of the present invention (Examples 1-6) show equivalent or improved performance while maintaining the long scorch times necessary for mixing, extrusion and fabricating articles. These silane compositions also offer a significant benefit in reducing the amounts of VOCs that are released.

COMPARATIVE EXAMPLES 7 AND 8

[0146] During the compounding of rubber, 3-thiooctanoylpropyltriethoxysilane (6.64 phr), 3- mercaptopropyltriethoxysilane (1.56 phr), and 2-methyl-1,3-propanediol (2.0 phr) were added, as described in the mixing procedure of Table 3, to provide the test plaque of Comparative Example 8. The uncured filled elastomer of Comparative Example 7, exhibited very short scorch times, as shown in Table 5, infra

EXAMPLE 13

[0147] Thiooctanoylpropyltriethoxysilane (213 g; 0.59 mole) was added to a round-bottomed flask. Sulfuric acid (0.25 g) and trimethylolpropane (235 g, 1.55 moles) were added to the reaction flask. The flask was heated to 70°C under a vacuum of 50 torr. The trimethylolpropane melted and dissolved. Ethanol (80 g) was collected. A 21% ethanolic solution of sodium ethoxide (0.97 g) was added and the mixture was heated to 100-120°C under atmospheric pressure for several hours.

EXAMPLE 14

[0148] To a 2-liter round bottomed flask was charged 3-octanoylthio-1-propyltriethoxysilane (602 grams; 1.65 moles)

and diethylene glycol (526 grams; 4.96 moles). A catalytic amount (0.8 grams) of *para*-toluenesulfonic acid (PTSA) was then added to the mixture. The 2-liter flask with its contents was then immediately placed onto a rotary evaporator. The contents were subject to rotary evaporation using a mechanical pump as a vacuum source, a dry ice trap as a condenser, a needle valve as a flow regulator between the dry ice trap and vacuum pump, and a heated water bath as a dual source of heat and buoyancy. Rotary evaporation was begun with the water bath at ambient temperature, which was gradually raised to and then maintained at a maximum of 70 °C. Rotary evaporation was continued until no more condensation of ethanol was evident in the dry ice trap. The total time of rotary evaporation was 3.5 hours. The quantity of ethanol collected in the trap (213 grams; 4.63 moles) is consistent with 93% transesterification of the triethoxysilane group on the starting silane to DEG functionality. This reactant products is designated Silane A.

[0149] To a 2-liter round bottomed flask was charged 3-mercaptop-1-propyltriethoxysilane (238 grams; 1.00 mole) and diethylene glycol (318.4 grams; 3.00 moles). A catalytic amount (0.5 grams) of *para*-toluenesulfonic acid (PTSA) was then added to the mixture. The 2-liter flask with its contents was then immediately placed onto a rotary evaporator. The contents were subject to rotary evaporation using a mechanical pump as a vacuum source, a dry ice trap as a condenser, a needle valve as a flow regulator between the dry ice trap and vacuum pump, and a heated water bath as a dual source of heat and buoyancy. Rotary evaporation was begun with the water bath at ambient temperature, which was gradually raised to and then maintained at a maximum of 64 °C. Rotary evaporation was continued until no more condensation of ethanol was evident in the dry ice trap. The quantity of ethanol collected in the trap (133 grams; 2.9 moles) is consistent with 97% transesterification of the triethoxysilane group on the starting silane to DEG functionality. This reaction product is designated Silane B.

[0150] Into a 100 ml round bottom flask equipped with a mechanical stirrer was charged Silane A (85 grams). Silane A was stirred at room temperature and then slowly Silane B (15 grams) was added thereto. This mixture of Silane A and B is designated Silane C.

EXAMPLE 15

[0151] Into a 100 ml round bottom flask equipped with a mechanical stirrer was charged Silane A (65 grams). Silane A was stirred at room temperature and the slowly Silane B (35 grams) was added. The mixture of Silane A and B is designated Silane D.

EXAMPLE 16

[0152] To a 2-liter round bottomed flask was charged 3-octanoylthio-1-propyltriethoxysilane (234 grams; 0.64 moles), 3-mercaptop-1-propyltriethoxysilane (76.7 grams; 0.32 moles), and diethylene glycol (307 grams; 2.89 moles). A catalytic amount (0.4 grams) of *para*-toluenesulfonic acid (PTSA) was then added to the mixture. The 2-liter flask with its contents was then immediately placed onto a rotary evaporator. The contents were subject to rotary evaporation using a mechanical pump as a vacuum source, a dry ice trap as a condenser, a needle valve as a flow regulator between the dry ice trap and vacuum pump, and a heated water bath as a dual source of heat and buoyancy. Rotary evaporation was begun with the water bath at ambient temperature, which was gradually raised to and then maintained at a maximum of 96 °C. Rotary evaporation was continued until no more condensation of ethanol was evident in the dry ice trap. The total time of rotary evaporation was 4 hours and 30 minutes. The quantity of ethanol collected in the trap (129 grams; 2.8 moles) is consistent with 97% transesterification of the triethoxysilane group on the starting silane to DEG functionality. This reaction product is designated silane E.

[0153] Table 5 below sets forth the properties of the cured rubber test plaques of Comparative Example 8 and examples 17-19.

[0154] TABLE 5: Physical and Dynamic Properties of Cured Rubber Compositions of Comparative Example 8 and Examples 17-19:

TABLE 5


	Comp. Ex. 8	Ex.17	Ex.18	Ex.19
Silane	Comp. Ex. 7	Ex.14	Ex.15	Ex.16
%SH Titration	2.5			

(continued)


5	Mooney Viscosity @100°C				
	ML1+4	70.9	51.8	55.0	54.1
10	Mooney Scorch @135°C				
	M _v	44.97	24.72	26.67	26.67
	MS1 +, t ₃ , minutes	0.05	5.36	4.26	5.18
15	MS1 +, t ₁₈ , minutes	10.25	7.43	6.10	7.25
	Oscillating Disc Rheometer @ 149°C, 1° arc, 30 minute timer				
	M _L , dNm	8.42	7.57	8.82	8.34
20	M _H , dNm	30.63	30.38	30.66	30.69
	t _{s1} , minutes	4.28	3.44	2.68	3.45
	t90, minutes	13.21	7.79	6.60	8.21
25	M _H , dNm-M _L	22.20	22.81	21.84	22.35
	Physical Properties, cured t90 @ 149°C				
	Hardness, Shore A	53			
30	Elongation, %	351			
	25% Modulus, MPa	0.96			
	100% Modulus, MPa	2.54			
	300% Modulus, MPa	15.86			
35	Tensile, MPa	20.00			
	RI 300/25	16.45			
	RI 300/100	6.25			

35 **Claims**

1. An organofunctional silane composition comprising at least one organofunctional silane having a chemical structure selected from the group consisting of:



and



wherein:

50 each occurrence of Y is independently selected from a polyvalent species (Q)_zA(=E), wherein the atom (A) attached to an unsaturated heteroatom (E) is attached to a sulfur, which in turn is linked by means of a group G² to a silicon atom;

each occurrence of R is independently selected from the group consisting of hydrogen, straight, cyclic or branched alkyl that may or may not contain unsaturation, alkenyl groups, aryl groups, and aralkyl groups, wherein each R, other than hydrogen, contains from 1 to 18 carbon atoms;

each occurrence of G¹ is independently selected from the group consisting of monovalent and polyvalent groups derived by substitution of alkyl, alkenyl, aryl, or aralkyl wherein G¹ can have from 1 to 30 carbon atoms, with the proviso that if G¹ is univalent, G¹ can be hydrogen;

each occurrence of G² is independently selected from the group consisting of divalent or polyvalent group derived by substitution of alkyl, alkenyl, aryl, or aralkyl wherein G² can have from 1 to 30 carbon atoms;

each occurrence of X is independently selected from the group consisting of -Cl, -Br, RO-, RC(=O)O-, R₂C=NO-, R₂NO-, R₂N-, -R, HO(R⁰CR⁰)_fO, wherein each R is as above and each occurrence of R⁰ is independently given by one of the members listed above for R;

5 each occurrence of Z^b, which forms a bridging structure between two silicon atoms, is independently selected from the group consisting of (-O-)_{0.5}, and [-O(R⁰CR⁰)_fO-]_{0.5}, wherein each occurrence of R⁰ is independently given by one of the members listed above for R;

each occurrence of Z^c, which forms a cyclic structure with a silicon atom, is independently given by -O(R⁰CR⁰)_fO- wherein each occurrence of R⁰ is independently given by one of the members listed above for R;

10 each occurrence of Q is independently selected from the group consisting of oxygen, sulfur, and (-NR-);

each occurrence of A is independently selected from the group consisting of carbon, sulfur, phosphorus, and sulfonyl;

each occurrence of E is independently selected from the group consisting of oxygen, sulfur, and (-NR-); each occurrence of the subscripts, a, b, c, f j, k, m, n, p, q, r, s, u, v, w, and z is independently given by

a is 0 to 7;

15 b is 1 to 3;

c is 1 to 6;

f is 2 to 15,

j is 0 to 1, but j may be 0 only if p is 1;

20 k is 1 to 2, with the provisos that if A is carbon, sulfur, or sulfonyl, then (i) a+b=2 and (ii) k=1; if A is phosphorus, then a+b=3 unless both (i) c>1 and (ii) b=1, in which case a=c+1; and if A is phosphorus, then k is 2;

m is 1 to 20,

n is 1 to 20,

p is 0 to 5,

25 q is 0 to 6;

r is 1 to 3;

s is 1 to 3;

u is 0 to 3;

v is 0 to 3;

30 w is 0 to 1 with the proviso that u+v+2w=3;

z is 0 to 3; and

with the proviso that the each of the above structures contains at least one hydrolysable group, Z^b or Z^c, that is a difunctional alkoxy group.

2. The composition of claim 1, wherein Y is selected from the group consisting of -C(=NR)-; -SC(=NR)-; -SC(=O)-; (-NR)C(=O)-; (-NR)C(=S)-; -OC(=O)-; -OC(=S)-; -C(=O)-; -SC(=S)-; -C(=S)-; -S(=O)-; -S(=O)₂-; -OS(=O)₂-; (-NR)S(=O)₂-; -SS(=O)-; -OS(=O)-; (-NR)S(=O)-; -SS(=O)₂-; (-S)₂P(=O)-; -(S)P(=O)-; -P(=O)(-); (-S)₂P(=S)-; -(S)P(=S)-; -P(=S)(-); (-NR)₂P(=O)-; (-NR)(-S)P(=O)-; (-O)(-NR)P(=O)-; (-O)(-S)P(=O)-; (-O)₂P(=O)-; -(O)P(=O)-; -(NR)P(=O)-; (-NR)₂P(=S)-; (-NR)(-S)P(=S)-; (-O)(-NR)P(=S)-; (-O)(-S)P(=S)-; (-O)₂P(=S)-; -(O)P(=S)-; and -(NR)P(=S)-, and is preferably -C(=O)-.

3. The composition of any preceding claim, wherein G¹ has a primary carbon atom attached to a carbonyl and is a C₁-C₁₈ alkyl.

4. The composition of any preceding claim, wherein G¹ is a monovalent straight chain group derived from a C₃-C₁₀ alkyl, preferably from a C₆-C₈ alkyl.

5. The composition of any preceding claim, wherein G¹ is CH₃(CH₂)_g- and g is from 1 to 29, and is preferably selected from the group consisting of methyl, ethyl, propyl, hexyl, heptyl, benzyl, phenyl, octyl and dodecyl.

50 6. The composition of any preceding claim, wherein G² is a divalent or polyvalent group derived by substitution of C₁-C₁₂ alkyl.

7. The composition any preceding claim, wherein G² is a divalent or polyvalent group derived by substitution of a C₃-C₁₀ alkyl, p is 0, j is 1, k is 1, and the ratio of m to n is from 20:1 to 3:1.

55 8. The composition of claim 7, wherein G² is a divalent or polyvalent group derived by substitution of a C₃ to C₆ alkyl, and the ratio of m to n is from 10:1 to 4:1.


nethioic acid S-[3-((3-hydroxy-2-methyl-propoxy)-{3-[{3-[bis-(3-hydroxy-2-methyl-propoxy)-(3-mercaptopropyl)-silanyloxy]-2-methyl-propoxy}-(3-mercaptopropyl)-(3-hydroxy-2-methyl-propoxy)-silanyloxy]-2-methyl-propoxy)-(3-hydroxy-2-methyl-propoxy)-silanyl]ester; dimethyl-thiocarbamic acid S-[3-((3-hydroxy-2-methyl-propoxy)-{3-[{3-hydroxy-2-methyl-propoxy}-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl]ester; dimethyl-dithiocarbamic acid 3-((3-hydroxy-2-methyl-propoxy)-{3-[{3-hydroxy-2-methyl-propoxy}-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy)-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy)-methyl-silanyl)-propyl ester; dimethyl-dithiocarbamic acid 3-((3-hydroxy-2-methyl-propoxy)-{3-[{3-hydroxy-2-methyl-propoxy}-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy)-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy)-methyl-silanyl)-propyl ester; thiocarbonic acid O-ethyl ester S-[3-((3-hydroxy-2-methyl-propoxy)-{3-[{3-hydroxy-2-methyl-propoxy}-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl]ester; trithiocarbonic acid ethyl ester 3-((3-hydroxy-2-methyl-propoxy)-{3-[{3-hydroxy-2-methyl-propoxy}-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl]ester; dithiobutyric acid 3-((3-hydroxy-2-methyl-propoxy)-{3-[{3-hydroxy-2-methyl-propoxy}-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl ester; dithiobutyric acid 3-((3-hydroxy-2-methyl-propoxy)-{3-[{2-(3-mercaptopropyl)-5-methyl-[1,3,2]dioxasilinan-2-yloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl ester; diethyl-dithiocarbamic acid 3-((3-hydroxy-2-methyl-propoxy)-{3-[{3-hydroxy-2-methyl-propoxy}-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl ester; diethyl-dithiocarbamic acid 3-((3-hydroxy-2-methyl-propoxy)-{3-[{2-(3-mercaptopropyl)-5-methyl-[1,3,2]dioxasilinan-2-yloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl ester; N-methyl-thiobutyrimidic acid 3-((3-hydroxy-2-methyl-propoxy)-{3-[{2-(3-mercaptopropyl)-5-methyl-[1,3,2]dioxasilinan-2-yloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl ester; N-methyl-thiobutyrimidic acid 3-((3-hydroxy-2-methyl-propoxy)-{3-[{3-hydroxy-2-methyl-propoxy}-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl ester; thiophosphoric acid O,O'-diethyl ester S-[3-((3-hydroxy-2-methyl-propoxy)-{3-[{3-hydroxy-2-methyl-propoxy}-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl]ester; thiophosphoric acid O-ethyl ester S-[3-((3-hydroxy-2-methyl-propoxy)-{3-[{2-(3-mercaptopropyl)-5-methyl-[1,3,2]dioxasilinan-2-yloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl]ester O'-propyl ester; dithiophosphoric acid O-ethyl ester S-[3-((3-hydroxy-2-methyl-propoxy)-{3-[{2-(3-mercaptopropyl)-5-methyl-[1,3,2]dioxasilinan-2-yloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl]ester O'-propyl ester; trithiophosphoric acid S,S'-diethyl ester S"--[3-((3-hydroxy-2-methyl-propoxy)-{3-[{3-hydroxy-2-methyl-propoxy}-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl]ester; tetrathiophosphoric acid diethyl ester 3-((3-hydroxy-2-methyl-propoxy)-{3-[{3-hydroxy-2-methyl-propoxy}-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl ester; tetrathiophosphoric acid diethyl ester 3-((3-hydroxy-2-methyl-propoxy)-{3-[{3-hydroxy-2-methyl-propoxy}-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl ester; tetrathiophosphoric acid diethyl ester 3-((3-hydroxy-2-methyl-propoxy)-{3-[{3-hydroxy-2-methyl-propoxy}-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl ester; methyl-phosphonodithioic acid S-ethyl ester S-[3-((3-hydroxy-2-methyl-propoxy)-{3-[{3-hydroxy-2-methyl-propoxy}-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl]ester; and, dimethyl-phosphinothioic acid S-[3-((3-hydroxy-2-methyl-propoxy)-{3-[{3-hydroxy-2-methyl-propoxy}-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy}-methyl-silanyl)-propyl]ester, and mixtures thereof.

- 40 14. The composition of any preceding claim, wherein the cyclic and bridging dialkoxy free and blocked mercaptofunctional silane is selected from the group consisting of octanethioic acid S-[3-((3-hydroxy-2-methyl-propoxy)-{3-[{3-[bis-(3-hydroxy-2-methyl-propoxy)-(3-mercaptopropyl)-silanyloxy]-2-methyl-propoxy}-(3-mercaptopropyl)-(3-hydroxy-2-methyl-propoxy)-silanyloxy]-2-methyl-propoxy)-(3-hydroxy-2-methyl-propoxy)-silanyloxypropyl]ester; octanethioic acid S-[3-((3-hydroxy-2-methyl-propoxy)-{3-[{3-[{3-hydroxy-2-methyl-propoxy}-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy}-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy}-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy)-methyl-silanyl]ester; octanethioic acid 3-(2-{3-[2-(3-mercaptopropyl)-5-methyl-[1,3,2]dioxasilinan-2-yloxy]-2-methyl-propoxy}-5-methyl-[1,3,2]dioxasilinan-2-yloxy)-propyl ester; octanethioic acid S-[3-(2-{3-[2-(3-mercaptopropyl)-4,4,6-trimethyl-[1,3,2]dioxasilinan-2-yloxy]-1,1-dimethyl-butoxy}-4,4,6-trimethyl-[1,3,2]dioxasilinan-2-yloxy)-1,1-dimethyl-butoxy]-4,4,6-trimethyl-[1,3,2]dioxasilinan-2-yloxy]-propyl]ester; octanethioic acid S-[3-(2-{3-[2-(3-mercaptopropyl)-4-methyl-[1,3,2]dioxasilinan-2-yloxy]-butoxy}-4-methyl-[1,3,2]dioxasilinan-2-yloxy)-propyl]ester; undecanethioic acid S-[3-(2-{3-[2-(3-mercaptopropyl)-4-methyl-[1,3,2]dioxasilinan-2-yloxy]-butoxy}-4-methyl-[1,3,2]dioxasilinan-2-yloxy)-4-methyl-[1,3,2]dioxasilinan-2-yloxy]-propyl]ester; heptanethioic acid S-[3-((3-hydroxy-2-methyl-propoxy)-(3-mercaptopropyl)-methyl-silanyloxy]-2-methyl-propoxy)-5-methyl-[1,3,2]dioxasilanep-2-yloxy]-propyl]ester; thiopropionic acid 3-{2-[3-(3-mercaptopropyl)-methyl-{2-methyl-3-[5-methyl-2-(3-propionylsulfanyl-propyl)-[1,3,2]dioxasilinan-2-yloxy]-propoxy}-silanyloxy]-2-methyl-propoxy}-5-methyl-[1,3,2]dioxasilanep-2-yloxy]-propyl ester; and octanethioic acid 3-{2-[3-(3-mercaptopropyl)-methyl-{2-methyl-3-[5-methyl-2-(3-octanoylsulfanyl-propyl)-[1,3,2]dioxasilinan-2-yloxy]-propoxy}-silanyloxy]-2-methyl-propoxy}-5-methyl-[1,3,2]dioxasilanep-2-yloxy]-propyl ester.

Patentansprüche


1. Organofunktionelle Silan-Zusammensetzung, umfassend wenigstens ein organofunktionelles Silan, das eine chemische Struktur aufweist, ausgewählt aus der Gruppe, bestehend aus:

5



und

10



worin :

- jedes Vorkommen von Y unabhängig ausgewählt ist aus einer mehrwertigen Spezies $(Q)_2A(=E)$, worin das Atom (A), das an ein ungesättigtes Heteroatom (E) angelagert ist, an einen Schwefel gebunden ist, welcher wiederum mittels einer Gruppe G^2 an ein Siliziumatom geknüpft ist;
- jedes Vorkommen von R unabhängig ausgewählt ist aus der Gruppe, bestehend aus Wasserstoff, geradem, ringförmigem oder verzweigtem Alkyl, der eine Ungesättigtheit enthalten kann oder auch nicht, Alkenylgruppen, Arylgruppen und Aralkylgruppen, worin jedes R, das anderes als Wasserstoff ist, von 1 bis 18 Kohlenstoffatome enthält;
- jedes Vorkommen von G^1 unabhängig ausgewählt ist aus der Gruppe, bestehend aus einwertigen und mehrwertigen Gruppen, die durch Substitution von Alkyl, Alkenyl, Aryl oder Aralkyl abgeleitet sind, worin G^1 von 1 bis 30 Kohlenstoffatome aufweisen kann, mit der Maßgabe, dass dann, wenn G^1 einwertig ist, G^1 Wasserstoff sein kann;
- jedes Vorkommen von G^2 unabhängig ausgewählt ist aus der Gruppe, bestehend aus zweiwertigen oder mehrwertigen Gruppen, die durch Substitution von Alkyl, Alkenyl, Aryl oder Aralkyl abgeleitet sind, worin G^2 von 1 bis 30 Kohlenstoffatome aufweisen kann;
- jedes Vorkommen von X unabhängig ausgewählt ist aus der Gruppe, bestehend aus -Cl, -Br, RO-, RC(=O)O-, $R_2C=NO$ -, R_2NO -, R_2N -, -R, $HO(R^0CR^0)_fO$, worin jedes R wie oben ist und jedes Vorkommen von R^0 unabhängig durch eines der oben für R aufgelisteten Elemente gegeben ist;
- jedes Vorkommen von Z^b , welches eine brückenbildende Struktur zwischen zwei Siliziumatomen bildet, unabhängig ausgewählt ist aus der Gruppe, bestehend aus $(-O)_{0,5}$ und $[-O(R^0CR^0)_fO]_{0,5}$, worin jedes Vorkommen von R^0 unabhängig durch eines der oben für R aufgelisteten Elemente gegeben ist;
- jedes Vorkommen von Z^c , welches eine ringförmige Struktur mit einem Siliziumatom bildet, unabhängig durch $-O(R^0CR^0)_fO$ - gegeben ist, worin jedes Vorkommen von R^0 unabhängig durch eines der oben für R aufgelisteten Elemente gegeben ist;
- jedes Vorkommen von Q unabhängig ausgewählt ist aus der Gruppe, bestehend aus Sauerstoff, Schwefel und $(-NR-)$;
- jedes Vorkommen von A unabhängig ausgewählt ist aus der Gruppe, bestehend aus Kohlenstoff, Schwefel, Phosphor und Sulfonyl;
- jedes Vorkommen von E unabhängig ausgewählt ist aus der Gruppe, bestehend aus Sauerstoff, Schwefel und $(-NR-)$;
- jedes Vorkommen der tiefgestellten Buchstaben a, b, c, f, j, k, m, n, p, q, r, s, u, v, w und z unabhängig gegeben ist durch:
- 45 a ist 0 bis 7;
- b ist 1 bis 3;
- c ist 1 bis 6;
- f ist 2 bis 15;
- j ist 0 bis 1, doch kann j nur dann 0 sein, wenn p 1 ist;
- 50 k ist 1 bis 2, mit der Maßgabe, dass dann, wenn A Kohlenstoff, Schwefel oder Sulfonyl ist, (i) $a+b=2$ und (ii) $k=2$ ist; dann, wenn A Phosphor ist, $a+b=3$ ist, sofern nicht sowohl (i) $c>1$ als auch (ii) $b=1$, in welchem Fall $a=c+1$; und dann, wenn A Phosphor ist, $k=2$ ist;
- m ist 1 bis 20;
- 55 n ist 1 bis 10;
- p ist 0 bis 5;
- q ist 0 bis 6;
- r ist 1 bis 3;

s ist 1 bis 3;
u ist 0 bis 3;
v ist 0 bis 3;
w ist 0 bis 1, mit der Maßgabe, dass $u+v+2w=3$ ist;

z ist 0 bis 3; und mit der Maßgabe, dass jede von den obigen Strukturen wenigstens eine hydrolysierbare Gruppe, Z^b oder Z^c , enthält, die eine difunktionelle Alkoxygruppe ist

-CH₂-, -CH₂CH₂-, -CH₂CH₂CH₂-, -CH₂CH₂CH₂CH₂CH₂CH₂CH₂CH₂-, -CH₂(CH₂)_iCH(CH₃)-, worin i 0 bis 16 ist; -CH₂CH₂C(CH₃)₂CH₂-; -CH₂CH(CH₃)CH₂-; -CH₂CH₂(C₆H₄)₂CH₂CH₂-; -CH₂CH₂(C₆H₄)CH(CH₃)-; -CH₂CH(CH₃)(C₆H₄)CH(CH₃)CH₂-; -CH₂CH₂CH₂CH₂-; -CH₂CH₂CH(CH₃)-; -CH₂CH(CH₂CH₃)-; -CH₂CH₂CH₂CH(CH₃)-; -CH₂CH₂CH(CH₂CH₃)-; -CH₂CH(CH₂CH₂CH₃)-; -CH₂CH(CH₂CH₂CH₃)-; -CH₂CH(CH₃)CH₂CH₂-; -CH₂CH(CH₃)CH(CH₃)-; -CH₂C(CH₃)(CH₂CH₃)-; -CH₂CH₂CH(CH₃)CH₂-; -CH₂CH₂C(CH₃)₂-; -CH₂CH[CH(CH₃)₂]-; -CH₂CH₂-Norbornyl-, -CH₂CH₂-Cyclohexyl; irgendeinem der Diradikale, gewinnbar aus von Norbornan, Cyclohexan, Cyclopantan, Tetrahydronyclopentadien oder Cyclooctadien durch Verlust zweier Wasserstoffatome; den Strukturen, ableitbar von Limonen, -CH₂CH(4-CH₃-1-C₆H₉)CH₃; -CH₂CH₂(VinylC₆H₉)CH₂CH₂- und -CH₂CH₂(VinylC₆H₉)CH(CH₃)-; -CH₂CH[CH₂CH₂CH-C(CH₃)₂]CH₂CH₃)-; -CH₂CH[CH₂CH₂CHC(CH₃)₂]CH(CH₃)-; -CH₂C[CH₂CH₂CH-C(CH₃)₂](CH₂CH₃)-; -CH₂CH₂CH[CH₂CH₂CHC(CH₃)₂]CH₂-; -CH₂CH₂(C-)(CH₃)[CH₂CH₂CH-C(CH₃)₂]-; -CH₂CH[CH(CH₃)[CH₂CH₂CH-C(CH₃)₂]]-; -CH₂CH(CH-CH₂)CH₂CH₂C(CH₃)₂-; -CH₂CH(CH-CH₂)CH₂CH₂CH[CH(CH₃)₂]-; -CH₂C(CH-CH₃)CH₂CH₂C(CH₃)₂-; -CH₂C(CH-CH₃)CH₂CH₂CH[CH(CH₃)₂]-; -CH₂CH₂C(CH₂)CH₂CH₂CH₂C(CH₃)₂-; -CH₂CH₂C(CH₂)CH₂CH₂CH₂C(CH₃)₂-; -CH₂CH-C(CH₃)₂CH₂-und- CH₂CH-C(CH₃)₂CH₂.


13. Zusammensetzung nach jedem vorangehenden Anspruch, worin das zyklische und/oder brückenbildende Dialkoxysilan ausgewählt ist aus der Gruppe, bestehend aus Thioessigsäure 2-(2-{3-[2-(3-Mercaptopropyl)-5-methyl-[1,3,2]dioxasilinan-2-yloxy]-2-methylpropoxy}-5-methyl-[1,3,2]dioxasilinan-2-yl)-ethylester; Thioessigsäure 3-(2-{3-[2-(3-Mercaptopropyl)-5-methyl-[1,3,2]dioxasilinan-2-yloxy]-2-methylpropoxy}-5-methyl-[1,3,2]dioxasilinan-2-yl)-propylester; Thiobuttersäure 3-(2-{3-[2-(3-Mercaptopropyl)-5-methyl-[1,3,2]dioxasilinan-2-yloxy]-2-methylpropoxy}-5-methyl-[1,3,2]dioxasilinan-2-yl)-propylester; Oktanthiosäure 3-(2-{3-[2-(3-Mercaptopropyl)-5-methyl-[1,3,2]dioxasilinan-2-yloxy]-2-methylpropoxy}-5-methyl-[1,3,2]dioxasilinan-2-yl)-propylester; Oktanthiosäure S-[3-(2-{3-[2-(3-Mercaptopropyl)-4,4,6-trimethyl-[1,3,2]dioxasilinan-2-yloxy]-1,1-dimethylbutoxy}-4,4,6-trimethyl-[1,3,2]dioxasilinan-2-yl)-propylester; Oktanthiosäure S-[3-(2-{3-[2-(3-Mercaptopropyl)-4-methyl-[1,3,2]dioxasilinan-2-yloxy]-4-methyl-[1,3,2]dioxasilinan-2-yl)-propylester; Undecanthiosäure S-[3-(2-{3-[2-(3-Mercaptopropyl)-4-methyl-[1,3,2]dioxasilinan-2-yloxy]-4-methyl-[1,3,2]dioxasilinan-2-yl)-butoxy]-4-methyl-[1,3,2]dioxasilinan-2-yl)-propylester; Heptanthiosäure S-[3-(3-Hydroxy-2-methylpropoxy)-{3-[{3-hydroxy-2-methylpropoxy)-(3-mercaptopropyl)-methylsilanyloxy]-2-methylpropoxy}-methylsilanyl]-propyl]ester; Heptanthiosäure S-[3-(2-{3-[{3-Hydroxy-2-methylpropoxy)-(3-mercaptopropyl)-methylsilanyloxy]-2-methylpropoxy}-5-methyl-[1,3,2]dioxasilepan-2-yl)-propyl]ester; Thiopropionsäure 3-{2-[3-{(3-Mercaptopropyl)-methyl-{2-methyl-3-[5-methyl-2-(3-propionylsulfanylpropyl)-[1,3,2]dioxasilinan-2-yloxy]-propoxy}-silanyloxy)-2-methylpropoxy]-5-methyl-[1,3,2]dioxasilepan-2-yl}-propylester; Oktanthiosäure 3-{2-[3-{(3-Mercaptopropyl)-methyl-{2-methyl-3-[5-methyl-2-(3-oktanoylsulfanylpropyl)-[1,3,2]dioxasilinan-2-yloxy]-propoxy}-silanyloxy)-2-methylpropoxy]-5-methyl-[1,3,2]dioxasilepan-2-yl}-propylester; Oktanthiosäure S-[3-(3-Hydroxy-2-methylpropoxy)-{3-[{3-[{3-hydroxy-2-methylpropoxy)-(3-mercaptopropyl)-methylsilanyloxy]-2-methylpropoxy}-methyl-(3-oktanoylsulfanylpropyl)-silanyloxy]-2-methylpropoxy}-methylsilanyl]-propyl]ester; Oktanthiosäure S-[3-(3-Hydroxy-2-methylpropoxy)-{3-[{3-[{3-hydroxy-2-methylpropoxy)-(3-mercaptopropyl)-methylsilanyloxy]-2-methylpropoxy}-3-mercaptopropyl)-methylsilanyloxy]-2-methylpropoxy}-3-mercaptopropyl)-methylsilanyloxy]-2-methylpropoxy)-methylsilanyl]-propyl]ester; Oktanthiosäure S-[3-(3-Hydroxy-2-methylpropoxy)-{3-[{3-[{3-hydroxy-2-methylpropoxy)-(3-mercaptopropyl)-methylsilanyloxy]-2-methylpropoxy}-3-mercaptopropyl)-methylsilanyloxy]-2-methylpropoxy}-methylsilanyl]-propyl]ester; Dimethylthiocarbamsäure S-[3-(3-Hydroxy-2-methylpropoxy)-{3-[{3-hydroxy-2-methylpropoxy)-(3-mercaptopropyl)-methylsilanyloxy]-2-methylpropoxy}-methylsilanyl]-propyl]ester; Dimethylthiocarbamsäure 3-(3-Hydroxy-2-methylpropoxy)-{3-[{3-hydroxy-2-methylpropoxy)-(3-mercaptopropyl)-methylsilanyloxy]-2-methylpropoxy}-methylsilanyl]-propylester; Dimethylthiocarbamsäure 3-(3-Hydroxy-2-methylpropoxy)-{3-[2-(3-mercaptopropyl)-5-methyl-[1,3,2]dioxasilinan-2-yloxy]-2-methylpropoxy}-methylsilanyl]-propylester; Thiocarbonsäure-O-ethylester S-[3-(3-Hydroxy-2-methylpropoxy)-{3-[{3-hydroxy-2-methylpropoxy)-(3-mercaptopropyl)-methylsilanyloxy]-2-methylpropoxy}-methylsilanyl]-propylester; Trithiocarbonsäureethylester 3-(3-Hydroxy-2-methylpropoxy)-{3-[{3-hydroxy-2-methylpropoxy)-(3-mercaptopropyl)-methylsilanyloxy]-2-methylpropoxy}-methylsilanyl]-propylester; Trithiocarbonsäureethylester 3-(3-Hydroxy-2-methylpropoxy)-{3-[{3-hydroxy-2-methylpropoxy)-(3-mercaptopropyl)-methylsilanyloxy]-2-methylpropoxy}-methylsilanyl]-propylester; Dithiobuttersäure 3-(3-Hydroxy-2-methylpropoxy)-{3-[{3-hydroxy-2-methylpropoxy)-(3-mercaptopropyl)-methylsilanyloxy]-2-methylpropoxy}-methylsilanyl]-propylester; Dithiobuttersäure 3-(3-Hydroxy-2-methylpropoxy)-{3-[2-(3-mercaptopropyl)-5-methyl-[1,3,2]dioxasilinan-2-yloxy]-2-methylpropoxy}-methylsilanyl]-propylester; Diethylthiocarbamsäure 3-(3-Hydroxy-2-methylpropoxy)-{3-[{3-hydroxy-2-methylpropoxy)-(3-mercaptopropyl)-methylsilanyloxy]-2-methylpropoxy}-methylsilanyl]-propylester; Diethylthiocarbamsäure 3-(3-Hydroxy-2-methylpropoxy)-{3-[{3-hydroxy-2-methylpropoxy)-(3-mercaptopropyl)-methylsilanyloxy]-2-methylpropoxy}-methylsilanyl]-propylester; Diethylthiocarbamsäure 3-(3-Hydroxy-2-methylpropoxy)-{3-[{3-hydroxy-2-methylpropoxy)-(3-mercaptopropyl)-methylsilanyloxy]-2-methylpropoxy}-methylsilanyl]-propylester; N-Methylthiobutyrimidsäure 3-(3-Hydroxy-2-methylpropoxy)-{3-[2-(3-mercaptopropyl)-5-methyl-[1,3,2]dioxasilinan-2-yloxy]-2-methylpropoxy}-methylsilanyl]-propylester; N-Methylthiobutyrimidsäure 3-(3-Hydroxy-2-methylpropoxy)-{3-[{3-hydroxy-2-methylpropoxy)-(3-mercaptopropyl)-methylsilanyloxy]-2-methylpropoxy}-methylsilanyl]-propylester; Thio-

phosphorsäure-O,O'-diethylester S-[3-((3-Hydroxy-2-methylpropoxy)-{3-[(3-hydroxy-2-methylpropoxy)-(3-mercaptopropyl)-methylsilanyloxy]-2-methylpropoxy}-methylsilanyl)-propyl]ester; Thiophosphorsäure-O-ethylester S-[3-((3-Hydroxy-2-methylpropoxy)-{3-[2-(3-mercaptopropyl)-5-methyl-[1,3,2]dioxasilinan-2-yloxy]-2-methylpropoxy}-methylsilanyl)-propyl]ester-O'-propylester; Dithiophosphorsäure-O-ethylester S-[3-((3-Hydroxy-2-methylpropoxy)-{3-[2-(3-mercaptopropyl)-5-methyl-[1,3,2]dioxasilinan-2-yloxy]-2-methylpropoxy}-methylsilanyl)-propyl]ester-O'-propylester; Trithiophosphorsäure-S,S'-diethylester S"--[3-((3-Hydroxy-2-methylpropoxy)-{3-[(3-hydroxy-2-methylpropoxy)-(3-mercaptopropyl)-methylsilanyloxy]-2-methylpropoxy}-methylsilanyl)-propyl]ester; Tetrathiophosphorsäurediethylester 3-((3-Hydroxy-2-methylpropoxy)-{3-[(3-hydroxy-2-methylpropoxy)-(3-mercaptopropyl)-methylsilanyloxy]-2-methylpropoxy}-methylsilanyl)-propylester; Tetrathiophosphorsäurediethylester 3-((3-Hydroxy-2-methylpropoxy)-{3-[(3-hydroxy-2-methylpropoxy)-(3-mercaptopropyl)-methylsilanyloxy]-2-methylpropoxy}-methylsilanyl)-propylester; Tetrathiophosphorsäureethylester 3-((3-Hydroxy-2-methylpropoxy)-{3-[2-(3-mercaptopropyl)-5-methyl-[1,3,2]dioxasilinan-2-yloxy]-2-methylpropoxy}-methylsilanyl)-propylester; Methylphosphon-dithiosäure-S-ethylester S-[3-((3-Hydroxy-2-methylpropoxy)-{3-[(3-hydroxy-2-methylpropoxy)-(3-mercaptopropyl)-methylsilanyloxy]-2-methylpropoxy}-methylsilanyl)-propyl]ester und Dimethylphosphinthsäure S-[3-((3-Hydroxy-2-methylpropoxy)-{3-[(3-hydroxy-2-methylpropoxy)-(3-mercaptopropyl)-methylsilanyloxy]-2-methylpropoxy}-methylsilanyl)-propyl]ester und Gemische davon.


14. Zusammensetzung nach jedem vorangehenden Anspruch, worin das zyklische und brückenbildende Dialkoxy-freie und blockierte mercaptofunktionelle Silan ausgewählt ist aus der Gruppe, bestehend aus Oktanthiosäure S-[3-((3-Hydroxy-2-methylpropoxy)-{3-[3-[(3-hydroxy-2-methylpropoxy)-(3-mercaptopropyl)-silanyloxy]-2-methylpropoxy}-3-mercaptopropyl)-(3-hydroxy-2-methylpropoxy)-silanyloxy]-2-methylpropoxy)-(3-hydroxy-2-methylpropoxy)-silanyl)-propyl]ester; Oktanthiosäure S-[3-((3-Hydroxy-2-methylpropoxy)-{3-[3-[(3-hydroxy-2-methylpropoxy)-(3-mercaptopropyl)-methylsilanyloxy]-2-methylpropoxy}-3-mercaptopropyl)-methylsilanyloxy]-2-methylpropoxy)-methylsilanyl)-propyl]ester; Oktanthiosäure 3-(2-{3-[2-(3-Mercaptopropyl)-5-methyl-[1,3,2]dioxasilinan-2-yloxy]-2-methylpropoxy}-5-methyl-[1,3,2]dioxasilinan-2-yl)-propylester; Oktanthiosäure S-[3-(2-{3-[2-(3-Mercaptopropyl)-4,4,6-trimethyl-[1,3,2]dioxasilinan-2-yloxy]-1,1-dimethylbutoxy}-4,4,6-trimethyl-[1,3,2]dioxasilinan-2-yl)-propyl]ester; Oktanthiosäure S-[3-(2-{3-[2-(3-Mercaptopropyl)-4-methyl-[1,3,2]dioxasilinan-2-yloxy]-butoxy}-4-methyl-[1,3,2]dioxasilinan-2-yl)-propyl]ester; Undecanthiosäure S-[3-(2-{3-[2-(3-Mercaptopropyl)-4-methyl-[1,3,2]dioxasilinan-2-yloxy]-butoxy}-4-methyl-[1,3,2]dioxasilinan-2-yl)-propyl]ester; Heptanthiosäure S-[3-((3-Hydroxy-2-methylpropoxy)-{3-[(3-hydroxy-2-methylpropoxy)-(3-mercaptopropyl)-methylsilanyloxy]-2-methylpropoxy}-methylsilanyl)-propyl]ester; Heptanthiosäure S-[3-(2-{3-[3-[(3-Hydroxy-2-methylpropoxy)-(3-mercaptopropyl)-methylsilanyloxy]-2-methylpropoxy}-methylsilanyl)-propyl]ester; Heptanthiosäure S-[3-(2-{3-[2-(3-Mercaptopropyl)-4-methyl-[1,3,2]dioxasilinan-2-yl)-propyl]ester]; Thiopropionsäure 3-{2-[3-(3-Mercaptopropyl)-methyl-{2-methyl-3-[5-methyl-2-(3-propionylsulfanylpropyl)-[1,3,2]dioxasilinan-2-yloxy]-propoxy}-silanyloxy}-2-methylpropoxy]-5-methyl-[1,3,2]dioxasilinan-2-yl)-propylester; und Oktanthiosäure 3-{2-[3-(3-Mercaptopropyl)-methyl-{2-methyl-3-[5-methyl-2-(3-oktanoylsulfanylpropyl)-[1,3,2]dioxasilinan-2-yloxy]-propoxy}-silanyloxy}-2-methylpropoxy]-5-methyl-[1,3,2]dioxasilinan-2-yl)-propylester.

Revendications

1. Composition de silanes organofonctionnels comprenant au moins un silane organofonctionnel présentant un e structure chimique choisie dans le groupe consistant en :



et



où :

chaque occurrence de Y est indépendamment choisie parmi une espèce polyvalente (Q_zA(=E), où l' atome (A) fixé à un hétéroatome insaturé (E) est fixé à un atome de soufre qui est à son tour lié par un groupe G² à un atome de silicium ;

chaque occurrence de R est indépendamment choisie dans le groupe consistant en un atome d'hydrogène, un groupe alkyle linéaire, cyclique ou ramifié qui peut ou peut ne pas contenir d'insaturation, les groupes alcényles, les groupes aryles et les groupes aralkyles, où chaque radical R autre qu'un atome d'hydrogène comporte de 1 à 18 atomes de carbone ;

5 chaque occurrence de G^1 est indépendamment choisie dans le groupe consistant en groupes monovalents et polyvalents dérivés par la substitution d'un groupe alkyle, alcényle, aryle ou aralkyle, où G^1 peut comporter de 1 à 30 atomes de carbone à condition que si G^1 est univalent, G^1 puisse être un atome d'hydrogène ;

10 chaque occurrence de G^2 est indépendamment choisie dans le groupe consistant en un groupe divalent ou polyvalent dérivé par la substitution d'un groupe alkyle, alcényle, aryle ou aralkyle, où G^2 peut comporter de 1 à 30 atomes de carbone ;

15 chaque occurrence de X est indépendamment choisie dans le groupe consistant en -Cl, -Br, RO-, RC(=O)O-, $R_2C=NO-$, R_2NO- , R_2N- , -R, HO(R^0CR^0)_fO, où chaque R est comme ci-dessus et chaque occurrence de R^0 est indépendamment donnée par un des membres énumérés ci-dessus pour R ;

20 chaque occurrence de Z^b , qui forme une structure de pontage entre deux atomes de silicium, est indépendamment choisie dans le groupe consistant en $(-O)_{0,5}$ et $[-O(R^0CR^0)_fO]_{0,5}$, où chaque occurrence de R^0 est indépendamment donnée par un des membres énumérés ci-dessus pour R ;

25 chaque occurrence de Z^c , qui forme une structure cyclique avec un atome de silicium, est indépendamment donnée par $-O(R^0CR^0)_fO-$ où chaque occurrence de R^0 est indépendamment donnée par un des membres énumérés ci-dessus pour R ;

30 chaque occurrence de Q est indépendamment choisie dans le groupe consistant en un atome d'oxygène, un atome de soufre et un groupe (-NR-) ;

35 chaque occurrence de A est indépendamment choisie dans le groupe consistant en un atome de carbone, un atome de soufre, un atome de phosphore et un groupe sulfonyle ;

40 chaque occurrence de E est indépendamment choisie dans le groupe consistant en un atome d'oxygène, un atome de soufre et un groupe (-NR-) ;

45 chaque occurrence des indices a, b, c, f, j, k, m, n, p, q, r, s, u, v, w et z est indépendamment donnée par a vaut de 0 à 7 ;

50 b vaut de 1 à 3 ;

55 c vaut de 1 à 6 ;

60 f vaut de 2 à 15,

65 j vaut de 0 à 1, mais j ne peut valoir 0 que si p vaut 1 ;

70 k vaut de 1 à 2, à condition que si A représente un atome de carbone, un atome de soufre ou un groupe sulfonyle, alors (i) a + b = 2 et (ii) k = 1 ; si A représente un atome de phosphore, alors a + b = 3 à moins que les deux relations (i) c > 1 et (ii) b = 1 soient satisfaites, auquel cas a = c + 1 ; et si A représente un atome de phosphore, alors k vaut 2 ;

75 m vaut de 1 à 20,

80 n vaut de 1 à 20,

85 p vaut de 0 à 5,

90 q vaut de 0 à 6 ;

95 r vaut de 1 à 3 ;

100 s vaut de 1 à 3 ;

105 u vaut de 0 à 3 ;

110 v vaut de 0 à 3 ; et

115 w vaut de 0 à 1, à condition que u + v + 2w = 3 ;

120 z vaut de 0 à 3 ; et

125 à condition que chacune des structures ci-dessus contienne au moins un groupe hydrolysable, Z^b ou Z^c , à savoir un groupe alcoxy difonctionnel.

- 130 2. Composition selon la revendication 1, où Y est choisi dans le groupe consistant en les groupes -C(=NR) - ; -SC(=NR) - ; -SC(=O) - ; (-NR)C(=O) - ; (-NR)C(=S) - ; -OC(=O) - ; -OC(=S) - ; -C(=O) - ; -SC(=S) - ; -C(=S) - ; -S(=O) - ; -S(=O) - ; -OS(=O) - ; (-NR)S(=O) - ; -SS(=O) - ; -OS(=O) - ; (-NR)S(=O) - ; -SS(=O) - ; (-S)2P(=O) - ; (-S)2P(=O) - ; -P(=O)(-O) - ; (-S)2P(=S) - ; -(-S)P(=S) - ; -P(=S)(-O) - ; (-NR)2P(=O) - ; (-NR)(-S)P(=O) - ; (-O)(-NR)P(=O) - ; (-O)(-S)P(=O) - ; (-O)2P(=O) - ; -(-O)P(=O) - ; (-NR)P(=O) - ; (-NR)2P(=S) - ; (-NR)(-S)P(=S) - ; (-O)(-NR)P(=S) - ; (-O)(-S)P(=S) - ; (-O)2P(=S) - ; -(-O)P(=S) - ; et -(-NR)P(=S) - , et est de préférence un groupe -C(=O) - .
- 135 3. Composition selon l'une quelconque des revendications précédentes, où G^1 possède un atome de carbone primaire fixé un groupe carbonyle et représente un groupe alkyle en C_1 à C_{18} .
- 140 4. Composition selon l'une quelconque des revendications précédentes, où G^1 représente un groupe monovalent à chaîne linéaire dérivé d'un groupe alkyle en C_3 à C_{10} , de préférence un groupe alkyle en C_6 à C_8 .
- 145 5. Composition selon l'une quelconque des revendications précédentes, où G^1 représente un groupe $CH_3(CH_2)_g-$ et

g vaut de 1 à 29, et est de préférence choisi dans le groupe consistant en les groupes méthyle, éthyle, propyle, hexyle, heptyle, benzyle, phényle, octyle et dodécyle.

14. Composition selon l'une quelconque des revendications précédentes, où le groupe dialcoxy silane mercaptofonctionnel libre et bloqué cyclique et de pontage est choisi dans le groupe consistant en ester S-[3-((3-hydroxy-2-méthyl-propoxy)-{3-[{3-[bis-(3-hydroxy-2-méthyl-propoxy)-(3-mercaptopropyl)-silanyloxy]-2-méthyl-propoxy}-{3-mercaptopropyl)-(3-hydroxy-2-méthyl-propoxy)-silanyloxy]-2-méthyl-propoxy}-{3-hydroxy-2-méthyl-propoxy)-silanyl)-propylique] de l'acide octanethioïque; ester S-[3-((3-hydroxy-2-méthyl-propoxy)-{3-[{3-[{3-hydroxy-2-méthyl-propoxy)-(3-mercaptopropyl)-méthyl-silanyloxy]-2-méthyl-propoxy}-{3-mercaptopropyl)-méthyl-silanyloxy]-2-méthyl-propoxy}-{méthyl-silanyl)-propylique] de l'acide octanethioïque; ester 3-(2-{3-[2-(3-mercaptopropyl)-5-méthyl-[1,3,2]dioxasilinan-2-yloxy]-2-méthyl-propoxy}-5-méthyl-[1,3,2]dioxasilinan-2-yl)-propylique de l'acide octanethioïque; ester S-[3-(2-{3-[2-(3-mercaptopropyl)-4,4,6-triméthyl-[1,3,2]dioxasilinan-2-yloxy]-1,1-diméthyl-butoxy}-4,4,6-triméthyl-[1,3,2]dioxasilinan-2-yl)-propylique] de l'acide octanethioïque; ester S-[3-(2-{3-[2-(3-mercaptopropyl)-4-méthyl[1,3,2]dioxasilinan-2-yloxy]-butoxy}-4-méthyl-[1,3,2]dioxasilinan-2-yl)-propylique] de l'acide octanethioïque; ester S-[3-(2-{3-[2-(3-mercaptopropyl)-4-méthyl-[1,3,2]dioxasilinan-2-yloxy]-butoxy}-4-méthyl-[1,3,2]dioxasilinan-2-yl)-propylique] de l'acide undécanethioïque; ester S-[3-((3-hydroxy-2-méthyl-propoxy)-(3-mercaptopropyl)-méthyl-silanyloxy]-2-méthyl-propoxy)-méthyl-silanyl)-propylique de l'acide heptanethioïque; ester S-[3-(2-{3-[{3-hydroxy-2-méthyl-propoxy)-(3-mercaptopropyl)-méthyl-silanyloxy]-2-méthyl-propoxy}-5-méthyl-[1,3,2]dioxasilépan-2-yl)-propylique] de l'acide heptanethioïque; ester 3-{2-[3-((3-mercaptopropyl)-méthyl-{2-méthyl-3-[5-méthyl-2-(3-propionylsulfanyl-propyl)-[1,3,2]dioxasilinan-2-yloxy]-2-méthyl-propoxy}-5-méthyl-[1,3,2]dioxasilépan-2-yl)-propylique de l'acide thiopropionique; et ester 3-{2-[3-((3-mercaptopropyl)-méthyl-{2-méthyl-3-[5-méthyl-2-(3-octanoylsulfanyl-propyl)-[1,3,2]dioxasilinan-2-yloxy]-propoxy}-silanyloxy)-2-méthyl-propoxy]-5-méthyl-[1,3,2]dioxasilépan-2-yl)-propylique de l'acide octanethioïque.

25

30

35

40

45

50

55

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 6127468 A [0004]
- US 6414061 B [0004]
- US 6528673 B [0004]
- US 20050245753 A [0005]
- US 10410305 A [0005]
- US 11208367 B [0005]
- US 6849754 B [0005]
- US 6635700 B [0006]
- US 20040014840 A [0006]
- US 20030199619 A1 [0007]
- AU 1008297 A [0101]
- US 5116886 A [0115]
- EP 631982 A [0115]

Non-patent literature cited in the description

- **M. G. VORONKOV ; V. P. MILESHKEVICH ; YU. A. YUZHELEVSKII.** The Siloxane Bond, Physical Properties and Chemical Transformations. Consultants Bureau, a division of Plenum Publishing Company, 1978 [0069]
- **J. VAN ALPHEN.** Rubber Chemicals. Plastics and Rubber Research Institute TNO, 1973 [0100]
- The Vanderbilt Rubber Handbook. Vanderbilt Company, Inc, 1990 [0112]
- Manual For The Rubber Industry. 1993 [0112]
- *Journal of the American Chemical Society*, 1930, vol. 60, 304 [0118]
- **WINSLOW et al.** *ASTM bulletin*, 1959, 39 [0119]