



(11) **EP 2 336 289 A1**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
22.06.2011 Bulletin 2011/25

(51) Int Cl.:
C11D 11/02 (2006.01)

(21) Application number: **09180008.6**

(22) Date of filing: **18.12.2009**

(84) Designated Contracting States:
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL
PT RO SE SI SK SM TR**

(71) Applicant: **The Procter & Gamble Company
Cincinnati, OH 45202 (US)**

(72) Inventors:
• **Cardozo, Larry Savio
Newcastle upon Tyne, NE12 8WE (GB)**
• **Tantawy, Hossam Hassan
Morpeth, Northumberland NE61 3JT (GB)**

• **Lickiss, James Robert
Morpeth, Northumberland NE65 7NS (GB)**
• **Somerville Roberts, Nigel Patrick
Newcastle upon Tyne, NE20 9AU (GB)**

(74) Representative: **Howard, Phillip Jan et al
Procter & Gamble
Technical Centres Limited
Whitley Road
Longbenton
Newcastle upon Tyne NE12 9TS (GB)**

(54) **A spray-drying process**

(57) The present invention relates to a process for preparing a spray-dried detergent powder comprising: (i) deterative surfactant; and (ii) other detergent ingredients; wherein the process comprises the steps of: (a) forming an aqueous detergent slurry in a mixer; (b) transferring the aqueous detergent slurry from the mixer to a pipe leading through a first pump and then through a second pump to a spray nozzle; (c) contacting a detergent ingredient to the aqueous detergent slurry in the pipe after the

first pump and before the second pump to form a mixture; (d) spraying the mixture through the spray nozzle into a spray-drying tower; and (e) spray-drying the mixture to form a spray-dried powder, wherein the pressure drop between (i) the pressure in the pipe at the outlet of the first pump to (ii) the pressure in the pipe at the inlet to the second pump is less than 8×10^5 Pa.

EP 2 336 289 A1

Description

FIELD OF THE INVENTION

5 **[0001]** The present invention relates to a spray-drying process.

BACKGROUND OF THE INVENTION

10 **[0002]** Spray-drying is the standard method for manufacturing laundry detergent base powder. Typically, detergent ingredients are mixed together to form an aqueous detergent slurry in a mixer, such as a crutcher mixer. This slurry is then transferred along a pipe through a first low pressure pump and then through a second high pressure pump to a spray nozzle, and the slurry is sprayed into a spray-drying tower, and spray-dried to form a spray-dried powder.

15 **[0003]** The low pressure pump needs to be positioned as close to the mixer, such as crutcher mixer, as possible. This is to avoid starvation of the low pressure pump and to ensure consistent feed to the low pressure pump. However, it is also desirable to limit the length of the portion of the pipe that needs to handle the outlet pressure from the high pressure pump due to the cost and complexity of the high pressure capable pipe work. In other words, it is desirable to position the high pressure pump as close as possible to the spray nozzle. This means that typically there is a need to have a significant distance between the low pressure pump and the high pressure pump. However, this significant distance results in a significant pressure drop along the portion of the pipe between the two pumps. This is problematic because
20 the high pressure pump has a minimum inlet feed pressure to avoid starvation of the high pressure pump, so one is constrained by how far apart (i.e. the length of connecting pipe) these two pumps can be. This in turns results in a dichotomy of process requirements.

25 **[0004]** The inventors have overcome this problem by introducing a stream of detergent ingredient, especially viscosity increasing detergent ingredients such as alkyl benzene sulphonic acid, into the pipe between the low pressure pump and high pressure pump, and carefully controlling its flow rate and point of addition so as to control the pressure drop between the two pumps. This minimizes the pressure drop between the two pumps, enabling the two pumps to be placed further apart (i.e. allowing the length of the connecting pipe between the two pumps to be increased) whilst maintaining efficient operation of the pumps.

30 SUMMARY OF THE INVENTION

[0005] The present invention relates to a process according to claim 1.

DETAILED DESCRIPTION OF THE INVENTION

35 A process for preparing a spray-dried detergent powder

40 **[0006]** The process typically comprises the steps of: (a) forming an aqueous detergent slurry in a mixer; (b) transferring the aqueous detergent slurry from the mixer to a pipe leading through a first pump and then through a second pump to a spray nozzle; (c) contacting a detergent ingredient to the aqueous detergent slurry in the pipe after the first pump and before the second pump to form a mixture; (d) spraying the mixture through the spray nozzle into a spray-drying tower; and (e) spray-drying the mixture to form a spray-dried powder, wherein the pressure drop between (i) the pressure in the pipe at the outlet of the first pump to (ii) the pressure in the pipe at the inlet to the second pump is less than 8×10^5 Pa., preferably less than 6×10^5 Pa., or less than 5×10^5 Pa., or less than 4×10^5 Pa., or less than 3×10^5 Pa., or less than 2×10^5 Pa., or even preferably less than 1×10^6 Pa. The pressure in the pipe is typically measured by standard pressure gauges present in the wall of the pipe at the appropriate position (i.e. at the outlet of the first pump, and at the inlet of the second pump).

[0007] Step (a): the aqueous detergent slurry can be formed by mixing in any suitable vessel, such as mixer, in the standard manner. Suitable mixers include vertical mixers, slurry mixers, tank agitators, crutcher mixers and the like.

50 **[0008] Step (b):** the aqueous detergent slurry is transferred from the mixer through at least one pump to a spray nozzle. Typically, the aqueous detergent slurry is transferred in a pipe. The aqueous slurry is typically transferred through an intermediate storage vessel such as a drop tank, for example when the process is semi-continuous. Alternatively, the process can be a continuous process, in which case no intermediate storage vessel is required. The aqueous detergent slurry is transferred through at least one pump, preferably at least two, or even at least three or more pumps, although one or two, preferably two pumps may be preferred. Typically, when two or more pumps are used, the first pump is a low pressure pump, such as a pump that is capable of generating a pressure of from 3×10^5 to 1×10^6 Pa, and the second pump is a high pressure pump, such as a pump that is capable of generating a pressure of from 2×10^6 to 1×10^7 Pa. Optionally, the aqueous detergent slurry is transferred through a disintegrator, such as disintegrators supplied

by Hosakawa Micron. The disintegrator can be positioned before the pump, or after the pump. If two or more pumps are present, then the disintegrator can also be positioned between the pumps. Typically, the pumps, disintegrators, intermediate storage vessels, if present, are all in series configuration. However, some equipment may be in a parallel configuration. A suitable spray nozzle is a Spray Systems T4 Nozzle.

[0009] Step (c): a detergent ingredient is contacted to the aqueous detergent slurry in the pipe after the first pump and before the second pump to form a mixture. Suitable detergent ingredients for use in step (c) are described in more detail later in the description. Preferably, the mixture formed in step (c) comprises from 20wt% to 35wt% water. The pressure drop between the first and second pumps can be controlled by controlling the flow rate of the detergent ingredient into the pipe, and the viscosity of the detergent ingredient and/or resultant mixture formed in step (c). The pressure drop between the first and second pumps can be controlled by controlling the point of addition of the detergent ingredient between the two pumps. Preferably, the detergent ingredient is contacted to the aqueous detergent slurry at a point in the pipe that is nearer to the second pump than the first pump. It may even be preferred for the detergent ingredient to be contacted to the aqueous detergent slurry in the pipe just prior to the entrance to the second pump.

[0010] The flow rate of the aqueous detergent slurry along the pipe between the first and second pump prior to step (c) is typically in the range of from 800kg/hour to 2,000kg/hour, and the flow rate of the detergent ingredient into the pipe during step (c) is typically in the range of from 100kg/hour to 400kg/hour. The ratio of: (i) the flow rate of the aqueous detergent slurry along the pipe between the first and second pump prior to step (c) to (ii) the flow rate of the detergent ingredient into the pipe during step (c) is typically in the range of from 3:1 to 30:1, preferably 3:1 to 20:1, or even from 4:1 to 10:1. The mixture formed in step (c) typically has a viscosity of from 0.8 Pas to 8 Pas, preferably from 1 Pas to 5 Pas. The viscosity is typically measured using a rheometer at a shear rate of 100s^{-1} and at a temperature of 70°C .

[0011] Step (d): the mixture formed in step (c) is sprayed through the spray nozzle into a spray-drying tower. Preferably, the mixture is at a temperature of from 60°C to 130°C when it is sprayed through the spray nozzle into a spray-drying tower. Suitable spray-drying towers are cocurrent or counter-current spray-drying towers. The mixture is typically sprayed at a pressure of from 6×10^6 Pa to 1×10^7 Pa.

[0012] Step (e): the mixture is spray-dried to form a spray-dried powder. Preferably, the exhaust air temperature is in the range of from 60°C to 100°C .

Aqueous detergent slurry

[0013] The aqueous detergent slurry typically comprises detergent ingredients, such as alkalinity source, polymer, builder, deterative surfactant, filler salts and mixtures thereof. However, it may be especially preferred for the aqueous detergent slurry to comprise low levels, or even be free, of deterative surfactant. It may also be especially preferred for the aqueous detergent slurry to comprise low levels, or even be free, of builder. Preferably, the aqueous detergent slurry comprises from 0wt% to 5wt%, or to 4wt%, or to 3wt%, or to 2wt%, or to 1wt% deterative surfactant. It may even be preferred for the aqueous detergent slurry to be essentially free of deterative surfactant. By essentially free of it is typically meant herein to mean: "comprises no deliberately added".

[0014] It may be highly advantageous for the aqueous detergent slurry to comprise low levels, or even be completely free, of deterative surfactants that are difficult to process when in slurry form and exposed to the residency time and process conditions typically experienced by an aqueous detergent slurry during a conventional spray-drying process. Such deterative surfactants include mid-chain branched deterative surfactants, especially mid-chain branched anionic deterative surfactants, and/or alkoxylated deterative surfactants, especially alkoxylated anionic deterative surfactants. Preferably, the aqueous detergent slurry formed in step (a) comprises from 0wt% to 2wt%, preferably to 1wt% mid-chain branched deterative surfactant. Preferably, the aqueous detergent slurry formed in step (a) is essentially free from mid-chain branched deterative surfactant. By essentially free from, it is typically meant herein to mean: "comprises no deliberately added". Preferably, the aqueous detergent slurry formed in step (a) comprises from 0wt% to 2wt%, preferably to 1wt% alkoxylated deterative surfactant. Preferably, the aqueous detergent slurry formed in step (a) is essentially free from alkoxylated deterative surfactant. By essentially free from, it is typically meant herein to mean: "comprises no deliberately added".

[0015] Preferably, the aqueous detergent slurry comprises from 0wt% to 10wt%, or to 9wt%, or to 8wt%, or to 7wt%, or to 6wt%, or to 5wt%, or to 4wt%, or to 3wt%, or to 2wt%, or to 1wt% zeolite builder. Preferably, the aqueous detergent slurry is essentially free of zeolite builder.

[0016] Preferably, the aqueous detergent slurry comprises from 0wt% to 10wt%, or to 9wt%, or to 8wt%, or to 7wt%, or to 6wt%, or to 5wt%, or to 4wt%, or to 3wt%, or to 2wt%, or to 1wt% phosphate builder. Preferably, the aqueous detergent slurry is essentially free of phosphate builder.

[0017] Preferably the aqueous detergent slurry is alkaline. Preferably, the aqueous detergent slurry has a pH of greater than 7.0, preferably greater than 7.7, or greater than 8.1, or even greater than 8.5, or greater than 9.0, or greater than 9.5, or greater than 10.0, or even greater than 10.5, and preferably to 14, or to 13, or to 12.

[0018] Preferably, the aqueous detergent slurry has a viscosity of from 0.1 Pas to 0.5 Pas. The viscosity is typically

measured using a rheometer at a shear of 100s^{-1} and a temperature of 70°C .

Spray-dried detergent powder

[0019] The spray-dried detergent powder typically comprises: (i) deterative surfactant; and (ii) other detergent ingredients. Highly preferably, the spray-dried detergent powder comprises:

(a) from 0wt% to 10wt% zeolite builder; (b) from 0wt% to 10wt% phosphate builder; and (c) optionally from 0wt% to 15wt% silicate salt.

[0020] The spray-dried detergent powder is suitable for any detergent application, for example: laundry, including automatic washing machine laundering and hand laundering, and even bleach and laundry additives; hard surface cleaning; dish washing, especially automatic dish washing; carpet cleaning and freshening. However, highly preferably, the spray-dried detergent powder is a spray-dried laundry detergent powder.

[0021] The spray-dried detergent powder can be a fully formulated detergent product, such as a fully formulated laundry detergent product, or it can be combined with other particles to form a fully formulated detergent product, such as a fully formulated laundry detergent product. The spray-dried laundry detergent particles may be combined with other particles such as: enzyme particles; perfume particles including agglomerates or extrudates of perfume microcapsules, and perfume encapsulates such as starch encapsulated perfume accord particles; surfactant particles, such as non-ionic deterative surfactant particles including agglomerates or extrudates, anionic deterative surfactant particles including agglomerates and extrudates, and cationic deterative surfactant particles including agglomerates and extrudates; polymer particles including soil release polymer particles, cellulosic polymer particles; filler particles including sulphate salt particles, especially sodium sulphate particles; buffer particles including carbonate salt and/or silicate salt particles, preferably a particle comprising carbonate salt and silicate salt such as a sodium carbonate and sodium silicate co-particle, and particles and sodium bicarbonate; other spray-dried particles; fluorescent whitening particles; aesthetic particles such as coloured noodles or needles or lamellae particles; bleaching particles such as percarbonate particles, especially coated percarbonate particles, including carbonate and/or sulphate coated percarbonate, silicate coated percarbonate, borosilicate coated percarbonate, sodium perborate coated percarbonate; bleach catalyst particles, such as transition metal catalyst bleach particles, and imine bleach boosting particles; performed peracid particles; hueing dye particles; and any mixture thereof.

[0022] In a highly preferred embodiment of the present invention, the spray-dried detergent powder comprises: (a) from 15wt% to 30wt% deterative surfactant; (b) from 0wt% to 4wt% zeolite builder; (c) from 0wt% to 4wt% phosphate builder; and (d) optionally from 0wt% to 15wt% silicate salt.

[0023] The spray-dried powder typically comprises from 0wt% to 7wt%, preferably from 1wt% to 5wt%, and preferably from 2wt% to 3wt% water.

[0024] The spray-dried particle is typically flowable, typically having a cake strength of from 0 N to 20 N, preferably from 0 N to 15 N, more preferably from 0 N to 10 N, most preferably from 0 N to 5 N. The method to determine the cake strength is described in more detail elsewhere in the description.

Method for measuring cake strength

[0025] A smooth plastic cylinder of internal diameter 6.35 cm and length 15.9 cm is supported on a suitable base plate. A 0.65 cm hole is drilled through the cylinder with the centre of the hole being 9.2cm from the end opposite the base plate.

[0026] A metal pin is inserted through the hole and a smooth plastic sleeve of internal diameter 6.35cm and length 15.25 cm is placed around the inner cylinder such that the sleeve can move freely up and down the cylinder and comes to rest on the metal pin. The space inside the sleeve is then filled (without tapping or excessive vibration) with the spray-dried powder such that the spray-dried powder is level with the top of the sleeve. A lid is placed on top of the sleeve and a 5 kg weight placed on the lid. The pin is then pulled out and the spray-dried powder is allowed to compact for 2 minutes. After 2 minutes the weight is removed, the sleeve is lowered to expose the powder cake with the lid remaining on top of the powder.

[0027] A metal probe is then lowered at 54 cm/min such that it contacts the centre of the lid and breaks the cake. The maximum force required to break the cake is recorded and is the result of the test. A cake strength of 0 N refers to the situation where no cake is formed.

Detergent ingredient suitable for contacting to the aqueous detergent slurry in step (c)

[0028] Any detergent ingredient can be used for contacting the aqueous detergent slurry in step (c). However, highly

preferred detergent ingredients are selected from: alkyl benzene sulphonic acid or salt thereof; polymer; alkoxyated deterative surfactant; sodium hydroxide; mid-chain branched deterative surfactant; cationic deterative surfactant; and mixtures thereof.

[0029] Preferably, in step (c) the detergent ingredient comprises alkyl benzene sulphonic acid or salt thereof. Preferably, in step (c) the detergent ingredient comprises polymer. Preferably, in step (c) the detergent ingredient comprises alkoxyated deterative surfactant. Preferably, in step (c) the detergent ingredient comprises sodium hydroxide. Preferably, in step (c) the detergent ingredient comprises mid-chain branched deterative surfactant. Preferably, in step (c) the detergent ingredient comprises cationic deterative surfactant.

Deterative surfactant

[0030] Suitable deterative surfactants include anionic deterative surfactants, non-ionic deterative surfactant, cationic deterative surfactants, zwitterionic deterative surfactants and amphoteric deterative surfactants.

[0031] Preferred anionic deterative surfactants include sulphate and sulphonate deterative surfactants.

[0032] Preferred sulphonate deterative surfactants include alkyl benzene sulphonate, preferably C₁₀₋₁₃ alkyl benzene sulphonate. Suitable alkyl benzene sulphonate (LAS) is obtainable, preferably obtained, by sulphonating commercially available linear alkyl benzene (LAB); suitable LAB includes low 2-phenyl LAB, such as those supplied by Sasol under the tradename Isochem® or those supplied by Petresa under the tradename Petrelab®, other suitable LAB include high 2-phenyl LAB, such as those supplied by Sasol under the tradename Hyblene®. A suitable anionic deterative surfactant is alkyl benzene sulphonate that is obtained by DETAL catalyzed process, although other synthesis routes, such as HF, may also be suitable.

[0033] Preferred sulphate deterative surfactants include alkyl sulphate, preferably C₈₋₁₈ alkyl sulphate, or predominantly C₁₂ alkyl sulphate.

[0034] Another preferred sulphate deterative surfactant is alkyl alkoxyated sulphate, preferably alkyl ethoxyated sulphate, preferably a C₈₋₁₈ alkyl alkoxyated sulphate, preferably a C₈₋₁₈ alkyl ethoxyated sulphate, preferably the alkyl alkoxyated sulphate has an average degree of alkoxylation of from 0.5 to 20, preferably from 0.5 to 10, preferably the alkyl alkoxyated sulphate is a C₈₋₁₈ alkyl ethoxyated sulphate having an average degree of ethoxylation of from 0.5 to 10, preferably from 0.5 to 7, more preferably from 0.5 to 5 and most preferably from 0.5 to 3.

[0035] The alkyl sulphate, alkyl alkoxyated sulphate and alkyl benzene sulphonates may be linear or branched, substituted or un-substituted.


[0036] Suitable non-ionic deterative surfactants are selected from the group consisting of: C_{8-C18} alkyl ethoxylates, such as, NEODOL® non-ionic surfactants from Shell; C_{6-C12} alkyl phenol alkoxyates wherein preferably the alkoxyate units are ethyleneoxy units, propyleneoxy units or a mixture thereof; C_{12-C18} alcohol and C_{6-C12} alkyl phenol condensates with ethylene oxide/propylene oxide block polymers such as Pluronic® from BASF; C_{14-C22} mid-chain branched alcohols; C_{14-C22} mid-chain branched alkyl alkoxyates, preferably having an average degree of alkoxylation of from 1 to 30; alkylpolysaccharides, preferably alkylpolyglycosides; polyhydroxy fatty acid amides; ether capped poly(oxyalkylated) alcohol surfactants; and mixtures thereof.

[0037] Preferred non-ionic deterative surfactants are alkyl polyglucoside and/or an alkyl alkoxyated alcohol.

[0038] Preferred non-ionic deterative surfactants include alkyl alkoxyated alcohols, preferably C₈₋₁₈ alkyl alkoxyated alcohol, preferably a C₈₋₁₈ alkyl ethoxyated alcohol, preferably the alkyl alkoxyated alcohol has an average degree of alkoxylation of from 1 to 50, preferably from 1 to 30, or from 1 to 20, or from 1 to 10, preferably the alkyl alkoxyated alcohol is a C₈₋₁₈ alkyl ethoxyated alcohol having an average degree of ethoxylation of from 1 to 10, preferably from 1 to 7, more preferably from 1 to 5 and most preferably from 3 to 7. The alkyl alkoxyated alcohol can be linear or branched, and substituted or un-substituted.

[0039] Suitable cationic deterative surfactants include alkyl pyridinium compounds, alkyl quaternary ammonium compounds, alkyl quaternary phosphonium compounds, alkyl ternary sulphonium compounds, and mixtures thereof.

[0040] Preferred cationic deterative surfactants are quaternary ammonium compounds having the general formula:



wherein, R is a linear or branched, substituted or unsubstituted C₆₋₁₈ alkyl or alkenyl moiety, R₁ and R₂ are independently selected from methyl or ethyl moieties, R₃ is a hydroxyl, hydroxymethyl or a hydroxyethyl moiety, X is an anion which provides charge neutrality, preferred anions include: halides, preferably chloride; sulphate; and sulphonate. Preferred cationic deterative surfactants are mono-C₆₋₁₈ alkyl mono-hydroxyethyl di-methyl quaternary ammonium chlorides. Highly preferred cationic deterative surfactants are mono-C₈₋₁₀ alkyl mono-hydroxyethyl di-methyl quaternary ammonium chloride, mono-C₁₀₋₁₂ alkyl mono-hydroxyethyl di-methyl quaternary ammonium chloride and mono-C₁₀ alkyl mono-hydroxyethyl di-methyl quaternary ammonium chloride.

Polymer

[0041] The polymer can be any suitable polymer.

[0042] One suitable polymer is an amphiphilic graft polymer (AGP). Suitable AGPs are obtainable by grafting a polyalkylene oxide of number average molecular weight from about 2,000 to about 100,000 with vinyl acetate, which may be partially saponified, in a weight ratio of polyalkylene oxide to vinyl acetate of about 1:0.2 to about 1:10. The vinyl acetate may, for example, be saponified to an extent of up to 15%. The polyalkylene oxide may contain units of ethylene oxide, propylene oxide and/or butylene oxide. Selected embodiments comprise ethylene oxide.

[0043] In some embodiments the polyalkylene oxide has a number average molecular weight of from about 4,000 to about 50,000, and the weight ratio of polyalkylene oxide to vinyl acetate is from about 1:0.5 to about 1:6. A material within this definition, based on polyethylene oxide of molecular weight 6,000 (equivalent to 136 ethylene oxide units), containing approximately 3 parts by weight of vinyl acetate units per 1 part by weight of polyethylene oxide, and having itself a molecular weight of about 24,000, is commercially available from BASF as Sokalan HP22.

[0044] Suitable AGPs may be present in the detergent composition at weight percentages of from about 0 to about 5%, preferably from about above 0% to about 4%, or from about 0.5% to about 2%. In some embodiments, the AGP is present at greater than about 1.5wt%. The AGPs are found to provide excellent hydrophobic soil suspension even in the presence of cationic coacervating polymers.

[0045] Preferred AGPs are based on water-soluble polyalkylene oxides as a graft base and side chains formed by polymerization of a vinyl ester component. These polymers having an average of less than or equal to one graft site per 50 alkylene oxide units and mean molar masses (Mw) of from about 3000 to about 100,000.

[0046] Another suitable polymer is polyethylene oxide, preferably substituted or unsubstituted.

[0047] Another suitable polymer is cellulosic polymer, preferably selected from alkyl cellulose, alkyl alkoxyalkyl cellulose, carboxylalkyl cellulose, alkyl carboxyalkyl, more preferably selected from carboxymethyl cellulose (CMC) including blocky CMC, methyl cellulose, methyl hydroxyethyl cellulose, methyl carboxymethyl cellulose, and mixtures thereof.

[0048] Other suitable polymers are soil release polymers. Suitable polymers include polyester soil release polymers. Other suitable polymers include terephthalate polymers, polyurethanes, and mixtures thereof. The soil release polymers, such as terephthalate and polyurethane polymers can be hydrophobically modified, for example to give additional benefits such as sudsing.

[0049] Other suitable polymers include polyamines, preferably polyethylene imine polymers, preferably having ethylene oxide and/or propylene oxide functionalized blocks

[0050] Other suitable polymers include synthetic amino containing amphoteric/and/or zwitterionic polymers, such as those derived from hexamethylene diamine.

[0051] Another suitable polymer is a polymer that can be co-micellized by surfactants, such as the AGP described in more detail above.

[0052] Other suitable polymers include carboxylate polymers, such as polyacrylates, and acrylate/maleic co-polymers and other functionalized polymers such as styrene acrylates.

[0053] Other suitable polymers include silicone, including amino-functionalised silicone.

[0054] Other suitable polymers include polysaccharide polymers such as celluloses, starches, lignins, hemicellulose, and mixtures thereof.

[0055] Other suitable polymers include cationic polymers, such as deposition aid polymers, such as cationically modified cellulose such as cationic hydroxy ethylene cellulose, cationic guar gum, cationic starch, cationic acrylamides and mixtures thereof.

[0056] Mixtures of any of the above described polymers can be used herein.

Zeolite builder

[0057] Suitable zeolite builder includes include zeolite A, zeolite P and zeolite MAP. Especially suitable is zeolite 4A.

Phosphate builder

[0058] A typical phosphate builder is sodium tri-polyphosphate.

Silicate salt

[0059] A suitable silicate salt is sodium silicate, preferably 1.6R and/or 2.0R sodium silicate.

Other detergent ingredients

[0060] The composition typically comprises other detergent ingredients. Suitable detergent ingredients include: transition metal catalysts; imine bleach boosters; enzymes such as amylases, carbohydrases, cellulases, laccases, lipases, bleaching enzymes such as oxidases and peroxidases, proteases, pectate lyases and mannanases; source of peroxygen such as percarbonate salts and/or perborate salts, preferred is sodium percarbonate, the source of peroxygen is preferably at least partially coated, preferably completely coated, by a coating ingredient such as a carbonate salt, a sulphate salt, a silicate salt, borosilicate, or mixtures, including mixed salts, thereof; bleach activator such as tetraacetyl ethylene diamine, oxybenzene sulphonate bleach activators such as nonanoyl oxybenzene sulphonate, caprolactam bleach activators, imide bleach activators such as N-nonanoyl-N-methyl acetamide, preformed peracids such as N,N-phthaloylamino peroxyacetic acid, nonylamido peroxyadipic acid or dibenzoyl peroxide; suds suppressing systems such as silicone based suds suppressors; brighteners; hueing agents; photobleach; fabric-softening agents such as clay, silicone and/or quaternary ammonium compounds; flocculants such as polyethylene oxide; dye transfer inhibitors such as polyvinylpyrrolidone, poly 4-vinylpyridine N-oxide and/or co-polymer of vinylpyrrolidone and vinylimidazole; fabric integrity components such as oligomers produced by the condensation of imidazole and epichlorhydrin; soil dispersants and soil anti-redeposition aids such as alkoxylated polyamines and ethoxylated ethyleneimine polymers; anti-redeposition components such as polyesters and/or terephthalate polymers, polyethylene glycol including polyethylene glycol substituted with vinyl alcohol and/or vinyl acetate pendant groups; perfumes such as perfume microcapsules, polymer assisted perfume delivery systems including Schiff base perfume/polymer complexes, starch encapsulated perfume accords; soap rings; aesthetic particles including coloured noodles and/or needles; dyes; fillers such as sodium sulphate, although it may be preferred for the composition to be substantially free of fillers; carbonate salt including sodium carbonate and/or sodium bicarbonate; silicate salt such as sodium silicate, including 1.6R and 2.0R sodium silicate, or sodium metasilicate; co-polyesters of di-carboxylic acids and diols; cellulosic polymers such as methyl cellulose, carboxymethyl cellulose, hydroxyethoxycellulose, or other alkyl or alkylalkoxy cellulose, and hydrophobically modified cellulose; carboxylic acid and/or salts thereof, including citric acid and/or sodium citrate; and any combination thereof.

EXAMPLES

Example 1. A spray-dried laundry detergent powder and process of making it.Aqueous alkaline slurry composition.**[0061]**

Component	Aqueous slurry (parts)
Sodium Silicate	8.5
Acrylate/maleate copolymer	3.2
Hydroxyethane di(methylene phosphonic acid)	0.6
Sodium carbonate	8.8
Sodium sulphate	42.9
Water	19.7
Miscellaneous, such as magnesium sulphate, and one or more stabilizers	1.7
Aqueous alkaline slurry parts	85.4

Preparation of a spray-dried laundry detergent powder.

[0062] An alkaline aqueous slurry having the composition as described above is prepared in a slurry making vessel (crutcher). The moisture content of the above slurry is 23.1 %. Any ingredient added above in liquid form is heated to 70°C, such that the aqueous slurry is never at a temperature below 70°C. Saturated steam at a pressure of 6.0×10^5 Pa is injected into the crutcher to raise the temperature to 90°C. The slurry is then pumped into a low pressure line (having a pressure at the outlet of the first pump of 9.0×10^5 Pa). Separately, 11.4 parts of C₈-C₂₄ alkyl benzene sulphonic acid (HLAS), and 3.2 parts of a 50w/w% aqueous sodium hydroxide solution are pumped into the low pressure line. The viscosity of the resultant mixture increases. The resultant mixture is then pumped by a high pressure pump into a high

pressure line (the pressure in the pipe at the inlet of the second pump is 4×10^5 Pa, and the exit pressure is 8.0×10^6 Pa).

[0063] By controlling the point of addition of the detergent ingredients to the aqueous slurry between the low and high pressure pumps (i.e. in the low pressure line), the length of pipe between the two pumps between which a pressure drop of 5×10^5 Pa occurs, can be controlled. For example, if the detergent ingredients are contacted to the aqueous detergent slurry just prior to the entrance of the pipe into the second (high pressure) pump, then the length of pipe between the two pumps in the example is 331m, if the detergent ingredients are contacted at the mid-point between the two pumps, then the pipe distance between the pumps is 61.2m (and for illustrative purposes only, if the detergent ingredients are contacted to the aqueous detergent slurry prior to the first pump (outside of the scope of the present invention), then the length of the pipe between the two pumps is 33.75m.

[0064] The mixture is then sprayed at a rate of 1,640kg/hour at a pressure of 8.0×10^6 Pa and at a temperature of $90^\circ\text{C} \pm 2^\circ\text{C}$ through a spray pressure nozzle into a counter current spray-drying tower with an air inlet temperature of 300°C . The mixture is atomised and the atomised slurry is dried to produce a solid mixture, which is then cooled and sieved to remove oversize material ($>1.8\text{mm}$) to form a spray-dried powder, which is free-flowing. Fine material ($<0.15\text{mm}$) is elutriated with the exhaust the exhaust air in the spray-drying tower and collected in a post tower containment system. The spray-dried powder has a moisture content of 2.5wt%, a bulk density of 510 g/l and a particle size distribution such that greater than 80wt% of the spray-dried powder has a particle size of from 150 to 710 micrometers. The composition of the spray-dried powder is given below.

Spray-dried laundry detergent powder composition

[0065]

Component	%w/w Spray Dried Powder
Sodium silicate salt	10.0
C ₈ -C ₂₄ alkyl benzene sulphonate	15.1
Acrylate/maleate copolymer	4.0
Hydroxyethane di(methylene phosphonic acid)	0.7
Sodium carbonate	11.9
Sodium sulphate	53.7
Water	2.5
Miscellaneous, such as magnesium sulphate, and one or more stabilizers	2.1
Total Parts	100.00

A granular laundry detergent composition.

[0066]

Component	%w/w granular laundry detergent composition
Spray-dried powder of example 1 (described above)	59.38
91.6wt% active linear alkyl benzene sulphonate flake supplied by Stepan under the tradename Nacconol 90G®	0.22
Citric acid	5.00
Sodium percarbonate (having from 12% to 15% active AvOx)	14.70
Photobleach particle	0.01
Lipase (11.00mg active/g)	0.70
Amylase (21.55mg active/g)	0.33
Protease (56.00mg active/g)	0.43
Tetraacetyl ethylene diamine agglomerate (92wt% active)	4.35

(continued)

Component	%w/w granular laundry detergent composition
Suds suppressor agglomerate (11.5wt% active)	0.87
Acrylate/maleate copolymer particle (95.7wt% active)	0.29
Green/Blue carbonate speckle	0.50
Sodium Sulphate	9.59
Solid perfume particle	0.63
Ethoxylated C ₁₂ -C ₁₈ alcohol having an average degree of ethoxylation of 7 (AE7)	3.00
Total Parts	100.00

[0067] The above laundry detergent composition was prepared by dry-mixing all of the above particles (all except the AE7) in a standard batch mixer. The AE7 in liquid form is sprayed on the particles in the standard batch mixer. Alternatively, the AE7 in liquid form is sprayed onto the spray-dried powder of example 1. The resultant powder is then mixed with all of the other particles in a standard batch mixer.

[0068] The dimensions and values disclosed herein are not to be understood as being strictly limited to the exact numerical values recited. Instead, unless otherwise specified, each such dimension is intended to mean both the recited value and a functionally equivalent range surrounding that value. For example, a dimension disclosed as "40 mm" is intended to mean "about 40 mm".

Claims

1. A process for preparing a spray-dried detergent powder comprising:

- (i) deterative surfactant; and
 - (ii) other detergent ingredients;
- wherein the process comprises the steps of:

- (a) forming an aqueous detergent slurry in a mixer;
- (b) transferring the aqueous detergent slurry from the mixer to a pipe leading through a first pump and then through a second pump to a spray nozzle;
- (c) contacting a detergent ingredient to the aqueous detergent slurry in the pipe after the first pump and before the second pump to form a mixture;
- (d) spraying the mixture through the spray nozzle into a spray-drying tower; and
- (e) spray-drying the mixture to form a spray-dried powder, wherein the drop in pressure between (i) the pressure in the pipe at the outlet of the first pump to (ii) the pressure in the pipe at the inlet to the second pump is less than $8 \times 10^5 \text{ Pa}$.

2. A process according to claim 1, wherein the pressure drop between (i) the pressure in the pipe at the outlet of the first pump to (ii) the pressure in the pipe at the inlet to the second pump is less than $6 \times 10^5 \text{ Pa}$.

3. A process according to any preceding claim, wherein the aqueous detergent slurry comprises from 25wt% to 35wt% water.

4. A process according to any preceding claim, wherein the pressure in the pipe at the outlet of the first pump is less than $1 \times 10^6 \text{ Pa}$.

5. A process according to any preceding claim, wherein the pressure in the pipe at the inlet of the second pump is at least than $3 \times 10^5 \text{ Pa}$.

6. A process according to any preceding claim, wherein in step (c) the detergent ingredient comprises deterative surfactant and/or an acid precursor thereof.

7. A process according to any preceding claim, wherein in step (c) the detergent ingredient comprises polymer.
8. A process according to any preceding claim, wherein in step (c) the detergent ingredient comprises sodium hydroxide.
- 5 9. A process according to any preceding claim, wherein in step (c) the detergent ingredient comprises sodium chloride.
10. A process according to any preceding claim, wherein the aqueous detergent slurry comprises from 0wt% to 5wt% deterative surfactant.
- 10 11. A process according to any preceding claim, wherein the spray-dried detergent powder is spray-dried laundry detergent powder.
12. A process according to any preceding claim, wherein the spray-dried detergent powder comprises:
- 15 (a) from 0wt% to 10wt% zeolite builder;
(b) from 0wt% to 10wt% phosphate builder; and
(c) optionally from 0wt% to 15wt% silicate salt.
- 20 13. A process according to any preceding claim, wherein the spray-dried detergent powder comprises:
- (a) from 0wt% to 10wt% zeolite builder;
(b) from 0wt% to 10wt% phosphate builder; and
(c) optionally from 0wt% to 15wt% silicate salt,
wherein the pressure drop between (i) the pressure in the pipe at the outlet of the first pump to (ii) the pressure
25 in the pipe at the inlet to the second pump is less than 6×10^5 Pa.



EUROPEAN SEARCH REPORT

Application Number
EP 09 18 0008

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (IPC)
A	GB 2 020 687 A (UNILEVER LTD) 21 November 1979 (1979-11-21) * claims; examples *	1-13	INV. C11D11/02
A	EP 1 914 297 A1 (PROCTER & GAMBLE [US]) 23 April 2008 (2008-04-23) * claims; examples *	1-13	
			TECHNICAL FIELDS SEARCHED (IPC)
			C11D
The present search report has been drawn up for all claims			
Place of search Munich		Date of completion of the search 25 May 2010	Examiner Péntek, Eric
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

4
EPO FORM 1503 03.82 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 09 18 0008

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

25-05-2010

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
GB 2020687	A	21-11-1979	NONE	

EP 1914297	A1	23-04-2008	CA 2663386 A1	24-04-2008
			CN 101522880 A	02-09-2009
			WO 2008047301 A1	24-04-2008
			JP 2010505972 T	25-02-2010
