



Europäisches
Patentamt
European
Patent Office
Office européen
des brevets



EP 2 500 333 A8

(12)

CORRECTED EUROPEAN PATENT APPLICATION

published in accordance with Art. 153(4) EPC

(15) Correction information:

Corrected version no 1 (W1 A1)
Corrections, see
Bibliography INID code(s) 54

(51) Int Cl.:

C04B 35/599 (2006.01) **C01B 21/082 (2006.01)**
C04B 35/645 (2006.01) **C04B 41/80 (2006.01)**
C09K 11/08 (2006.01) **C09K 11/64 (2006.01)**

(48) Corrigendum issued on:

21.11.2012 Bulletin 2012/47

(86) International application number:

PCT/JP2010/069448

(43) Date of publication:

19.09.2012 Bulletin 2012/38

(87) International publication number:

WO 2011/058902 (19.05.2011 Gazette 2011/20)

(21) Application number: **10829862.1**

(22) Date of filing: **01.11.2010**

(84) Designated Contracting States:

**AL AT BE BG CH CY CZ DE DK EE ES FI FR GB
GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO
PL PT RO RS SE SI SK SM TR**

• **YAMADA Suzuya**

**Machida-city
Tokyo 194-8560 (JP)**

• **HASHIMOTO Hisayuki**

**Machida-city
Tokyo 194-8560 (JP)**

(30) Priority: 13.11.2009 JP 2009260243

(74) Representative: **Gulde Hengelhaupt Ziebig & Schneider**

**Patentanwälte - Rechtsanwälte
Wallstrasse 58/59
10179 Berlin (DE)**

(71) Applicant: **Denki Kagaku Kogyo Kabushiki Kaisha**

Tokyo 103-8338 (JP)

(72) Inventors:

• **NOMIYAMA Tomohiro**
Machida-city
Tokyo 194-8560 (JP)

(54) METHOD FOR PRODUCING BETA-SIALON PHOSPHOR

(57) Provided is a production method of a β -sialon phosphor that europium ions are solid-solved in β -sialon, including a mixing process for mixing raw materials of the β -sialon phosphor; a burning process for burning the raw materials after the mixing process to form the β -sialon phosphor; a HIP treatment process in which the β -sialon phosphor after the burning process is subjected to a HIP treatment; an annealing process in which the β -sialon

phosphor after the HIP treatment process is subjected to an annealing treatment; and an acid treatment process in which the β -sialon phosphor after the annealing process is subjected to an acid treatment. According to the production method of a β -sialon phosphor, a β -sialon phosphor excellent in luminescence intensity is obtained.