

(19)



(11)

EP 2 614 733 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention of the grant of the patent:
14.11.2018 Bulletin 2018/46

(51) Int Cl.:
A41D 19/00 (2006.01)

(21) Application number: **13150468.0**

(22) Date of filing: **08.01.2013**

(54) **Glove**

Handschuh

Gant

(84) Designated Contracting States:
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

(30) Priority: **16.01.2012 JP 2012005943**

(43) Date of publication of application:
17.07.2013 Bulletin 2013/29

(73) Proprietor: **SHOWA GLOVE Co.**
Himeji-shi
Hyogo 670-0802 (JP)

(72) Inventors:
• **Kishihara, Hidetoshi**
Himeji-shi, Hyogo 670-0802 (JP)
• **Ii, Yasuyuki**
Himeji-shi, Hyogo 670-0802 (JP)

(74) Representative: **Vossius & Partner**
Patentanwälte Rechtsanwälte mbB
Siebertstrasse 3
81675 München (DE)

(56) References cited:
JP-A- H0 649 702 JP-A- 2009 167 565
JP-A- 2010 100 964 US-A1- 2007 044 201
US-A1- 2011 016 607 US-A1- 2011 099 689

EP 2 614 733 B1

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

5 [0001] The present invention relates to a glove whose outer surface side and inner surface side are both superior in slip resistance, and more particularly, relates to a glove that is superior in slip resistance of the inner surface side of the glove and also is superior in the adhesion strength of the outer surface side of the glove from a coating layer of a rubber or a resin formed on the outer surface side of the glove.

[0002] Conventionally, fibrous gloves having a coating layer have been used widely in the fields of metal processing, physical distribution, assembly, packing, civil engineering and construction, precision, medical treatment, plantation, etc.

10 [0003] Among those, in the fields where dust of fibers of fibrous gloves becomes a problem, there have been used long fibers such as polyester and polyamide (nylon). However, such fibers are problematic in that their slip resistance is insufficient due to their smaller frictional resistance with hand skin in comparison with spun yarns of short fibers such as cotton, acrylic fibers and polyester, and therefore fingers slip easily within gloves, resulting in poor workability.

[0004] In order to solve this problem, there has been proposed, for example, a glove whose gripping property has been improved by forming a foamed coating of a rubber or a resin on a fibrous glove knitted from elastic fibers and inelastic fibers (for example, JP 2008 075201 A).

15 [0005] Moreover, a highly adherent glove whose outer and inner surface sides are formed of woven and knitted fabrics consisting of ultra finefiber bundles has been proposed (for example, JP H04 5763 B2).

[0006] The glove disclosed in JP 2008 075201 A has sufficient slip resistance on its outer surface side because the outer surface side is covered with a foamed coating of a rubber or a resin, but the inner surface side of the glove is not always sufficient in slip resistance. For example, there is a disadvantage that fingers slip in a glove and the glove sometimes comes off during a work in which a large force is applied in the longitudinal direction of a glove, e.g., dragging an object.

20 [0007] The glove disclosed in JP H04 5763 B2 is satisfactory in slip resistance on the inner surface side thereof, but the slip resistance of the outer surface side is not sufficient and, as a result, it has a disadvantage that when gripping a heavy object, the heavy object slips down.

[0008] JP 2010 100964 A relates to a fabric for gloves and a fibrous product. The fabric for the gloves which has a woven or knitted construction, contains a polyester filament yarn having a single fiber diameter of 10 - 1,000 nm and a polyester filament yarn having a single fiber diameter of more than 1 μm . The polyester filament yarn is exposed in at least any one of the surface side and reverse side of the fabric. The fibrous product is provided by using the fabric.

30 [0009] In light of the above situations, it is an object of the present invention to provide a glove that has excellent slip resistance on both the outer surface side and the inner surface side thereof and also is superior in adhesion strength of a coating layer.

[0010] This object is solved with the features of the claims.

35 [0011] In order to improve the slip resistance of the inner surface side of a glove for the attainment of the above-described object, the present inventors have tried to form a coating layer of a rubber or a vinyl chloride-based resin on the outer surface side of a fibrous glove whose outer surface side and inner surface side of the glove are made of microfibers. Although the slip resistance of the inner surface side of the glove has been improved, such a coating layer sometimes peels off during use due to low adhesion strength between microfibers and a rubber or a vinyl chloride-based resin, so that satisfactory gloves could not be obtained.

40 [0012] Then, the present inventors have further studied and eventually have found that a glove with sufficient adhesion strength can be obtained by forming a coating layer of a rubber or a vinyl chloride-based resin by a specific method even if the outer surface side is formed of microfibers.

[0013] Moreover, the present inventors have further found that a coating layer superior in adhesion strength can be formed not by a specific method but by an ordinary method by including non- microfibers in the outer surface side on which the coating layer is to be formed.

45 [0014] The present invention has been accomplished on the basis of these findings.

[0015] The glove of the present invention is superior in slip resistance and is prevented from causing troubles such as slipping off of the glove during use due to the slip of fingers in the glove because the inner surface side thereof contains a microfiber which has high frictional resistance to fingers and the microfiber comes into contact with fingers. On the other hand, since a coating layer of a rubber or a vinyl chloride-based resin has been formed on the outer surface side and the coating layer has excellent adhesion strength to the outer surface side of the glove, a trouble that the coating layer peels off during use is prevented and a high performance glove excellent in slip resistance on both the inner and outer surface sides can be provided.

50 [0016] The glove of the present invention has a feature that it comprises a fibrous glove and a coating layer of a rubber or a vinyl chloride-based resin formed on an outer surface side of the fibrous glove, wherein an inner surface side of the fibrous glove includes a yarn comprising 50% by weight or more of a microfiber having a diameter of a monofilament of not more than 6 μm .

55 [0017] In the present invention, the term "an outer surface side" indicates a side not in contact with fingers and the

term "an inner surface side" indicates a side in contact with fingers.

[0018] Further, in the present invention, the term "a diameter" does not indicate a diameter of a bundle of microfibers, but a diameter of a monofilament of microfibers.

[0019] Further, in the present invention, the term "splittable fiber" indicates a fiber before splitting and the term "split fiber" indicates a microfiber after splitting.

[0020] Furthermore, in the present invention, the terms "a", "an", "the" and the similar terms are to be construed to include the singular and the plural, unless otherwise indicated or contradicted in the context of the present invention.

[0021] The fibrous glove usable as a base material in the present invention includes, at least on the inner surface side of the fibrous glove, microfiber having a diameter of a monofilament (hereinafter, referred simply to as "diameter") of not more than 6 μm . The diameter of the microfiber is not particularly limited in its lower limit, but neither microfibers having a diameter of less than 0.1 μm nor splittable fibers capable of affording such microfibers after splitting are commercially available. Accordingly, the lower limit of the diameter of the microfiber is about 0.1 μm in view of current availability. On the other hand, if the diameter exceeds 6 μm , frictional resistance with fingers becomes small and desired slip resistance cannot be obtained sufficiently.

[0022] Generally, microfibers are available commercially in the form of splittable fibers. For example, one splittable fiber is split into several fibers by a hot water treatment with 1 to 5% NaOH at 80 to 100°C for 10 to 40 minutes, thereby becoming microfibers. Polyester and nylon are preferred as such microfibers, and splittable fibers such as NANOFRONT (registered trademark of Teijin Fibers, Ltd.) and COSMOALPHA (registered trademark of KB SEIREN Co., Ltd.) are suitably used as commercial available products.

[0023] Although fibers usually have a circular cross-section, splittable fibers can be polygonal microfibers (split fibers) after splitting due to the method of their production and the corners of the polygon are considered to effectively contribute to slip resistant effect. Accordingly, microfibers are preferably fibers having corners.

[0024] Such microfibers may be used either as a single fiber or as a composite fiber in which a core yarn of nylon, polyester, polyurethane elastic yarns, cotton or the like has been covered with a microfiber usually in 100 to 600 T (twists)/M (the number of windings per meter), preferably 300 to 600 T/M.

[0025] The yarn to be located on the inner surface side is a yarn composed of a microfiber and a non-microfiber aligned together, the proportion of the microfiber is more than 50% by weight, preferably, more than 80% by weight, and more preferably, more than 95% by weight.

[0026] In view of the knitting and weaving of a fibrous glove, it is preferred to perform the splitting treatment of splittable fibers into microfibers (split fibers) after knitting or weaving a fibrous glove. After the split treatment, dyeing with a direct dye, a disperse dye, an acid dye, or the like may be applied depending upon respective materials.

[0027] Although the outer surface side of the fibrous glove may be made of microfibers, it is preferred, in view of the adhesion strength between the fibrous glove and a coating layer of a rubber or a vinyl chloride resin, to include non-microfibers. Although non-microfibers are just required to be fibers larger in diameter than microfibers, those in filaments are about 15 to about 30 μm in diameter are preferred. Examples of such non-microfibers include single yarn and covered composite yarn of synthetic fibers such as acryl, polyester, nylon, aramid and polyethylene; natural fibers such as cotton, hemp and silk; and regenerated fibers such as rayon. Especially, polyurethane elastic yarns covered with at least one member selected from nylon, polyester and cotton are preferred. By the elastic yarns, slip resistance is further improved due to their compressive force and fitting force.

[0028] In addition, as the non-microfibers, cut-resistant fibers having a high crystallizability such as ultra high molecular weight polyethylene having high strength, aramide, etc. These fibers tend to slip and by providing the microfibers to the inner surface side of these fibers, slip resistance as well as cut-resistant property is imparted to both the outer surface side and the inner surface side of a glove, and thus a glove excellent in workability can be provided. Further, by using acrylic fiber, regenerated fibers such as rayon, etc., on the outer surface side, a glove excellent in protection against the cold can be provided.

[0029] As the method for including non-microfibers into the fibrous glove, there are exemplified a method for plating non-microfibers to the outer surface side using a seamless knitting machine of 7G or more, a method for sewing a fabric obtained by plating microfibers and non-microfibers by the use of a circular knitting machine and using it so that the non-microfibers are located on the outer surface side, and a method for obtaining two kinds of cloth; one is made of microfibers and the other is made of non-microfibers, and sticking them into a double-material structure. The proportion of the non-microfiber of the outer surface side is preferably more than 50% by weight, more preferably, more than 80% by weight, and even more preferably, more than 95% by weight.

[0030] Examples of the rubber in the present invention include natural rubber, isoprene, chloroprene, acrylic ester, styrene-butadiene copolymers, acrylonitrile-butadiene copolymers, polyurethane, butyl rubber, polybutadiene rubber and silicone rubber, and moreover, copolymers having up to 10% by weight of carboxyl modification group and blends thereof are also used. Generally, well-known additives including crosslinking agents such as sulfur and zinc oxide, vulcanization accelerators, antiaging agents, pigments, and thickeners are added to the rubber. In order to provide air permeability or wet gripping property, it is possible to form an open-cell coating by mechanically foaming by the addition

of a frothing agent, a foam stabilizer, a foaming agent, etc. and it is also possible to reduce steaming feel by a synergistic effect of the air permeability caused by this coating and the moisture absorbing and quick drying ability of microfibers.

[0031] Moreover, the adhesion strength of a rubber coating layer formed by a heat sensitive method can be enhanced by adding a thermosensitive gelling agent such as polyvinyl methyl ether, organopolysiloxane, and surfactants having a cloud point of 30 to 50°C.

[0032] Examples of the vinyl chloride-based resin in the present invention include homopolymers of vinyl chloride, copolymers of vinyl chloride with vinyl acetate or the like, and blends thereof. Generally, well-known additives including plasticizers, stabilizers, thickeners and pigments are added to the vinyl chloride-based resin. As in the case of rubber, steaming feel can be reduced, or air permeability or wet gripping property can be enhanced by foaming.

[0033] On the outer surface side of a fibrous glove is formed the above-described coating of a rubber or a vinyl chloride-based resin. Although the position where the coating layer is to be formed is not limited particularly, it is usually the palm region or fingertip regions of a glove, such portions being to come into contact with objects and being required to have slip resistance.

[0034] The method of forming a coating layer of rubber includes a coagulation method and a heat sensitive method.

[0035] In one preferred example of the coagulation method, a fibrous glove is put on a hand-shaped mold made of metal, porcelain, etc. and dipped in a coagulant. Examples of the coagulant include solutions in warm water or methanol containing metal salts such as calcium nitrate, calcium chloride, sodium chloride, and magnesium hydroxide, acetic acid, cyclohexylamine sulfate, etc. The concentration is usually 0.1 to 10 parts by weight based on 100 parts by weight of warm water or methanol. When less than 0.1 part by weight, a rubber formulation liquid tends to permeate easily. When exceeding 10 parts by weight, adhesion strength between a rubber coating and a fibrous glove tends to lower. Accordingly, the concentration of a coagulant is adjusted to a coagulant concentration balanced so that a rubber coating may not fully cover a fiber bundle on the inner surface side of a fibrous glove, in other words, a rubber coating may not permeate a fiber bundle completely and adhesion strength may not lower. Generally, a solution of calcium nitrate in methanol or warm water is used suitably. Next, after pulling up the fibrous glove, excess coagulant is allowed to drop for 3 to 20 seconds with the fingertips of the fibrous glove put on the hand-shaped mold facing downward and then the fingertips of the fibrous glove put on the hand-shaped mold is caused to face upward for 3 to 20 seconds, thereby allowing the coagulant gathered in the fingertips to become uniform at the dipping surface of the coagulant.

[0036] Then, after dipping in a compound of rubber, pulling out, and then drying at about 60 to 130°C for about 6 to 20 minutes, the fibrous glove is removed from the hand-shaped mold, followed by leaching at about 25 to 60°C for about 10 to 60 minutes. Then, if necessary, the glove is put again on a hand-shaped mold having a shape that the thumb, the remaining four fingers and the palm are curved inward so that the center of the palm becomes concave (curve approximately in the shape formed when a person has relaxed hand force) and is subjected to a heat treatment at about 100 to about 140°C for about 20 to about 60 minutes. The heat treatment means vulcanization and the state where moisture has merely removed by drying and a great improvement in strength has not been achieved is an unvulcanized state. Leaching may be carried out after the heat treatment. The heat treatment may be performed directly without removing the glove from the hand-shaped mold after drying. The coating may be formed in which two or three layers including a slip-resistant layer have been stacked. To allow a compound of rubber to permeate a fiber bundle completely, thereby covering the fibrous glove with the rubber to the inner surface side of is undesirable because parts where fibers come into contact with fingers are eliminated, so that feeling of discomfort is raised and slip is caused by sweat inside of the glove.

[0037] In the heat sensitive method, a fibrous glove is put on a hand-shaped mold, heated to about 50 to about 90°C, dipped in a compound of rubber, and then dried. Drying conditions, leaching, heat treatment, etc. after the drying are the same as those of the above-described coagulation method.

[0038] When the outer surface side of a fibrous glove is made of microfibers, the heat sensitive method is preferred compared to the coagulation method because a glove superior in the adhesion property of a rubber coating can be obtained.

[0039] On the other hand, when the outer surface side of a fibrous glove contains non-microfibers, a glove superior in adhesion property can be obtained by either the coagulation method or the heat sensitive method.

[0040] Although the method of forming a coating layer of a vinyl chloride-based resin is not restricted particularly, a glove superior in adhesion property in the case where the outer surface side of a fibrous glove is made of microfibers can be obtained by applying oil-repellent treatment with an oil repellent agent in advance to a fibrous glove. Specifically, for example, a fibrous glove is dipped in an oil repellent agent such as fluorine-based resin, silicone-based resin, etc., in an amount of 1 to 3% owf based on the weight of the fibrous glove, wrung and dried at 80 to 130°C. Subsequently, this fibrous glove is put on a hand-shaped mold, then a vinyl chloride-based resin (paste) is applied, and heat treatment is carried out at about 180 to about 210°C for about 10 to about 20 minutes.

[0041] In the case of using a polyurethane elastic fiber on the outer surface side of a fibrous glove, since elastic fibers are sensitive to heat and deteriorate easily, it is preferred to use a fiber in which a core yarn made of elastic fiber is covered with nylon, polyester fiber, or the like for the purpose of preventing the elastic fiber from exposing. Thereby, elastic fibers can maintain their elastic force also after heat treatment. In another method, it is also possible to lower the

EP 2 614 733 B1

heat treatment temperature to about 140 to about 160°C and thereby secure elastic force after heat treatment by the use of a copolymer of vinyl chloride and vinyl acetate.

[0042] In the case of including non-microfibers into the outer surface side of a fibrous glove, a glove with satisfactory adhesion strength can be obtained either by applying oil-repellent treatment in advance or by failing to apply such treatment.

[0043] The present invention will be described in more detail below with reference to examples and comparative examples, but the invention is not limited thereby.

[0044] Formulations 1 to 5 of coating layers (rubber and vinyl chloride-based resin) to be used for the examples and comparative examples are shown in Tables 1 to 5, and the methods i to v for the formation of coating layers of rubber and vinyl chloride-based resin are shown in Table 6.

(1) Formulations of coating layer

[0045]

Table 1

Formulation 1	
NR latex *1	100 parts by wt. **
10%KOH	1 parts by wt. **
Colloidal sulfur	1.0 parts by wt.
Zinc oxide	0.75 parts by wt.
Vulcanization accelerator (diethyldithio carbamic acid zinc salt)	0.2 parts by wt.
Antioxidant (2,2'-methylenebis (4-ethyl 6-tert-butylphenol))	1.0 parts by wt.
Heat sensitizer (polyvinyl methyl ether)	1.5 parts by wt.
Solid content	53 % by wt.
** Solid content	

Table 2

Formulation 2	
Polyvinyl chloride paste resin *2	100 parts by wt. **
Plasticizer *3	100 parts by wt.
Thickener *4	1.0 parts by wt.
Stabilizer *5	3.0 parts by wt.
** Solid content	

Table 3

Formulation 3	
NBR latex	100 parts by wt. **
Colloidal sulfur	1.0 parts by wt.
Zinc oxide	0.75 parts by wt.
Vulcanization accelerator (diethyldithio carbamic acid zinc salt)	0.2 parts by wt.
Antioxidant (2,2'-methylenebis (4-ethyl 6-tert-butylphenol))	1.0 parts by wt.
Thickener *6 (polyacrylic acid ester-based)	0.3 parts by wt.
Foam stabilizer (lauryl dipropionic acid sodium salt)	3.0 parts by wt.

EP 2 614 733 B1

(continued)

Formulation 3	
Solid content	38 % by wt.
** Solid content	

Table 4

Formulation 4	
NBR latex	100 parts by wt. **
Colloidal sulfur	1.0 parts by wt.
Zinc oxide	0.75 parts by wt.
Vulcanization accelerator (diethyldithio carbamic acid zinc salt)	0.2 parts by wt.
Antioxidant (2,2'-methylenebis (4-ethyl 6-tert-butylphenol))	1.0 parts by wt.
Thickener *6 (polyacrylic acid ester-based)	0.3 parts by wt.
Solid content	40 % by wt.
** Solid content	

Table 5

Formulation 5	
NR latex	100 parts by wt. **
10%KOH	1.0 parts by wt. **
Colloidal sulfur	1.0 parts by wt.
Zinc oxide	0.75 parts by wt.
Vulcanization accelerator (diethyldithio carbamic acid zinc salt)	0.2 parts by wt.
Antioxidant (2,2'-methylenebis (4-ethyl 6-tert-butylphenol))	1.0 parts by wt.
Thickener *6 (polyacrylic acid ester-based)	0.3 parts by wt.
Solid content	53 % by wt.
** Solid content	
*1 to *6 in Tables 1 to 5 are as follows, respectively.	
*1: LA-TZ produced by SUNWISE, *2: ZEST P21 produced by Shin Dai-Ichi Vinyl Corporation, *3: diisononyl phthalate (DINP), *4: Reolosil QS102 produced by Tokuyama Corporation, *5: SC72 produced by Adeka Corporation, *6: Aron A-7075 produced by Toagosei Co., Ltd.	

(2) Methods of forming coating layer

[0046]

EP 2 614 733 B1

Table 6

	Formation methods	Formation conditions
5	i NR heat sensitive method	A fibrous glove was put on a hand-shaped mold A and heated so that the mold temperature would become 80°C, then only the palm was dipped in a natural rubber compound of formulation 1, followed by drying at 75°C for 10 minutes. Then, the fibrous glove was removed from the mold, leached at 30°C for 60 minutes, put on a hand-shaped mold B, then heat treated at 120°C for 20 minutes to give a glove.
10	ii NR coagulation method	A fibrous glove was put on a hand-shaped mold A and heated so that the mold temperature would become 60°C. Then, it was dipped in a 3 wt% calcium nitrate solution in methanol and further dipped in NR compound of formulation 5, followed by drying at 120°C for 10 minutes. Then, the fibrous glove was removed from the mold, water-leached at 30°C for 60 minutes, put on a hand-shaped mold B, then heat treated at 120°C for 20 minutes to give a glove.
15	iii NBR coagulation method	A fibrous glove was put on a hand-shaped mold A and heated so that the mold temperature would become 60°C. Then, it was dipped in a 3 wt% calcium nitrate solution in methanol and further dipped in NBR compound prepared by foaming formulation 3 to a volume ratio of 1.5 by using a hand mixer, followed by drying at 120°C for 10 minutes. Then, the fibrous glove was removed from the mold, water-leached at 30°C for 60 minutes, put on a hand-shaped mold B, and then cured at 130°C for 40 minutes to give a glove.
20	iv NBR coagulation method-2	A fibrous glove was put on a hand-shaped mold A and heated so that the mold temperature would become 60°C. Then, it was dipped in a 3 wt% calcium nitrate solution in methanol and further dipped in non-foamable formulation 4, followed by drying at 120°C for 10 minutes. Then, the fibrous glove was removed from the mold, water-leached at 30°C for 60 minutes, put on a hand-shaped mold B, then heat treated at 130°C for 40 minutes to give a glove.
25	v PVC application method	A fibrous glove base was caused to fully adsorb 1 wt% aqueous solution of Asahi Guard AG7105 produced by Meisei Chemical Works, Ltd. at 25°C for 10 minutes, then wrung to a water content of 30% by weight, followed by drying at 130°C for 10 minutes. This glove was put on a hand-shaped mold A and the resin compound of formulation 2 was applied only to the palm of a glove. Then, heat treatment was performed at 190°C for 10 minutes to give a glove.
30		
35		

Hand-shaped mold A:

[0047] Since rubber or resin is applied only to the palm of a glove, a hand-shaped mold in which the thumb, the remaining four fingers, and the palm are positioned substantially coplanarly is used as a hand-shaped mold to be used in coating.

Hand-shaped mold B:

[0048] In the case of undergoing a step of removing a glove from a hand-shaped mold and leaching it, the mold to be used for the subsequent heat treatment is a mold in a shape that the thumb, the remaining four fingers and the palm are curved inward so that the center of the palm will become concave (curve approximately in the shape formed when a person has relaxed hand force).

(3) Methods of measurement and evaluation of physical properties

[0049] The measurement and evaluation of the physical properties of the gloves obtained in the example and the comparative example were performed by the following methods:

Diameter of fiber:

[0050] From the monofilaments of microfibers contained in a unit area (50 × 50 μm) on a screen taken by using an optical microscope (VHX-900) manufactured by Keyence Co., five fibers in increasing order of area and other five fibers

EP 2 614 733 B1

in decreasing order of area were chosen respectively, and the average of them was calculated, so that a diameter in the case of considering as being a perfect circle was calculated.

Measurement of coefficient of dynamic friction:

5

[0051] A test piece (63.5 mm × 63.5 mm) was cut from the palm surface of a glove, and the coefficient of dynamic friction (μ_K) thereof was measured. This method is based on ASTM D1894. The test piece is attached to a movable weight (200 g, friction surface: 63.5 mm × 63.5 mm) of a measuring device of coefficient of friction, then the movable weight is caused to run just a travel distance of 130 mm at 150 mm/min on a stainless steel plate, then the frictional force in this operation is measured, and a running resistance (coefficient of dynamic friction) produced by the friction between the test piece and the stainless steel plate is calculated according to the following formula. Measurement under WET conditions is performed with the friction surface of the test piece being wetted with 1 g of water uniformly. The higher the value of the coefficient of dynamic friction, the higher the slip-resistant performance is evaluated.

10

15

$$\mu_K (\text{coefficient of dynamic friction}) = C/D$$

[0052] C is an average frictional force after becoming regular running, and D is the normal reaction of the movable weight.

20

Slip resistance of the inner surface side of a glove:

[0053] Twenty subjects were designated, and when a carton box of 3 kg in weight was held on both sides (side faces) between hands with gloves, the slip resisting effect of the inner surface sides of the gloves was evaluated on five scales using the following criteria:

25

A: Do not slide at all, B: Do not slide, C: Neutral, D: Slide slightly, E: Slide.

Adhesion strength:

30

[0054] A test piece (25 mm in width, 120 mm in length) extending along the longitudinal direction of fingers was cut out from the palm of a glove and the coating layer and the fibrous glove were peeled from each other over about 20 mm from the finger side of the test piece. The ends of both the parts were clamped by a tensile testing machine so as to form an angle of 180 degrees, and the force applied in peeling is measured. When a chuck was moved over 150 mm at a moving rate of 50 mm/min, the force applied during running from 30 mm to 130 mm was averaged and the average was taken as peel force.

35

[0055] Peel strength is calculated using the following formula.

[0056] In the present invention, the higher the value, the larger the adhesion strength is evaluated.

40

$$T_F = F_F/b$$

[0057] T_F is peel strength (N/mm), F_F is peel force (N), and b is the width of a test piece (mm).

[0058] In the case of the preparation by formation method (iii) shown in Table 6, the coating layer is spongelike and does not have strength enough for withstanding a peeling test. Then, only in a peeling test, non-foamed NBR was applied onto a coating layer of (iii), thereby reinforcing the coating, and then measurement was carried out. The adhesion strength is preferably 0.32 N/mm or more, more preferably, 0.4 N/mm or more.

45

[0059] A glove has too much enough practical utility when it has adhesion strength of 0.8 N/mm or more. Accordingly, when being 0.8 N/mm or more, the adhesion strength was described as 0.8 N/mm and no further measurement was carried out.

50

Degree of permeation of coating:

[0060] The degree of permeation of a coating (coating layer) was evaluated visually using the following criteria:

55

Not permeated: The coating has not permeated to the inner surface side of the glove.

[0061] Permeated: The coating has permeated to the inner surface side of the glove.

Cut-resistant property:

[0062] The cut-resistant property was observed by a level divided in accordance with EN 388.

5 Warmth:

[0063] Twenty subjects were designated, and a working was done with gloves on under a low temperature (8°C), the warmth felt at that time was evaluated on three scales; Good, Average, and Poor.

10 Example 1

(Preparation of fibrous glove (A))

15 **[0064]** A fibrous glove knitted by the 18G knitting machine was prepared using three ply yarns of Teijin Nanofiber (NANOFRONT 56dT(dtex)-10F (the number of filaments)). Subsequently, fibers were split under stirring in a 2% aqueous sodium hydroxide solution of a weight 20 times the weight of the glove at 95°C for 10 minutes. Then, the glove was water-leached (twice in a 20-fold water bath at 90°C for 10 minutes) and dried at 60°C for 30 minutes. The diameter of the monofilament of NANOFRONT after splitting was 0.7 μm.

20 (Preparation of fibrous glove base (B))

[0065] A fibrous glove knitted by the 13G knitting machine was prepared using four single yarns of microfiber (COSMOALPHA 84dT-25F) of KB SEIREN Co., Ltd.

25 **[0066]** Subsequently, splitting, leaching, and drying were carried out by the same methods as described above. The diameter of the monofilament of microfiber after splitting was 3 μm.

(Preparation of fibrous gloves (C) and (D))

30 **[0067]** Fibrous gloves were prepared which had been knitted using yarns covered at 300 T/M or 600 T/M (hereinafter described as composite yarn (I) of 300 T/M or composite yarn (II) of 600 T/M) using two single yarns of microfiber (COSMOALPHA 84dT-25F) of KB SEIREN Co., Ltd. as sheath yarn and a composite yarn (an elastic yarn (22dT) of polyurethane covered with woolly nylon (78dT-24F)) as core yarn. Subsequently, splitting, leaching, and drying were carried out by the same methods as described above to give a fibrous glove (C) having a diameter of the monofilament of microfiber after splitting of 3 μm (using composite yarn (I) of 300 T/M) and a fibrous glove (D) having a diameter of
35 the monofilament of microfiber after splitting of 3 μm (using composite yarn (II) of 600 T/M).

(Formation of coating layer)

40 **[0068]** Coating layers of a rubber or a vinyl chloride-based resin was formed on the palms of the above-described fibrous gloves (A) to (D) by the method (i) of forming a coating layer described in Table 6. The results of the measurement and evaluation of the physical properties of the gloves obtained are given in Table 7.

Example 2

45 **[0069]** Using fibrous gloves (A) to (D) having a diameter of the monofilament of microfiber after splitting of 0.7 μm or 3 μm, coating layers were formed by the method (v) of forming a coating layer described in Table 6. The results of the measurement and evaluation of the physical properties of the gloves obtained are given in Table 7.

Example 3

50

(Preparation of fibrous glove (E))

[0070] Using the 13G knitting machine, a fibrous glove, the inner surface side of which was made of microfibers was prepared by plating two single yarns of microfiber (COSMOALPHA 84dT-25F) of KB SEIREN Co., Ltd. and two ply yarns of woolly nylon (WN)(78dT-24F). Subsequently, splitting, leaching, and drying were carried out by the same methods as those used in Example 1 to give a fibrous glove (E) having a diameter of the monofilament of microfiber after splitting of 3 μm.

(Formation of coating layer)

5 **[0071]** Using the fibrous glove (E) described above, a coating layer was formed by the methods (i) to (v) of forming a coating layer described in Table 6. The results of the measurement and evaluation of the physical properties of the gloves obtained are given in Table 7.

Example 4

10 (Preparation of fibrous glove (F1))

15 **[0072]** Using the 13G knitting machine, a fibrous glove, the inner surface side of which was made of microfibers was prepared by plating-knitting two single yarns of microfiber (COSMOALPHA 84dT-25F) of KB SEIREN Co., Ltd. and one composite yarn composed of an elastic fiber 22dT of polyurethane (PU) covered with woolly nylon (WN)(78dT-24F) at 300T/M. Subsequently, splitting, leaching, and drying were carried out by the same methods as those used in Example 1 to give a fibrous glove (F1) having a diameter of the monofilament of microfiber after splitting of 3 μ m.

(Formation of coating layer)

20 **[0073]** Using the fibrous glove (F1) described above, coating layers were formed by the methods (i) to (v) of forming a coating layer described in Table 6. The results of the measurement and evaluation of the physical properties of the gloves obtained are given in Table 7.

(Preparation of fibrous glove (F2))

25 **[0074]** Using the 13G knitting machine, a fibrous glove, the inner surface side of which was made of microfibers was prepared by plating-knitting two single yarns of microfiber (COSMOALPHA 84dT-25F) of KB SEIREN Co., Ltd. and one composite yarn composed of one elastic fiber 22dT of polyurethane (PU) covered with one woolly polyester (PE) 84dT-36F at 300T/M. Subsequently, splitting, leaching, and drying were carried out by the same methods as those used in Example 1 to give a fibrous glove (F2) having a diameter of the monofilament of microfiber after splitting of 3 μ m.

30 (Formation of coating layer)

35 **[0075]** Using the fibrous glove (F2) described above, a coating layer was formed by method (iv) of forming a coating layer described in Table 6. The results of the measurement and evaluation of the glove obtained are given in Table 7.

(Preparation of fibrous glove (F3))

40 **[0076]** Using the 13G knitting machine, a fibrous glove, the inner surface side of which was made of microfibers was prepared by plating-knitting two single yarns of microfiber (COSMOALPHA 84dT-25F) of KB SEIREN Co., Ltd. and one composite yarn composed of one elastic fiber 22dT of polyurethane (PU) covered with one 30-count cotton (CO) at 300T/M. Subsequently, splitting, leaching, and drying were carried out by the same methods as those used in Example 1 to give a fibrous glove (F3) having a diameter of the monofilament of microfiber after splitting of 3 μ m.

45 (Formation of coating layer)

[0077] Using the fibrous glove (F3) described above, a coating layer was formed by the method (iv) of forming a coating layer described in Table 6. The results of the measurement and evaluation of the gloves obtained are given in Table 7.

50 Example 5

(Preparation of fibrous gloves (G) and (H))

55 **[0078]** Using the 13G knitting machine, a fibrous glove, the inner surface side of which was made of microfibers was prepared by plating composite fiber (I) of 300 T/M or composite fiber (II) of 600 T/M of Example 1 and two ply yarns of woolly nylon (78dT-24F). Subsequently, splitting, leaching, and drying were carried out by the same methods as those used in Example 1 to give a fibrous glove (G) (using composite yarn (I) of 300 T/M) and a fibrous glove (H)(using composite yarn (II) of 600 T/M), having a diameter of the monofilament of microfiber after splitting of 3 μ m.

(Formation of coating layer)

[0079] Subsequently, using the fibrous gloves (G) and (H), coating layers were formed by the methods (i) to (v) of forming a coating layer described in Table 6. The results of the measurement and evaluation of the physical properties of the gloves obtained are given in Table 7.

Table 7

	Fibrous glove (diameter)	Formation method of coating layer	Coefficient of dynamic friction of inner surface side of glove in dry condition (μ K)	Coefficient of dynamic friction of inner surface side of glove in wet condition (μ K)	Organoleptic evaluation of slip resistance of inner surface side of glove	Adhesion strength (N/mm)	Degree of permeation of coating
Ex. 1	Microfibers of (A) ($0.7 \mu\text{m}$)	(i)	1.95	0.7	B	0.8 or more	Not permeated
	Microfibers of (B) ($3 \mu\text{m}$)	(i)	0.7	0.65	B	0.8 or more	Not permeated
	Microfibers of (C) ($3 \mu\text{m}$)	(i)	0.51	0.41	C	0.8 or more	Not permeated
	Microfibers of (D) ($3 \mu\text{m}$)	(i)	0.53	0.43	C	0.8 or more	Not permeated
Ex. 2	Microfibers of (A) ($0.7 \mu\text{m}$)	(v)	1.92	0.71	B	0.8 or more	Not permeated
	Microfibers of (B) ($3 \mu\text{m}$)	(v)	0.7	0.55	B	0.8 or more	Not permeated
	Microfibers of (C) ($3 \mu\text{m}$)	(v)	0.51	0.42	C	0.8 or more	Not permeated
	Microfibers of (D) ($3 \mu\text{m}$)	(v)	0.55	0.42	C	0.8 or more	Not permeated
Ex. 3	Microfibers of (E) ($3 \mu\text{m}$) (Plating with WN)	(i)	0.66	0.66	B	0.8 or more	Not permeated
		(ii)	0.68	0.63	B	0.52	Not permeated
		(iii)	0.67	0.68	B	0.54	Not permeated
		(iv)	0.65	0.65	B	0.52	Not permeated
		(v)	0.68	0.7	B	0.8 or more	Not permeated
Ex. 4	Microfibers of (F1) ($3 \mu\text{m}$)	(i)	0.67	0.64	A	0.8 or more	Not permeated
		(ii)	0.66	0.68	A	0.48	Not permeated

EP 2 614 733 B1

(continued)

	Fibrous glove (diameter)	Formation method of coating layer	Coefficient of dynamic friction of inner surface side of glove in dry condition (μ K)	Coefficient of dynamic friction of inner surface side of glove in wet condition (μ K)	Organoleptic evaluation of slip resistance of inner surface side of glove	Adhesion strength (N/mm)	Degree of permeation of coating	
5								
10								
15	Ex. 4 (Plating with composite fiber WN/PU)	(iii)	0.67	0.69	A	0.52	Not permeated	
		(iv)	0.68	0.66	A	0.52	Not permeated	
		(v)	0.68	0.67	A	0.8 or more	Not permeated	
20	Microfibers of (F2) (Plating with composite fiber PE/PU)	(iv)	0.65	0.65	A	0.42	Not permeated	
25	Microfibers of (F3) (Plating with composite fiber CO/PU)	(iv)	0.67	0.68	A	0.42	Not permeated	
30		(i)	0.67	0.61	C	0.8 or more	Not permeated	
35	Ex. 5 Microfibers of (G) (3 μ m) (Plating with composite fiber I)	(ii)	0.59	0.6	C	0.51	Not permeated	
		(iii)	0.62	0.6	C	0.54	Not permeated	
		(iv)	0.63	0.63	C	0.52	Not permeated	
		(v)	0.62	0.64	C	0.8 or more	Not permeated	
40			(i)	0.62	0.68	C	0.8 or more	Not permeated
45	Microfibers of (H) (31 μ m) (Plating with composite fiber II)	(ii)	0.68	0.64	C	0.51	Not permeated	
		(iii)	0.65	0.62	C	0.54	Not permeated	
		(iv)	0.66	0.6	C	0.53	Not permeated	
50			(v)	0.63	0.61	C	0.8 or more	Not permeated

55 Comparative Example 1

[0080] Using fibrous gloves (B) to (D), having a diameter of the monofilament of microfiber after splitting of 3 μ m, coating layers were formed by the method (ii) of forming a coating layer described in Table 6. The results of the meas-

EP 2 614 733 B1

urement and evaluation of the physical properties of the gloves obtained are given in Table 8.

Comparative Example 2

5 **[0081]** Using the 13G knitting machine, a fibrous glove was prepared by knitting using two high multifilaments (Polyester 176dT-288F, 7 μm in diameter) of Senshin (Taiwan). Subsequently, leaching and drying were carried out by the same methods as those used in Example 1 to give a fibrous glove (I) having a diameter of 7 μm .

10 **[0082]** Then, using the fibrous glove (I), coating layers were formed by the methods (i) to (v) of forming a coating layer described in Table 6. The results of the measurement and evaluation of the physical properties of the glove obtained are given in Table 8.

Comparative Example 3

15 **[0083]** Using the 13G knitting machine, there was prepared a fibrous glove knitted by aligning two single yarns of microfiber (COSMOALPHA 84dT-25F) of KB SEIREN Co., Ltd. and two ply yarns of woolly nylon (78dT). Subsequently, splitting, leaching, and drying were carried out by the same methods as those used in Example 1 to give a fibrous glove base (J) having a diameter of the monofilament of microfiber after splitting of 3 μm .

20 **[0084]** Then, using the fibrous glove (J) described above, coating layers were formed by the methods (ii) to (iii) of forming a coating layer described in Table 6. The results of the measurement and evaluation of the physical properties of the gloves obtained are given in Table 8.

Comparative Example 4

25 **[0085]** Using the 13G knitting machine, there was prepared a fibrous glove knitted by aligning two single yarns of microfiber (COSMOALPHA 84dT-25F) of KB SEIREN Co., Ltd. and one composite yarn composed of an elastic fiber 22dT of polyurethane covered with woolly nylon (78dT-24F) at 300T/M. Subsequently, splitting, leaching, and drying were carried out by the same methods as those used in Example 1 to give a the fibrous glove (K) having a diameter of the monofilament of microfiber after splitting of 3 μm .

30 **[0086]** Then, using the fibrous glove (K), coating layers were formed by the methods (ii) and (iii) of forming a coating layer described in Table 6. The results of the measurement and evaluation of the physical properties of the gloves obtained are given in Table 8.

Table 8

	Fibrous glove (diameter)	Formation method of coating layer	Coefficient of dynamic friction of inner surface side of glove in dry condition (μK)	Coefficient of dynamic friction of inner surface side of glove in wet condition (μK)	Organoleptic evaluation of slip resistance of inner surface side of glove	Adhesion strength (N/mm)	Degree of permeation of coating
35							
40							
45	Microfibers of (8) (3 μm)	(ii)	0.69	0.67	B	0.2	Not permeated
	Microfibers of (C) (3 μm)	(ii)	0.5	0.48	C	0.22	Not permeated
50	Microfibers of (D) (3 μm)	(ii)	0.52	0.49	C	0.21	Not permeated

55

EP 2 614 733 B1

(continued)

	Fibrous glove (diameter)	Formation method of coating layer	Coefficient of dynamic friction of inner surface side of glove in dry condition (μ K)	Coefficient of dynamic friction of inner surface side of glove in wet condition (μ K)	Organoleptic evaluation of slip resistance of inner surface side of glove	Adhesion strength (N/mm)	Degree of permeation of coating
5 10 15 20	Comp. Ex. 2 Microfibers of (I) (7μ m)	(i)	0.30	0.29	E	0.8 or more	Not permeated
		(ii)	0.32	0.29	E	0.62	Not permeated
		(iii)	0.30	0.30	E	0.31	Not permeated
		(iv)	0.32	0.32	E	0.30	Not permeated
		(v)	0.33	0.31	E	0.8 or more	Not permeated
25	Comp. Ex. 3 Microfibers of (J) (3μ m) (Aligned with WN)	(ii)	0.38	0.34	E	0.38	Not permeated
		(iii)	0.35	0.33	E	0.42	Not permeated
30	Comp. Ex. 4 Microfibers of (K) (3μ m) (Aligned with composite yarn)	(ii)	0.35	0.36	D	0.34	Not permeated
		(iii)	0.33	0.32	D	0.38	Not permeated

Comparative Examples 5 to 8

[0087] Using a fibrous glove (woolly nylon) (L) knitted by the 13G knitting machine using two ply yarns of woolly nylon 78dT, a fibrous glove (wooly polyester) (M) knitted using two ply yarns of woolly polyester 84dT, a fibrous glove (cotton) (N) knitted using two 30-count cottons, and a fibrous glove (SCY) (O) knitted using three composite yarns composed of an elastic fiber 22dT of polyurethane covered with woolly nylon 78dt-24F at 300T/M, coating layers were formed by the methods (i) to (v) of forming a coating layer described in Table 6. The leaching and drying of the fibrous glove are the same as those of Example 1. The results of the measurement and evaluation of the physical properties of the gloves obtained are given in Table 9.

Table 9

	Fibrous glove (diameter)	Formation method of coating layer	Coefficient of dynamic friction of inner surface side of glove in dry condition (μ K)	Coefficient of dynamic friction of inner surface side of glove in wet condition (μ K)	Organoleptic evaluation of slip resistance of inner surface side of glove	Adhesion strength (N/mm)	Degree of permeation of coating
5	Woolly nylon of (L)	(i)	0.27	0.25	E	0.8 or more	Not permeated
10		(ii)	0.27	0.20	E	0.71	Not permeated
15		(iii)	0.29	0.28		0.67	Not permeated
20		(iv)	0.30	0.29	E	0.67	Not permeated
25		(v)	0.28	0.28	E	0.8 or more	Not permeated
30	Woolly polyester of (M)	(i)	0.24	0.22	E	0.51	Not permeated
35		(ii)	0.22	0.24	E	0.48	Not permeated
40		(iii)	0.23	0.22	E	0.74	Not permeated
45		(iv)	0.24	0.19	E	0.72	Not permeated
50		(v)	0.24	0.21	E	0.8 or more	Not permeated
55	Cotton of (N)	(i)	0.27	0.39	D	0.8以上	Not permeated
		(ii)	0.27	0.30	D	0.74	Not permeated
		(iii)	0.29	0.37	D	0.79	Not permeated
		(iv)	0.27	0.34	D	0.80	Not permeated
		(v)	0.28	0.37	D	0.8 or more	Not permeated

EP 2 614 733 B1

(continued)

	Fibrous glove (diameter)	Formation method of coating layer	Coefficient of dynamic friction of inner surface side of glove in dry condition (μ K)	Coefficient of dynamic friction of inner surface side of glove in wet condition (μ K)	Organoleptic evaluation of slip resistance of inner surface side of glove	Adhesion strength (N/mm)	Degree of permeation of coating
Comp. Ex. 8	SCY of (O)	(i)	0.29	0.24	D	0.8以上	Not permeated
		(ii)	0.25	0.27	D	0.68	Not permeated
		(iii)	0.28	0.25	D	0.71	Not permeated
		(iv)	0.27	0.25	D	0.68	Not permeated
		(v)	0.30	0.26	D	0.8 or more	Not permeated

Examples 6 and 7

[0088] Using the 13G knitting machine, a fibrous glove, the inner surface side of which was made of microfiber and woolly nylon and the outer surface side of which was made of woolly nylon was prepared by plating-knitting a yarn of microfibers (COSMOALPHA 84dT-25F) of KB SEIREN of the number given in Table 10 and woolly nylon 78dT aligned together and woolly nylon. Subsequently, splitting, leaching, and drying were carried out by the same methods as those used in Example 1 to give a fibrous gloves (P) having a diameter of the monofilament of microfiber after splitting of 3 μ m.

(Formation of coating layer)

[0089] Using the fibrous gloves (P) described above, coating layers were formed by the method (iv) of forming a coating layer described in Table 6. The results of the measurement and evaluation of the physical properties of the gloves obtained are given in Table 10.

5
10
15
20
25
30
35
40
45
50
55

Table 10

	Inner surface side			Outer surface side	Adhesion strength (N/mm)	Organoleptic evaluation of slip resistance of inner surface side of glove	Coefficient of dynamic friction of inner surface side of glove in dry condition (μ K)
	COSMOALPHA		WN				
	Before splitting (dT*Number)	After splitting (dT)	(dT*Number)				
Ex. 6	84*5	310	78*1	78*2	0.49	B	0.65
	84*4	250	78*1	78*2	0.52	C	0.59
	84*3	208	78*1	78*2	0.50	C	0.58
	84*2	130	78*1	78*2	0.51	C	0.52
Ex. 7	84*2	130	78*2	78*2	0.51	E	0.34

Example 8

(Preparation of fibrous glove (Q))

5 [0090] Using the 13G knitting machine, a fibrous glove, the inner surface side of which was made of microfibers was prepared by plating-knitting two single yarns of microfiber (COSMOALPHA 84dT-25F) of KB SEIREN Co., Ltd. and one composite yarn composed of one elastic fiber 22dT of polyurethane (PU) covered with one Dyneema (Registered trademark of Toyobo Co., Ltd. 22dT-192F) at 200T/M. Subsequently, splitting, leaching, and drying were carried out by the same methods as those used in Example 1 to give a fibrous glove (Q) having a diameter of the monofilament of
10 microfiber after splitting of 3 μ m.

(Formation of coating layer)

15 [0091] Using the fibrous glove (Q) described above, a coating layer was formed by the methods (i) to (iv) of forming a coating layer described in Table 6. The results of the measurement and evaluation of the glove obtained are given in Table 11.

Example 9

20 (Preparation of fibrous glove (R))

[0092] Using the 10G knitting machine, a fibrous glove, the inner surface side of which was made of microfibers was prepared by plating-knitting two single yarns of microfiber (COSMOALPHA 84dT-25F) of KB SEIREN Co., Ltd. and one Kevlar (Registered trademark of Toray-DuPont, 20-count). Subsequently, splitting, leaching, and drying were carried
25 out by the same methods as those used in Example 1 to give a fibrous glove (R) having a diameter of the monofilament of microfiber after splitting of 3 μ m.

(Formation of coating layer)

30 [0093] Using the fibrous glove (R) described above, a coating layer was formed by the methods (i) to (v) of forming a coating layer described in Table 6. The results of the measurement and evaluation of the glove obtained are given in Table 11.

Example 10

35 [0094] In Example 4, with respect to the gloves obtained by using a fibrous glove (F1) and forming a coating layer by the methods (i) to (v), the cut-resistant property was evaluated.

[0095] The results of the evaluation are given in Table 11.

40

45

50

55

Table 11

Fibrous glove (diameter)	Formation method of coating layer	Coefficient of dynamic friction of inner surface side of glove in dry condition (μ K)	Coefficient of dynamic friction of inner surface side of glove in wet condition (μ K)	Organoleptic evaluation of slip resistance of inner surface side of glove	Adhesion strength (N/mm)	Degree of permeation of coating	Cut-resistant property EN388 (Level)
Ex. 8 Microfibers of (Q) (3μ m)	(i)	0.67	0.63	A	0.54	Not permeated	2
	(ii)	0.65	0.65	A	0.53	Not permeated	2
	(iii)	0.66	0.66	A	0.43	Not permeated	2
	(iv)	0.66	0.65	A	0.41	Not permeated	2
Ex. 9 Microfibers of (R) (3μ m)	(i)	0.6	0.6	B	0.56	Not permeated	2
	(ii)	0.63	0.61	B	0.53	Not permeated	2
	(iii)	0.61	0.62	B	0.42	Not permeated	2
	(iv)	0.6	0.61	B	0.4	Not permeated	2
	(v)	0.62	0.6	B	0.65	Not permeated	2

5
10
15
20
25
30
35
40
45
50
55

(continued)

	Fibrous glove (diameter)	Formation method of coating layer	Coefficient of dynamic friction of inner surface side of glove in dry condition (μ K)	Coefficient of dynamic friction of inner surface side of glove in wet condition (μ K)	Organoleptic evaluation of slip resistance of inner surface side of glove	Adhesion strength (N/mm)	Degree of permeation of coating	Cut-resistant property EN388 (Level)
Ex. 10	Microfibers of (F1) (3 μ m) (Plating with composite fiber WN/PU)	(i)	0.67	0.64	A	0.8 or more	Not permeated	1
		(ii)	0.66	0.68	A	0.48	Not permeated	1
		(iii)	0.67	0.69	A	0.52	Not permeated	1
		(iv)	0.68	0.66	A	0.52	Not permeated	1
		(v)	0.68	0.67	A	0.8 or more	Not permeated	1

EP 2 614 733 B1

Example 11

(Preparation of fibrous glove (S))

5 **[0096]** Using the 13G knitting machine, a fibrous glove, the inner surface side of which was made of microfibers was prepared by plating-knitting two single yarns of microfiber (COSMOALPHA 84dT-25F) of KB SEIREN Co., Ltd. and one acryl (Toray Industries, Inc., 40-count). Subsequently, splitting, leaching, and drying were carried out by the same methods as those used in Example 1 to give a fibrous glove (S) having a diameter of the monofilament of microfiber after splitting of 3 μ m.

10

(Formation of coating layer)

[0097] Using the fibrous glove (S) described above, a coating layer was formed by the methods (i) to (v) of forming a coating layer described in Table 6. The results of the measurement and evaluation of the glove obtained are given in Table 12.

15

Example 12

[0098] In Example 4, with respect to the gloves obtained by using a fibrous glove (F1) and forming a coating layer by the methods (i) to (v), the warmth was evaluated.

20

[0099] The results of the evaluation are given in Table 12.

25

30

35

40

45

50

55

Table 12

Ex. 11	Microfibers of (S) (3 μ m)	(i)	0.65	0.68	B	0.8 or more	Not permeated	Good		
		(ii)	0.66	0.69	B	0.8 or more	Not permeated	Good		
		(iii)	0.65	0.65	B	0.52	Not permeated	Good		
		(iv)	0.65	0.66	B	0.8 or more	Not permeated	Good		
		(v)	0.68	0.67	B	0.8 or more	Not permeated	Good		
Ex. 12	Microfibers of (F1) (3 μ m) (Plating with composite fiber WN/PU)	(i)	0.67	0.64	A	0.8 or more	Not permeated	Poor		
		(ii)	0.66	0.68	A	0.48	Not permeated	Poor		
		(iii)	0.67	0.69	A	0.52	Not permeated	Poor		
		(iv)	0.68	0.66	A	0.52	Not permeated	Poor		
		(v)	0.68	0.67	A	0.8 or more	Not permeated	Poor		

[0100] As is clearly shown by Examples 1 and 2 in Table 7, a glove superior in the slip resistance of the inner surface side of the glove and also superior in adhesion strength (0.32 N/mm or more, preferably 0.4 N/mm or more) can be obtained by using a fibrous glove made of microfibers for both the inner surface side and the outer surface side, and forming a coating layer by a heat sensitive method (i) in the case of forming a coating layer of rubber on the outer surface side (Example 1) or by forming a coating layer by method (v) including applying oil-repellent treatment to the fibrous glove in advance in the case of forming a coating layer of vinyl chloride-based resin (Example 2).

[0101] Especially, in the case of the microfibers (C) and (D) in Examples 1 and 2, the coefficient of dynamic friction of the inner surface side covered with microfibers is somewhat low, but compressive force and fitting force have been enhanced by polyurethane elastic fibers and accordingly the slip resistance of the inner surface side of the glove is good.

[0102] In the case of the microfibers of (E) in Example 3, the slip resistance of the inner surface side of the glove is good because of the execution of plating with woolly nylon (WN).

[0103] In Example 4, which are embodiments where elastic fibers have been added to the fibrous glove base of Example 3, compressive force and fitting force to a hand have been enhanced and the slip resistance of the inner surface side of the glove has been increased more in comparison with the glove of Example 3.

[0104] As is clear from Examples 4 and 5, by including non-microfibers in the outer surface side, there can be obtained a glove superior in the adhesion strength of a coating layer of rubber or vinyl chloride-based resin by any of methods (i) to (v) of forming a coating layer.

[0105] As is clearly shown by Comparative Example 1 in Table 8, in the case where a coating layer of rubber is formed on the outer surface side of a fibrous glove, both the inner surface side and the outer surface side of which are made of microfibers, a glove superior in adhesion strength cannot be obtained by a coagulation method (ii).

[0106] As is clear from Comparative Example 2, when the diameter of the monofilament of microfiber is larger than 6 μm , the slip resistance of the inner surface side of a glove tends to lower, whereas in the case of fibers having a diameter of 7 μm , the adhesion strength of a coating layer of rubber or vinyl chloride-based resin also tends to lower.

[0107] Moreover, as is shown by Comparative Examples 3 and 4, in the case of merely aligning microfibers and non-microfibers together, sufficient slip resistance on the inner surface side of a glove cannot be obtained because both types of fibers are mixed randomly and accordingly the proportion of the microfibers in the inner surface side which comes into contact with hand, skin becomes smaller.

[0108] Moreover, as is clear from Comparative Examples 5 to 8 in Table 9, the slip resistance of the inner surface side of a glove has been lowered in the case where the inner surface side of the glove is made of not microfibers but non-microfibers of the general purpose grade (the diameter of monofilament is 15 to 30 μm).

[0109] Moreover, Examples 6 and 7 in Table 10 show that even if microfibers and non-microfibers have been aligned together, the slip resistance of the inner surface side of a glove is improved when the proportion of microfibers to the whole fibers in the inside of the glove is greater than 50% by weight.

[0110] Furthermore, as is clear from the comparison of Examples 8, 9 and Example 10 in Table 11, the gloves of Examples 8, 9 in which microfibers were provided to the inner surface side of a fibrous glove including cut-resistant fibers as the non-microfibers, slip resistance as well as cut-resistant property is imparted to both the outer surface side and the inner surface side of a glove, and therefore, a glove excellent in workability can be provided, as compared with the gloves of Example 10 not containing the cut-resistant fibers.

[0111] Furthermore, as is clear from the comparison of Example 11 and Example 12 in Table 12, the gloves of Example 11 in which acrylic fibers were provided to the outer surface side are excellent in warmth, and thus a glove excellent in protection against the cold can be provided.

[0112] As described above, according to the present invention, there can be provided a glove having high performance that is superior in slip resistance on both the outer surface side and the inner surface side thereof and also superior in adhesion strength to rubber or resin formed on the outer surface side.

Claims

1. A glove comprising a fibrous glove and a coating layer of a rubber or a vinyl chloride-based resin formed on an outer surface side of the fibrous glove, **characterized in that** an inner surface side and the outer surface side of the fibrous glove are knitted separately by plating, and 50% by weight or more of the yarn used in the inner surface side comprises a microfiber having a diameter of a monofilament of not more than 6 μm .
2. The glove according to claim 1, wherein the outer surface side of the fibrous glove includes a single yarn and/or a covered composite yarn of a non-microfiber having a diameter of a monofilament of more than 6 μm .
3. The glove according to claim 2, wherein the non-microfiber comprises at least one member selected from the group

consisting of nylon, polyester and cotton.

4. The glove according to any one of claims 2 or 3, wherein the non-microfiber comprises a polyurethane elastic yarn covered with at least one member selected from the group consisting of nylon, polyester and cotton.

5. The glove according to any one of claims 1 to 4, wherein the microfiber comprises a split fiber.

6. The glove according to any one of claims 1 to 5, wherein adhesion strength of the coating layer is not less than 0.32 N/mm, said adhesion strength being tested by a method comprising the steps:

cutting out a test piece of 25 mm in width and 120 mm in length extending along the longitudinal direction of fingers from the palm of a glove and peeling the coating layer and the fibrous glove from each other over about 20 mm from the finger side of the test piece, clamping the ends of both parts by a tensile testing machine so as to form an angle of 180 degrees, and measuring a force applied in peeling,

wherein, when a chuck is moved over 150 mm at a moving rate of 50 mm/min, the force applied during running from 30 mm to 130 mm is averaged and the average is taken as peel force, wherein T_F [peel strength: N/mm] = F_F [peel force: N] / b [width of the test piece] .

7. A method for producing the glove according to any one of claims 1 to 6, comprising the step of:

forming the coating layer of a rubber on the outer surface side of the fibrous glove by a heat sensitive method or a coagulation method.

8. A method for producing the glove according to any one of claims 1 to 6, comprising the steps of:

applying or not applying an oil-repellent treatment to the outer surface side of the fibrous glove, and forming the coating layer of a vinyl chloride-based resin thereon.

Patentansprüche

1. Handschuh, aufweisend einen Faserhandschuh und eine auf einer Außenflächenseite des Faserhandschuhs gebildete Überzugschicht aus einem Gummi oder einem Harz auf Vinylchlorid-Basis,

dadurch gekennzeichnet, dass

eine Innenflächenseite und die Außenflächenseite des Faserhandschuhs separat gewirkt sind durch Plattieren, und 50 Gewichtsprozent oder mehr des in der Innenflächenseite verwendeten Garns eine Mikrofaser aufweist, die einen Durchmesser eines Monofilaments von nicht mehr als 6µm hat.

2. Handschuh nach Anspruch 1, wobei die Außenflächenseite des Faserhandschuhs ein Einfachgarn und/oder ein umhülltes Verbundgarn aus einer Nicht-Mikrofaser, die einen Durchmesser eines Monofilaments von mehr als 6µm hat, aufweist.

3. Handschuh nach Anspruch 2, wobei die Nicht-Mikrofaser mindestens ein aus der folgenden Gruppe ausgewähltes Element aufweist: Nylon, Polyester und Baumwolle.

4. Handschuh nach einem der Ansprüche 2 oder 3, wobei die Nicht-Mikrofaser ein elastisches Polyurethan-Garn aufweist, das mit mindestens einem aus der folgenden Gruppe ausgewählten Element umhüllt ist: Nylon, Polyester und Baumwolle.

5. Handschuh nach einem der Ansprüche 1 bis 4, wobei die Mikrofaser eine Spaltfaser aufweist.

6. Handschuh nach einem der Ansprüche 1 bis 5, wobei eine Haftfestigkeit der Überzugschicht nicht kleiner als 0,32N/mm ist, wobei die Haftfestigkeit mit einem Verfahren getestet ist, das die folgenden Schritte aufweist:

EP 2 614 733 B1

Ausschneiden eines Teststücks von 25mm in der Breite und 120mm in der sich entlang der Fingerlängsrichtung erstreckenden Länge aus der Handinnenfläche eines Handschuhs und Lösen der Überzugschicht und des Faserhandschuhs voneinander über ungefähr 20mm von der Fingerseite des Teststücks aus,
Einspannen der Enden beider Teile mit Hilfe einer Zugtestvorrichtung, um so einen Winkel von 180 Grad zu bilden, und
Messen einer beim Schälen anliegenden Kraft,

wobei, wenn ein Spannfutter über 150 mm mit einer Bewegungsrate von 50 mm/min bewegt wird, die anliegende Kraft während des Laufs von 30 mm bis 130 mm gemittelt wird und der Durchschnitt als Lösekraft genommen wird, wobei T_F [Schälfestigkeit: N/mm] = F_F [Abzugskraft: N] / b [Breite des Teststücks].

7. Verfahren zur Herstellung des Handschuhs nach einem der Ansprüche 1 bis 6 mit den folgenden Schritten:

Bilden der Überzugschicht aus Gummi an der Außenflächenseite des Faserhandschuhs durch ein wärmeempfindliches Verfahren oder ein Koagulationsverfahren.

8. Verfahren zur Herstellung des Handschuhs nach einem der Ansprüche 1 bis 6 mit den folgenden Schritten:

Anwenden oder nicht Anwenden einer ölabweisenden Behandlung auf der Außenflächenseite des Faserhandschuhs und
Bilden der Überzugschicht aus einem Harz auf Vinylchlorid-Basis auf dieser.

Revendications

1. Gant comprenant un gant fibreux et une couche de revêtement d'un caoutchouc ou d'une résine à base de chlorure de vinyle formée sur une surface externe du gant fibreux, **caractérisé en ce que** un côté de surface interne et le côté de surface externe du gant fibreux sont tricotés séparément par placage, et 50% en poids ou plus du fil utilisé dans le côté de surface interne comprend une microfibre ayant un diamètre d'un monofilament égal ou inférieur à 6 μm .
2. Gant selon la revendication 1, dans lequel le côté de surface externe du gant fibreux comprend un fil unique et/ou un fil composite recouvert d'une non microfibre ayant un diamètre d'un mono-filament supérieur à 6 μm .
3. Gant selon la revendication 2, dans lequel la non micro fibre comprend au moins un élément sélectionné parmi le groupe constitué de nylon, de polyester et de coton.
4. Gant selon l'une quelconque des revendications 2 ou 3, dans lequel la non microfibre comprend un fil élastique en polyuréthane recouvert avec au moins un élément sélectionné parmi le groupe constitué de nylon, de polyester et de coton.
5. Gant selon l'une quelconque des revendications 1 à 4, dans lequel la microfibre comprend une fibre divisée.
6. Gant selon l'une quelconque des revendications 1 à 5, dans lequel une force d'adhésion de la couche de revêtement n'est pas inférieure à 0,32 N/ mm, ladite force d'adhésion étant testée par une méthode comprenant les étapes consistant à :

couper un morceau d'essai de 25 mm de largeur et de 120 mm de longueur s'étendant le long de la direction longitudinale des doigts à partir de la paume d'un gant et détacher la couche de revêtement et le gant fibreux l'un de l'autre sur environ 20 mm à partir du côté de doigt du morceau d'essai,
attacher les extrémités des deux parties par une machine de test de traction de façon à former un angle de 180 degrés, et
mesurer une force appliquée au détachement,
dans lequel, quand un morceau est déplacé de 150 mm à un taux de déplacement de 50 mm/min, la force appliquée pendant l'exécution de 30 mm à 130 mm est moyennée et la moyenne est prise en tant que force de détachement,
dans lequel T_F [résistance au détachement : N/mm] = F_F [force de détachement : N] / b [largeur du morceau d'essai].

EP 2 614 733 B1

7. Méthode de production du gant selon l'une quelconque des revendications 1 à 6, comprenant les étapes consistant à :

former la couche de revêtement d'un caoutchouc sur la surface externe du gant fibreux par une méthode thermosensible ou une méthode de coagulation.

5

8. Méthode de production du gant selon l'une quelconque des revendications 1 à 6, comprenant les étapes consistant à :

appliquer ou ne pas appliquer un traitement oléophobe au côté de surface externe du gant fibreux, et former la couche de revêtement d'une résine à base de chlorure de vinyle sur celui-ci.

10

15

20

25

30

35

40

45

50

55

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- JP 2008075201 A [0004] [0006]
- JP H045763 B [0005] [0007]
- JP 2010100964 A [0008]