



(11) **EP 2 615 123 B9**

(12) **CORRECTED EUROPEAN PATENT SPECIFICATION**

- (15) Correction information:  
**Corrected version no 1 (W1 B1)**  
**Corrections, see**  
**Description Paragraph(s) 64, 66, 87, 94, 97**
- (48) Corrigendum issued on:  
**13.11.2019 Bulletin 2019/46**
- (45) Date of publication and mention  
of the grant of the patent:  
**17.07.2019 Bulletin 2019/29**
- (21) Application number: **11823355.0**
- (22) Date of filing: **29.07.2011**
- (51) Int Cl.:  
**C08G 63/16** (2006.01) **C08G 63/78** (2006.01)  
**C08K 3/32** (2006.01)
- (86) International application number:  
**PCT/JP2011/067436**
- (87) International publication number:  
**WO 2012/032876 (15.03.2012 Gazette 2012/11)**

(54) **METHOD FOR PRODUCING POLYESTER COMPOSITIONS**

VERFAHREN ZUR HERSTELLUNG VON POLYESTERZUSAMMENSETZUNGEN

PROCÉDÉ DE PRODUCTION DE COMPOSITIONS DE POLYESTER

- |   |  |
|---|--|
| <p>(84) Designated Contracting States:<br/><b>AL AT BE BG CH CY CZ DE DK EE ES FI FR GB<br/>GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO<br/>PL PT RO RS SE SI SK SM TR</b></p> <p>(30) Priority: <b>08.09.2010 JP 2010200524</b></p> <p>(43) Date of publication of application:<br/><b>17.07.2013 Bulletin 2013/29</b></p> <p>(73) Proprietor: <b>Toray Industries, Inc.</b><br/><b>Tokyo, 103-8666 (JP)</b></p> <p>(72) Inventors:<br/>• <b>SUNAKO, Mayumi</b><br/><b>Shizuoka</b><br/><b>411-8652 (JP)</b><br/>• <b>KOJIMA, Hiroji</b><br/><b>Shizuoka</b><br/><b>411-8652 (JP)</b></p> | <p>• <b>SAKAMOTO, Jun</b><br/><b>Otsu-shi</b><br/><b>Shiga 520-8558 (JP)</b></p> <p>(74) Representative: <b>Mewburn Ellis LLP</b><br/><b>City Tower</b><br/><b>40 Basinghall Street</b><br/><b>London EC2V 5DE (GB)</b></p> <p>(56) References cited:<br/><b>EP-A1- 2 495 283 JP-A- 8 059 810</b><br/><b>JP-A- 2002 047 340 JP-A- 2002 047 340</b><br/><b>JP-A- 2007 277 548 JP-A- 2007 277 548</b></p> <p>• <b>KAZUO YUKI HOWA POLYESTER JUSHI</b><br/><b>HANDBOOK, THE NIKKAN KOGYO SHINBUN,</b><br/><b>LTD. 22 December 1989, pages 154 - 166,</b><br/><b>XP008171566</b></p> |
|---|--|

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

**EP 2 615 123 B9**

**Description**

## TECHNICAL FIELD

**[0001]** The present invention relates to a process for producing a polyester composition with good hydrolysis resistance.

## BACKGROUND ART

**[0002]** Polyester has excellent mechanical properties, thermal properties, chemical resistance, electrical properties, and formability and has been used in various applications.

**[0003]** However, because polyester decreases its mechanical properties due to hydrolysis, when used over a long period of time or used in humid situations, various studies to suppress hydrolysis have been carried out. Particularly in films for a solar battery, the outdoor lifetime of 20 years or more is required, and therefore high hydrolysis resistance is required.

## PRIOR ART DOCUMENTS

**[0004]** Patent Document 1, (JP2001-114881A), describes a process for producing polyester containing phosphate of an alkali metal or an alkaline earth metal.

**[0005]** Further, Patent Document 2, (JP2007-277548A), describes a process for producing polyester containing inorganic phosphate, and phosphoric acid is used in combination in Examples.

**[0006]** Patent Document 3, (JP2008-7750A), describes polyethylene terephthalate containing a buffer phosphorus compound, and a phosphorus compound is used in combination in Examples. EP 2495 283A, cited under Art 54(3) EPC, concerns a polyethylene terephthalate composition comprising a copolymer component having at least 3 functional groups in an amount of 0.01mol% to 1.00mol% with response to ethylene terephthalate units.

## PROBLEMS TO BE SOLVED BY THE INVENTION

**[0007]** Only by a metal phosphate, as in the process for producing polyester disclosed in Patent Document 1, initial COOH terminal groups can be suppressed, but it is difficult to suppress the increase in the amount of COOH terminal groups due to hydrolysis, and sufficient hydrolysis resistance cannot be obtained in applications that require long-term durability such as solar battery application.

**[0008]** In the case of the process for producing polyester disclosed in Patent Document 2, because the ratio of phosphoric acid to inorganic phosphate and their amount were inappropriate, inorganic phosphate readily turned into a foreign body, and, although the short-term hydrolysis resistance was excellent, the hydrolysis resistance over a long period of time required in solar battery application and the like was insufficient, and mechanical properties of a film was reduced by the foreign bodies.

**[0009]** In the case of polyethylene terephthalate disclosed in Patent Document 3, the appropriateness of the type, the ratio, the amount, and the like of the phosphorus compound is insufficient, and therefore the hydrolysis resistance and mechanical properties are insufficient for solar battery application.

**[0010]** Examples of the process for producing polyester include the method in which polycondensation is carried out after esterification reaction using dicarboxylic acid as a main raw material (direct polymerization method) and the method in which polycondensation is carried out after transesterification reaction using dicarboxylic acid ester as a main raw material (DMT method). The DMT method disperses particle components well and is excellent in suppression of foreign bodies, but has a problem in that the raw material cost is high compared to the direct polymerization method. On the other hand, the direct polymerization method allows an esterification reaction without a catalyst and further is very cost-effective because the raw material is inexpensive, but has a problem in that the hydrolysis resistance decreases because the amount of COOH terminal groups in the resulting polyester is high compared to the case of the DMT method.

**[0011]** An object of the present invention is to solve the above-described problems in the prior art and provide a process for producing a polyester composition suitable for use in a film with excellent hydrolysis resistance.

## MEANS FOR SOLVING THE PROBLEMS

**[0012]** The invention provides a process for producing a polyester composition as defined in the accompanying claims. Thus, the problem of the present invention can be solved by a process for producing a polyester composition, comprising: carrying out an esterification reaction of dicarboxylic acid component with diol component; and then carrying out a polycondensation reaction, wherein the diol component is added portionwise in at least two portions during the time from the completion of the esterification reaction until the start of the polycondensation reaction, and then alkali metal

phosphate is subsequently added to an esterification reactant having an amount of COOH terminal groups of not more than 150 eq/ton.

## EFFECTS OF THE INVENTION

**[0013]** According to the process for producing polyester of the present invention, the amount of COOH terminal groups of a polyester composition can be controlled, and, at the same time, a polyester composition with excellent hydrolysis resistance can be provided.

## BEST MODE FOR CARRYING OUT THE INVENTION

**[0014]** The present invention will now be described in detail.

**[0015]** In the process for producing a polyester composition of the present invention, it is necessary that, in the process for producing polyester comprising carrying out an esterification reaction of dicarboxylic acid component with diol component, and carrying out a polycondensation reaction, the diol component be added twice or more during the time from the completion of the esterification reaction until the start of the polycondensation reaction, and alkali metal phosphate be added with the amount of COOH terminal groups of an esterification reactant being not more than 150 eq/ton.

**[0016]** As dicarboxylic acid component in the present invention, various dicarboxylic acid components such as aromatic dicarboxylic acids, chain aliphatic dicarboxylic acids, and alicyclic dicarboxylic acids can be used. Among them, aromatic dicarboxylic acids are preferred from the standpoint of mechanical properties, heat resistance, and wet heat resistance of the polyester composition. In particular, terephthalic acid, isophthalic acid, and naphthalene dicarboxylic acid are preferred in view of polymerizability and mechanical properties.

**[0017]** As diol component in the present invention, various diols can be used. Example thereof include, aliphatic diols such as ethylene glycol, 1,2-propanediol, 1,3-propanediol, butanediol, 2-methyl-1,3-propanediol, hexanediol, and neopentyl glycol; alicyclic diols including saturated alicyclic primary diols such as cyclohexanedimethanol, cyclohexanediethanol, decahydronaphthalenedimethanol, decahydronaphthalenediethanol, norbornanedimethanol, norbornanediethanol, tricyclodecanedimethanol, tricyclodecane diethanol, tetracyclododecanedimethanol, tetracyclododecanediethanol, decalin dimethanol, and decalin diethanol, saturated heterocyclic primary diols containing a cyclic ether, such as 2,6-dihydroxy-9-oxabicyclo[3,3,1]nonane, 3,9-bis(2-hydroxy-1,1-dimethylethyl)-2,4,8,10-tetraoxaspiro[5,5]undecane (spiroglycol), 5-methylol-5-ethyl-2-(1,1-dimethyl-2-hydroxyethyl)-1,3-dioxane, and isosorbide, and further various alicyclic diols such as cyclohexanediol, bicyclohexyl-4,4'-diol, 2,2-bis(4-hydroxycyclohexyl)propane, 2,2-bis(4-(2-hydroxyethoxy)cyclohexyl)propane, cyclopentanediol, 3-methyl-1,2-cyclopentanediol, 4-cyclopentene-1,3-diol, and adamantanediol; and aromatic cyclic diols such as bisphenol A, bisphenol S, styrene glycol, 9,9-bis(4-(2-hydroxyethoxy)phenyl)fluorene, and 9,9'-bis(4-hydroxyphenyl)fluorene. In addition to the diols, polyfunctional alcohols such as trimethylolpropane and pentaerythritol can also be used.

**[0018]** Among them, diols having a boiling point of 230°C or lower are preferred because of the ease of distillation out of the reaction system, and aliphatic diols are more preferred because of low cost and high reactivity. Further, ethylene glycol is particularly preferred from the standpoint of mechanical properties.

**[0019]** Generally, when an esterification reaction is carried out using dicarboxylic acid component and diol component as a material, the method in which an esterification reactant is pooled in advance, and a slurry of dicarboxylic acid and diol is added thereto to initiate the esterification reaction is selected in view of improving the handleability of dicarboxylic acid insoluble in diol and reducing the reaction time. The esterification reaction proceeds without pooling an esterification reactant, but pressurizing equipment or a catalyst can be necessary. Also in the present invention, it is desirable to carry out an esterification reaction using a pooled esterification reactant.

**[0020]** In the process for producing a polyester composition in the present invention, when an esterification reactant is obtained from the dicarboxylic acid component and the diol component described above, the molar ratio of the diol component to the dicarboxylic acid component before the start of esterification reaction (diol component/dicarboxylic acid component) is preferably in the range of 1.05 to 1.40 from the standpoint of esterification reactivity and heat resistance. When the molar ratio is in this preferred range, the time cycle can be shortened because the esterification reaction proceeds efficiently, and the heat resistance is maintained because of reduced by-product formation of dimers of the diol component. More preferred is 1.05 to 1.30, and still more preferred is 1.05 to 1.20.

**[0021]** Further, in the esterification reaction in the present invention, an alkali metallic salt, titanium compound, ammonium salt, and the like may be used as a catalyst, but the esterification reaction is preferably carried out without a catalyst because pyrolysis, generation of foreign bodies, and the like at the polycondensation reaction stage can be problematic. The esterification reaction proceeds sufficiently even without a catalyst by autocatalysis of COOH terminal groups.

**[0022]** In the present invention, it is necessary to add the diol component twice or more to the esterification reactant after esterification reaction. By adding the diol component to the esterification reactant, the amount of COOH terminal

groups of the esterification reactant is controlled; the amount of COOH terminal groups of the polyester composition after polycondensation reaction is reduced; and hydrolysis resistance is improved. In addition, by adding alkali metal phosphate before polycondensation reaction, the increase in COOH terminal groups is suppressed, and high hydrolysis resistance is provided.

**[0023]** The addition of the diol component needs to be carried out during the time from the completion of the esterification reaction until the start of the polycondensation reaction. If the addition of the diol component is carried out during the polycondensation reaction, the effect of reducing the amount of COOH terminal groups of the polyester composition finally obtained will be reduced because the diol component does not react efficiently with COOH terminal groups of the esterification reactant. It is preferable to add the diol component during the time from when the esterification reaction rate reaches 90% or more until the intrinsic viscosity reaches 0.3 in the esterification reaction using the dicarboxylic acid component and the diol component. When the addition of diol is carried out under this preferred conditions, by-product formation of diol component dimers is suppressed, and the heat resistance can be maintained; in addition, the amount of COOH terminal groups is less likely to increase because unreacted terephthalic acid is less likely to remain, and the hydrolysis resistance is maintained.

**[0024]** Further, the diol component needs to be added twice or more. By adding the diol component portionwise, the amount of COOH terminal groups of an esterification reactant can be reduced efficiently to minimize the time cycle extended by the addition. Further, by minimizing the extension of the time cycle, the content of dimers of the diol component can be 1.3% by weight or less based on the resulting polyester composition. If the diol component is added to the esterification reactant in one portion, there are concerns about stirring trouble due to solidification of the esterification reactant and delay of time cycle because the temperature in the reaction system decreases sharply. Although there is no upper limit on the number of additions, the number of additions is preferably not more than ten times and more preferably not more than five times. When the number is not more than such a preferred number of additions, the production efficiency will not be reduced, and the effect of reducing the amount of COOH terminal groups can be maintained.

**[0025]** When the diol component is added, the lower limit of the temperature in the reaction system is preferably not less than 210°C, and, further, adding while maintaining not less than 220°C is preferred. The upper limit of the temperature in the reaction system is preferably not more than 260°C and more preferably not more than 250°C. Further, the second and subsequent addition of the diol component is preferably carried out after the temperature in the reaction system returns to 230°C or higher and more preferably 235°C or higher. By maintaining the temperature in the system at 210 to 260°C, the addition can be repeated efficiently, and the amount of COOH terminal groups of the esterification reactant can be rapidly reduced.

Further, stirring trouble due to solidification of the esterification reactant and delay of time cycle can be prevented.

**[0026]** Further, the amount of the diol component added after the esterification reaction is preferably 0.15-fold to 0.5-fold mole compared to the amount of the total dicarboxylic acid component per addition in view of production efficiency and heat resistance, and more preferred is 0.15-fold to 0.3-fold mole. When the amount per addition is in this range, the COOH terminal groups of the esterification reactant can be reduced effectively without impairing the heat resistance, and a polyester composition with good hydrolysis resistance can be obtained. In addition, the amount may be varied from addition to addition.

**[0027]** The lower limit of the total amount of the diol component added is preferably 0.3-fold mole or greater, more preferably 0.4-fold mole or greater, and still more preferably 0.5-fold mole or greater compared to the amount of the total dicarboxylic acid component. The upper limit is preferably up to 1.5-fold mole, more preferably up to 1.0-fold mole, and still more preferably up to 0.9-fold mole. When the total amount of the diol component added is in the range described above, COOH terminal groups of the esterification reactant and the diol component can be reacted sufficiently; consequently, the amount of COOH terminal groups of the resulting polyester composition can be efficiently reduced, and a polyester composition having good hydrolysis resistance with maintained heat resistance can be obtained.

**[0028]** Further, it is preferable to distill the COOH terminal groups of the esterification reactant and the unreacted diol component out of the reaction system after the diol component is added in view of shorter time cycle, suppressed by-product formation of dimers of the diol component, and heat resistance. By distilling off the unreacted diol component out of the reaction system, the temperature rapidly returns, and consequently the content of dimers of the diol component can be 1.3% by weight or less based on the resulting polyester composition.

**[0029]** In the process for producing a polyester composition of the present invention, when the diol component is added, it is preferable to add a metal compound having an esterification reaction activity simultaneously with the diol component. As a metal compound in the present invention, metallic salts are preferred, and specific examples thereof include metal chlorides, metal acetates, metal carbonates, and the like, among which metal acetates such as sodium acetate, calcium acetate, magnesium acetate, manganese acetate, cobalt acetate, zinc acetate, and tin acetate are preferred. Further, in view of reactivity of COOH terminal groups of the esterification reactant with the diol component and hydrolysis resistance, calcium acetate, magnesium acetate, and manganese acetate are preferred. For reducing the amount of COOH terminal groups efficiently, the lower limit of the addition amount is preferably 1.0 mol/ton or more

and more preferably 2.0 mol/ton or more in terms of the concentration in the resulting polyester composition. The upper limit of the addition amount is preferably 3.5 mol/ton or less in view of hydrolysis resistance, and more preferred is 3.0 mol/ton or less. Further, when the diol component is added more than once, it is preferable to simultaneously add the whole amount of the metallic salt at the first addition. By adding the metallic salt together with the diol component, reactivity of COOH terminals of the esterification reactant with the diol component is improved, and the COOH terminals can be reduced efficiently, whereby a polyester composition with good hydrolysis resistance can be obtained.

**[0030]** In the process for producing a polyester composition of the present invention, after the addition of the diol component, it is necessary to add alkali metal phosphate during the time until the start of the polycondensation reaction. When alkali metal phosphate is added, it is necessary that, after the esterification reaction, the diol component is added, and then the alkali metal phosphate be added to a reaction system having an esterification reactant with the amount of COOH terminal groups of not more than 150 eq/ton, more preferably not more than 100 eq/ton, and still more preferably not more than 50 eq/ton. By adding alkali metal phosphate when the amount of COOH terminal groups of an esterification reactant is 150 eq/ton or less, the amount of COOH terminal groups of the resulting polyester composition can be 20 eq/ton or less, and a polyester composition having high hydrolysis resistance can be obtained. If the amount of COOH terminal groups of an esterification reactant when adding alkali metal phosphate is more than 150 eq/ton, the amount of COOH terminal groups of the resulting polyester composition will be large, and sufficient hydrolysis resistance cannot be obtained. The smaller the amount of COOH terminal groups of an esterification reactant, the better the hydrolysis resistance, but the criterion of the lower limit is preferably 10 eq/ton. If the amount of COOH terminal groups is not less than 10 eq/ton, it is not necessary to add a large amount of diol component over a long period of time, and reduced heat resistance due to by-product formation of dimers of the diol component can be prevented. The diol component may be further added after alkali metal phosphate was added.

**[0031]** Examples of the alkali metal phosphate in the present invention include sodium dihydrogenphosphate, disodium hydrogenphosphate, trisodium phosphate, potassium dihydrogenphosphate, dipotassium hydrogenphosphate, tripotassium phosphate, lithium dihydrogenphosphate, dilithium hydrogenphosphate, and trilithium phosphate, but are not limited thereto. Among them, sodium dihydrogenphosphate and potassium dihydrogenphosphate are preferred in view of hydrolysis resistance.

**[0032]** The lower limit of the addition amount of alkali metal phosphate, in view of hydrolysis resistance, is preferably 0.1 mol/ton or more and more preferably 0.4 mol/ton or more in terms of the concentration in the resulting polyester composition. The upper limit of the addition amount, in view of suppression of foreign bodies and hydrolysis resistance, is preferably 7.0 mol/ton or less, more preferably 4.0 mol/ton or less, and still more preferably 2.0 mol/ton or less. By adding alkali metal phosphate in this range, a polyester composition with good hydrolysis resistance can be obtained.

**[0033]** As a method of adding alkali metal phosphate, adding after mixing with the diol component and a phosphorus compound in advance is preferred in view of hydrolysis resistance. At this time, the phosphorus compound is preferably mixed in an amount of 0.1-fold mole to 7.5-fold mole, more preferably 0.3-fold mole to 5.0-fold mole, and still more preferably 1.0-fold mole to 2.0-fold mole compared to the amount of the alkali metal phosphate. By mixing the phosphorus compound in an amount of 0.1-fold mole to 7.5-fold mole compared to the amount of the alkali metal phosphate, the reaction activity in hydrolysis of the resulting polyester composition can be controlled, and a polyester composition with good hydrolysis resistance can be obtained.

**[0034]** The lower limit of the addition amount of the phosphorus compound mixed with alkali metal phosphate, in view of hydrolysis resistance and heat resistance, is preferably 0.1 mol/ton or more and more preferably 1.0 mol/ton or more in terms of the concentration in the resulting polyester composition. The upper limit of the addition amount is preferably 4.0 mol/ton or less and more preferably 2.5 mol/ton or less in view of hydrolysis resistance. By mixing the phosphorus compound with alkali metal phosphate in the range described above, hydrolysis resistance can be improved without impairing production efficiency.

**[0035]** Further, as a method of adding alkali metal phosphate, adding after making into a solution or slurry in advance is preferred in view of suppression of foreign bodies. As a solvent, a diol compound such as ethylene glycol is used, and it is preferable to prepare at a concentration of 0.5% by weight to 10% by weight and more preferably 1% by weight to 3% by weight. By adding as a solution of the concentration described above, a polyester composition with good hydrolysis resistance can be obtained without impairing heat resistance. Examples of the phosphorus compound mixed with alkali metal phosphate include phosphoric acid, trimethyl phosphate, trimethyl phosphonoacetate, dimethyl phenylphosphonate, and the like, but are not limited thereto. Among them, phosphoric acid is preferred from the standpoint of hydrolysis resistance.

**[0036]** A polymerization catalyst used in the process for producing a polyester composition of the present invention is not particularly limited, and various catalysts can be used. For example, complex oxides of aluminum and silica as well as antimony compounds such as antimony trioxide, germanium compounds such as germanium dioxide, and titanium compounds such as titanium alkoxide can be used.

**[0037]** In the process for producing a polyester composition of the present invention, it is preferable to add a tri- or more functional copolymer component during the time until the start of a polycondensation reaction. Examples of tri- or

more functional copolymer components include, for example, polycarboxylic acids such as trimellitic acid, cyclohexanetricarboxylic acid, biphenyltetracarboxylic acid, pyromellitic acid, butanetetracarboxylic acid, and trimer acids obtained by trimerizing long-chain aliphatic carboxylic acid, and anhydrides and esters thereof; polyhydric alcohols such as glycerin, pentaerythritol, dipentaerythritol, trimethylolpropane, ditrimethylolpropane, trihydroxybenzene carboxylic acid, and trihydroxyhexane; polyhydroxycarboxylic acids such as citric acid, dihydroxybenzene carboxylic acid, and dihydroxynaphthalene carboxylic acid, and anhydrides and esters thereof; and the like. In particular, a trifunctional copolymer component is preferred in view of film formability.

**[0038]** For the time for adding a tri- or more functional copolymer component, it is preferable to add during the time until the start of the polycondensation reaction, specifically, before the intrinsic viscosity reaches 0.3. A polyester oligomer with an intrinsic viscosity of less than 0.3, because of its low viscosity, is able to allow the tri- or more functional copolymer component to react uniformly. Further, from the standpoint of effectively preventing a local reaction from proceeding to cause large foreign bodies, the interval until the addition of other additives is preferably 5 minutes or more.

**[0039]** The lower limit of the addition amount of the tri- or more functional copolymer component, in view of the hydrolysis resistance after film formation, is preferably 0.01 mol% or more and more preferably 0.05 mol% or more based on the whole acid components obtained. The upper limit of the addition amount is preferably 1.00 mol% or less and more preferably 0.50 mol% or less in view of gelation control. When the addition amount of the tri- or more functional copolymer component is in the preferred range described above, a sufficient hydrolysis resistance effect is provided, and progression of gelation is prevented, whereby good formability can be maintained.

**[0040]** As a method of adding the tri- or more functional copolymer component, in view of reactivity and suppression of foreign bodies, adding as an ethylene glycol solution of 0.5% by mass to 5% by mass is preferred. By adding as an ethylene glycol solution in the range described above, the tri- or more functional copolymer component and the polyester oligomer can be allowed to react uniformly. When the concentration of the tri- or more functional copolymer component in the ethylene glycol solution is in the preferred range described above, the amount of ethylene glycol added into the system is not too large, and therefore the amount of diethylene glycol, a by-product, will not increase, whereby the heat resistance and hydrolysis resistance are maintained; at the same time, a local reaction is less likely to occur, and large foreign bodies are less likely to generate.

**[0041]** The process for producing a polyester composition in the present invention will now be described by way of specific example.

**[0042]** First, to an esterification reactor charged with bis(hydroxyethyl) terephthalate dissolved at 255°C, slurry of terephthalic acid and ethylene glycol (1.15-fold mole compared to the amount of terephthalic acid) is gradually added using a snake pump to promote an esterification reaction. The temperature in the reaction system is controlled to be 245 to 255°C, and the esterification reaction is considered to be complete when the reaction rate reached 95%.

**[0043]** To the esterification reactant at 255°C thus obtained, ethylene glycol and manganese acetate in an amount of 0.27-fold mole compared to the amount of terephthalic acid are simultaneously added. At this time, it is preferable to set the temperature in the system at 210 to 260°C so that the esterification reactant will not be solidified. Unreacted ethylene glycol is distilled off, and when the temperature in the system returns to 235°C, the second addition is carried out using ethylene glycol in an amount of 0.27-fold mole compared to the amount of terephthalic acid. Ethylene glycol is distilled off, and when the temperature returns to 235°C again, the third addition is carried out using ethylene glycol in an amount of 0.27-fold mole; ethylene glycol in an amount of 0.81-fold mole in total is added in three portions. Depending on the addition amount, the amount per addition and the number of addition can be varied.

**[0044]** After the total amount is added, a sodium dihydrogenphosphate/phosphoric acid/ethylene glycol mixed solution is added when the temperature in the system returns to 235°C.

**[0045]** Thereafter, while increasing the temperature in a polymerization apparatus gradually to 280°C, the pressure in the polymerization apparatus is gradually reduced from normal pressure to 133 Pa or less to distill off ethylene glycol. At this time, if the amount of COOH terminal groups of the polyester composition is desired to be lower, it is preferable to set the polymerization temperature low. The reaction is terminated when a predetermined stirring torque is reached, and the reaction system is brought to normal pressure with nitrogen. The resultant is discharged in strands into cold water and cut to obtain a polyester composition in the form of a pellet.

## EXAMPLES

**[0046]** The present invention will now be described specifically by way of example.

**[0047]** The measurements of physical properties were performed according to the following method.

### (1) Intrinsic Viscosity (IV)

**[0048]** The measurement was made at 25°C using o-chlorophenol as a solvent.

## (2) The Amount of COOH Terminal Groups

**[0049]** The measurement was made according to the Maurice's method described in the literature below.

**[0050]** M. J. Maurice, F. Huizinga "Anal. Chim. Acta" Vol. 22, p-363 (1960)

(3) Evaluation of Hydrolysis Resistance ( $\Delta$ COOH)

**[0051]** A polyester composition in the form of a pellet was heat treated at 155°C and 100% RH for 4 hours, and the difference in the amount of COOH terminal groups before and after the treatment (the amount of COOH terminal groups after treatment - the amount of COOH terminal groups before treatment) was compared. When the difference in the amount of COOH terminal groups at this time ( $\Delta$ COOH) was 50 eq/ton or less, the polyester composition was judged to have good hydrolysis resistance.

**[0052]** As a treatment apparatus, a heat treatment apparatus PRESSER COOKER 306SIII (manufactured by HIRAYA-MA MANUFACTURING CORP.) was used.

## (4) DEG (Diethylene Glycol) Content in Polyester Composition

**[0053]** A polyester composition was dissolved in monoethanolamine as a solvent, and a 1,6-hexanediol/methanol mixed solution was added to the solution. The resulting mixture was cooled and neutralized with terephthalic acid, and then centrifuged, after which a supernatant fluid was measured using gas chromatography (GC-14A, available from Shimadzu Corporation).

## (Example 1)

**[0054]** While maintaining the temperature in the reaction system in which an esterification reactor was charged in advance with 105 parts by weight of bis(hydroxyethyl) terephthalate (equivalent to 100 parts by weight of polyethylene terephthalate (hereinafter referred to as PET)) at 245 to 255°C, a slurry comprising 86 parts by weight of terephthalic acid and 37 parts by weight of ethylene glycol was fed into the reaction system with a snake pump, and esterification reaction was allowed to proceed to distill water. When the esterification reaction rate reached 95%, the esterification reaction was terminated to obtain an esterification reactant with the amount of COOH terminal groups of 334 eq/ton. The obtained esterification reactant in an amount of 105 parts by weight (equivalent to 100 parts by weight of PET) was loaded into a polymerization apparatus equipped with a distillation apparatus, and 0.06 parts by weight (equivalent to 2.4 mol/ton) of manganese acetate, 0.03 parts by weight (equivalent to 1.0 mol/ton) of antimony trioxide, and 8.7 parts by weight (0.27-fold mole compared to the amount of terephthalic acid in 100 parts by weight of PET) of ethylene glycol were simultaneously added to distill off unreacted ethylene glycol. When the temperature in the system returned to 235°C, 8.7 parts by weight of ethylene glycol was added again, after which the temperature was returned to 235°C again while distilling off the unreacted ethylene glycol, and, further, the third addition was carried out using 8.7 parts by weight of ethylene glycol; 26.1 parts by weight in total (0.81-fold mole compared to the amount of terephthalic acid in 100 parts by weight of PET) of ethylene glycol was added. After completion of the addition, when the reaction system temperature returned to 235°C while distilling off the unreacted ethylene glycol and the amount of COOH terminal groups decreased to 48 eq/ton, a solution of 0.027 parts by weight (equivalent to 1.7 mol/ton) of sodium dihydrogenphosphate dihydrate/0.02 parts by weight (equivalent to 2.0 mol/ton, 1.2-fold mole compared to the amount of alkali metal phosphate) of phosphoric acid/1.6 parts by weight of ethylene glycol was added. The ethylene glycol distilled off was 5.5 parts by weight in total.

**[0055]** Thereafter, while increasing the temperature in the polymerization apparatus from 235°C to 280°C over 90 minutes, the pressure in the polymerization apparatus was gradually reduced from normal pressure to 133 Pa or less to distill off ethylene glycol. The reaction was terminated when the melt viscosity equivalent to the intrinsic viscosity of 0.65 was reached, and the reaction system was brought to normal pressure with nitrogen gas and a molten polymer was discharged in strands from the lower part of the polymerization apparatus into cold water. The polyester strand discharged and solidified was cut to obtain a polyester composition in the form of a pellet. The properties of the polyester composition obtained are shown in Table 1. This polyester composition had good hydrolysis resistance.

## (Examples 2 to 9, Comparative Examples 1 to 3)

**[0056]** A polyester composition was obtained in the same manner as in Example 1 except that the amount of the ethylene glycol added and the number of additions were changed.

**[0057]** The polyester composition obtained in Examples 2 to 7 also had sufficient hydrolysis resistance.

**[0058]** The polyester composition obtained in Examples 8 and 9 had good hydrolysis resistance similar to that in Example 1.

**[0059]** In Comparative Example 1, the addition of ethylene glycol was not performed, and the amount of COOH terminal groups when adding alkali metal phosphate was over the upper limit; therefore, the amount of COOH terminal groups of the polyester composition was large, and sufficient hydrolysis resistance could not be obtained.

**[0060]** In Comparative Example 2, the amount of COOH terminal groups after the addition of ethylene glycol was over the upper limit; therefore, the amount of COOH terminal groups of the polyester composition was large, and sufficient hydrolysis resistance could not be obtained.

**[0061]** In Comparative Example 3, because of the addition of ethylene glycol in one portion, it took time for the temperature in the system to return, and, further, effective reaction with COOH terminal groups could not be achieved; therefore, the amount of COOH terminal groups of the polyester composition and the DEG content were large, and sufficient hydrolysis resistance could not be obtained.

**[0062]** The results of these Examples and Comparative Examples are shown in Tables 1 and 2.

(Example 10)

**[0063]** A polyester composition was obtained in the same manner as in Example 1 except that when ethylene glycol was added, the unreacted ethylene glycol was not distilled off but refluxed. This polyester composition had sufficient hydrolysis resistance. The results are shown in Table 3.

(Example 11)

**[0064]** While maintaining the temperature in the reaction system in which an esterification reactor was charged in advance with 105 parts by weight of bishydroxyethyl terephthalate (equivalent to 100 parts by weight of PET) at 245 to 255°C, a slurry comprising 86 parts by weight of terephthalic acid and 37 parts by weight of ethylene glycol was fed into the reaction system with a snake pump, and esterification reaction was allowed to proceed to distill water. When the esterification reaction rate reached 95%, the esterification reaction was terminated to obtain an esterification reactant with the amount of COOH terminal groups of 334 eq/ton. The obtained esterification reactant in an amount of 105 parts by weight (equivalent to 100 parts by weight of PET) was loaded into a polymerization apparatus equipped with a distillation apparatus, and 8.7 parts by weight (0.27-fold mole compared to the amount of terephthalic acid in 100 parts by weight of PET) of ethylene glycol was added to distill off unreacted ethylene glycol. When the temperature in the system returned to 235°C, 8.7 parts by weight of ethylene glycol was added again, after which the temperature was returned to 235°C again while distilling off the unreacted ethylene glycol, and, further, the third addition was carried out using 8.7 parts by weight of ethylene glycol; 26 parts by weight in total (0.8-fold mole compared to the amount of terephthalic acid in 100 parts by weight of PET) of ethylene glycol was added. After completion of the addition, when the amount of COOH terminal groups decreased to 88 eq/ton, 0.06 parts by weight of manganese acetate and 0.03 parts by weight of antimony trioxide were added, and, after 5 minutes, a solution of 0.027 parts by weight (equivalent to 1.7 mol/ton) of sodium dihydrogenphosphate dihydrate/0.02 parts by weight (equivalent to 2.0 mol/ton) of phosphoric acid/1.6 parts by weight of ethylene glycol was added. The ethylene glycol distilled off was 15.1 parts by weight in total.

**[0065]** Thereafter, while increasing the temperature in the polymerization apparatus from 235°C to 280°C over 90 minutes, the pressure in the polymerization apparatus was gradually reduced from normal pressure to 133 Pa or less to distill off ethylene glycol. The reaction was terminated when the melt viscosity equivalent to the intrinsic viscosity of 0.65 was reached, and the reaction system was brought to normal pressure with nitrogen gas and a molten polymer was discharged in strands from the lower part of the polymerization apparatus into cold water. The polyester strand discharged and cooled was cut to obtain a polyester composition in the form of a pellet. This polyester composition had sufficient hydrolysis resistance. The results are shown in Table 3.

(Example 12)

**[0066]** While maintaining the temperature in the reaction system in which an esterification reactor was charged in advance with 105 parts by weight of bishydroxyethyl terephthalate (equivalent to 100 parts by weight of PET) at 245 to 255°C, a slurry comprising 86 parts by weight of terephthalic acid and 37 parts by weight of ethylene glycol was fed into the reaction system with a snake pump, and esterification reaction was allowed to proceed to distill water. When the esterification reaction rate reached 95%, the esterification reaction was terminated to obtain an esterification reactant with the amount of COOH terminal groups of 334 eq/ton. The obtained esterification reactant in an amount of 105 parts by weight (equivalent to 100 parts by weight of PET) was loaded into a polymerization apparatus equipped with a distillation apparatus, and 0.06 parts by weight (equivalent to 2.4 mol/ton) of manganese acetate, 0.03 parts by weight (equivalent to 1.0 mol/ton) of antimony trioxide, and 8.7 parts by weight (0.27-fold mole compared to the amount of terephthalic acid in 100 parts by weight of PET) of ethylene glycol were simultaneously added to distill off unreacted ethylene glycol. When the temperature in the system returned to 225°C, 8.7 parts by weight of ethylene glycol was added



again, after which the temperature was returned to 225°C again while distilling off the unreacted ethylene glycol, and, further, the third addition was carried out using 8.7 parts by weight of ethylene glycol; 26.1 parts by weight in total (0.81-fold mole compared to the amount of terephthalic acid in 100 parts by weight of PET) of ethylene glycol was added. After completion of the addition, when the reaction system temperature returned to 235°C while distilling off the unreacted ethylene glycol and the amount of COOH terminal groups decreased to 125 eq/ton, a solution of 0.027 parts by weight (equivalent to 1.7 mol/ton) of sodium dihydrogenphosphate dihydrate/0.02 parts by weight (equivalent to 2.0 mol/ton, 1.2-fold mole compared to the amount of alkali metal phosphate) of phosphoric acid/1.6 parts by weight of ethylene glycol was added. The ethylene glycol distilled off was 8.5 parts by weight in total.

[0067] Thereafter, while increasing the temperature in the polymerization apparatus from 235°C to 280°C over 90 minutes, the pressure in the polymerization apparatus was gradually reduced from normal pressure to 133 Pa or less to distill off ethylene glycol. The reaction was terminated when the melt viscosity equivalent to the intrinsic viscosity of 0.65 was reached, and the reaction system was brought to normal pressure with nitrogen gas and a molten polymer was discharged in strands from the lower part of the polymerization apparatus into cold water. The polyester strand discharged and solidified was cut to obtain a polyester composition in the form of a pellet. This polyester composition had sufficient hydrolysis resistance. The results are shown in Table 3.

(Examples 13 to 20)

[0068] A polyester composition was obtained in the same manner as in Example 1 except that the amount of a metallic salt simultaneously added when ethylene glycol was added and the type of metallic salt were changed.

[0069] The polyester composition obtained in Examples 13 to 15 had such sufficient hydrolysis resistance that will not cause any problem when used in a solar battery or the like.

[0070] The polyester composition obtained in Examples 16 to 20 also had sufficient hydrolysis resistance.

[0071] The results of these Examples are shown in Table 4.

(Examples 21 to 28)

[0072] A polyester composition was obtained in the same manner as in Example 1 except that the amount of alkali metal phosphate added after addition and the type of alkali metal phosphate were changed.

[0073] The polyester composition obtained in Examples 21 to 25, 27, and 28 had good hydrolysis resistance similar to that in Example 1.

[0074] The polyester composition obtained in Example 26 had sufficient hydrolysis resistance.

[0075] The results of these Examples are shown in Table 5.

(Examples 29 to 37)

[0076] A polyester composition was obtained in the same manner as in Example 1 except that the type of phosphorus compound mixed with alkali metal phosphate, the addition amount of the phosphorus compound, and the molar ratio of the mixed phosphorus compound (to alkali metal phosphate) were changed.

[0077] The polyester composition obtained in Examples 29 and 30 had hydrolysis resistance at such a level that no problem occurs when used in solar battery application or the like.

[0078] The polyester composition obtained in Examples 31 to 33 had good hydrolysis resistance similar to that of Example 1.

[0079] The polyester composition obtained in Example 34 had hydrolysis resistance at such a level that no problem occurs when used in solar battery application or the like.

[0080] The polyester composition obtained in Examples 35 to 37 had sufficient hydrolysis resistance.

[0081] The results of these Examples are shown in Tables 6 and 7.

(Example 38)

[0082] While maintaining the temperature in the reaction system in which an esterification reactor was charged in advance with 105 parts by weight of bis(hydroxyethyl) terephthalate (equivalent to 100 parts by weight of PET) at 245 to 255°C, a slurry comprising 86 parts by weight of terephthalic acid and 37 parts by weight of ethylene glycol was supplied with a snake pump, and esterification reaction was allowed to proceed to distill water. When the esterification reaction rate reached 95%, the esterification reaction was terminated to obtain an esterification reactant with the amount of COOH terminal groups of 334 eq/ton. The obtained esterification reactant in an amount of 105 parts by weight (equivalent to 100 parts by weight of PET) was loaded into a polymerization apparatus equipped with a distillation apparatus, and 0.06 parts by weight (equivalent to 2.4 mol/ton) of manganese acetate, 0.03 parts by weight (equivalent to 1.0 mol/ton) of

antimony trioxide, and 8.7 parts by weight (0.27-fold mole compared to the amount of terephthalic acid in 100 parts by weight of PET) of ethylene glycol were simultaneously added to distill off unreacted ethylene glycol. When the temperature in the system returned to 235°C, 8.7 parts by weight of ethylene glycol was added again, after which the temperature was returned to 235°C again while distilling off the unreacted ethylene glycol, and, further, the third addition was carried out using 8.7 parts by weight of ethylene glycol; 26 parts by weight in total (0.8-fold mole compared to the amount of terephthalic acid in 100 parts by weight of PET) of ethylene glycol was added. After completion of the addition, when the reaction system temperature returned to 235°C while distilling off the unreacted ethylene glycol and the amount of COOH terminal groups decreased to 48 eq/ton, a solution of 0.027 parts by weight (equivalent to 1.7 mol/ton) of sodium dihydrogenphosphate dihydrate/1.4 parts by weight of ethylene glycol and 0.02 parts by weight (equivalent to 2.0 mol/ton) of phosphoric acid/0.2 parts by weight of ethylene glycol was added without mixing. The ethylene glycol distilled off was 5.5 parts by weight in total.

**[0083]** Thereafter, while increasing the temperature in the polymerization apparatus from 235°C to 280°C over 90 minutes, the pressure in the polymerization apparatus was gradually reduced from normal pressure to 133 Pa or less to distill off ethylene glycol. The reaction was terminated when the melt viscosity equivalent to the intrinsic viscosity of 0.65 was reached, and the reaction system was brought to normal pressure with nitrogen gas and a molten polymer was discharged in strands from the lower part of the polymerization apparatus into cold water. The polyester strand discharged and solidified was cut to obtain a polyester composition in the form of a pellet.

**[0084]** This polyester composition had hydrolysis resistance at such a level that no problem occurs when used in solar battery application or the like. The results are shown in Table 7.

(Comparative Example 4)

**[0085]** A polyester composition was obtained in the same manner as in Example 1 except that a metallic salt and alkali metal phosphate were not added.

**[0086]** Because a metallic salt was not added simultaneously in the addition, effective reaction with COOH terminal groups could not be achieved, and the amount of COOH terminal groups of the polyester composition and the DEG content tended to increase compared to Example 1. Further, because alkali metal phosphate was not added, this polyester composition of Comparative Example 4 did not provide sufficient hydrolysis resistance. The results are shown in Table 7.

(Example 39)

**[0087]** While maintaining the temperature in the reaction system in which an esterification reactor was charged in advance with 105 parts by weight of bis(hydroxyethyl) terephthalate (equivalent to 100 parts by weight of PET) at 245 to 255°C, a slurry comprising 86 parts by weight of terephthalic acid and 37 parts by weight of ethylene glycol was fed into the reaction system with a snake pump, and esterification reaction was allowed to proceed to distill water. When the esterification reaction rate reached 95%, the esterification reaction was terminated to obtain an esterification reactant with the amount of COOH terminal groups of 334 eq/ton. The obtained esterification reactant in an amount of 105 parts by weight (equivalent to 100 parts by weight of PET) was loaded into a polymerization apparatus equipped with a distillation apparatus, and 0.06 parts by weight (equivalent to 2.4 mol/ton) of manganese acetate, 0.03 parts by weight (equivalent to 1.0 mol/ton) of antimony trioxide, and 8.7 parts by weight (0.27-fold mole compared to the amount of terephthalic acid in 100 parts by weight of PET) of ethylene glycol were simultaneously added to distill off unreacted ethylene glycol. When the temperature in the system returned to 235°C, 8.7 parts by weight of ethylene glycol was added again, after which the temperature was returned to 235°C again while distilling off the unreacted ethylene glycol, and, further, the third addition was carried out using 8.7 parts by weight of ethylene glycol; 26.1 parts by weight in total (0.81-fold mole compared to the amount of terephthalic acid in 100 parts by weight of PET) of ethylene glycol was added. After completion of the addition, when the reaction system temperature returned to 235°C while distilling off the unreacted ethylene glycol, 0.01 parts by weight of trimellitic anhydride (1% by weight of ethylene glycol solution) was added as a copolymer component (the amount of COOH terminal groups after the addition was 45 eq/ton). After 5 minutes, a solution of 0.027 parts by weight (equivalent to 1.7 mol/ton) of sodium dihydrogenphosphate dihydrate/0.02 parts by weight (equivalent to 2.0 mol/ton, 1.2-fold mole compared to the amount of alkali metal phosphate) of phosphoric acid/1.6 parts by weight of ethylene glycol was added. The ethylene glycol distilled off was 5.5 parts by weight in total.

**[0088]** Thereafter, while increasing the temperature in the polymerization apparatus from 235°C to 280°C over 90 minutes, the pressure in the polymerization apparatus was gradually reduced from normal pressure to 133 Pa or less to distill off ethylene glycol. The reaction was terminated when the melt viscosity equivalent to the intrinsic viscosity of 0.65 was reached, and the reaction system was brought to normal pressure with nitrogen gas and a molten polymer was discharged in strands from the lower part of the polymerization apparatus into cold water. The polyester strand discharged and solidified was cut to obtain a polyester composition in the form of a pellet. Similarly to Example 1, a polyester composition with good hydrolysis resistance was obtained. The properties of the polyester composition obtained

are shown in Table 8.

(Examples 40 to 44)

- 5 **[0089]** A polyester composition was obtained in the same manner as in Example 39 except that the amount of the trimellitic anhydride added as a copolymer component was changed.
- [0090]** In Examples 40 and 41, the addition amount of trimellitic anhydride was increased compared to Example 39, whereby the polyester composition had a reduced amount of COOH terminal groups and had good hydrolysis resistance.
- 10 **[0091]** The polyester compositions obtained in Examples 42 and 43 had sufficient hydrolysis resistance and were at such a level that no problem occurs when used in solar battery application or the like.
- [0092]** The polyester composition obtained in Example 44 had sufficient hydrolysis resistance.
- [0093]** The results of these Examples are shown in Table 8.

(Example 45)

- 15 **[0094]** While maintaining the temperature in the reaction system in which an esterification reactor was charged in advance with 105 parts by weight of bishydroxyethyl terephthalate (equivalent to 100 parts by weight of PET) at 245 to 255°C, a slurry comprising 86 parts by weight of terephthalic acid, 0.2 parts by weight of trimellitic anhydride, and 37 parts by weight of ethylene glycol was fed into the reaction system with a snake pump, and esterification reaction was
- 20 allowed to proceed to distill water. When the esterification reaction rate reached 95%, the esterification reaction was terminated to obtain an esterification reactant with the amount of COOH terminal groups of 335 eq/ton. The obtained esterification reactant in an amount of 105 parts by weight (equivalent to 100 parts by weight of PET) was loaded into a polymerization apparatus equipped with a distillation apparatus, and 8.7 parts by weight (0.27-fold mole compared to the amount of terephthalic acid in 100 parts by weight of PET) of ethylene glycol was added to distill off unreacted
- 25 ethylene glycol. When the temperature in the system returned to 235°C, 8.7 parts by weight of ethylene glycol was added again, after which the temperature was returned to 235°C again while distilling off the unreacted ethylene glycol, and, further, the third addition was carried out using 8.7 parts by weight of ethylene glycol; 26 parts by weight in total (0.8-fold mole compared to the amount of terephthalic acid in 100 parts by weight of PET) of ethylene glycol was added. After completion of the addition, when the amount of COOH terminal groups decreased to 46 eq/ton, 0.06 parts by weight
- 30 of manganese acetate and 0.03 parts by weight of antimony trioxide were added, and, after 5 minutes, a solution of 0.027 parts by weight (equivalent to 1.7 mol/ton) of sodium dihydrogen phosphatedihydrate/0.02 parts by weight (equivalent to 2.0 mol/ton) of phosphoric acid/1.6 parts by weight of ethylene glycol was added. The ethylene glycol distilled off was 15.1 parts by weight in total.
- [0095]** Thereafter, while increasing the temperature in the polymerization apparatus from 235°C to 280°C over 90
- 35 minutes, the pressure in the polymerization apparatus was gradually reduced from normal pressure to 133 Pa or less to distill off ethylene glycol. The reaction was terminated when the melt viscosity equivalent to the intrinsic viscosity of 0.65 was reached, and the reaction system was brought to normal pressure with nitrogen gas and a molten polymer was discharged in strands from the lower part of the polymerization apparatus into cold water. The polyester strand discharged and cooled was cut to obtain a polyester composition in the form of a pellet.
- 40 **[0096]** The polyester composition obtained in Example 45 had sufficient hydrolysis resistance. The results are shown in Table 8.

(Example 46)

- 45 **[0097]** While maintaining the temperature in the reaction system in which an esterification reactor was charged in advance with 105 parts by weight of bishydroxyethyl terephthalate (equivalent to 100 parts by weight of PET) at 245 to 255°C, a slurry comprising 86 parts by weight of terephthalic acid and 37 parts by weight of ethylene glycol was fed into the reaction system with a snake pump, and esterification reaction was allowed to proceed to distill water. When the esterification reaction rate reached 95%, the esterification reaction was terminated to obtain an esterification reactant
- 50 with the amount of COOH terminal groups of 334 eq/ton. The obtained esterification reactant in an amount of 105 parts by weight (equivalent to 100 parts by weight of PET) was loaded into a polymerization apparatus equipped with a distillation apparatus, and 0.06 parts by weight (equivalent to 2.4 mol/ton) of manganese acetate, 0.03 parts by weight (equivalent to 1.0 mol/ton) of antimony trioxide, and 8.7 parts by weight (0.27-fold mole compared to the amount of terephthalic acid in 100 parts by weight of PET) of ethylene glycol were simultaneously added to distill off unreacted
- 55 ethylene glycol. When the temperature in the system returned to 235°C, 8.7 parts by weight of ethylene glycol was added again, after which the temperature was returned to 235°C again while distilling off the unreacted ethylene glycol, and, further, the third addition was carried out using 8.7 parts by weight of ethylene glycol; 26.1 parts by weight in total (0.81-fold mole compared to the amount of terephthalic acid in 100 parts by weight of PET) of ethylene glycol was added.

After completion of the addition, when the reaction system temperature returned to 235°C while distilling off the unreacted ethylene glycol and the amount of COOH terminal groups decreased to 48 eq/ton, a solution of 0.027 parts by weight (equivalent to 1.7 mol/ton) of sodium dihydrogenphosphate dihydrate/0.02 parts by weight (equivalent to 2.0 mol/ton, 1.2-fold mole compared to the amount of alkali metal phosphate) of phosphoric acid/1.6 parts by weight of ethylene glycol was added. The ethylene glycol distilled off was 5.5 parts by weight in total.

**[0098]** Thereafter, while increasing the temperature in the polymerization apparatus from 235°C to 280°C over 90 minutes, the pressure in the polymerization apparatus was gradually reduced from normal pressure to 133 Pa or less to distill off ethylene glycol. The reaction system was brought to normal pressure with nitrogen when the intrinsic viscosity reached 0.50, and 0.1 parts by weight of trimellitic anhydride (1% by weight of ethylene glycol solution) was added as a copolymer component. Thereafter, the resultant was stirred for 5 minutes, and the pressure was reduced to vacuum again to continue the polycondensation reaction. The reaction was terminated when the melt viscosity equivalent to the intrinsic viscosity of 0.65 was reached, and the reaction system was brought to normal pressure with nitrogen gas and a molten polymer was discharged in strands from the lower part of the polymerization apparatus into cold water. The polyester strand discharged and solidified was cut to obtain a polyester composition in the form of a pellet. The properties of the polyester composition obtained are shown in Table 8.

**[0099]** The polyester composition obtained in Example 46 had such hydrolysis resistance that will not cause any problem when used in solar battery application or the like.

Table 1

	Example 1	Example 2	Example 3	Example 4	Example 5	Example 6	Example 7
Addition times	3	2	2	3	3	4	4
1st addition amount (fold mole)	0.27	0.15	0.20	0.17	0.33	0.37	0.40
2nd addition amount (fold mole)	0.27	0.15	0.20	0.17	0.33	0.37	0.40
3rd addition amount (fold mole)	0.27	-	-	0.17	0.33	0.37	0.40
4th addition amount (fold mole)	-	-	-	-	-	0.37	0.40
Total addition amounts (fold mole)	0.81	0.30	0.40	0.51	0.99	1.48	1.60
Metallic salt	Manganese acetate	Manganese acetate	Manganese acetate	Manganese acetate	Manganese acetate	Manganese acetate	Manganese acetate
Addition amounts (mol/ton)	2.4	2.4	2.4	2.4	2.4	2.4	2.4
Alkali metal phosphate	Sodium dihydrogen-phosphate	Sodium dihydrogen-phosphate	Sodium dihydrogen-phosphate	Sodium dihydrogen-phosphate	Sodium dihydrogen-phosphate	Sodium dihydrogen-phosphate	Sodium dihydrogen-phosphate
Addition amounts (mol/ton)	1.7	1.7	1.7	1.7	1.7	1.7	1.7
Amount of COOH terminal groups when alkali metal phosphate is added (eq/ton)	48	149	121	98	43	32	31

(continued)

		Example 1	Example 2	Example 3	Example 4	Example 5	Example 6	Example 7
Phospho- rus com- pound	Phospho- rus com- pound	phosphoric acid	phosphoric acid	phosphoric acid	phosphoric acid	phosphoric acid	phosphoric acid	phosphoric acid
	Addition amounts (mol/ton)	2.0	2.0	2.0	2.0	2.0	2.0	2.0
Phosphorus compound mix ratio (compared to the amount of alkali metal phosphate)		1.2	1.2	1.2	1.2	1.2	1.2	1.2
Polymer properties	IV	0.66	0.68	0.64	0.67	0.68	0.67	0.66
	Amount of COOH ter- minal groups	11.6	15.2	14.4	12.9	11.5	11.2	14.2
	DEG (%)	0.78	0.80	0.78	0.82	0.95	1.28	1.29
	$\Delta$ COOH (eq/ton)	32.0	48.7	40.4	32.8	34.6	40.5	44.3

Table 2

	Example 8	Example 9	Comparative Example 1	Comparative Example 2	Comparative Example 3
Diol addition	Addition times	3	-	2	1
	1st addition amount (fold mole)	0.20	-	0.05	0.81
	2nd addition amount (fold mole)	0.27	-	0.05	-
	3rd addition amount (fold mole)	0.34	-	-	-
	4th addition amount (fold mole)	-	-	-	-
	Total addition amounts (fold mole)	0.81	-	0.10	0.81
Metallic salt	Metallic salt	Manganese acetate	Manganese acetate	Manganese acetate	Manganese acetate
	Addition amounts (mol/ton)	2.4	2.4	2.4	2.4
Alkali metal phosphate	Alkali metal phosphate	Sodium dihydrogenphosphate	Sodium dihydrogenphosphate	Sodium dihydrogenphosphate	Sodium dihydrogenphosphate
	Addition amounts (mol/ton)	1.7	1.7	1.7	1.7
Amount of COOH terminal groups when alkali metal phosphate is added (eq/ton)		47	334	231	61
Phosphorus compound	Phosphorus compound	phosphoric acid	phosphoric acid	phosphoric acid	phosphoric acid
	Addition amounts (mol/ton)	2.0	2.0	2.0	2.0
Phosphorus compound mix ratio (compared to the amount of alkali metal phosphate)		1.2	1.2	1.2	1.2

5  
10  
15  
20  
25  
30  
35  
40  
45  
50  
55

(continued)

		Example 8	Example 9	Comparative Example 1	Comparative Example 2	Comparative Example 3
Polymer properties	IV	0.67	0.66	0.66	0.64	0.67
	Amount of COOH terminal groups	11.8	12.1	20.4	18.1	15.8
	DEG (%)	0.79	0.79	0.82	0.79	1.95
	$\Delta$ COOH (eq/ton)	32.3	32.4	62.3	55.3	50.8



Table 3

		Example 10	Example 11	Example 12
5  10  15  20	Diol addition	Addition times	3	3
		1st addition amount (fold mole)	0.27	0.27
		2nd addition amount (fold mole)	0.27	0.27
		3rd addition amount (fold mole)	0.27	0.27
		4th addition amount (fold mole)	-	-
		Total addition amounts (fold mole)	0.81	0.81
25	Metalic salt	Metalic salt	Manganese acetate	Manganese acetate
		Addition amounts (mol/ton)	2.4	2.4
30	Alkali metal phosphate	Alkali metal phosphate	Sodium dihydrogenphosphate	Sodium dihydrogenphosphate
		Addition amounts (mol/ton)	1.7	1.7
35  40	Amount of COOH terminal groups when alkali metal phosphate is added		45	88
	Phosphorus compound	Phosphorus compound	phosphoric acid	phosphoric acid
		Addition amounts (mol/ton)	2.0	2.0
45  50  55	Phosphorus compound mix ratio (compared to the amount of alkali metal phosphate)		1.2	1.2
	Polymer properties	IV	0.66	0.67
		Amount of COOH terminal groups	10.1	17.5
		DEG (%)	2.10	1.10
		$\Delta$ COOH (eq/ton)	49.4	49.7

Table 4

	Example 13	Example 14	Example 15	Example 16	Example 17	Example 18	Example 19	Example 20
Addition times	3	3	3	3	3	3	3	3
1st addition amount (fold mole)	0.27	0.27	0.27	0.27	0.27	0.27	0.27	0.27
2nd addition amount (fold mole)	0.27	0.27	0.27	0.27	0.27	0.27	0.27	0.27
3rd addition amount (fold mole)	0.27	0.27	0.27	0.27	0.27	0.27	0.27	0.27
4th addition amount (fold mole)	-	-	-	-	-	-	-	-
Total addition amounts (fold mole)	0.81	0.81	0.81	0.81	0.81	0.81	0.81	0.81
Metallic salt	Manganese acetate	Manganese acetate	Manganese acetate	Manganese acetate	Manganese acetate	Manganese acetate	Magnesium acetate	Calcium acetate
	Addition amounts (mol/ton)	1.0	2.0	3.0	3.5	4.0	2.4	2.4

(continued)

Alkali metal phosphate	Example 13	Example 14	Example 15	Example 16	Example 17	Example 18	Example 19	Example 20
	Sodium dihydrogenphosphate	Sodium dihydrogenphosphate	Sodium dihydrogenphosphate	Sodium dihydrogenphosphate	Sodium dihydrogenphosphate	Sodium dihydrogenphosphate	Sodium dihydrogenphosphate	Sodium dihydrogenphosphate
Addition amounts (mol/ton)	1.7	1.7	1.7	1.7	1.7	1.7	1.7	1.7
Amount of COOH terminal groups when alkali metal phosphate is added (eq/ton)	77	62	55	46	46	44	66	49
Phosphorus compound	phosphoric acid	phosphoric acid	phosphoric acid	phosphoric acid	phosphoric acid	phosphoric acid	phosphoric acid	phosphoric acid
Addition amounts (mol/ton)	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0
Phosphorus compound mix ratio (compared to the amount of alkali metal phosphate)	1.2	1.2	1.2	1.2	1.2	1.2	1.2	1.2
Polymer properties	IV	0.67	0.67	0.66	0.64	0.66	0.67	0.65
	Amount of COOH terminal groups	13.7	12.9	12.6	17.3	17.4	12.9	13.8
	DEG (%)	0.83	0.80	0.79	0.81	0.88	0.92	0.84
	$\Delta$ COOH (eq/ton)	49.7	40.6	35.4	40.5	45.6	33.6	38.9

Table 5

	Example 21	Example 22	Example 23	Example 24	Example 25	Example 26	Example 27	Example 28
Addition times	3	3	3	3	3	3	3	3
1st addition amount (fold mole)	0.27	0.27	0.27	0.27	0.27	0.27	0.27	0.27
2nd addition amount (fold mole)	0.27	0.27	0.27	0.27	0.27	0.27	0.27	0.27
3rd addition amount (fold mole)	0.27	0.27	0.27	0.27	0.27	0.27	0.27	0.27
4th addition amount (fold mole)	-	-	-	-	-	-	-	-
Total addition amounts (fold mole)	0.81	0.81	0.81	0.81	0.81	0.81	0.81	0.81
Metallic salt	Manganese acetate	Manganese acetate	Manganese acetate	Manganese acetate	Manganese acetate	Manganese acetate	Manganese acetate	Manganese acetate
Addition amounts (mol/ton)	2.4	2.4	2.4	2.4	2.4	2.4	2.4	2.4

Diol addition

Metallic salt

(continued)

		Example 21	Example 22	Example 23	Example 24	Example 25	Example 26	Example 27	Example 28
Alkali metal phosphate	Alkali metal phosphate	Sodium dihydrogenphosphate	Sodium dihydrogenphosphate	Sodium dihydrogenphosphate	Sodium dihydrogenphosphate	Sodium dihydrogenphosphate	Sodium dihydrogenphosphate	Potassium dihydrogenphosphate	Disodium hydrogenphosphate
	Addition amounts (mol/ton)	0.1	0.4	2.0	4.0	7.0	8.3	1.7	1.7
Amount of COOH terminal groups when alkali metal phosphate is added (eq/ton)		48	48	48	48	48	48	48	48
Phosphorus compound	Phosphorus compound	phosphoric acid	phosphoric acid	phosphoric acid	phosphoric acid	phosphoric acid	phosphoric acid	phosphoric acid	phosphoric acid
	Addition amounts (mol/ton)	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0
Phosphorus compound mix ratio (compared to the amount of alkali metal phosphate)		20.0	5.0	1.0	0.5	0.3	0.2	1.2	1.2
Polymer properties	IV	0.68	0.67	0.67	0.66	0.68	0.64	0.66	0.65
	Amount of COOH terminal groups	11.5	11.2	11.2	11.3	11.6	18.2	12.7	12.4
	DEG (%)	0.81	0.78	0.78	0.85	0.95	0.98	0.80	0.79
	$\Delta$ COOH (eq/ton)	33.5	32.1	32.0	35.3	37.8	47.5	33.5	39.3

Table 6

	Example 29	Example 30	Example 31	Example 32	Example 33	Example 34
Addition times	3	3	3	3	3	3
1st addition amount (fold mole)	0.27	0.27	0.27	0.27	0.27	0.27
2nd addition amount (fold mole)	0.27	0.27	0.27	0.27	0.27	0.27
3rd addition amount (fold mole)	0.27	0.27	0.27	0.27	0.27	0.27
4th addition amount (fold mole)	-	-	-	-	-	-
Total addition amounts (fold mole)	0.81	0.81	0.81	0.81	0.81	0.81
Metallic salt	Manganese acetate	Manganese acetate	Manganese acetate	Manganese acetate	Manganese acetate	Manganese acetate
	Addition amounts (mol/ton)	2.4	2.4	2.4	2.4	2.4
Alkali metal phosphate	Sodium dihydrogen-phosphate	Sodium dihydrogen-phosphate	Sodium dihydrogen-phosphate	Sodium dihydrogen-phosphate	Sodium dihydrogen-phosphate	Sodium dihydrogen-phosphate
	Addition amounts (mol/ton)	1.7	1.7	1.7	0.7	0.5
Amount of COOH terminal groups when alkali metal phosphate is added (eq/ton)		48	48	48	48	48

(continued)

		Example 29	Example 30	Example 31	Example 32	Example 33	Example 34
Phosphorus compound	Phosphorus compound	phosphoric acid	phosphoric acid	phosphoric acid	phosphoric acid	phosphoric acid	phosphoric acid
	Addition amounts (mol/ton)	0.1	0.6	1.7	3.4	3.5	4.0
Phosphorus compound mix ratio (compared to the amount of alkali metal phosphate)		0.1	0.4	1.0	2.0	5.0	8.0
Polymer properties	IV	0.68	0.69	0.66	0.65	0.67	0.67
	Amount of COOH terminal groups	16.2	14.6	12.4	12.8	13.5	16.1
	DEG (%)	0.95	0.81	0.90	0.95	0.92	1.05
	$\Delta$ COOH (eq/ton)	48.3	48.0	34.4	32.9	39.7	49.6

Table 7

		Example 35	Example 36	Example 37	Example 38	Comparative Example 4
	Addition times	3	3	3	3	3
Diol addition	1st addition amount (fold mole)	0.27	0.27	0.27	0.27	0.27
	2nd addition amount (fold mole)	0.27	0.27	0.27	0.27	0.27
	3rd addition amount (fold mole)	0.27	0.27	0.27	0.27	0.27
	4th addition amount (fold mole)	-	-	-	-	-
	Total addition amounts (fold mole)	0.81	0.81	0.81	0.81	0.81
Metallic salt	Metallic salt	Manganese acetate	Manganese acetate	Manganese acetate	Manganese acetate	-
	Addition amounts (mol/ton)	2.4	2.4	2.4	2.4	-
Alkali metal phosphate	Alkali metal phosphate	Sodium dihydrogenphosphate	Sodium dihydrogenphosphate	Sodium dihydrogenphosphate	Sodium dihydrogenphosphate	-
	Addition amounts (mol/ton)	1.7	1.7	1.7	1.7	-
Amount of COOH terminal groups when alkali metal phosphate is added (eq/ton)		48	48	48	48	88



(continued)

		Example 35	Example 36	Example 37	Example 38	Comparative Example 4
Phosphorus compound	Phosphorus compound		TEPA	DPPO	phosphoric acid	phosphoric acid
	Addition amounts (mol/ton)	2.0	2.0	2.0	2.0	2.0
Phosphorus compound mix ratio (compared to the amount of alkali metal phosphate)		1.2	1.2	1.2	1.2	-
Polymer properties	IV	0.65	0.66	0.68	0.67	0.65
	Amount of COOHterminal groups	13.3	12.9	14.4	13.8	17.2
	DEG (%)	0.82	0.88	0.85	0.88	1.32
	$\Delta$ COOH (eq/ton)	44.8	47.9	48.9	40.5	74.5
TMPA : Trimethyl phosphate TEPA : Trimethyl phosphono acetate DPPO : Dimethyl phenylphosphonate						

Table 8

		Example 39	Example 40	Example 41	Example 42	Example 43	Example 44	Example 45	Example 46
	Addition times	3	3	3	3	3	3	3	3
Diol addition	1st addition amount (fold mole)	0.27	0.27	0.27	0.27	0.27	0.27	0.27	0.27
	2nd addition amount (fold mole)	0.27	0.27	0.27	0.27	0.27	0.27	0.27	0.27
	3rd addition amount (fold mole)	0.27	0.27	0.27	0.27	0.27	0.27	0.27	0.27
	4th addition amount (fold mole)	-	-	-	-	-	-	-	-
	Total addition amounts (fold mole)	0.81	0.81	0.81	0.81	0.81	0.81	0.81	0.81
Metallic salt	Metallic salt	Manganese acetate	Manganese acetate	Manganese acetate	Manganese acetate	Manganese acetate	Manganese acetate	Manganese acetate	Manganese acetate
	Addition amounts (mol/ton)	2.4	2.4	2.4	2.4	2.4	2.4	2.4	2.4

(continued)

			Example 39	Example 40	Example 41	Example 42	Example 43	Example 44	Example 45	Example 46
	Alkali metal phosphate	Alkali metal phosphate	Sodium dihydrogenphosphate	Sodium dihydrogenphosphate	Sodium dihydrogenphosphate	Sodium dihydrogenphosphate	Sodium dihydrogenphosphate	Sodium dihydrogenphosphate	Sodium dihydrogenphosphate	Sodium dihydrogenphosphate
		Addition amounts (mol/ton)	1.7	1.7	1.7	1.7	1.7	1.7	1.7	1.7
	Amount of COOH terminal groups when alkali metal phosphate is added (eq/ton)		45	43	42	41	38	38	46	48
	Phosphorus compound	Phosphorus compound	phosphoric acid	phosphoric acid	phosphoric acid	phosphoric acid	phosphoric acid	phosphoric acid	phosphoric acid	phosphoric acid
		Addition amounts (mol/ton)	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0
	Phosphorus compound mix ratio (compared to the amount of alkali metal phosphate)		1.2	1.2	1.2	1.2	1.2	1.2	1.2	1.2
	Tri- or more functional polymer component	Multi-functional polymer component	Trimellitic anhydride	Trimellitic anhydride	Trimellitic anhydride	Trimellitic anhydride	Trimellitic anhydride	Trimellitic anhydride	Trimellitic anhydride	Trimellitic anhydride
		Addition amounts (mol/ton)	0.01	0.03	0.10	0.50	0.90	1.10	0.10	0.10

5  
10  
15  
20  
25  
30  
35  
40  
45  
50  
55

(continued)

	Example 39	Example 40	Example 41	Example 42	Example 43	Example 44	Example 45	Example 46
IV	0.67	0.67	0.66	0.67	0.68	0.65	0.67	0.66
Amount of COOH terminal groups	12.9	12.4	11.3	12.2	12.0	11.5	12.5	12.9
DEG (%)	0.81	0.84	0.85	0.92	1.03	1.15	0.79	0.80
ΔCOOH (eq/ton)	33.3	32.7	31.4	32.6	32.3	31.9	33.0	33.2

## INDUSTRIAL APPLICABILITY

**[0100]** According to the production process of the present invention, the amount of COOH terminal groups can be controlled, and, at the same time, a polyester composition with good hydrolysis resistance can be provided, which allows suitable use in a film for a solar battery.

## Claims

1. A process for producing a polyester composition, comprising:

carrying out an esterification reaction of dicarboxylic acid component with diol component; and then carrying out a polycondensation reaction, wherein the diol component is added portionwise in at least two portions during the time from the completion of the esterification reaction until the start of the polycondensation reaction, and then alkali metal phosphate is subsequently added to an esterification reactant having an amount of COOH terminal groups of not more than 150 eq/ton.

2. The process for producing a polyester composition according to claim 1, wherein the amount of the diol component added per addition is 0.15-fold to 0.5-fold mole compared to the amount of the dicarboxylic acid component.

3. The process for producing a polyester composition according to claim 1 or 2, wherein a metallic salt compound is added in an amount of 1.0 mol/ton in terms of the concentration in the resulting polyester composition to 3.5 mol/ton together with the diol component added.

4. The process for producing a polyester composition according to any one of claims 1 to 3, wherein the amount of the alkali metal phosphate added is 0.1 mol/ton to 7.0 mol/ton in terms of the concentration in the resulting polyester composition.

5. The process for producing a polyester composition according to any one of claims 1 to 4, wherein the alkali metal phosphate is mixed with one or more phosphorus compounds selected from the group consisting of phosphoric acid, trimethyl phosphate, trimethyl phosphonoacetate, dimethyl phenylphosphonate and the diol component and added as a solution or slurry.

6. The process for producing a polyester composition according to claim 5, wherein the phosphorus compound is mixed in an amount of 0.1-fold to 7.5-fold mole compared to the amount of the alkali metal phosphate.

7. The process for producing a polyester composition according to any one of claims 1 to 6, comprising:

carrying out an esterification reaction of a dicarboxylic acid component with a diol component; and then carrying out a polycondensation reaction, wherein a tri- or more functional copolymer component is added during the time until the start of the polycondensation reaction.

## Patentansprüche

1. Verfahren zur Herstellung einer Polyesterzusammensetzung, wobei das Verfahren Folgendes umfasst:

das Durchführen einer Veresterungsreaktion einer Dicarbonsäurekomponente mit einer Diolkomponente und anschließend das Durchführen einer Polykondensationsreaktion, wobei die Diolkomponente portionsweise in zumindest zwei Portionen während des Zeitraums vom Abschluss der Veresterungsreaktion bis zum Beginn der Polykondensationsreaktion zugesetzt wird und dann Alkalimetallphosphat anschließend zu einem Veresterungsreaktanten zugesetzt wird, der eine Menge an endständigen COOH-Gruppen von nicht mehr als 150 Äqu./Tonne aufweist.

2. Verfahren zur Herstellung einer Polyesterzusammensetzung nach Anspruch 1, wobei die Menge der Diolkompo-

nente, die pro Zugabe zugesetzt wird, der 0,15- bis 0,5-fachen molaren Menge der Dicarbonsäurekomponente entspricht.

3. Verfahren zur Herstellung einer Polyesterzusammensetzung nach Anspruch 1 oder 2, wobei eine Metallsalzverbindung in einer Menge von 1,0 Mol/Tonne, bezogen auf die Konzentration in der resultierenden Polyesterzusammensetzung, bis 3,5 Mol/Tonne zusammen mit der zugesetzten Diolkomponente zugesetzt wird.

4. Verfahren zur Herstellung einer Polyesterzusammensetzung nach einem der Ansprüche 1 bis 3, wobei die Menge des zugesetzten Alkalimetallphosphats, bezogen auf die Konzentration in der resultierenden Polyesterzusammensetzung, 0,1 Mol/ Tonne bis 7,0 Mol/Tonne beträgt.

5. Verfahren zur Herstellung einer Polyesterzusammensetzung nach einem der Ansprüche 1 bis 4, wobei das Alkalimetallphosphat mit einer oder mehreren phosphorhaltigen Verbindungen, die aus der aus Phosphorsäure, Trimethylphosphat, Trimethylphosphonoacetat und Dimethylphenylphosphonat bestehenden Gruppe ausgewählt sind, und der Diolkomponente vermischt wird und als Lösung oder Aufschlämmung zugesetzt wird.

6. Verfahren zur Herstellung einer Polyesterzusammensetzung nach Anspruch 5, wobei die phosphorhaltige Verbindung in einer 0,1 - bis 7,5-fachen molaren Menge des Alkalimetallphosphats beigemischt wird.

7. Verfahren zur Herstellung einer Polyesterzusammensetzung nach einem der Ansprüche 1 bis 6, wobei das Verfahren Folgendes umfasst:

das Durchführen einer Veresterungsreaktion einer Dicarbonsäurekomponente mit einer Diolkomponente und anschließend

das Durchführen einer Polykondensationsreaktion, wobei eine trifunktionelle oder höherfunktionelle Copolymerkomponente während des Zeitraums bis zum Beginn der Polykondensationsreaktion zugesetzt wird.

## Revendications

1. Procédé pour produire une composition de polyester, comprenant :

la mise en œuvre d'une réaction d'estérification d'un composant acide dicarboxylique avec un composant diol ; et ensuite

la mise en œuvre d'une réaction de polycondensation, dans lequel le composant diol est ajouté par portions en au moins deux portions durant le temps allant de l'achèvement de la réaction d'estérification jusqu'au début de la réaction de polycondensation, après quoi un phosphate de métal alcalin est ensuite ajouté à un réactif d'estérification ayant une quantité de groupes terminaux COOH d'au plus 150 éq/tonne.

2. Procédé pour produire une composition de polyester selon la revendication 1, dans laquelle la quantité du composant diol ajouté par addition est de 0,15 à 0,5 fois en mole la quantité du composant acide dicarboxylique.

3. Procédé pour produire une composition de polyester selon la revendication 1 ou 2, dans lequel un composé sel métallique est ajouté en une quantité de 1,0 mol/tonne en termes de la concentration dans la composition de polyester résultante à 3,5 mol/tonne conjointement avec le composant diol ajouté.

4. Procédé pour produire une composition de polyester selon l'une quelconque des revendications 1 à 3, dans lequel la quantité du phosphate de métal alcalin ajouté est de 0,1 mol/tonne à 7,0 mol/tonne en termes de la concentration dans la composition de polyester résultante.

5. Procédé pour produire une composition de polyester selon l'une quelconque des revendications 1 à 4, dans lequel le phosphate de métal alcalin est mélangé avec un ou plusieurs composés du phosphore choisis dans l'ensemble constitué par l'acide phosphorique, le phosphate de triméthyle, le phosphonoacétate de triméthyle, le phénylphosphonate de diméthyle et le composant diol et ajouté sous la forme d'une solution ou suspension.

6. Procédé pour produire une composition de polyester selon la revendication 5, dans lequel le composé du phosphore

est mélangé en une quantité de 0,1 fois à 7,5 fois en moles la quantité du phosphate de métal alcalin.

7. Procédé pour produire une composition de polyester selon l'une quelconque des revendications 1 à 6, comprenant :

- 5            la mise en œuvre d'une réaction d'estérification d'un composant acide dicarboxylique avec un composant diol ;  
              et ensuite  
              la mise en œuvre d'une réaction de polycondensation,  
              dans lequel un composant copolymère trifonctionnel ou de fonctionnalité supérieure est ajouté durant le temps  
10            allant jusqu'au début de la réaction de polycondensation.

10

15

20

25

30

35

40

45

50

55

**REFERENCES CITED IN THE DESCRIPTION**

*This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.*

**Patent documents cited in the description**

- JP 2001114881 A [0004]
- JP 2007277548 A [0005]
- JP 2008007750 A [0006]
- EP 2495283 A [0006]

**Non-patent literature cited in the description**

- **M. J. MAURICE ; F. HUIZINGA.** *Anal. Chim. Acta*, 1960, vol. 22, 363 [0050]