



(12) **CORRECTED EUROPEAN PATENT APPLICATION**

(15) Correction information:
Corrected version no 1 (W1 A1)
Corrections, see
Bibliography INID code(s) 71

(51) Int Cl.:
H01L 31/18 (2006.01) **H01L 31/068** (2012.01)
H01L 31/0224 (2006.01) **H01B 1/16** (2006.01)
H01B 1/22 (2006.01)

(48) Corrigendum issued on:
02.10.2013 Bulletin 2013/40

(43) Date of publication:
24.07.2013 Bulletin 2013/30

(21) Application number: **12005699.9**

(22) Date of filing: **06.08.2012**

(84) Designated Contracting States:
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR
Designated Extension States:
BA ME

(30) Priority: **20.01.2012 KR 20120006525**

(71) Applicant: **LG Electronics Inc.**
Seoul 150-721 (KR)

(72) Inventors:
• **Sungjin, Kim**
Seocho-Gu
137-724 Seoul (KR)

• **Haejong, Cho**
Seocho-Gu
137-724 Seoul (KR)
• **Yangwoo, Byun**
Seocho-Gu
137-724 Seoul (KR)
• **Seongeun, Lee**
Seocho-Gu
137-724 Seoul (KR)

(74) Representative: **Katérle, Axel**
Wuesthoff & Wuesthoff
Patent- und Rechtsanwälte
Schweigerstraße 2
81541 München (DE)

(54) **Bifacial solar cell**

(57) A bifacial solar cell is discussed. The bifacial solar cell includes a substrate, a p⁺-type doped region positioned at a first surface of the substrate, a P-type electrode part electrically connected to the p⁺-type doped region, an n⁺-type doped region positioned at a second surface of the substrate, and an N-type electrode part electrically connected to the n⁺-type doped region. The P-type electrode part is formed of a first inorganic solid powder including a first powder, which contains silver (Ag) and has an average diameter of about 0.2 μm to 1 μm, and a second powder, which contains a group III element and has an average diameter of about 1 μm to 5 μm. The N-type electrode part is formed of a second inorganic solid powder including only the first powder.

FIG. 2

