



(12) **CORRECTED EUROPEAN PATENT APPLICATION**  
published in accordance with Art. 153(4) EPC

(15) Correction information:  
**Corrected version no 1 (W1 A1)**  
**Corrections, see**  
**Bibliography INID code(s) 72**

(51) Int Cl.:  
**B23K 35/30 (2006.01) C22C 19/05 (2006.01)**

(86) International application number:  
**PCT/JP2011/053005**

(48) Corrigendum issued on:  
**18.12.2013 Bulletin 2013/51**

(87) International publication number:  
**WO 2012/063503 (18.05.2012 Gazette 2012/20)**

(43) Date of publication:  
**18.09.2013 Bulletin 2013/38**

(21) Application number: **11840148.8**

(22) Date of filing: **14.02.2011**

(84) Designated Contracting States:  
**AL AT BE BG CH CY CZ DE DK EE ES FI FR GB**  
**GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO**  
**PL PT RO RS SE SI SK SM TR**

(30) Priority: **12.11.2010 JP 2010254214**

(71) Applicant: **Kabushiki Kaisha Kobe Seiko Sho**  
**Chuo-ku**  
**Kobe-shi**  
**Hyogo 651-8585 (JP)**

(72) Inventors:  
• **IKEDA, Tetsunao**  
**Kanagawa 251-0014 (JP)**

- **SHIMAMOTO, Masaki**  
**Hyogo 651-2271 (JP)**
- **IZUTANI, Shun**  
**Kanagawa 251-0014 (JP)**
- **KAWAMOTO, Hiroaki**  
**Kanagawa-shi 251-0014 (JP)**
- **SAWADA, Yushi**  
**Kanagawa-shi 251-0014 (JP)**
- **WATANABE, Hirohisa**  
**Kanagawa 251-0014 (JP)**

(74) Representative: **Müller-Boré & Partner**  
**Patentanwälte**  
**Grafinger Straße 2**  
**81671 München (DE)**

(54) **NI-BASED ALLOY SOLID WIRE FOR WELDING**

(57) An object of the present invention is to provide a Ni base alloy solid wire for welding, which has excellent cracking resistance to ductility dip cracking in weld metal, can increase the tensile strength of the weld metal to not less than the tensile strength of the base material, and has excellent weldability. The present invention provides a solid wire which has a composition containing Cr: 27.0

to 31.5 mass%, Ti: 0.50 to 0.90 mass%, Nb: 0.40 to 0.70 mass%, Ta: 0.10 to 0.30 mass%, C: 0.010 to 0.030 mass%, and Fe: 5.0 to 11.0 mass%, and is regulated to Al: 0.10 mass% or less, N: 0.020 mass% or less, Zr 0.005 mass% or less, P: 0.010 mass% or less, S: 0.0050 mass% or less, Si: 0.50 mass% or less, and Mn: 1.00 mass% or less, with the balance including Ni and inevitable impurities.

Fig. 1

