



(11) **EP 2 725 115 A1**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
30.04.2014 Bulletin 2014/18

(51) Int Cl.:
C23C 2/02 *(2006.01)* **C23C 2/06** *(2006.01)*
C23C 2/30 *(2006.01)*

(21) Application number: **13189716.7**

(22) Date of filing: **22.10.2013**

(84) Designated Contracting States:
**AL AT BE BG CH CY CZ DE DK EE ES FI FR GB
GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO
PL PT RO RS SE SI SK SM TR**
Designated Extension States:
BA ME

(30) Priority: **25.10.2012 GB 201219211**

(71) Applicant: **Fontaine Holdings NV**
3530 Houthalen (BE)

(72) Inventors:
• **WARICHET, David**
1970 Wezembeek-Oppem (BE)
• **BALDUYCK, Julien**
6951 Bande (BE)
• **MASQUELIER, Caroline**
7850 Marcq (BE)

(74) Representative: **Bird Goën & Co**
Wetenschapspark Arenberg
Gaston Geenslaan 9
3001 Heverlee (BE)

(54) **Flux compositions for steel galvanization**

(57) This invention relates to a flux composition for treating a metal surface, comprising (a) more than 40 and less than 70 wt.% zinc chloride, (b) 10 to 30 wt.% ammonium chloride, (c) more than 6 and less than 30 wt.% of a set of at least two alkali metal chlorides including sodium chloride and potassium chloride, (d) from 0 to 2 wt.% lead chloride, and (e) from 0 to 15 wt.% tin chloride, provided that the KCl/NaCl weight ratio of said set of at

least two alkali metal chlorides ranges from 2.0 to 8.0.

This invention also relates to a fluxing bath comprising this flux composition dissolved in water for use in galvanizing processes, by batch or continuously, of metal articles such as iron or steel long products and flat products including wires, plates, coils, rods, reinforcing bars, tubes, strips and sheets.

EP 2 725 115 A1

DescriptionFIELD OF THE INVENTION

5 **[0001]** The present invention relates to the field of galvanization, more specifically hot dip galvanization or hot-dip zinc coating. In particular the present invention relates to the galvanization of ferrous materials such as, but not limited to, iron, cast iron, steel and cast steel. More particularly the present invention relates to a range of flux compositions for treating the surface of a ferrous material such as iron and steel before it is dipped into a zinc-based molten bath. The present invention also relates to (1) galvanization processes, in particular hot dip galvanization, making use of the flux compositions in at least one process step, and (2) galvanized products, including galvanized ferrous products (e.g. steel flat and long products), made by a process wherein the product surface is treated with the novel flux compositions.

BACKGROUND OF THE INVENTION

15 **[0002]** The importance of providing protection against corrosion for ferrous (e.g. iron or steel) articles used outdoors such as fences, wires, bolts, cast iron elbows and automobile parts is well known, and coating a ferrous material with zinc is a very effective and economical means for accomplishing this goal. Zinc coatings are commonly applied by dipping or passing the article to be coated through a molten bath of the metal. This operation is termed "galvanizing", "hot galvanizing" or "hot-dip galvanizing" (HDG) to distinguish it from zinc electroplating processes. In this process, a solidified layer of zinc is formed on the article surface and the zinc coating layer formed as a result is strongly adhered to the surface of the article by an iron/zinc intermetallic alloy which forms during galvanizing. Oxides and other foreign materials ("soil") on the surface of the steel article interfere with the chemistry of the galvanizing process and prevent formation of a uniform, continuous, void-free coating. Accordingly, various techniques and combinations of techniques have been adopted in industry to reduce, eliminate, or at least accommodate, oxides and soil as much as possible.

25 **[0003]** Improvement in the properties of galvanized products can be achieved by alloying zinc with aluminum and/or magnesium. Addition of 5 wt.% aluminum produces an alloy with a lower melting temperature (eutectic point at 381 °C) which exhibits improved drainage properties relative to pure zinc. Moreover, galvanized coatings produced from this zinc-aluminum alloy have greater corrosion resistance, improved formability and better paintability than those formed from essentially pure zinc. However, zinc-aluminum galvanizing is particularly sensitive to surface cleanliness so that various difficulties, such as insufficient steel surface wetting, are often encountered when zinc-aluminum alloys are used in galvanizing.

35 **[0004]** Many techniques and combinations thereof have been adopted in industry to reduce, eliminate, or at least accommodate, oxides and soil as much as possible. In essentially all these processes, organic soil (i.e. oil, grease, rust preventive compounds), is first removed by contacting the surface to be coated with an alkaline aqueous wash (alkaline cleaning). This may be accompanied by additional techniques such as brush scrubbing, ultrasound treatment and/or electro-cleaning. Then follows rinsing with water, contacting the surface with an acidic aqueous wash for removing iron fines and oxides (pickling), and finally rinsing with water again. All these cleaning-pickling-rinsing procedures are common for most galvanizing techniques and are industrially carried out more or less accurately.

40 **[0005]** Another pre-treatment method used for high strength steels, steels with high carbon contents, cast iron and cast steels is a mechanical cleaning method called blasting. In this method, rust and dirt are removed from the steel or iron surface by projecting small shots and grits onto this surface. Depending on the shape, size and thickness of the parts to be treated, different blasting machines are used such as a tumble blasting machine for bolts, a tunnel blasting machine for automotive parts, etc.

45 **[0006]** There are two main galvanizing techniques used on cleaned metal (e.g. iron or steel) parts: (1) the fluxing method, and (2) the annealing furnace method.

[0007] The first galvanizing technique, i.e. the fluxing method, may itself be divided into two categories, the dry fluxing method and the wet fluxing method.

50 **[0008]** The dry fluxing method, which may be used in combination with one or more of the above cleaning, pickling, rinsing or blasting procedures, creates a salt layer on the ferrous metal surface by dipping the metal part into an aqueous bath containing chloride salts, called a "pre-flux". Afterwards, this layer is dried prior to the galvanizing operation, thus protecting the steel surface from re-oxidation until its entrance in a molten zinc bath. Such pre-fluxes normally comprise aqueous zinc chloride and optionally contain ammonium chloride, the presence of which has been found to improve wettability of the article surface by molten zinc and thereby promote formation of a uniform, continuous, void-free coating.

55 **[0009]** The concept of wet fluxing is to cover the galvanizing bath with a top flux also typically comprising zinc chloride, and usually ammonium chloride, but in this case these salts are molten and are floating on the top of the galvanizing bath. The purpose of a top flux, like a pre-flux, is to supply zinc chloride and preferably ammonium chloride to the system to aid wettability during galvanizing. In this case, all surface oxides and soil which are left after cleaning-pickling-rinsing are removed when the steel part passes through the top flux layer and is dipped into the galvanizing kettle. Wet fluxing

has several disadvantages such as, consuming much more zinc than dry fluxing, producing much more fumes, etc. Therefore, the majority of galvanizing plants today have switched their process to the dry fluxing method.

[0010] Below is a summary of the annealing furnace method. In continuous processes using zinc or zinc-aluminum or zinc-aluminum-magnesium alloys as the galvanizing medium, annealing is done under a reducing atmosphere such as a mixture of nitrogen and hydrogen gas. This not only eliminates re-oxidation of previously cleaned, pickled and rinsed surfaces but, also actually removes any residual surface oxides and soil that might still be present. The majority of steel coils are today galvanized according to this technology. A very important requirement is that the coil is leaving the annealing furnace by continuously going directly into the molten zinc without any contact with air. However this requirement makes it extremely difficult to use this technology for shaped parts, or for steel wire since wires break too often and the annealing furnace method does not allow discontinuity.

[0011] Another technique used for producing zinc-aluminum galvanized coatings comprises electro-coating the steel articles with a thin (i.e. 0.5 - 0.7 μm) layer of zinc (hereafter "pre-layer"), drying in a furnace with an air atmosphere and then dipping the pre-coated article into the galvanizing kettle. This is widely used for hot-dip coating of steel tubing in continuous lines and to a lesser extent for the production of steel strip. Although this does not require processing under reducing atmospheres, it is disadvantageous because an additional metal-coating step required.

[0012] Galvanizing is practiced either in batch operation or continuously. Continuous operation is typically practiced on articles amenable to this type of operation such as wire, sheet, strip, tubing, and the like. In continuous operation, transfer of the articles between successive treatments steps is very fast and done continuously and automatically, with operating personnel being present to monitor operations and fix problems if they occur. Production volumes in continuous operations are high. In a continuous galvanizing line involving use of an aqueous pre-flux followed by drying in a furnace, the time elapsing between removal of the article from the pre-flux tank and dipping into the galvanizing bath is usually about 10 to 60 seconds, instead of 10 to 60 minutes for a batch process.

[0013] Batch operations are considerably different. Batch operations are favored where production volumes are lower and the parts to be galvanized are more complex in shape. For example, various fabricated steel items, structural steel shapes and pipe are advantageously galvanized in batch operations. In batch operations, the parts to be processed are manually transferred to each successive treatment step in batches, with little or no automation being involved. This means that the time each piece resides in a particular treatment step is much longer than in continuous operation, and even more significantly, the time between successive treatment steps is much wider in variance than in continuous operation. For example, in a typical batch process for galvanizing steel pipe, a batch of as many as 100 pipes after being dipped together in a pre-flux bath is transferred by means of a manually operated crane to a table for feeding, one at a time, into the galvanizing bath.

[0014] Because of the procedural and scale differences between batch and continuous operations, techniques particularly useful in one type of operation are not necessarily useful in the other. For example, the use of a reducing furnace is restricted to continuous operation on a commercial or industrial scale. Also, the high production rates involved in continuous processes make preheating a valuable aid in supplying make-up heat to the galvanizing bath. In batch processes, delay times are much longer and moreover production rates, and hence the rate of heat energy depletion of the galvanizing bath, are much lower.

[0015] There is a need to combine good formability with enhanced corrosion protection of the ferrous metal article. However, before a zinc-based alloy coating with high amounts of aluminum (and optionally magnesium) can be introduced into the general galvanizing industry, the following difficulties have to be overcome:

- zinc alloys with high aluminum contents can hardly be produced using the standard zinc-ammonium chloride flux. Fluxes with metallic Cu or Bi deposits have been proposed earlier, but the possibility of copper or bismuth leaching into the zinc bath is not attractive. Thus, better fluxes are needed.
- high-aluminum content alloys tend to form outbursts of zinc-iron intermetallic alloy which are detrimental at a later stage in the galvanization. This phenomenon leads to very thick, uncontrolled and rough coatings. Control of outbursts is absolutely essential.
- wettability issues were previously reported in Zn-Al alloys with high-aluminum content, possibly due to a higher surface tension than pure zinc. Hence bare spots due to a poor wetting of steel are easily formed, and hence a need to lower the surface tension of the melt.
- a poor control of coating thickness was reported. in Zn-Al alloys with high-aluminum content, possibly depending upon parameters such as temperature, flux composition, dipping time, steel quality, etc.

[0016] WO 02/42512 describes a flux for hot dip galvanization comprising 60-80 wt.% zinc chloride; 7-20 wt.% ammonium chloride; 2-20 wt.% of at least one alkali or alkaline earth metal salt; 0.1-5 wt.% of at least one of NiCl_2 , CoCl_2

and MnCl_2 ; and 0.1-1.5 wt.% of at least one of PbCl_2 , SnCl_2 , SbCl_3 and BiCl_3 . Preferably this flux comprises 6 wt.% NaCl and 2 wt.% KCl. Examples 1-3 teach flux compositions comprising 0.7-1 wt.% lead chloride.

[0017] WO 2007/146161 describes a method of galvanizing with a molten zinc-alloy comprising the steps of (1) immersing a ferrous material to be coated in a flux bath in an independent vessel thereby creating a flux coated ferrous material, and (2) thereafter immersing the flux coated ferrous material in a molten zinc-aluminum alloy bath in a separate vessel to be coated with a zinc-aluminum alloy layer, wherein the molten zinc-aluminum alloy comprises 10-40 wt.% aluminum, at least 0.2 wt.% silicon, and the balance being zinc and optionally comprising one or more additional elements selected from the group consisting of magnesium and a rare earth element. In step (1), the flux bath may comprise from 10-40 wt.% zinc chloride, 1-15 wt.% ammonium chloride, 1-15 wt.% of an alkali metal chloride, a surfactant and an acidic component such that the flux has a final pH of 1.5 or less. In another embodiment of step (1), the flux bath may be as defined in WO 02/42512.

[0018] JP 2001/049414 describes producing a hot-dip Zn-Mg-Al base alloy coated steel sheet excellent in corrosion resistance by hot-dipping in a flux containing 61-80 wt.% zinc chloride, 5-20 wt.% ammonium chloride, 5-15 wt.% of one or more chloride, fluoride or silicofluoride of alkali or an alkaline earth metal, and 0.01-5 wt.% of one or more chlorides of Sn, Pb, In, Ti, Sb or Bi. More specifically, table 1 of JP 2001/049414 discloses various flux compositions with a KCl/NaCl weight ratio ranging from 0.38 to 0.60 which, when applied to a steel sheet in a molten alloy bath comprising 0.05-7 wt.% Mg, 0.01-20 wt.% Al and the balance being zinc, provide a good plating ability, no pin hole, no dross, and flat. By contrast, table 1 of JP 2001/049414 discloses a flux composition with a KCl/NaCl weight ratio of 1.0 which, when applied to a steel sheet in a molten alloy bath comprising 1 wt.% Mg, 5 wt.% Al and the balance being zinc, provides a poor plating ability, pin hole defect, some dross, and poorly flat.

[0019] Chinese patent application No. 101948990 teaches an electrolytic flux for hot dip galvanization of a steel wire, comprising g/L 30-220 g/L zinc chloride, 2-90 g/L ammonium chloride, 0-150 g/L potassium chloride, 0-150 g/L sodium chloride, 0-100 g/L boric acid, 0-70 g/L acetic acid, 1-25 g/L sodium fluoride, 2-50 g/L cerium chloride, 0-50 g/L potassium fluozirconate, 0-50 methanol, 0.5-20 g/L hydrogen peroxide, and the balance water. Hydrogen peroxide is used as an oxidant and, since the pH value is kept in a range of 4-5.5 by means of boric and acetic acids as buffer agents, $\text{Fe}(\text{OH})_3$ is precipitated from the solution, eliminating the undesirable influence of Fe^{2+} on the electrolytic flux. All exemplary embodiments of CN101948990 include fluoride salts and volatile organics which are banned by legislation (safety, toxicity) from industrial galvanization units.

[0020] Thus, the common teaching of the prior art is a preferred KCl/NaCl weight ratio below 1.0 in fluxing compositions with major proportions (more than 50 wt.%) of zinc chloride. However the prior art has still not resolved most of the technical problems outlined hereinbefore. Consequently there is still a need in the art for improved fluxing compositions and galvanizing methods making use thereof.

SUMMARY OF THE INVENTION

[0021] The object of the present invention is to provide a flux composition making it possible to produce continuous, more uniform, smoother and void-free coatings on metal articles, in particular iron or steel articles, of any shape and size by hot dip galvanization with pure zinc or zinc alloys, in particular zinc-aluminum alloys and zinc-aluminum-magnesium alloys of any composition. It has surprisingly been found that this can be achieved by providing flux compositions comprising potassium and sodium chlorides in a KCl/NaCl weight ratio well above 1.0. The above stated problems are thus solved by a flux composition as defined in claim 1 and a galvanization process as defined in claim 6. Specific embodiments of this invention are defined in dependent claims 2-5 and 7-15.

DETAILED DESCRIPTION OF THE INVENTION

[0022] As defined in claim 1, the essential feature of this invention is the recognition that huge improvements in galvanization of metals, in particular iron and steel, can be achieved when starting from a flux composition having a set of at least two alkali metal chlorides including sodium chloride and potassium chloride, provided that the KCl/NaCl weight ratio of said set of at least two alkali metal chlorides ranges from 2.0 to 8.0. This feature is associated with specific amounts of other flux components.

Definitions

[0023] The term "hot dip galvanization" is meant to designate the corrosion treatment of a metal article such as, but not limited to, an iron or steel article by dipping into a molten bath of pure zinc or a zinc-alloy, in continuous or batch operation, for a sufficient period of time to create a protective layer at the surface of said article. The term "pure zinc" refers to zinc galvanizing baths that may contain trace amounts of some additives such as for instance antimony, bismuth, nickel or cobalt. This is in contrast with "zinc alloys" that contain significant amounts of one or more other metals such

as aluminum or magnesium.

[0024] In the following the different percentages relate to the proportion by weight (wt.%) of each component with respect to the total weight (100%) of the flux composition or zinc-based bath. This implies that not all maximum or minimum percentages can be present at the same time, in order for the sum to match to 100 wt.%.

[0025] In one embodiment of this invention, the specified KCl/NaCl weight ratio is associated with the presence of lead chloride in the flux composition. The proportion of lead chloride may be at least 0.1 wt.%, or at least 0.4 wt.% or at least 0.7 wt.% of the flux composition. In another embodiment of this invention, the proportion of lead chloride in the flux composition may be at most 2 wt.%, or at most 1.5 wt.% or at most 1.2 wt.%. In a specific embodiment of this invention, the proportion of lead chloride in the flux composition is from 0.8 to 1.1 wt.%.

[0026] In one embodiment of this invention, the specified KCl/NaCl weight ratio is associated with the presence of tin chloride in the flux composition. The proportion of tin chloride in the flux composition may be at least 2 weight % or at least 3.5 weight % or at least 7 weight %. In another embodiment of this invention, the proportion of tin chloride in the flux composition is at most 14 weight %.

[0027] In one embodiment, the combined amounts of lead chloride and tin chloride represent at least 2.5 wt.%, or at most 14 wt.% of the flux composition. In another embodiment, the flux composition may further comprise other salts of lead and/or tin, such as the fluoride, or other chemicals that are inevitable impurities present in commercial sources of lead chloride and/or tin chloride.

[0028] In one aspect of this invention, the specified KCl/NaCl weight ratio is combined with specified proportions of other chlorides that make it possible to produce continuous, more uniform, smoother and void-free coatings on metal, in particular iron or steel, articles by galvanization, in particular hot dip galvanization, processes with molten zinc or zinc-based alloys, especially in batch operation or continuously.

[0029] For instance, the specified KCl/NaCl weight ratio in the flux composition is combined with more than 40 and less than 70 wt.% zinc chloride. In one embodiment of this invention, the proportion of zinc chloride in the flux composition is at least 45 wt.% or at least 50 wt.%. In another embodiment, the proportion of zinc chloride in the flux composition is at most 65 wt.% or at most 62 wt.%. These selected proportions of $ZnCl_2$ are capable, in combination with the specified KCl/NaCl weight ratio in the flux composition, to ensure a good coating of the metal article to be galvanized and to effectively prevent oxidation of the metal article during subsequent process steps such as drying, i.e. prior to galvanization itself.

[0030] In one aspect of this invention, the specified KCl/NaCl weight ratio in the flux composition is combined with 10-30 wt.% ammonium chloride. In one embodiment, the proportion of NH_4Cl in the flux composition is at least 13 wt.% or at least 17 wt.%. In another embodiment, the proportion of ammonium chloride in the flux composition is at most 26 wt.% or at most 22 wt.%. The optimum proportion of NH_4Cl may be determined by the skilled person, without extensive experimentation and depending upon parameters such as the metal to be galvanized and the weight proportions of the metal chlorides in the flux composition, by simply using the experimental evidence shown in the following examples, to achieve a sufficient etching effect during hot dipping to remove residual rust or poorly pickled spots, while however avoiding the formation of black spots, i.e. uncoated areas of the metal article. In some circumstances it may be useful to substitute a minor part (e.g. less than 1/3 by weight) of NH_4Cl with one or more alkyl quaternary ammonium salt(s) wherein at least one alkyl group has from 8 to 18 carbon atoms such as described in EP 0488.423, for instance an alkyl-trimethylammonium chloride (e.g. trimethylauryl-ammonium chloride) or a dialkyldimethylammonium chloride.

[0031] In one aspect of this invention, the specified KCl/NaCl weight ratio in the flux composition is further combined with the presence of suitable amounts of alkali or alkaline earth metal halides, in particular optional halides from alkali or alkaline earth metals other than K and Na. These halides are preferably or predominantly chlorides (bromides and iodides may be useful as well), and the other alkali or alkaline earth metals may be selected (sorted in decreasing order of preference in each metal class) from the group consisting of Li, Cs, Mg, Ca, Sr and Ba. Preferably, fluorides should be avoided for safety and/or toxicity reasons, i.e. the flux compositions should be fluoride salts-free. In one embodiment, the set of at least two alkali metal chlorides, optionally together with halides from alkali or alkaline earth metals other than K and Na, represents 6-30 wt.% of the flux composition. In another embodiment, the set of at least two alkali metal chlorides includes sodium chloride and potassium chloride as major or only components. In another embodiment, the set of at least two alkali metal chlorides (e.g. including sodium chloride and potassium chloride as major or only components) represents at least 12 wt.% or at least 15 wt.% of the flux composition. In another embodiment, the set of at least two alkali metal chlorides (e.g. including sodium chloride and potassium chloride as or only major components) represents at most 25 wt.%, or at most 21 wt.%, of the flux composition. NaBr, KBr, $MgCl_2$ and/or $CaCl_2$ may be present as minor components in each of the above stated embodiments.

[0032] In one aspect of this invention, the specified KCl/NaCl weight ratio in the flux composition is further combined with the presence of suitable amounts of one or more other metal (e.g. transition metal or rare earth metal) chlorides such as, but not limited to, nickel chloride, cobalt chloride, manganese chloride, cerium chloride and lanthanum chloride. For instance, some examples below demonstrate that the presence of up to 1 wt.% (even up to 1.5 wt.%) nickel chloride is not detrimental to the behavior of the flux composition of the present invention in terms of quality of the coating obtained

after hot dip galvanization. Other metal chlorides that may be present include bismuth chloride, antimony chloride and the like.

[0033] In order to solve the stated problems and achieve the stated advantages, the KCl/NaCl weight ratio is important. In anyone embodiment of this invention, the KCl/NaCl weight ratio may for instance be from 3.5 to 5.0, or from 3.0 to 6.0.

[0034] In other aspects of this invention, the specified respective KCl/NaCl weight ratio in the flux composition is further combined with the presence of other additives, preferably functional additives participating in tuning or improving some desirable properties of the flux composition. Such additives are presented below.

[0035] For instance the flux composition of this invention may further comprise at least one nonionic surfactant or wetting agent which, when combined with the other ingredients, is capable of achieving a predetermined desirable surface tension. Essentially any type of nonionic surfactant, but preferably liquid water-soluble, can be used. Examples thereof include ethoxylated alcohols such as nonyl phenol ethoxylate, alkyl phenols such as Triton X-102 and Triton N101 (e.g. from Union Carbide), block copolymers of ethylene oxide and propylene oxide such as L-44 (from BASF), and tertiary amine ethoxylates derived from coconut, soybean, oleic or tallow oils (e.g. Ethomeen from AKZO NOBEL), polyethoxylated and polypropoxylated derivatives of alkylphenols, fatty alcohols, fatty acids, aliphatic amines or amides containing at least 12 carbon atoms in the molecule, alkylarene-sulfonates and dialkylsulfosuccinates, such as polyglycol ether derivatives of aliphatic and cycloaliphatic alcohols, saturated and unsaturated fatty acids and alkylphenols, said derivatives preferably containing 3-10 glycol ether groups and 8-20 carbon atoms in the (aliphatic) hydrocarbon moiety and 6-18 carbon atoms in the alkyl moiety of the alkylphenol, water-soluble adducts of polyethylene oxide with polypropylene glycol, ethylene-diaminopolypropylene glycol containing 1-10 carbon atoms in the alkyl chain, which adducts contain 20-250 ethyleneglycol ether groups and/or 10-100 propyleneglycol ether groups, and mixtures thereof. Such compounds usually contain from 1-5 ethyleneglycol (EO) units per propyleneglycol unit. Representative examples are nonylphenol-polyethoxyethanol, castor oil polyglycolic ethers, polypropylene-polyethylene oxide adducts, tributylphenoxypolyethoxy-ethanol, polyethylene-glycol and octylphenoxypolyethoxyethanol. Fatty acid esters of polyethylene sorbitan (such as polyoxyethylene sorbitan trioleate), glycerol, sorbitan, sucrose and pentaerythritol, and mixtures thereof, are also suitable non-ionic surfactants. Low foaming wetting agents such as the ternary mixtures described in U.S. Patent No. 7,560,494 are also suitable. Commercially available non-ionic surfactants of the above-mentioned types include those marketed by Zschimmer & Schwarz GmbH & Co KG (Lahnstein, Germany) under the trade names OXETAL, ZUSOLAT and PROPETAL, and those marketed by Alfa Kimya (Istanbul, Turkey) under the trade name NETZER SB II. Various grades of suitable non-ionic surfactants are available under the trade name MERPOL.

[0036] The hydrophilic-lipophilic balance (HLB) of said at least one nonionic surfactant is not a critical parameter of this invention and may be selected by the skilled person within a wide range from 3 to 18, for instance from 6 to 16. E.g. the HLB of MERPOL-A is 6 to 7, the HLB of MERPOL-SE is 11, and the HLB of MERPOL-HCS is 15. Another feature of the nonionic surfactant is its cloud point (i.e. the temperature of phase separation as may be determined e.g. by ASTM D2024-09 standard test method; this behavior is characteristic of non-ionic surfactants containing polyoxyethylene chains, which exhibit reverse solubility versus temperature in water and therefore "cloud out" at some point as the temperature is raised; glycols demonstrating this behavior are known as "cloud-point glycols") which should preferably be higher than the flux working temperature as defined below with respect to the use of a fluxing bath in a hot dip galvanization process. Preferably the cloud point of the nonionic surfactant should be higher than 90 °C.

[0037] Suitable amounts of nonionic surfactants are well known from the skilled person and usually range from 0.02 to 2.0 wt.%, preferably from 0.5 to 1.0 wt.%, of the flux composition, depending upon the selected type of compound.

[0038] The flux compositions of the invention may further comprise at least one corrosion inhibitor, i.e. a compound inhibiting the oxidation of steel particularly in oxidative or acidic conditions. In one embodiment, the corrosion inhibitor includes at least an amino group. Inclusion of such amino derivative corrosion inhibitors in the flux compositions can significantly reduce the rate of iron accumulation in the flux tank. By "amino derivative corrosion inhibitor" is meant herein a compound which inhibits the oxidation of steel and contains an amino group. Aliphatic alkyl amines and quaternary ammonium salts (preferably containing 4 independently selected alkyl groups with 1-12 carbon atoms) such as alkyl dimethyl quaternary ammonium nitrate are suitable examples of this type of amino compounds. Other suitable examples include hexamethylenediamines. In another embodiment, the corrosion inhibitor includes at least one hydroxyl group, or both a hydroxyl group and an amino group and are well known to those skilled in the art. Suitable amounts of the corrosion inhibitor are well known from the skilled person and usually range from 0.02 to 2.0 wt.%, preferably 0.1-1.5 wt.%, or 0.2-1.0 wt.%, depending upon the selected type of compound. The flux compositions of the invention may comprise both at least one corrosion inhibitor and a nonionic surfactant or wetting agent as defined hereinabove.

[0039] In anyone of the above embodiments, the flux compositions of the invention are preferably free from volatile organics, e.g. acetic acid, boric acid and methanol, especially those banned from galvanization units by legislation (safety, toxicity).

[0040] The flux compositions of the invention may be produced by various methods. They can simply be produced by mixing, preferably thoroughly (e.g. under high shear), the essential components (i.e. zinc chloride, ammonium chloride, alkali metal chlorides) and, if need be, the optional ingredients (i.e. lead chloride, tin chloride, alkyl quaternary ammonium

salt(s), other transition or rare earth metal chlorides, other alkali or alkaline earth metal halides, corrosion inhibitor(s) and/or nonionic surfactant(s)) in any possible order in one or more mixing steps. The flux compositions of the invention may also be produced by a sequence of at least two steps, wherein one step comprises the dissolution of lead chloride in ammonium chloride or sodium chloride or a mixture thereof, and wherein in a further step the solution of lead chloride in ammonium chloride or sodium chloride or a mixture thereof is then mixed with the other essential components (i.e. zinc chloride, potassium chloride) and, if need be, the optional ingredients (as listed above) of the composition. In one embodiment of the latter method, dissolution of lead chloride is carried out in the presence of water. In another embodiment of the latter method, it is useful to dissolve an amount ranging from 8 to 35 g/l lead chloride in an aqueous mixture comprising from 150 to 450 g/l ammonium chloride and/or sodium chloride and the balance being water. In particular the latter dissolution step may be performed at a temperature ranging from 55°C to 75°C for a period of time ranging from 4 to 30 minutes and preferably with stirring.

[0041] A significant advantage of a flux composition of the invention is its broad field of applicability (use). The present flux compositions are particularly suitable for batch hot dip galvanizing processes using a wide range of zinc alloys but also pure zinc. Moreover, the present flux can also be used in continuous galvanizing processes using either zinc-aluminum or zinc-aluminum-magnesium or pure zinc baths, for galvanizing a wide range of metal pieces, e.g. wires, pipes, tubes or coils (sheets), especially made from ferrous materials like iron and steel (e.g. steel flat and long products).

[0042] According to another aspect, the present invention thus relates to a fluxing bath for galvanization, in particular hot dip galvanization, wherein a suitable amount of a flux composition according to any one of the above embodiments is dissolved in water or an aqueous medium. Methods for water-dissolving a flux composition based on zinc chloride, ammonium chloride, alkali metal chlorides and optionally one or more chlorides of a transition or rare earth metal (e.g. lead, tin, nickel, cobalt, cerium, lanthanum) are well known in the art. The total concentration of components of the flux composition in the fluxing bath may range within very wide limits such as 200-750 g/l, preferably 350-750 g/l, most preferably 500-750 g/l or 600-750 g/l. This fluxing bath is particularly adapted for hot dip galvanizing processes using zinc-aluminum baths, but also with pure zinc galvanizing baths, either in batch or continuous operation.

[0043] For use in hot dip galvanization processes (whether batch or continuous), the fluxing bath of this invention should advantageously be maintained at a temperature within a range of 50°C-90°C, preferably 60°C-90°C, most preferably 65°C-85°C. The process comprises a step of treating (fluxing), e.g. immersing, a metal article in a fluxing bath according to any one of the above embodiments. Preferably, in discontinuous (batch) operation, said treatment step is performed at a speed output in the range of 1-12 m/min. or 2-8 m/min, for a period of time ranging from 0.01 to 30 minutes, or 0.03 to 20 minutes, or 0.5 to 15 minutes, or 1 to 10 minutes depending upon operating parameters such as the composition and/or temperature of the fluxing bath, the composition of the metal (e.g. steel) to be galvanized, the shape and/or size of the article. As is well known to the skilled person, the treatment time may widely vary from one article to the other: the shorter times (close to or even below 0.1 minute) are suitable for wires, whereas the longer times (closer to 15 minutes or more) are more suitable for instance for rods. In continuous operation, the metal treatment step, i.e. immersion in the fluxing bath, may be performed at a speed from 0.5 to 10 m/minute, or 1-5 m/minute. Much higher speeds of 10-100 m/min, e.g. 20-60 m/min, can also be achieved.

[0044] Practically, any metal surface susceptible to corrosion, for instance any type of iron or steel article may be treated this way. The shape (flat or not), geometry (complex or not) or the size of the metal article are not critical parameters of the present invention. The article to be galvanized may be a so-called long product. As used herein the term "long product" refers to products with one dimension (length) being at least 10 times higher than the two other dimensions (as opposed to flat products wherein two dimensions (length and width) are at least 10 times higher than thickness, the third dimension) such as, wires (coiled or not, for making e.g. bolts and fences), rods, bobbins, reinforcing bars, tubes (welded or seamless), rails, structural shapes and sections (e.g. I-beams, H-beams, L-beams, T-beams and the like), or pipes of any dimensions e.g. for use in civil construction, mechanical engineering, energy, transport (railway, tramway), household and furniture. The metal article to be galvanized may also be, without limitation, in the form of a flat product such as plates, sheets, panels, hot-rolled and cold-rolled strips (either wide 600 mm and above, or narrow below 600 mm, supplied in regularly wound coils or super imposed layers) being rolled from slabs (50-250 mm thick, 0.6-2.6 m wide, and up to 12 m long) and being useful in automotive, heavy machinery, construction, packaging and appliances.

[0045] It is important in any galvanizing process for the surface of the article to be galvanized to be suitably cleaned before performing the fluxing step. Techniques for achieving a desirable degree of surface cleanliness are well known in the art, and may be repeated, such as alkaline cleaning, followed by aqueous rinsing, pickling in acid and finally aqueous rinse. Although all of these procedures are well known, the following description is presented for the purpose of completeness.

[0046] Alkaline cleaning can conveniently be carried out with an aqueous alkaline composition also containing phosphates and silicates as builders as well as various surfactants. The free alkalinity of such aqueous cleaners can vary broadly. Thus at an initial process step, the metal article is submitted to cleaning (degreasing) in a degreasing bath such as an ultrasonic, alkali degreasing bath. Then, in a second step, the degreased metal article is rinsed. Next the metal

article is submitted to one or more pickling treatment(s) by immersion into an aqueous strongly acidic medium, e.g. hydrochloric acid or sulfuric acid, usually at a temperature from 15°C to 60°C and during 1-90 minutes (preferably 3-60 minutes), and optionally in the presence of a ferrous and/or ferric chloride. Acid concentrations of about 5 to 15 wt.%, e.g. 8-12 wt.%, are normally used, although more concentrated acids can be used. In a continuous process the pickling time typically ranges from 5 to 30 seconds, more typically 10 to 15 seconds. In order to prevent over-pickling, one may include in the pickling bath at least one corrosion inhibitor, typically a cationic or amphoteric surface active agent, typically in an amount ranging from 0.02 to 0.2 wt.%, preferably 0.05-0.1 wt.%. Pickling can be accomplished simply by dipping the article in a pickling tank. Additional processing steps can also be used. For example, the article can be agitated either mechanically or ultrasonically, and/or an electric current can be passed through the article for electro-pickling. As is well known these additional processing means usually shorten pickling time significantly. Clearly these pre-treatment steps may be repeated individually or by cycle if needed until the desirable degree of cleanliness is achieved. Then, preferably immediately after the cleaning steps, the metal article is treated (fluxed), e.g. immersed, in a fluxing bath of the invention, preferably under the total salt concentration, temperature and time conditions specified above, in order to form a protective film on its surface.

[0047] The fluxed metal (e.g. iron or steel) article, i.e. after immersion in the fluxing bath during the appropriate period of time and at the suitable temperature, is preferably subsequently dried. Drying may be effected, according to prior art conditions, by transferring the fluxed metal article through a furnace having an air atmosphere, for instance a forced air stream, where it is heated at a temperature from 220 °C to 250 °C until its surface exhibited a temperature between 170 °C and 200 °C, e.g. for 5 to 10 minutes. However it has also been surprisingly found that milder heating conditions may be more appropriate when a fluxing composition of the invention, or any particular embodiment thereof, is used.

[0048] Thus it has been found that it may be sufficient for the surface of the metal (e.g. steel) article to exhibit a temperature from 100° to 200 °C during the drying step. This can be achieved for instance by using a heating temperature ranging from 100 °C to 200 °C. This can also be achieved by using a poorly oxidative atmosphere during the drying step. In one embodiment of the invention, the surface temperature of the metal article may range from 100 °C to 160 °C, or 125-150 °C, or 140-170 °C. In another embodiment, drying may be effected for a period of time ranging from 0.5 to 10 minutes, or 1-5 minutes. In another embodiment, drying may be effected in specific gas atmospheres such as a water-depleted air atmosphere, a water-depleted nitrogen atmosphere, or a water-depleted nitrogen-enriched air atmosphere (e.g. wherein the nitrogen content is above 20%).

[0049] At a next step of the galvanization process, the fluxed and dried metal article is dipped into a molten zinc-based galvanizing bath to form a metal coating thereon. As is well known, the dipping time may be defined depending upon a set of parameters including the size and shape (e.g. flat or long) of the article, the desired coating thickness, and the exact composition of the zinc bath, in particular its aluminum content (when a Zn-Al alloy is used as the galvanizing bath) or magnesium content (when a Zn-Al-Mg alloy is used as the galvanizing bath). In one embodiment, the molten zinc-based galvanizing bath may comprise (a) from 4 to 24 wt.% (e.g. 5 to 20 wt.%) aluminum, (b) from 0.5 to 6 wt.% (e.g. 1 to 4 wt.%) magnesium, and (c) the rest being essentially zinc. In another embodiment, the molten zinc-based galvanizing bath may comprise tiny amounts (i.e. below 1.0 wt.%) or trace amounts (i.e. unavoidable impurities) of other elements such as, but not limited to, silicon (e.g. up to 0.3 wt.%), tin, lead, titanium or vanadium. In another embodiment, the molten zinc-based galvanizing bath may be agitated during a part of this treatment step. During this process step the zinc-based galvanizing bath is preferably maintained at a temperature ranging from 360 °C to 600 °C. It has been surprisingly found that with the flux composition of the invention it is possible to lower the temperature of the dipping step whilst obtaining thin protective coating layers of a good quality, i.e. which are capable of maintaining their protective effect for an extended period of time such as five years or more, or even 10 years or more, depending upon the type of environmental conditions (air humidity, temperature, etc). Thus in one embodiment, the molten zinc-based galvanizing bath is kept at a temperature ranging from 350 °C to 550 °C, or 380-520 °C, or 420-520 °C, the optimum temperature depending upon the content of aluminum and/or magnesium optionally present in the zinc-based bath. In another particular embodiment of the galvanization process of the invention, dipping is performed at a temperature ranging between 380 °C and 440 °C, and said molten zinc-based galvanizing bath comprises (a) from 4 to 7 weight % aluminum, (b) from 0.5 to 3 weight % magnesium, and (c) the rest being essentially zinc.

[0050] In one embodiment, the thickness of the protective coating layer obtained by carrying out the dipping step on a metal article, e.g. an iron or steel article, that has been treated with the flux composition of this invention may range from 5 to 50 µm, for instance from 8 to 30 µm. This can be appropriately selected by the skilled person, depending upon a set of parameters including the thickness and/or shape of the metal article, the stress and environmental conditions that the metal article is supposed to withstand during its lifetime, the expected durability in time of the protective coating layer formed, etc. For instance a 5-15 µm thick coating layer is suitable for a steel article being less than 1.5 mm thick, and a 20-35 µm thick coating layer is suitable for a steel article being more than 6 mm thick.

[0051] Finally, the metal, e.g. iron or steel, article is removed from the galvanizing bath and cooled. This cooling step may conveniently be carried out either by dipping the galvanized metal article in water or simply by allowing it to cool down in air.

[0052] The present hot dip galvanization process has been found to allow the continuous or batch deposition of thinner, more uniform, smoother and void-free, protective coating layers on iron or steel articles (both flat and long products), especially when a zinc-aluminum or zinc-aluminum-magnesium galvanizing bath with not more than 95% zinc was used. Regarding roughness, the coating surface quality is equal to or better than that achieved with a conventional HDG zinc layer according to EN ISO 1461 (i.e. with not more than 2% other metals in the zinc bath). Regarding corrosion resistance, the coating layers of this invention achieve about 1,000 hours in the salt spray test of ISO 9227 which is much better than the about 600 hours achieved with a conventional HDG zinc layer according to EN ISO 1461. Moreover, pure zinc galvanizing baths may also be used in the present invention.

[0053] Moreover the process of the present invention is well adapted to galvanize steel articles of any shape (flat, cylindrical, etc.) such as wires, sheets, tubes, rods, rebars and the like, being made from a large variety of steel grades, in particular articles made from steel grades having a carbon content up to 0.30 wt.%, a phosphorous content between 0.005 and 0.1 wt.% and a silicon content between 0.0005 and 0.5 wt.%, as well as stainless steel. The classification of steel grades is well known to the skilled person, in particular through the Society of Automotive Engineers (SAE). In one embodiment, the metal may be a chromium/nickel or chromium/nickel/molybdenum steel susceptible to corrosion. Optionally the steel grade may contain other elements such as sulfur, aluminum, and copper. Suitable examples include, but are not limited to, the steel grades known as AISI 304 (*1.4301), AISI 304L (1.4307, 1.4306), AISI 316 (1.4401), AISI 316L (1.4404, 1.4435), AISI316Ti (1.4571), or AISI 904L (1.4539) [*1.xxxx = according to DIN 10027-2]. In another embodiment of the present invention, the metal may be a steel grade referenced as S235JR (according to EN 10025) or S460MC (according to EN 10149) or 20MnB4 (*1.5525, according to EN 10263).

[0054] The following examples are given for understanding and illustrating the invention and should not be construed as limiting the scope of the invention, which is defined only by the appended claims.

EXAMPLE 1 - general procedure for galvanization at 440 °C

[0055] A plate (2 mm thick, 100 mm wide and 150 mm long) made from the steel grade S235JR (weight contents : 0.114% carbon, 0.025% silicon, 0.394% manganese, 0.012% phosphorus, 0.016% sulfur, 0.037% chromium, 0.045% nickel, 0.004% molybdenum, 0.041% aluminum and 0.040% copper) was pre-treated according the following pre-treatment sequential procedure:

- first alkaline degreasing by means of SOLVOPOL SOP (50 g/l) and a tenside mixture EMULGATOR SEP (10 g/l), both available from Lutter Galvanotechnik GmbH, at 65 °C for 20 minutes;
- rinsing with water;
- first pickling in a hydrochloric acid based bath (composition: 10 wt% HCl, 12 wt% FeCl₂) at 25 °C for 1 hour;
- rinsing with water;
- second alkaline degreasing for 10 minutes in a degreasing bath with the same chemical composition as in the first step;
- rinsing with water;
- second pickling for 10 minutes in a pickling bath with the same chemical composition as above;
- rinsing with water,
- fluxing in a flux composition as described in one of the following tables for 180 seconds at a concentration of 650 g/l and 0,3% by weight Netzer 4 (a non-ionic wetting agent commercially available from Lutter Galvanotechnik GmbH);
- drying at 100 - 150 °C for 200 seconds;
- galvanizing for 3 minutes at 440 °C at a dipping speed of 1.4 m/minute in a zinc-based bath comprising 5,0% by weight aluminum, 1,0% by weight magnesium, trace amounts of silicon and lead, the balance being zinc; and
- cooling in air.

EP 2 725 115 A1

EXAMPLES 2 to 17 - steel treatment with illustrative flux compositions of this invention before galvanizing at 440 °C

[0056] The experimental procedure of example 1 has been repeated with various flux compositions wherein the proportions of the various chloride components are as listed in table 1. The coating quality has been assessed by a team of three persons evaluating the percentage (expressed on a scale from 0 to 100) of the steel surface that is perfectly coated with the alloy, the value indicated in the last column of table 1 below being the average of these three individual notations. The coating quality has been assessed while keeping the fluxing bath at 72 °C (examples 1 to 10, no asterisk) or at 80 °C (examples 11 to 17, marked with an asterisk).

Table 1

Ex.	ZnCl ₂ %	NH ₄ Cl %	NaCl %	KCl %	SnCl ₂ %	PbCl ₂ %	Coating quality
1 *	59	20	3	12	4	1	75
2	60	20	3	12	4	1	90
3 *	52.5	17.5	3	12	13	1	75
4	53	18	3	12	13	1	80
5 *	52	21	4	17	4	1	70
6	52.5	21.5	4	17	4	1	60
7	60.5	12	4.5	18	4	1	60
8	57	19	3	12	8	1	85
9	59	20	4.5	11.5	4	1	70
10	59	20	2.5	13.5	4	1	70
11	61.3	20.4	3.1	12.3	2	1	95 *
12	55	25	3	12	4	1	95 *
13	56.1	25.5	3.1	12.2	2	1	90 *
14	50	30	3	12	4	1	60 *
15	54.1	18	2.7	20.7	3.6	0.9	70 *
16	62.5	20.8	3.2	12.5	0	1	80 *
17	57.3	26	3.2	12.5	0	1	85 *
• The flux compositions of examples 1, 3 and 5 additionally contain 1 wt.% NiCl ₂ to match up to 100% by weight.							

COMPARATIVE EXAMPLE 18

[0057] The experimental procedure of example 1 has been repeated with a flux composition comprising 60 wt% zinc chloride, 20 wt% ammonium chloride, 10 wt% sodium chloride, 5 wt% potassium chloride and 5 wt% tin chloride,. The coating quality has been assessed by the same methodology as in the previous examples and has found been found 20%. This comparative example demonstrates that when a KCl/NaCl weight ratio of 1/3 is used as in the prior art, then the coating quality is significantly lower than for examples 1 to 17.

EXAMPLE 19 - general procedure for galvanization at 520 °C

[0058] The sequential procedure of example 1 is repeated, the treatment step with a fluxing composition being performed at 80 °C, except that in the penultimate step galvanizing was effected at 520 °C at a dipping speed of 4 m/minute in a zinc-based bath comprising 20.0 wt.% aluminum, and 1.0 wt.% magnesium, trace amounts of silicon and lead, the balance being zinc.

EXAMPLES 20 to 25 - steel treatment with illustrative flux compositions of this invention before galvanizing at 520 °C

[0059] The experimental procedure of example 19 has been repeated with various flux compositions wherein the

proportions of the various chloride components are as listed in table 2 below. The coating quality has been assessed by the same methodology as in the previous examples.

Table 2

Ex.	ZnCl ₂ %	NH ₄ Cl %	NaCl %	KCl %	SnCl ₂ %	PbCl ₂ %	Coating quality
20	60	20	3	12	4	1	95
21	57	19	3	12	8	1	80
22	61.3	20.4	3.1	12.3	2	1	85
23	55	25	3	12	4	1	80
24	56.1	25.5	3.1	12.2	2	1	85
25	54.1	18	2.7	20.7	3.6	0.9	75

Table 2 (end)

EXAMPLE 26 - general procedure for galvanization at 460 °C

[0060] The sequential procedure of example 1 was repeated, the treatment step with a fluxing composition being performed at 80 °C, except that in the penultimate step galvanizing was effected at 460 °C at a dipping speed of 4 m/minute in a zinc-based bath comprising 11.0 wt.% aluminum, 3.0 wt.% magnesium, trace amounts of silicon and lead, the balance being zinc.

EXAMPLES 27 to 29 - steel treatment with illustrative flux compositions of this invention before galvanizing at 460 °C

[0061] The experimental procedure of example 26 has been repeated with various flux compositions wherein the proportions of the various chloride components are as listed in table 3 below. The coating quality has been assessed by the same methodology as in the previous examples.

Table 3

Ex.	ZnCl ₂ %	NH ₄ Cl %	NaCl %	KCl %	SnCl ₂ %	PbCl ₂ %	Coating quality
27	61.3	20.4	3.1	12.3	2	1	95
28	55	25	3	12	4	1	95
29	56.1	25.5	3.1	12.2	2	1	95

[0062] As a summary, examples 20-25 and 27-29 demonstrate that the present invention achieves outstanding coating quality whatever the composition of the zinc-based galvanization bath may be.

EXAMPLE 30 - galvanization of steel plates at 510 °C

[0063] A steel plate (thickness 2.0 mm) from a steel grade S235JR (composition as defined in example 1) was treated according the following procedure:

- first alkaline degreasing at 60 °C by means of SOLVOPOL SOP (50 g/l) and a tenside mixture Emulgator Staal (10 g/l), both available from Lutter Galvanotechnik GmbH, for 30 minutes;
- rinsing with water;
- first pickling in a hydrochloric acid based bath (composition: 12 wt% HCl, 15 wt% FeCl₂, 1 wt% FeCl₃, 2 ml/l of inhibitor HM and 2.5 ml/l Emulgator C75 from Lutter Galvanotechnik GmbH) at 25 °C for 60 minutes;
- rinsing with water;
- second alkaline degreasing bath at 60 °C for 5 minutes in a degreasing bath with the same chemical composition as in the first step;
- rinsing with water;
- second pickling in a hydrochloric acid based bath with the same composition as in the first pickling step at 25 °C for 5 minutes;

- rinsing with water;
- fluxing the steel plate at 80 °C for 3 minutes in a flux composition (comprising 60 wt.% zinc chloride, 20 wt.% ammonium chloride, 3 wt.% sodium chloride, 12 wt.% potassium chloride, 4 wt.% tin chloride and 1 wt.% lead chloride) with a total salt concentration of 750 g/l and in the presence of 1 ml/l Netzer 4 (a wetting agent from Lutter Galvanotechnik GmbH), by using an extraction speed of 4m/min or higher;
- drying until the steel plate surface temperature reaches 120 °C;
- galvanizing the fluxed steel plate for 3 minutes at 510 °C in a zinc-based bath comprising 20.0 wt.% aluminum, 4.0 wt.% magnesium, 0.2 wt.% silicon, trace amounts of lead, the balance being zinc; and
- cooling down the galvanized steel plate in air.

[0064] This procedure has been found to provide a superior coating quality similar to example 20. The following variants of this procedure also provide superior coating quality:

- Idem but 650 g/l total salt concentration, 2 ml/l Netzer 4 in flux, and galvanizing in the zinc-based bath at 490 °C,
- Idem but 650 g/l total salt concentration, 2 ml/l Netzer 4 in flux, and galvanizing in the zinc-based bath at 500 °C during 1 minute,
- Idem but 650 g/l total salt concentration, fluxing for 5 minutes with 2 ml/l Netzer 4 in flux, and galvanizing in the zinc-based bath at 510 °C during 10 minutes,
- Idem but 650 g/l total salt concentration, fluxing for 5 minutes with 2 ml/l Netzer 4 in flux, and galvanizing in the zinc-based bath at 530 °C during 5 minutes, and
- Idem but 650 g/l total salt concentration, fluxing for 5 minutes with 2 ml/l Netzer 4 in flux, and galvanizing in the zinc-based bath at 530 °C during 15 minutes.

EXAMPLE 31 - galvanization of steel plates at 520 °C

[0065] A steel plate (thickness 2.0 mm) from a steel grade S235JR (composition as defined in example 1) was treated according the same procedure as in example 30, except for the following operating conditions:

- in the fluxing step, a total salt concentration of 650 g/l in the presence of 2 ml/l Netzer 4, and
- a galvanizing step of 3 minutes at 520 °C in a zinc-based bath comprising 20.0 wt.% aluminum, 2.0 wt.% magnesium, 0.13 wt.% silicon, trace amounts of lead, the balance being zinc.

[0066] This procedure has been found to provide a superior coating quality similar to example 20.

Claims

1. A flux composition for treating a metal surface, comprising (a) more than 40 and less than 70 wt.% zinc chloride, (b) 10 to 30 wt.% ammonium chloride, (c) more than 6 and less than 30 wt.% of a set of at least two alkali metal chlorides including sodium chloride and potassium chloride, (d) from 0 to 2 wt.% lead chloride, and (e) from 0 to 15 wt.% tin chloride, provided that the KCl/NaCl weight ratio of said set of at least two alkali metal chlorides ranges from 2.0 to 8.0
2. A flux composition according to claim 1, wherein said the combined amounts of lead chloride and tin chloride represent at least 2.5 wt.% of said composition.
3. A flux composition according to claim 1 or claim 2, further comprising at least one nonionic surfactant and/or at least one corrosion inhibitor.
4. A fluxing bath for hot dip galvanization comprising a flux composition according to any one of claims 1 to 3 dissolved in water.
5. A fluxing bath according to claim 4, wherein the total concentration of components of the flux composition in water ranges from 200 to 750 g/l.
6. A process for the hot dip galvanization of a metal article, comprising a step of treating said article in a fluxing bath according to claim 4 or claim 5.

7. A hot dip galvanization process according to claim 6, wherein said metal article is an iron or steel article.
8. A hot dip galvanization process according to claim 6 or claim 7, wherein said treating step consists of immersing said article in said fluxing bath for a period of time from 0.01 to 30 minutes.
9. A hot dip galvanization process according to any one of claims 6 to 8, wherein said treating step is performed at a temperature ranging from 70 °C to 90 °C.
10. A hot dip galvanization process according to any one of claims 6 to 9, wherein the treated article is further dried until its surface temperature ranges from 100 °C to 200 °C.
11. A hot dip galvanization process according to claim 10, wherein said drying step is performed under a poorly oxidative atmosphere.
12. A hot dip galvanization process according to any one of claims 6 to 11, further comprising a step of dipping the treated article in a molten zinc-based galvanizing bath.
13. A hot dip galvanization process according to claim 12, wherein said molten zinc-based galvanizing bath comprising (a) from 4 to 24 wt.% aluminum, (b) from 0.5 to 6 wt.% magnesium, and (c) the rest being essentially zinc.
14. A hot dip galvanization process according to claim 12, wherein dipping is performed at a temperature between 380 and 440 °C and wherein said molten zinc-based galvanizing bath comprising (a) from 4 to 7 wt.% aluminum, (b) from 0.5 to 3 wt.% magnesium, and (c) the rest being essentially zinc.
15. A galvanized iron or steel product being pre-treated with a flux composition according to any one of claims 1 to 3, having a protective coating layer with a thickness ranging from 5 to 30 μm.



EUROPEAN SEARCH REPORT

Application Number
EP 13 18 9716

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (IPC)
Y	GB 1 040 958 A (WILLIAM BLYTHE AND COMPANY LTD) 1 September 1966 (1966-09-01)	1,3-15	INV. C23C2/02 C23C2/06 C23C2/30
A	* page 1, line 3 - line 39 * * page 2, line 30 - line 75 * * claims 1-10 *	2	
Y,D	----- CN 101 948 990 B (UNIV NORTHEASTERN) 11 January 2012 (2012-01-11)	1,3-15	
A	* the whole document *	2	
Y	----- EP 1 209 245 A1 (GALVAPOWER GROUP N V [BE]) 29 May 2002 (2002-05-29)	3,6-13	
A	* page 3, paragraph 11 - paragraph 14 * * claims 8-11 * * claims 13,15,17 *	2,14	TECHNICAL FIELDS SEARCHED (IPC) C23C
Y	----- EP 0 905 270 A2 (NISSHIN STEEL CO LTD [JP]) 31 March 1999 (1999-03-31)	12-15	
Y	* claims 5,6,13,14 * * page 13, paragraph 0089 - page 14, paragraph 0092; table 3 * * example 8; table 8 *	12-15	
Y	----- "Next Level HDG technologies", Fontaine Technologie 25 July 2012 (2012-07-25), XP002719188, Retrieved from the Internet: URL:http://fontaine-technologie.net/index.php/next-level-hdg-technologies [retrieved on 2014-01-22] * the whole document *	12-15	
A,D	----- JP 2001 049414 A (NIPPON STEEL CORP) 20 February 2001 (2001-02-20) * the whole document *	1-14	
The present search report has been drawn up for all claims			
Place of search Munich		Date of completion of the search 6 February 2014	Examiner Tsipouridis, P
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

2

EPO FORM 1503 03.82 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 13 18 9716

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

06-02-2014

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
GB 1040958	A	01-09-1966	NONE	

CN 101948990	B	11-01-2012	NONE	

EP 1209245	A1	29-05-2002	AT 346177 T	15-12-2006
			AU 1914202 A	03-06-2002
			AU 2002219142 B2	26-10-2006
			BR 0115529 A	11-01-2005
			CA 2428887 A1	30-05-2002
			CN 1476487 A	18-02-2004
			CZ 20031760 A3	18-02-2004
			DE 60124767 T2	24-05-2007
			DK 1352100 T3	12-02-2007
			EP 1209245 A1	29-05-2002
			EP 1352100 A1	15-10-2003
			ES 2274916 T3	01-06-2007
			HU 0302756 A2	28-11-2003
			JP 3770875 B2	26-04-2006
			JP 2004514789 A	20-05-2004
			MX PA03004543 A	03-12-2004
			NO 333662 B1	05-08-2013
			PL 361743 A1	04-10-2004
			PT 1352100 E	28-02-2007
			RU 2277606 C2	10-06-2006
			SK 7772003 A3	02-12-2003
			US 2003219543 A1	27-11-2003
			WO 0242512 A1	30-05-2002
			ZA 200303797 A	16-08-2004

EP 0905270	A2	31-03-1999	AU 736197 B2	26-07-2001
			AU 5411698 A	03-07-1998
			CN 1211286 A	17-03-1999
			CN 1523129 A	25-08-2004
			DE 69730212 D1	16-09-2004
			DE 69730212 T2	18-08-2005
			EP 0905270 A2	31-03-1999
			ES 2225997 T3	16-03-2005
			NZ 331311 A	25-08-2000
			US 6235410 B1	22-05-2001
			US 6379820 B1	30-04-2002
			WO 9826103 A1	18-06-1998

JP 2001049414	A	20-02-2001	JP 3501697 B2	02-03-2004
			JP 2001049414 A	20-02-2001

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- WO 0242512 A [0016] [0017]
- WO 2007146161 A [0017]
- JP 2001049414 A [0018]
- CN 101948990 [0019]
- EP 0488423 A [0030]
- US 7560494 B [0035]