

(19)



(11)

EP 2 847 167 B9

(12)

CORRECTED EUROPEAN PATENT SPECIFICATION

(15) Correction information:

Corrected version no 1 (W1 B1)
Corrections, see
Description Paragraph(s) 3, 84, 87
Claims EN 1
Claims FR 1, 2, 3

(51) Int Cl.:

C07D 209/88 ^(2006.01) **G03F 7/031** ^(2006.01)

(86) International application number:

PCT/EP2013/059348

(87) International publication number:

WO 2013/167515 (14.11.2013 Gazette 2013/46)

(48) Corrigendum issued on:

20.02.2019 Bulletin 2019/08

(45) Date of publication and mention of the grant of the patent:

18.07.2018 Bulletin 2018/29

(21) Application number: **13721682.6**

(22) Date of filing: **06.05.2013**

(54) **OXIME ESTER PHOTOINITIATORS**

OXIMESTER-FOTOINITIATOREN

PHOTO-INITIATEURS À BASE D'ESTER D'OXIME

(84) Designated Contracting States:

AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

(30) Priority: **09.05.2012 US 201261644460 P**

09.05.2012 EP 12167309

(43) Date of publication of application:

18.03.2015 Bulletin 2015/12

(60) Divisional application:

15178223.2 / 2 963 014

15178230.7 / 2 963 015

15178244.8 / 2 963 016

18157333.8 / 3 354 641

(73) Proprietor: **BASF SE**

67056 Ludwigshafen am Rhein (DE)

(72) Inventors:

- **NISHIMAE, Yuichi**
Ibaraki-Shi
Osaka 567-0887 (JP)

- **KURA, Hisatoshi**
Takarazuka-shi
Hyogo 665-0013 (JP)
- **KUNIMOTO, Kazuhiko**
Kawanishi 666-0145 (JP)
- **YAMAGAMI, Ryuhei**
Osaka-City
Osaka 531-0013 (JP)
- **TANAKA, Keita**
Hyogo 663-8183 (JP)

(74) Representative: **Maiwald Patent- und Rechtsanwaltsgesellschaft mbH**
Elisenhof
Elisenstraße 3
80335 München (DE)

(56) References cited:

EP-A1- 2 072 500 **WO-A1-2012/045736**

WO-A2-2004/050653

EP 2 847 167 B9

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

- TAKOMA TECHNOLOGY CO LTD: "Compounds - KR20090046108", CAS DATABASE, 1 January 2009 (2009-01-01), XP055066740, -& KR 2009 0046108 A (TAKOMA TECHNOLOGY CO LTD [KR]) 11 May 2009 (2009-05-11)
- DATABASE CA [Online] CHEMICAL ABSTRACTS SERVICE, COLUMBUS, OHIO, US; 2008, MOROISHI, NOBUYUKI ET AL: "Photo-curable ink-jet inks with good curability and freedom from bleed and volatile substance", XP002693676, retrieved from STN Database accession no. 2008:217361 & JP 2008 037930 A (TOYO INK MFG. CO., LTD., JAPAN) 21 February 2008 (2008-02-21)
- DATABASE CA [Online] CHEMICAL ABSTRACTS SERVICE, COLUMBUS, OHIO, US; 2008, MATSUMOTO, AKIRA ET AL: "Oxime ester photoinitiators for coatings and resists", XP002693677, retrieved from STN Database accession no. 2008:1398437 & WO 2008/138733 A1 (CIBA HOLDING INC., SWITZ.) 20 November 2008 (2008-11-20)
- DATABASE CA [Online] CHEMICAL ABSTRACTS SERVICE, COLUMBUS, OHIO, US; 2011, WANG, ZHIGANG ET AL: "Multifunctional carbazole oxime ester derivative, its preparation method and application as photopolymerization initiator", XP002693678, retrieved from STN Database accession no. 2011:62756 -& CN 101 941 939 A (SHENZHEN YOUWEI CHEMICAL TECHNOLOGY CO., LTD., PEOP. REP. CHINA) 12 January 2011 (2011-01-12)
- DATABASE CA [Online] CHEMICAL ABSTRACTS SERVICE, COLUMBUS, OHIO, US; 2010, TAGUCHI, HIROSHI: "Oxime esters having carbazole structures, photopolymerization initiators containing them, and photosensitive resin compositions containing them", XP002693679, retrieved from STN Database accession no. 2010:1096303 & JP 2010 189280 A (NIPPON CHEMICAL WORKS CO., LTD., JAPAN) 2 September 2010 (2010-09-02)
- DATABASE CA [Online] CHEMICAL ABSTRACTS SERVICE, COLUMBUS, OHIO, US; 2007, MATSUMOTO, AKIRA ET AL: "Oxime esters for photoinitiators in photopolymerizable compositions", XP002693680, retrieved from STN Database accession no. 2007:706018 & WO 2007/071497 A1 (CIBA SPECIALTY CHEMICALS HOLDING INC., SWITZ.) 28 June 2007 (2007-06-28)

Description


[0001] The invention pertains to new oxime ester compounds based on specific carbazole derivatives and their use as photoinitiators in photopolymerizable compositions, in particular in photoresist formulations, for example in resins for black matrix in color filter applications.

Oxime ester compounds having carbazole moieties are known in the art as photoinitiators. For example WO02/100903 discloses corresponding compounds. The broad generic scopes of JP2006-030809-A, JP2006-162784 and JP2009-128419 also encompass compounds with a carbazole moiety. In JP2005-099258-A dimeric carbazole compounds are described.

However, none of the specific examples provide compounds with the features as given for the compounds of the invention.


[0002] In photopolymerization technology there still exists a need for highly reactive, easy to prepare and easy to handle photoinitiators. For example, in color filter resist applications, highly pigmented resists are required for the high color quality property. With the increase of the pigment content, the curing of color resists becomes more difficult. Hence, photoinitiators having a high sensitivity are required. In addition, also such new photoinitiators must meet the high requirements of the industry regarding properties like, for example, easy handling, high solubility, thermal stability and storage stability.. Furthermore the initiators in display applications should contribute to surface smoothness of a pattern, adhesiveness to the substrate etc.. Further, easy access to corresponding intermediates for the preparation of the compounds should be given. Thus, there is still a need for photoinitiator compounds providing a perfect balance of the requirements as given above. E.g. an acceptable balance between accessibility in view of preparation methods and processes as well as properties of the compound as for example sensitivity, solubility etc.

[0003] It now has been found, that selected compounds in particular provide these properties. Thus, subject of the invention are compounds of the formula I



wherein

Z is




R₁, R₂, R₃, R₄, R₅ and R₆ independently of each other are hydrogen, halogen, OR₁₆, SR₁₇, NR₁₈R₁₉, or C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, OR₁₆, COOR₁₆, CONR₁₈R₁₉ or NR₁₈R₁₉;

or **R₁, R₂, R₃, R₄, R₅ and R₆** independently of each other are C₆-C₂₀aryl, or C₄-C₂₀heteroaryl, each of which is unsubstituted or substituted by one or more C₁-C₆alkyl, C₁-C₄haloalkyl or halogen;

R₉, R₁₀, R₁₁, R₁₂ and R₁₃ independently of each other are hydrogen, halogen, OR₁₆, SR₁₇, NR₁₈R₁₉, CN, NO₂ or C₂-C₂₀alkyl which is interrupted by one or more O, S or NR₂₁, wherein the interrupted C₂-C₂₀alkyl is unsubstituted or substituted by one or more halogen, OR₁₆, COOR₁₆, SR₁₇, CONR₁₈R₁₉, C₆-C₂₀aryl, C₃-C₂₀heteroaryl or C₃-C₂₀cycloalkyl, C₃-C₂₀cycloalkyl interrupted by one or more O, S, NR₂₁;

or **R₉, R₁₀, R₁₁, R₁₂ and R₁₃** independently of each other are C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, OR₁₆, SR₁₇, COOR₁₆, CONR₁₈R₁₉, NR₁₈R₁₉, phenyl, C₃-C₈-cycloalkyl, C₃-C₂₀heteroaryl or M; **provided that R₉ and R₁₃ are neither hydrogen nor fluorine;**

R₁₄ is C₆-C₂₀aryl or C₃-C₂₀heteroaryl each of which is unsubstituted or substituted by one or more phenyl, halogen, C₁-C₄haloalkyl, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉, PO(OC_kH_{2k+1})₂, SO-C₁-C₁₀alkyl, SO₂-C₁-C₁₀alkyl, M,




5

or by C₂-C₂₀alkyl which is interrupted by one or more O, CO, S, C(O)O, OC(O), phenylene, naphthylene or by NR₂₁, or each of which C₆-C₂₀aryl or C₃-C₂₀heteroaryl is substituted by one or more C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, COOR₁₆, CONR₁₈R₁₉, phenyl, C₃-C₈cycloalkyl, C₃-C₂₀heteroaryl, C₆-C₂₀aryloxycarbonyl, C₃-C₂₀heteroaryloxycarbonyl, OR₁₆, SR₁₇, NR₁₈R₁₉ or by M;

10

M is


15



20

or

25



G is NO₂ or -COR₂₈;

30

R''₁₄ is C₁-C₂₀alkyl which is unsubstituted or substituted by phenyl or by phenyl which is substituted by one or more halogen, C₁-C₂₀alkyl, C₁-C₄haloalkyl, OR₁₆, SR₁₇ or by NR₁₈R₁₉;

or **R''₁₄** is C₂-C₂₀alkyl which is interrupted by one or more O, CO, S, C(O)O, OC(O), phenylene, naphthylene or NR₂₁, wherein the interrupted C₂-C₂₀alkyl is unsubstituted or substituted by one or more halogen, OR₁₆, COOR₁₆, CONR₁₈R₁₉, phenyl or by phenyl which is substituted by OR₁₆, SR₁₇ or NR₁₈R₁₉;

35

or **R''₁₄** is CN, CONR₁₈R₁₉, NO₂, C₁-C₄haloalkyl, S(O)_m-C₁-C₆alkyl; S(O)_m-phenyl which is unsubstituted or substituted by C₁-C₁₂alkyl or SO₂-C₁-C₆alkyl;

or **R''₁₄** is SO₂O-phenyl which is unsubstituted or substituted by C₁-C₁₂alkyl; or is diphenyl phosphinoyl or di-(C₁-C₄alkoxy)-phosphinoyl;

40

or **R''₁₄** is C₆-C₂₀aryl or C₃-C₂₀heteroaryl each of which is unsubstituted or substituted by one or more phenyl, halogen, C₁-C₄haloalkyl, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉, PO(OC_kH_{2k+1})₂, SO-C₁-C₁₀alkyl, SO₂-C₁-C₁₀alkyl, or by C₂-C₂₀alkyl which is interrupted by one or more O, CO, S, C(O)O, OC(O), phenylene, naphthylene or by NR₂₁, or each of which is substituted by one or more C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, COOR₁₆, CONR₁₈R₁₉, phenyl, C₃-C₈cycloalkyl, C₃-C₂₀heteroaryl, C₆-C₂₀aryloxycarbonyl, C₃-C₂₀heteroaryloxycarbonyl, OR₁₆, SR₁₇ or by NR₁₈R₁₉;

R₁₅ is hydrogen, C₃-C₈cycloalkyl, C₂-C₅alkenyl or phenyl;

45

k is an integer 1-10;

m is an integer 1 or 2;

R'₁₄ has one of the meanings as given for R₁₄ or is C₁-C₂₀alkyl;

R'₁₅ has one of the meanings as given for R₁₅;

X₁ is O, CO, S or a direct bond;

50

X₃ is O, S or NR'₂₀;

R₁₆ is hydrogen, phenyl-C₁-C₃alkyl, C₁-C₂₀alkyl, which is unsubstituted or substituted by one or more halogen, OH, SH, CN, C₃-C₆alkenoxy, O(C₁-C₄alkyl), OCH₂CH₂CN, OCH₂CH₂(CO)O(C₁-C₄alkyl), O(CO)-(C₁-C₄alkyl), O(CO)-(C₂-C₄)alkenyl, O(CO)-phenyl, (CO)OH, (CO)O(C₁-C₄alkyl), C₃-C₂₀cycloalkyl, SO₂-(C₁-C₄haloalkyl), O(C₁-C₄haloalkyl), O(C₁-C₂₀arylene)-M, or by C₃-C₂₀cycloalkyl which is interrupted by one or more O;


55

or **R₁₆** is C₂-C₂₀alkyl which is interrupted by one or more O, S or NR₂₁, which interrupted C₂-C₂₀alkyl is unsubstituted or substituted by O-C₆-C₂₀arylene-M, in which O-C₆-C₂₀arylene-M, the arylene is unsubstituted or substituted by one or more C₁-C₆alkyl or O(C₁-C₆alkyl);

or **R₁₆** is (CH₂CH₂O)_{n+1}H, (CH₂CH₂O)_n(CO)-(C₁-C₈alkyl), C₁-C₈alkanoyl, C₂-C₁₂alkenyl, C₃-C₆alkenyl, or

EP 2 847 167 B9

C₃-C₂₀cycloalkyl which is uninterrupted or interrupted by one or more O, S, CO or NR₂₁;
 or R₁₆ is C₁-C₈alkyl-C₃-C₁₀cycloalkyl which is uninterrupted or interrupted by one or more O;
 or R₁₆ is benzoyl which is unsubstituted or substituted by one or more C₁-C₆alkyl, halogen, OH, or C₁-C₃alkoxy;
 or R₁₆ is phenyl, naphthyl or C₃-C₂₀heteroaryl, each of which is unsubstituted or substituted by one or more halogen,
 5 OH, C₁-C₁₂alkyl, C₁-C₁₂alkoxy, CN, NO₂, phenyl-C₁-C₃alkyloxy, phenoxy, C₁-C₁₂alkylsulfanyl, phenylsulfanyl,
 N(C₁-C₁₂alkyl)₂, diphenylamino or



n is 1-20;

R₁₇ is hydrogen, C₂-C₁₂alkenyl, C₃-C₂₀cycloalkyl or phenyl-C₁-C₃alkyl, wherein the C₂-C₁₂alkenyl, C₃-C₂₀cycloalkyl
 or phenyl-C₁-C₃alkyl is uninterrupted or interrupted by one or more O, S, CO or NR₂₁;

or R₁₇ is C₁-C₂₀alkyl which is unsubstituted or substituted by one or more OH, SH, CN, C₃-C₆alkenoxy, OCH₂CH₂CN,
 15 OCH₂CH₂(CO)O(C₁-C₄alkyl), O(CO)-(C₂-C₄alkenyl), O(CO)-(C₁-C₄alkyl), O(CO)-phenyl, COOR₁₆ or S-
 C₆-C₂₀arylene-M;


or R₁₇ is C₁-C₂₀alkyl which is unsubstituted or substituted by one or more OH, SH, CN, C₃-C₆alkenoxy, OCH₂CH₂CN,
 OCH₂CH₂(CO)O(C₁-C₄alkyl), O(CO)-(C₂-C₄alkenyl), O(CO)-(C₁-C₄alkyl), O(CO)-phenyl or COOR₁₆;

or R₁₇ is C₂-C₂₀alkyl which is interrupted by one or more O, S, CO or NR₂₁, which interrupted C₂-C₂₀alkyl is
 20 unsubstituted or substituted by S-C₆-C₂₀arylene-M;

or R₁₇ is (CH₂CH₂O)_nH, (CH₂CH₂O)_n(CO)-(C₁-C₈alkyl), C₂-C₈alkanoyl or C₃-C₆alkenyl;

or R₁₇ is benzoyl which is unsubstituted or substituted by one or more C₁-C₆alkyl, halogen, OH, C₁-C₄alkoxy or
 C₁-C₄alkylsulfanyl;


or R₁₇ is phenyl, naphthyl or C₃-C₂₀heteroaryl, each of which is unsubstituted or substituted by one or more halogen,
 25 C₁-C₁₂alkyl, C₁-C₄haloalkyl, C₁-C₁₂alkoxy, CN, NO₂, phenyl-C₁-C₃alkyloxy, phenoxy, C₁-C₁₂alkylsulfanyl, phenyl-
 sulfanyl, N(C₁-C₁₂alkyl)₂, diphenylamino, (CO)O(C₁-C₈alkyl), (CO)-C₁-C₈alkyl, (CO)N(C₁-C₈alkyl)₂ or




R₁₈ and R₁₉ independently of each other are hydrogen, C₁-C₂₀alkyl, C₂-C₄hydroxyalkyl, C₂-C₁₀alkoxyalkyl,
 35 C₂-C₅alkenyl, C₃-C₂₀cycloalkyl, phenyl-C₁-C₃alkyl, C₁-C₈alkanoyl, C₁-C₈alkanoyloxy, C₃-C₁₂alkenyl,
 SO₂-(C₁-C₄haloalkyl) or benzoyl;

or R₁₈ and R₁₉ are phenyl, naphthyl or C₃-C₂₀heteroaryl, each of which is unsubstituted or substituted by one or
 more halogen, C₁-C₄haloalkyl, C₁-C₂₀alkoxy, C₁-C₁₂alkyl, benzoyl or C₁-C₁₂alkoxy;

or R₁₈ and R₁₉ together with the N-atom to which they are attached form a 5- or 6-membered saturated or unsaturated
 40 ring which is uninterrupted or is interrupted by O, S, or NR₂₁, and which 5- or 6-membered saturated or unsaturated
 ring is unsubstituted or substituted by one or more C₁-C₂₀alkyl, C₁-C₂₀alkoxy, =O, OR₁₆, SR₁₇, NR₃₁R₃₂, COR₄₁,
 NO₂, halogen, C₁-C₄-haloalkyl, CN, phenyl,



or by C₃-C₂₀cycloalkyl which is uninterrupted or is interrupted by one or more O, S, CO or NR₂₁; or R₁₈ and R₁₉
 50 together with the N-atom to which they are attached form a group




R₂₀ is hydrogen, COR₄₁ or C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, OR₁₆, SR₁₇,

COOR₁₆, CONR₁₈R₁₉, NR₁₈R₁₉, PO(OC_kH_{2k+1})₂ or M;

or R₂₀ is C₂-C₂₀alkyl which is interrupted by one or more O, CO, C(O)O, OC(O) or NR₂₁, wherein the interrupted C₂-C₂₀alkyl is unsubstituted or substituted by one or more halogen, OR₁₆, SR₁₇, COOR₁₆, CONR₁₈R₁₉, NR₁₈R₁₉ or M;

or R₂₀ is C₆-C₂₀aryl or C₃-C₂₀heteroaryl each of which is unsubstituted or substituted by one or more phenyl, halogen, C₁-C₄haloalkyl, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉, M, Z,




or by C₁-C₂₀alkyl which is interrupted by one or more O, S or NR₂₁, or each of which C₆-C₂₀aryl or C₃-C₂₀heteroaryl is substituted by one or more C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, COOR₁₆, CONR₁₈R₁₉, phenyl, C₃-C₈cycloalkyl, C₃-C₂₀heteroaryl, C₆-C₂₀aryloxy carbonyl, C₃-C₂₀heteroaryloxy carbonyl, OR₁₆, SR₁₇ or NR₁₈R₁₉;

R'₂₀ is hydrogen, COR₄₁ or C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, OR₁₆, SR₁₇, COOR₁₆, CONR₁₈R₁₉, NR₁₈R₁₉ or PO(OC_kH_{2k+1})₂;

or R'₂₀ is C₂-C₂₀alkyl of which is interrupted by one or more O, CO, C(O)O, OC(O) or NR₂₁, wherein the interrupted C₂-C₂₀alkyl is unsubstituted or substituted by one or more halogen, OR₁₆, SR₁₇, COOR₁₆, CONR₁₈R₁₉ or NR₁₈R₁₉;


or R'₂₀ is C₆-C₂₀aryl or C₃-C₂₀heteroaryl each of which is unsubstituted or substituted by one or more phenyl, halogen, C₁-C₄haloalkyl, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉,




or by C₁-C₂₀alkyl which is interrupted by one or more O, S or NR₂₁, or each of which C₆-C₂₀aryl or C₃-C₂₀heteroaryl is substituted by one or more C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, COOR₁₆, CONR₁₈R₁₉, phenyl, C₃-C₈cycloalkyl, C₃-C₂₀heteroaryl, C₆-C₂₀aryloxy carbonyl, C₃-C₂₀heteroaryloxy carbonyl, OR₁₆, SR₁₇ or NR₁₈R₁₉;

R₂₁ is hydrogen, C₁-C₂₀alkyl, C₁-C₄haloalkyl or C₂-C₂₀alkyl which is interrupted by one or more O, CO, C(O)O or OC(CO),

or R₂₁ is COR₄₁, phenyl-C₁-C₄alkyl or C₃-C₈cycloalkyl which is uninterrupted or is interrupted by one or more O or CO, or R₂₁ is phenyl or naphthyl both of which are unsubstituted or substituted by one or more C₁-C₂₀alkyl, halogen, C₁-C₄haloalkyl, OR₁₆, SR₁₇, NR₁₈R₁₉ or



R₂₂, R₂₃, R₂₄, R₂₅, R₂₆ or R₂₇ independently of each other are hydrogen, COR₄₁, NO₂ or



or one of R₂₂, R₂₃ or R₂₄ and one of R₂₅, R₂₆ or R₂₇ together with X₃ and the phenyl rings to which they are attached form a heteroaromatic ring system;


R₂₈ is C₆-C₂₀aryl or C₃-C₂₀heteroaryl each of which is unsubstituted or substituted by one or more phenyl, halogen, C₁-C₄haloalkyl, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉ or by C₂-C₂₀alkyl which is interrupted by one or more O, S or NR₂₁, or each of which C₆-C₂₀aryl or C₃-C₂₀heteroaryl is substituted by one or more C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, COOR₁₆, CONR₁₈R₁₉, phenyl, C₃-C₈cycloalkyl, C₃-C₂₀heteroaryl, C₆-C₂₀aryloxy carbonyl, C₃-C₂₀heteroaryloxy carbonyl, OR₁₆, SR₁₇ or NR₁₈R₁₉;

R₃₁ and R₃₂ independently of each other are hydrogen, C₁-C₂₀alkyl, C₁-C₄haloalkyl, C₃-C₁₀cycloalkyl or phenyl;

or R₃₁ and R₃₂ together with N-atom to which they are attached form a 5- or 6-membered saturated or unsaturated ring, which is uninterrupted or is interrupted by O, S or NR₂₁, and which 5- or 6-membered saturated or unsaturated ring is not condensed or to which 5- or 6-membered saturated or unsaturated ring a benzene ring is condensed;

R₃₃, R₃₄, R₃₅, R₃₆, R₃₇, R₃₈, R₃₉ and R₄₀ independently of each other are hydrogen,


EP 2 847 167 B9



5 NO₂, COR₄₁, C₁-C₂₀alkyl, C₁-C₄haloalkyl, OR₁₆, SR₁₇, NR₁₈R₁₉, halogen, CN, phenyl or C₃-C₂₀cycloalkyl which is uninterrupted or is interrupted by one or more O, S, CO or NR₂₁;
or R₃₅ and R₃₆ or R₃₇ and R₃₈ or both, R₃₅ and R₃₆ and R₃₇ and R₃₈ are



R₄₁ is C₆-C₂₀aryl or C₃-C₂₀heteroaryl each of which is unsubstituted or substituted by one or more phenyl, halogen, C₁-C₄haloalkyl, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉ or by C₂-C₂₀alkyl which is interrupted by one or more O, S or NR₂₁,
15 or each of which C₆-C₂₀aryl or C₃-C₂₀heteroaryl is substituted by one or more C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, COOR₁₆, CONR₁₈R₁₉, phenyl, C₃-C₈cycloalkyl, C₃-C₂₀heteroaryl, C₆-C₂₀aryloxycarbonyl, C₃-C₂₀heteroaryloxycarbonyl, OR₁₆, SR₁₇ or NR₁₈R₁₉;
or R₄₁ is



25 or R₄₁ is hydrogen, OH, C₁-C₂₀alkyl, C₁-C₄haloalkyl, C₂-C₂₀alkyl which is interrupted by one or more O, CO or NR₂₁, or R₄₁ is C₃-C₂₀cycloalkyl which is uninterrupted or is interrupted by O, S, CO or NR₂₁.

30 **[0004]** Interesting are compounds of the formula I wherein

Z is



40 R₁, R₂, R₃, R₄, R₅ and R₆ independently of each other are hydrogen, halogen, OR₁₆, SR₁₇, NR₁₈R₁₉, or C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, OR₁₆, COOR₁₆, CONR₁₈R₁₉ or NR₁₈R₁₉;
or R₁, R₂, R₃, R₄, R₅ and R₆ independently of each other are C₆-C₂₀aryl, or C₄-C₂₀heteroaryl, each of which is unsubstituted or substituted by one or more C₁-C₆alkyl, C₁-C₄haloalkyl or halogen;

45 R₉, R₁₀, R₁₁, R₁₂ and R₁₃ independently of each other are hydrogen, halogen, OR₁₆, SR₁₇, NR₁₈R₁₉, CN, NO₂ or C₂-C₂₀alkyl which is interrupted by one or more O, S or NR₂₁, wherein the interrupted C₂-C₂₀alkyl is unsubstituted or substituted by one or more halogen, OR₁₆, COOR₁₆, SR₁₇, CONR₁₈R₁₉, C₆-C₂₀aryl, C₃-C₂₀heteroaryl or C₃-C₂₀cycloalkyl, C₃-C₂₀cycloalkyl interrupted by one or more O, S, NR₂₁;

or R₉, R₁₀, R₁₁, R₁₂ and R₁₃ independently of each other are C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, OR₁₆, SR₁₇, COOR₁₆, CONR₁₈R₁₉, NR₁₈R₁₉, phenyl, C₃-C₈-cycloalkyl, C₃-C₂₀heteroaryl or M;
50 **provided that** R₉ and R₁₃ are neither hydrogen nor fluorine;

R₁₄ is C₆-C₂₀aryl or C₃-C₂₀heteroaryl each of which is unsubstituted or substituted by one or more phenyl, halogen, C₁-C₄haloalkyl, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉, PO(OC_kH_{2k+1})₂, SO-C₁-C₁₀alkyl, SO₂-C₁-C₁₀alkyl, M,




or by C₂-C₂₀alkyl which is interrupted by one or more O, CO, S, C(O)O, OC(O), phenylene, naphthylene or by NR₂₁,

or each of which C₆-C₂₀aryl or C₃-C₂₀heteroaryl is substituted by one or more C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, COOR₁₆, CONR₁₈R₁₉, phenyl, C₃-C₈cycloalkyl, C₃-C₂₀heteroaryl, C₆-C₂₀aryloxycarbonyl, C₃-C₂₀heteroaryloxycarbonyl, OR₁₆, SR₁₇, NR₁₈R₁₉ or by M;

M is

5


10



or

15

20



G is NO₂ or -COR₂₈;

R''₁₄ is C₁-C₂₀alkyl which is unsubstituted or substituted by phenyl or by phenyl which is substituted by one or more halogen, C₁-C₂₀alkyl, C₁-C₄haloalkyl, OR₁₆, SR₁₇ or by NR₁₈R₁₉;

or **R''₁₄** is C₂-C₂₀alkyl which is interrupted by one or more O, CO, S, C(O)O, OC(O), phenylene, naphthylene or NR₂₁, wherein the interrupted C₂-C₂₀alkyl is unsubstituted or substituted by one or more halogen, OR₁₆, COOR₁₆, CONR₁₈R₁₉, phenyl or by phenyl which is substituted by OR₁₆, SR₁₇ or NR₁₈R₁₉;

or **R''₁₄** is CN, CONR₁₈R₁₉, NO₂, C₁-C₄haloalkyl, S(O)_m-C₁-C₆alkyl; S(O)_m-phenyl which is unsubstituted or substituted by C₁-C₁₂alkyl or SO₂-C₁-C₆alkyl;

or **R''₁₄** is SO₂O-phenyl which is unsubstituted or substituted by C₁-C₁₂alkyl; or is diphenyl phosphinoyl or di-(C₁-C₄alkoxy)-phosphinoyl;

or **R''₁₄** is C₆-C₂₀aryl or C₃-C₂₀heteroaryl each of which is unsubstituted or substituted by one or more phenyl, halogen, C₁-C₄haloalkyl, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉, PO(OC_kH_{2k+1})₂, SO-C₁-C₁₀alkyl, SO₂-C₁-C₁₀alkyl, or by C₂-C₂₀alkyl which is interrupted by one or more O, CO, S, C(O)O, OC(O), phenylene, naphthylene or by NR₂₁, or

each of which is substituted by one or more C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, COOR₁₆, CONR₁₈R₁₉, phenyl, C₃-C₈cycloalkyl, C₃-C₂₀heteroaryl, C₆-C₂₀aryloxycarbonyl, C₃-C₂₀heteroaryloxycarbonyl, OR₁₆, SR₁₇ or by NR₁₈R₁₉;

R₁₅ is hydrogen, C₃-C₈cycloalkyl, C₂-C₅alkenyl or phenyl;

k is an integer 1-10;

m is an integer 1 or 2;

R'₁₄ has one of the meanings as given for R₁₄;

R'₁₅ has one of the meanings as given for R₁₅;

X₁ is O, CO, S or a direct bond;

X₃ is O, S or NR'₂₀;

R₁₆ is hydrogen, phenyl-C₁-C₃alkyl, C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, OH, SH, CN, C₃-C₆alkenoxy, OCH₂CH₂CN, OCH₂CH₂(CO)O(C₁-C₄alkyl), O(CO)-(C₁-C₄alkyl), O(CO)-(C₂-C₄alkenyl), O(CO)-phenyl, (CO)OH, (CO)O(C₁-C₄alkyl), C₃-C₂₀cycloalkyl, SO₂-(C₁-C₄haloalkyl), O(C₁-C₄haloalkyl), O(C₁-C₂₀arylene)-M, or by C₃-C₂₀cycloalkyl which is interrupted by one or more O;

or **R₁₆** is C₂-C₂₀alkyl which is interrupted by one or more O, S or NR₂₁;


or **R₁₆** is (CH₂CH₂O)_{n+1}H, (CH₂CH₂O)_n(CO)-(C₁-C₈alkyl), C₁-C₈alkanoyl, C₂-C₁₂alkenyl, C₃-C₆alkenoyl, or C₃-C₂₀cycloalkyl which is uninterrupted or interrupted by one or more O, S, CO or NR₂₁;

or **R₁₆** is C₁-C₈alkyl-C₃-C₁₀cycloalkyl which is uninterrupted or interrupted by one or more O;

or **R₁₆** is benzoyl which is unsubstituted or substituted by one or more C₁-C₆alkyl, halogen, OH, or C₁-C₃alkoxy;

or **R₁₆** is phenyl, naphthyl or C₃-C₂₀heteroaryl, each of which is unsubstituted or substituted by one or more halogen, OH, C₁-C₁₂alkyl, C₁-C₁₂alkoxy, CN, NO₂, phenyl-C₁-C₃alkyloxy, phenoxy, C₁-C₁₂alkylsulfanyl, phenylsulfanyl, N(C₁-C₁₂alkyl)₂, diphenylamino or

55



5 **n** is 1-20;

R₁₇ is hydrogen, C₂-C₁₂alkenyl, C₃-C₂₀cycloalkyl or phenyl-C₁-C₃alkyl, wherein the C₂-C₁₂alkenyl, C₃-C₂₀cycloalkyl or phenyl-C₁-C₃alkyl is uninterrupted or interrupted by one or more O, S, CO or NR₂₁;


or **R**₁₇ is C₁-C₂₀alkyl which is unsubstituted or substituted by one or more OH, SH, CN, C₃-C₆alkenoxy, OCH₂CH₂CN, OCH₂CH₂(CO)O(C₁-C₄alkyl), O(CO)-(C₂-C₄)alkenyl, O(CO)-(C₁-C₄alkyl), O(CO)-phenyl or COOR₁₆;

10 or **R**₁₇ is C₂-C₂₀alkyl which is interrupted by one or more O, S, CO or NR₂₁;

or **R**₁₇ is (CH₂CH₂O)_nH, (CH₂CH₂O)_n(CO)-(C₁-C₈alkyl), C₂-C₈alkanoyl or C₃-C₆alkenoyl;

or **R**₁₇ is benzoyl which is unsubstituted or substituted by one or more C₁-C₆alkyl, halogen, OH, C₁-C₄alkoxy or C₁-C₄alkylsulfanyl;

15 or **R**₁₇ is phenyl, naphthyl or C₃-C₂₀heteroaryl, each of which is unsubstituted or substituted by one or more halogen, C₁-C₁₂alkyl, C₁-C₄haloalkyl, C₁-C₁₂alkoxy, CN, NO₂, phenyl-C₁-C₃alkyloxy, phenoxy, C₁-C₁₂alkylsulfanyl, phenylsulfanyl, N(C₁-C₁₂alkyl)₂, diphenylamino, (CO)O(C₁-C₈alkyl), (CO)-C₁-C₈alkyl, (CO)N(C₁-C₈alkyl)₂ or




20 **R**₁₈ and **R**₁₉ independently of each other are hydrogen, C₁-C₂₀alkyl, C₂-C₄hydroxyalkyl, C₂-C₁₀alkoxyalkyl, C₂-C₅alkenyl, C₃-C₂₀cycloalkyl, phenyl-C₁-C₃alkyl, C₁-C₈alkanoyl, C₁-C₈alkanoyloxy, C₃-C₁₂alkenoyl, SO₂-(C₁-C₄haloalkyl) or benzoyl;

25 or **R**₁₈ and **R**₁₉ are phenyl, naphthyl or C₃-C₂₀heteroaryl, each of which is unsubstituted or substituted by one or more halogen, C₁-C₄haloalkyl, C₁-C₂₀alkoxy, C₁-C₁₂alkyl, benzoyl or C₁-C₁₂alkoxy;

or **R**₁₈ and **R**₁₉ together with the N-atom to which they are attached form a 5- or 6-membered saturated or unsaturated ring which is uninterrupted or is interrupted by O, S, or NR₂₁, and which 5- or 6-membered saturated or unsaturated ring is unsubstituted or substituted by one or more C₁-C₂₀alkyl, C₁-C₂₀alkoxy, =O, OR₁₆, SR₁₇, NR₃₁R₃₂, COR₄₁, NO₂, halogen, C₁-C₄-haloalkyl, CN, phenyl,

30



35 or by C₃-C₂₀cycloalkyl which is uninterrupted or is interrupted by one or more O, S, CO or NR₂₁; or **R**₁₈ and **R**₁₉ together with the N-atom to which they are attached form a group

40




45 **R**₂₀ is hydrogen, COR₄₁ or C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, OR₁₆, SR₁₇, COOR₁₆, CONR₁₈R₁₉, NR₁₈R₁₉, PO(OC_kH_{2k+1})₂ or M;

or **R**₂₀ is C₂-C₂₀alkyl of which is interrupted by one or more O, CO, C(O)O, OC(O) or NR₂₁, wherein the interrupted C₂-C₂₀alkyl is unsubstituted or substituted by one or more halogen, OR₁₆, SR₁₇, COOR₁₆, CONR₁₈R₁₉, NR₁₈R₁₉ or M;

50 or **R**₂₀ is C₆-C₂₀aryl or C₃-C₂₀heteroaryl each of which is unsubstituted or substituted by one or more phenyl, halogen, C₁-C₄haloalkyl, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉, M, Z,

55




or by C₁-C₂₀alkyl which is interrupted by one or more O, S or NR₂₁, or each of which C₆-C₂₀aryl or C₃-C₂₀heteroaryl

is substituted by one or more C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, COOR₁₆, CONR₁₈R₁₉, phenyl, C₃-C₈cycloalkyl, C₃-C₂₀heteroaryl, C₆-C₂₀aryloxy carbonyl, C₃-C₂₀heteroaryloxy carbonyl, OR₁₆, SR₁₇ or NR₁₈R₁₉;

R₂₀ is hydrogen, COR₄₁ or C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, OR₁₆, SR₁₇, COOR₁₆, CONR₁₈R₁₉, NR₁₈R₁₉ or PO(OC_kH_{2k+1})₂;


or R'₂₀ is C₂-C₂₀alkyl of which is interrupted by one or more O, CO, C(O)O, OC(O) or NR₂₁, wherein the interrupted C₂-C₂₀alkyl is unsubstituted or substituted by one or more halogen, OR₁₆, SR₁₇, COOR₁₆, CONR₁₈R₁₉ or NR₁₈R₁₉; or R'₂₀ is C₆-C₂₀aryl or C₃-C₂₀heteroaryl each of which is unsubstituted or substituted by one or more phenyl, halogen, C₁-C₄haloalkyl, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉,




or by C₁-C₂₀alkyl which is interrupted by one or more O, S or NR₂₁, or each of which C₆-C₂₀aryl or C₃-C₂₀heteroaryl is substituted by one or more C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, COOR₁₆, CONR₁₈R₁₉, phenyl, C₃-C₈cycloalkyl, C₃-C₂₀heteroaryl, C₆-C₂₀aryloxy carbonyl, C₃-C₂₀heteroaryloxy carbonyl, OR₁₆, SR₁₇ or NR₁₈R₁₉;

R₂₁ is hydrogen, C₁-C₂₀alkyl, C₁-C₄haloalkyl or C₂-C₂₀alkyl which is interrupted by one or more O, CO, C(O)O or OC(CO),

or R₂₁ is COR₄₁, phenyl-C₁-C₄alkyl or C₃-C₈cycloalkyl which is uninterrupted or is interrupted by one or more O or CO, or R₂₁ is phenyl or naphthyl both of which are unsubstituted or substituted by one or more C₁-C₂₀alkyl, halogen, C₁-C₄haloalkyl, OR₁₆, SR₁₇, NR₁₈R₁₉ or



R₂₂, R₂₃, R₂₄, R₂₅, R₂₆ or R₂₇ independently of each other are hydrogen, COR₄₁, NO₂ or




or one of R₂₂, R₂₃ or R₂₄ and one of R₂₅, R₂₆ or R₂₇ together with X₃ and the phenyl rings to which they are attached form a heteroaromatic ring system;

R₂₈ is C₆-C₂₀aryl or C₃-C₂₀heteroaryl each of which is unsubstituted or substituted by one or more phenyl, halogen, C₁-C₄haloalkyl, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉ or by C₂-C₂₀alkyl which is interrupted by one or more O, S or NR₂₁, or each of which C₆-C₂₀aryl or C₃-C₂₀heteroaryl is substituted by one or more C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, COOR₁₆, CONR₁₈R₁₉, phenyl, C₃-C₈cycloalkyl, C₃-C₂₀heteroaryl, C₆-C₂₀aryloxy carbonyl, C₃-C₂₀heteroaryloxy carbonyl, OR₁₆, SR₁₇ or NR₁₈R₁₉;


R₃₁ and R₃₂ independently of each other are hydrogen, C₁-C₂₀alkyl, C₁-C₄haloalkyl, C₃-C₁₀cycloalkyl or phenyl; or R₃₁ and R₃₂ together with N-atom to which they are attached form a 5- or 6-membered saturated or unsaturated ring, which is uninterrupted or is interrupted by O, S or NR₂₁, and which 5- or 6-membered saturated or unsaturated ring is not condensed or to which 5- or 6-membered saturated or unsaturated ring a benzene ring is condensed;

R₃₃, R₃₄, R₃₅, R₃₆, R₃₇, R₃₈, R₃₉ and R₄₀ independently of each other are hydrogen,




NO₂, COR₄₁, C₁-C₂₀alkyl, C₁-C₄haloalkyl, OR₁₆, SR₁₇, NR₁₈R₁₉, halogen, CN, phenyl or C₃-C₂₀cycloalkyl which is uninterrupted or is interrupted by one or more O, S, CO or NR₂₁;

or R₃₅ and R₃₆ or R₃₇ and R₃₈ or both, R₃₅ and R₃₆ and R₃₇ and R₃₈ are



R_{41} is C_6 - C_{20} aryl or C_3 - C_{20} heteroaryl each of which is unsubstituted or substituted by one or more phenyl, halogen, C_1 - C_4 haloalkyl, CN, NO_2 , OR_{16} , SR_{17} , $NR_{18}R_{19}$ or by C_2 - C_{20} alkyl which is interrupted by one or more O, S or NR_{21} , or each of which C_6 - C_{20} aryl or C_3 - C_{20} heteroaryl is substituted by one or more C_1 - C_{20} alkyl which is unsubstituted or substituted by one or more halogen, $COOR_{16}$, $CONR_{18}R_{19}$, phenyl, C_3 - C_8 cycloalkyl, C_3 - C_{20} heteroaryl, C_6 - C_{20} aryloxy carbonyl, C_3 - C_{20} heteroaryloxy carbonyl, OR_{16} , SR_{17} or $NR_{18}R_{19}$; or R_{41} is



or R_{41} is hydrogen, OH, C_1 - C_{20} alkyl, C_1 - C_4 haloalkyl, C_2 - C_{20} alkyl which is interrupted by one or more O, CO or NR_{21} , or R_{41} is C_3 - C_{20} cycloalkyl which is uninterrupted or is interrupted by O, S, CO or NR_{21} .

[0005] The compounds of the formula I are characterized in that they comprise substituents in both ortho-positions of the benzoyl group and in that the substituent R_{14} at the oxime group is either an aryl or a heteroaryl moiety.



[0006] C_1 - C_{20} alkyl is linear or branched and is, for example, C_1 - C_{18} -, C_1 - C_{14} -, C_1 - C_{12} -, C_1 - C_8 -, C_1 - C_6 -, C_1 - C_4 alkyl or C_4 - C_{12} - or C_4 - C_8 alkyl. Examples are methyl, ethyl, propyl, isopropyl, n-butyl, sec-butyl, isobutyl, tert-butyl, pentyl, hexyl, heptyl, 2,4,4-trimethylpentyl, 2-ethylhexyl, octyl, nonyl, decyl, dodecyl, tetradecyl, pentadecyl, hexadecyl, octadecyl and icosyl. C_1 - C_6 alkyl and C_1 - C_{12} alkyl have the same meanings as given above for C_1 - C_{20} alkyl up to the corresponding number of C-atoms.

[0007] C_1 - C_4 haloalkyl is C_1 - C_4 alkyl as defined above substituted by halogen as defined below. The alkyl radical is for example halogenated once, twice or three times, or mono- or poly-halogenated, up to the exchange of all H-atoms by halogen. It is for example $C_nH_xHal_y$, wherein $x+y = 2n+1$ and Hal is halogen, preferably F. Specific examples are chloromethyl, trichloromethyl, trifluoromethyl or 2-bromopropyl, especially trifluoromethyl or trichloromethyl.

[0008] C_2 - C_4 hydroxyalkyl means C_2 - C_4 alkyl, which substituted by one or more, in particular one or two OH groups. The alkyl radical is linear or branched. Examples are 2-hydroxyethyl, 1-hydroxyethyl, 1-hydroxypropyl, 2-hydroxypropyl, 3-hydroxypropyl, 1-hydroxybutyl, 4-hydroxybutyl, 2-hydroxybutyl, 3-hydroxybutyl, 2,3-dihydroxypropyl, or 2,4-dihydroxybutyl.


[0009] C_2 - C_{10} alkoxyalkyl is linear or branched C_2 - C_{10} alkyl, which is interrupted by one O-atom. C_2 - C_{10} alkyl has the same meanings as given above for C_1 - C_{20} alkyl up to the corresponding number of C-atoms. Examples are methoxymethyl, methoxyethyl, methoxypropyl, ethoxymethyl, ethoxyethyl, ethoxypropyl, propoxymethyl, propoxyethyl, propoxypropyl.

[0010] C_2 - C_{20} alkyl which is interrupted by one or more O, CO, S, $C(O)O$, $OC(O)$, phenylene, naphthylene or NR_{21} , is for example interrupted 1-9, 1-5, 1-3 or once or twice by O, CO, S, $C(O)O$, $OC(O)$, phenylene, naphthylene or NR_{21} . If more than one of the defined interrupting radicals are present they are of the same kind or different. Two O-atoms are separated by at least one methylene group, preferably at least two methylene groups, namely ethylene. The alkyl groups are linear or branched. For example the following structural units will occur, $-CH_2-CH_2-O-CH_2CH_3$, $-[CH_2CH_2O]_y-CH_3$, wherein $y = 1-9$, $-(CH_2-CH_2O)_7-CH_2CH_3$, $-CH_2-CH(CH_3)-O-CH_2-CH_2CH_3$, $-CH_2-CH(CH_3)-O-CH_2-CH_3$, $-CH_2-CH_2-S-CH_2CH_3$, $-CH_2-CH(CH_3)-NR_{21}-CH_2-CH_3$, $-CH_2-CH_2-COO-CH_2CH_3$ or $-CH_2-CH(CH_3)-OCO-CH_2-CH_2CH_3$, $-CH_2-CH_2-O(CO)-CH_2CH_3$, $-CH_2-CH_2-(CO)O-CH_2CH_3$, $-CH_2-CH(CH_3)-O(CO)-CH_2-CH_2CH_3$,




etc..

[0011] C_1 - C_{20} alkylene is linear or branched alkylene, for example methylene, ethylene, propylene, 1-methylethylene, 1,1-dimethylethylene, butylene, 1-methylpropylene, 2-methylpropylene, pentylene, hexylene, heptylene, octylene, nonylene, decylene, dodecylene, tetradecylene, hexadecylene or octadecylene. In particular, C_1 - C_{12} alkylene, for example ethylene, decylene,



5



10

[0012] C_2 - C_{20} alkylene which is interrupted one or more times by O is, for example, interrupted 1-9 times, for example 1-7 times or once or twice by O. This produces structural units such as, for example, $-\text{CH}_2\text{-O-CH}_2-$, $-\text{CH}_2\text{-CH}_2\text{-O-CH}_2\text{-CH}_2-$, $-\text{[CH}_2\text{CH}_2\text{O]}_y-$, $-\text{[CH}_2\text{CH}_2\text{O]}_y\text{-CH}_2-$, where $y = 1-9$, $-(\text{CH}_2\text{CH}_2\text{O})_7\text{CH}_2\text{CH}_2-$, $-\text{CH}_2\text{-CH}(\text{CH}_3)\text{-O-CH}_2\text{-CH}(\text{CH}_3)-$ or $-\text{CH}_2\text{-CH}(\text{CH}_3)\text{-O-CH}_2\text{-CH}_2\text{CH}_2-$. The interrupting atoms are non-successive.

15


[0013] C_2 - C_{12} alkenylene is mono- or polyunsaturated and is, for example, ethenylene, 1-propenylene, 1-butenylene, 3-butenylene, 2-butenylene, 1,3-pentadienylene, 5-hexenylene or 7-octenylene.

[0014] C_3 - C_{10} cycloalkyl and C_3 - C_8 cycloalkyl in the context of the present application is to be understood as alkyl which at least comprises one ring. It is for example cyclopropyl, cyclobutyl, cyclopentyl, cyclohexyl, cyclooctyl, especially cyclopentyl and cyclohexyl.

20


[0015] C_3 - C_{10} cycloalkyl in the context of the present invention is also meant to cover bicyclic rings, in other words a bridged ring, such as for example

25




and corresponding rings. Further examples are structures like

30




35



as well as bridged or fused ring systems, e.g.


40




etc. are also meant to be covered by the term.


[0016] C_3 - C_{20} cycloalkyl which is interrupted by O, S, CO or NR_{21} has the meanings given above for C_3 - C_{20} cycloalkyl, wherein at least one CH_2 -group of the alkyl is exchanged by either O, S, CO or NR_{21} . Examples are structures like

50





55






etc..

[0017] C_1 - C_8 alkyl- C_3 - C_{10} cycloalkyl is C_3 - C_{10} cycloalkyl as defined above which is substituted by one or more alkyl groups with up to 8 carbon atoms. Examples are



etc. Further, corresponding interrupted C_1 - C_8 alkyl- C_3 - C_{10} cycloalkyl interrupted by one or more O refers to the C_1 - C_8 alkyl- C_3 - C_{10} cycloalkyl as defined above, where the interrupting atoms are considered as interrupting either the C_1 - C_8 alkyl or the C_3 - C_{10} cycloalkyl, or both.

[0018] Examples are



etc.

[0019] C_1 - C_{20} alkoxy is linear or branched and is C_1 - C_{20} alkyl, which is substituted by one O-atom, namely C_1 - C_{20} alkyl-O-. C_1 - C_{20} alkyl has the same meanings as given above for C_1 - C_{20} alkyl up to the corresponding number of C-atoms. C_1 - C_{20} alkoxy is for example C_1 - C_{18} -, C_1 - C_{12} -, C_1 - C_{10} -, C_1 - C_8 -, C_1 - C_4 - or C_1 - C_3 alkoxy. Examples are methoxy, ethoxy, propoxy, isopropoxy, n-butyloxy, sec-butyloxy, isobutyloxy, tert-butyloxy. C_1 - C_8 alkoxy and C_1 - C_4 -alkoxy have the same meanings as described above up to the corresponding numbers of C-atoms.

[0020] C_1 - C_{12} alkylsulfanyl is linear or branched and is C_1 - C_{12} alkyl, which is substituted by one S-atom, namely C_1 - C_{12} alkyl-S-. C_1 - C_{12} alkyl has the same meanings as given above for C_1 - C_{20} alkyl up to the corresponding number of C-atoms. C_1 - C_4 alkylsulfanyl is linear or branched, for example, methylsulfanyl, ethylsulfanyl, propylsulfanyl, isopropylsulfanyl, n-butylysulfanyl, sec-butylysulfanyl, isobutylysulfanyl, tert-butylysulfanyl.

[0021] Phenyl- C_1 - C_3 alkyl or phenyl- C_1 - C_4 alkyl is for example benzyl, phenylethyl, α -methylbenzyl, α,α -dimethylbenzyl, especially benzyl.

[0022] Phenyl- C_1 - C_3 alkyl interrupted by one or more O, S, CO or NR_{21} is phenyl- C_1 - C_3 alkyl as defined above, wherein the alkyl moiety is interrupted by one or two O, S, CO or NR_{21} . If more than one of the defined interrupting radicals are present they are of the same kind or different. Two O-atoms are separated by a methylene group. The alkyl groups are linear or branched.

[0023] Phenyl- C_1 - C_3 alkoxy or phenyl- C_1 - C_4 alkoxy is for example benzyloxy, phenylethyloxy, α -methylbenzyloxy or α,α -dimethylbenzyloxy, especially benzyloxy.

[0024] C_2 - C_{12} alkenyl or C_2 - C_5 alkenyl radicals are linear or branched and are mono- or polyunsaturated and are for example C_2 - C_{10} -, C_2 - C_8 -, C_2 - C_5 -alkenyl e.g. vinyl, allyl, methallyl, 1,1-dimethylallyl, 1-butenyl, 3-butenyl, 2-butenyl, 1,3-pentadienyl, 5-hexenyl, 7-octenyl or dodecenyl, especially allyl. C_2 - C_5 alkenyl radicals have the same meanings as given above for C_2 - C_{12} alkenyl radicals up to the corresponding number of C-atoms.

[0025] C_2 - C_{12} alkenyl which is interrupted by one or more O, S, CO or NR_{21} s for example interrupted 1-9, 1-5, 1-3 or once or twice by O, S, CO or NR_{21} . If more than one of the interrupting radicals are present they are of the same kind or different. Two O-atoms are separated by at least one methylene group, preferably at least two methylene groups, namely ethylene. The alkenyl groups are linear or branched and are defined as above. For example following structural units can be formed $-CH=CH-O-CH_2CH_3$, $-CH=CH-O-CH=CH_2$ etc..

[0026] C_3 - C_6 alkenoxy is mono or polyunsaturated, linear or branched, and has one of the meanings given for alkenyl above with the attached oxy group up to the corresponding number of C-atoms. Examples are allyloxy, methallyloxy, butenyloxy, pentenoxy, 1,3-pentadienyloxy, 5-hexenyloxy.

[0027] C_1-C_8 alkanoyl = C_1-C_8 alkylcarbonyl is linear or branched and is, for example, C_1-C_6 - or C_1-C_4 alkanoyl or C_4-C_8 alkanoyl. Examples are formyl, acetyl, propionyl, butanoyl, isobutanoyl, pentanoyl, hexanoyl, heptanoyl or octanoyl, preferably acetyl.

[0028] C_1-C_8 alkanoyloxy is C_1-C_8 alkanoyl-O-, wherein the C_1-C_8 alkanoyl is defined as above.

[0029] C_3-C_6 alkenoyl is mono or polyunsaturated, linear or branched, and is for example propenoyl, 2-methyl-propenoyl, butenoyl, pentenoyl, 1,3-pentadienoyl, 5-hexenoyl.

[0030] C_6-C_{20} aryloxycarbonyl is for example phenyloxycarbonyl [= phenyl-O-(CO)-], naphtyloxycarbonyl, anthryloxy-carbonyl etc.

[0031] C_5-C_{20} heteroaryloxycarbonyl is C_5-C_{20} heteroaryl-O-CO-.

[0032] C_1-C_{20} alkylphenyl refers to phenyl which is substituted by one or more alkyl groups, where the sum of the C atoms is up to 20.

[0033] C_6-C_{20} aryl is for example phenyl, naphthyl, anthryl, phenanthryl, pyrene, chrysene, naphthacene, triphenylene etc., in particular phenyl or naphthyl, preferably phenyl.

[0034] C_7-C_{20} aroyl is meant to be C_6-C_{19} aroyl-CO-, wherein the aroyl is as defined above up to the corresponding number of C-atoms.

[0035] C_6-C_{20} arylene is for example phenylene, biphenylene, o-, m- and p-terphenylene, triphenylphenylene, naphthylene, binaphthylene, anthracenylene, phenanthrylene or pyrenylene, in particular phenylene or naphthylene, especially phenylene.


[0036] Naphthyl is 1-naphthyl or 2-naphthyl.

[0037] In the context of the present invention C_3-C_{20} heteroaryl is meant to comprise either one ring or a multiple ring system, e.g. a fused ring-system. Examples are thienyl, benzo[b]thienyl, naphtho[2,3-b]thienyl, thianthrenyl, furyl, dibenzofuryl, chromenyl, xanthenyl, thioxanthenyl, phenoxathiinyl, pyrrolyl, imidazolyl, pyrazolyl, pyrazinyl, pyrimidinyl, pyridazinyl, indolizynyl, isoindolyl, indolyl, indazolyl, purinyl, quinolizynyl, isoquinolyl, quinolyl, phthalazinyl, naphthyridinyl, quinoxalynyl, quinazolynyl, cinnolynyl, pteridinyl, carbazolyl, β -carbolinyl, phenanthridinyl, acridinyl, perimidinyl, phenanthrolinyl, phenazinyl, isothiazolyl, phenothiazinyl, isoxazolyl, furazanyl, phenoxazinyl, 7-phenanthryl, anthraquinone-2-yl (= 9,10-dioxo-9,10-dihydroanthracen-2-yl), 3-benzo[b]thienyl, 5-benzo[b]thienyl, 2-benzo[b]thienyl, 4-dibenzofuryl, 4,7-dibenzofuryl, 4-methyl-7-dibenzofuryl, 2-xanthenyl, 8-methyl-2-xanthenyl, 3-xanthenyl, 2-phenoxyathiinyl, 2,7-phenoxyathiinyl, 2-pyrrolyl, 3-pyrrolyl, 5-methyl-3-pyrrolyl, 2-imidazolyl, 4-imidazolyl, 5-imidazolyl, 2-methyl-4-imidazolyl, 2-ethyl-4-imidazolyl, 2-ethyl-5-imidazolyl, 1H-tetrazol-5-yl, 3-pyrazolyl, 1-methyl-3-pyrazolyl, 1-propyl-4-pyrazolyl, 2-pyrazinyl, 5,6-dimethyl-2-pyrazinyl, 2-indolizynyl, 2-methyl-3-isoindolyl, 2-methyl-1-isoindolyl, 1-methyl-2-indolyl, 1-methyl-3-indolyl, 1,5-dimethyl-2-indolyl, 1-methyl-3-indazolyl, 2,7-dimethyl-8-purinyl, 2-methoxy-7-methyl-8-purinyl, 2-quinolizynyl, 3-isoquinolyl, 6-isoquinolyl, 7-isoquinolyl, 3-methoxy-6-isoquinolyl, 2-quinolyl, 6-quinolyl, 7-quinolyl, 2-methoxy-3-quinolyl, 2-methoxy-6-quinolyl, 6-phthalazinyl, 7-phthalazinyl, 1-methoxy-6-phthalazinyl, 1,4-dimethoxy-6-phthalazinyl, 1,8-naphthyridin-2-yl, 2-quinoxalynyl, 6-quinoxalynyl, 2,3-dimethyl-6-quinoxalynyl, 2,3-dimethoxy-6-quinoxalynyl, 2-quinazolynyl, 7-quinazolynyl, 2-dimethylamino-6-quinazolynyl, 3-cinnolynyl, 6-cinnolynyl, 7-cinnolynyl, 3-methoxy-7-cinnolynyl, 2-pteridinyl, 6-pteridinyl, 7-pteridinyl, 6,7-dimethoxy-2-pteridinyl, 2-carbazolyl, 3-carbazolyl, 9-methyl-2-carbazolyl, 9-methyl-3-carbazolyl, β -carbolin-3-yl, 1-methyl- β -carbolin-3-yl, 1-methyl- β -carbolin-6-yl, 3-phenanthridinyl, 2-acridinyl, 3-acridinyl, 2-perimidinyl, 1-methyl-5-perimidinyl, 5-phenanthrolinyl, 6-phenanthrolinyl, 1-phenazinyl, 2-phenazinyl, 3-isothiazolyl, 4-isothiazolyl, 5-isothiazolyl, 2-phenothiazinyl, 3-phenothiazinyl, 10-methyl-3-phenothiazinyl, 3-isoxazolyl, 4-isoxazolyl, 5-isoxazolyl, 4-methyl-3-furazanyl, 2-phenoxazinyl, 10-methyl-2-phenoxazinyl, etc..

[0038] C_3-C_{20} heteroaryl in particular is thienyl, benzo[b]thienyl, carbazolyl, thianthrenyl, thioxanthenyl, 1-methyl-2-indolyl or 1-methyl-3-indolyl; especially thienyl.

[0039] C_4-C_{20} heteroaroyl is meant to be C_3-C_{19} heteroaryl-CO-, wherein the heteroaryl is as defined above, up to the corresponding number of C-atoms.

[0040] C_3-C_{20} heteroarylene is for example furanylene, thiophenylene, pyridinylene, quinolinylene, isoquinolinylene or



in particular thiophenylene.

[0041] Substituted aryl radicals phenyl, naphthyl, C_6-C_{20} aryl, C_5-C_{20} heteroaryl, C_6-C_{20} arylene or C_3-C_{20} heteroarylene etc. are substituted 1 to 7, 1 to 6 or 1 to 4 times respectively, in particular one, two or three times. It is evident that a defined aryl or heteroaryl radical cannot have more substituents than free "CH" or "NH" positions are at the defined ring. Substituents on the phenyl ring are preferably in positions 4 or in 3,4-, 3,4,5-, 2,6-, 2,4- or 2,4,6-configuration on the phenyl ring.

[0042] Interrupted radicals which are interrupted once or more times are for example interrupted 1-19, 1-15, 1-12, 1-9,


EP 2 847 167 B9

1-7, 1-5, 1-4, 1-3 or once or twice (it is evident, that the number of interrupting atoms depends on the number of C-atoms to be interrupted). *Substituted radicals*, which are substituted once or more times have for example 1-7, 1-5, 1-4, 1-3 or one or two identical or different substituents.


[0043] A radical substituted by *one or more* defined substituents is meant to have either one substituent or more substituents of identical or different definitions as given.

[0044] *Halogen* is fluorine, chlorine, bromine and iodine, especially fluorine, chlorine and bromine, preferably fluorine and chlorine.


[0045] If M is a group (X)




for example structures like the following are formed



(R₂₀ = C₁-C₂₀alkyl substituted by M),




(R₂₀ = C₆-C₂₀aryl substituted by M), etc..If M is a group



for example structures like

5




10

(R₂₀= C₁-C₂₀alkyl substituted by M) or

15

20




25

(R₂₀= C₆-C₂₀aryl substituted by M), etc. are formed. If M is a group (Z)

30


35



for example structures like

40


45



50

(R₂₀= C₁-C₂₀alkyl substituted by M) or

55




(R_{20} = C_6 - C_{20} aryl substituted by M) are formed.

15 **[0046]** R_{18} and R_{19} together with the N-atom to which they are attached form a 5- or 6-membered saturated or unsaturated ring which is uninterrupted or is interrupted by O, S, or NR_{21} , saturated or unsaturated rings are formed, for example aziridine, pyrrole, thiazole, pyrrolidine, oxazole, pyridine, 1,3-diazine, 1,2-diazine, piperidine or morpholine. Preferably, if R_{18} and R_{19} together with the N-atom to which they are attached form a 5- or 6-membered saturated or unsaturated ring which optionally is interrupted by O, S or NR_{21} , 5- or 6-membered saturated rings which are not

20 interrupted or which are interrupted by O or NR_{21} , in particular by O, are formed.

[0047] If R_{31} and R_{32} together with N-atom to which they are attached form a 5- or 6-membered saturated or unsaturated ring, which is uninterrupted or is interrupted by O, S or NR_{21} , and which 5- or 6-membered saturated or unsaturated ring is not condensed or to which 5- or 6-membered saturated or unsaturated ring a benzene ring is condensed saturated or unsaturated rings are formed, for example aziridine, pyrrole, thiazole, pyrrolidine, oxazole, pyridine, 1,3-diazine, 1,2-diazine, piperidine or morpholine, or corresponding annelated rings, e.g.





25




etc..

[0048] If one of R_{22} , R_{23} or R_{24} and one of R_{25} , R_{26} or R_{27} together with X_3 and the phenyl rings to which they are attached form a heteroaromatic ring system which is unsubstituted or substituted, for example structures like the following are formed

35



, etc., in particular



[0049] If one of R_{22} , R_{23} or R_{24} and one of R_{25} , R_{26} or R_{27} together with X_3 and the phenyl rings to which they are attached form a heteroaromatic ring system which is unsubstituted or substituted, preferably a carbazolyl structure is formed.

[0050] The terms "and/or" or "or/and" in the present context are meant to express that not only one of the defined alternatives (substituents) may be present, but also several of the defined alternatives (substituents) together, namely mixtures of different alternatives (substituents).

[0051] The term "at least" is meant to define one or more than one, for example one or two or three, preferably one or two.

[0052] The term "optionally substituted" means, that the radical to which it refers is either unsubstituted or substituted.

[0053] Throughout this specification and the claims which follow, unless the context requires otherwise, the word "comprise", or variations such as "comprises" or "comprising", will be understood to imply the inclusion of a stated integer or step or group of integers or steps but not the exclusion of any other integer or step or group of integers or steps.


[0054] The term "(meth)acrylate" in the context of the present application is meant to refer to the acrylate as well as to the corresponding methacrylate.

[0055] The preferences indicated above for the compounds according to the present invention in the context of this invention are intended to refer to all categories of the claims, that is to the composition, use, process and preparation process claims as well.

[0056] It is to be understood that this invention is not limited to particular compounds, configurations, method steps, substrates, and materials disclosed herein as such compounds, configurations, method steps, substrates, and materials may vary somewhat. It is also to be understood that the terminology employed herein is used for the purpose of describing particular embodiments only and is not intended to be limiting since the scope of the present invention is limited only by the appended claims and equivalents thereof. It must be noted that, as used in this specification and the appended claims, the singular forms "a", "an" and "the" include plural referents unless the context clearly dictates otherwise.

[0057] If nothing else is defined, any terms and scientific terminology used herein are intended to have the meanings commonly understood by those of skill in the art to which this invention pertains.



[0058] The oxime esters of the formula I are for example prepared by methods described in the literature, for example by reaction of the corresponding oximes with an acyl halide, in particular a chloride, or an anhydride in an inert solvent such as for example *t*-butyl methyl ether, tetrahydrofuran (THF) or dimethylformamide in the presence of a base, for example triethylamine or pyridine, or in a basic solvent such as pyridine.



[0059] Z, R₁, R₂, R₃, R₄, R₅, R₆, R₂₀, R₁₄, and R₁₅ are as defined above, Hal means a halogen atom, in particular Cl.

[0060] R₁₅ preferably is methyl.

[0061] Subject of the invention therefore also is a process for the preparation of a compound of the formula I as defined above by reacting the corresponding oxime compound of formula IA, as defined above, with an acyl halide of the formula (2) or an anhydride of the formula (3)



wherein Hal is a halogen, in particular Cl, and R₁₅ is as defined above, in the presence of a base or a mixture of bases.


[0062] The oximes required as starting materials can be obtained by a variety of methods described in standard chemistry textbooks (for instance in J. March, Advanced Organic Chemistry, 4th Edition, Wiley Interscience, 1992), or in specialized monographs, for example, S.R. Sandler & W. Karo, Organic functional group preparations, Vol. 3, Academic Press.

One of the most convenient methods is, for example, the reaction of aldehydes or ketones with hydroxylamine or its salt in polar solvents like dimethylacetamide (DMA), aqueous DMA, ethanol or aqueous ethanol. In that case, a base such as sodium acetate or pyridine is added to control the pH of the reaction mixture. It is well known that the rate of the reaction is pH-dependent, and the base can be added at the beginning or continuously during the reaction. Basic solvents such as pyridine can also be used as base and/or solvent or cosolvent. The reaction temperature is generally from room temperature to the refluxing temperature of the mixture, usually about 20-120°C.

[0063] The corresponding ketone intermediates are for example prepared by the methods described in the literature,

for example in standard chemistry textbooks (for instance in J. March, Advanced Organic Chemistry, 4th Edition, Wiley Interscience, 1992). In addition, successive Friedel-Crafts reaction is effective for synthesis of the intermediates. Such reactions are well known to those skilled in the art.

[0064] Another embodiment of the invention is the free oxime compounds of the IA



wherein **Z**, **R₁**, **R₂**, **R₃**, **R₄**, **R₅**, **R₆**, **R₂₀**, and **R₁₄** are as defined above.

[0065] The preferences for the radicals defined for the compounds of the formula (IA) correspond to the ones as given for the compounds of the formula (I) as given in the remaining context of the description, except that defined oxime ester groups are exchanged by the corresponding free oxime radical.

[0066] Every oxime ester group can exist in two configurations, (Z) or (E). It is possible to separate the isomers by conventional methods, but it is also possible to use the isomeric mixture as such as photoinitiating species. Therefore, the invention also relates to mixtures of configurational isomers of compounds of the formula I.

[0067] **X₁** is for example O, S or a direct bond; or is for example O, CO or a direct bond; or is for example O or a direct bond; or is for example S or a direct bond; or is for example S or CO; or is for example S and a direct bond; preferably **X₁** is a direct bond.

X₃ is for example O or NR'₂₀; or is for example S or NR'₂₀; **X₃** preferably is NR'₂₀.

[0068] **R₉**, **R₁₀**, **R₁₁**, **R₁₂** and **R₁₃** for example independently of each other are hydrogen, halogen, OR₁₆, SR₁₇, NR₁₈R₁₉ or C₂-C₂₀alkyl which is interrupted by one or more O, S or NR₂₁, wherein the interrupted C₂-C₂₀alkyl is unsubstituted or substituted by one or more halogen, OR₁₆, COOR₁₆, SR₁₇, CONR₁₈R₁₉; or **R₉**, **R₁₀**, **R₁₁**, **R₁₂** and **R₁₃** independently of each other are C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, OR₁₆, SR₁₇, COOR₁₆, CONR₁₈R₁₉, NR₁₈R₁₉, phenyl, C₃-C₈-cycloalkyl, C₃-C₂₀heteroaryl or M; provided that **R₉** and **R₁₃** are neither hydrogen nor fluorine.

Or **R₉**, **R₁₀**, **R₁₁**, **R₁₂** and **R₁₃** for example independently of each other are hydrogen, OR₁₆, SR₁₇, NR₁₈R₁₉ or C₂-C₂₀alkyl which is interrupted by one or more O or NR₂₁, wherein the interrupted C₂-C₂₀alkyl is unsubstituted or substituted by one or more halogen, OR₁₆, COOR₁₆ or CONR₁₈R₁₉; or **R₉**, **R₁₀**, **R₁₁**, **R₁₂** and **R₁₃** independently of each other are C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, OR₁₆, SR₁₇, COOR₁₆, CONR₁₈R₁₉, NR₁₈R₁₉, phenyl, C₃-C₈-cycloalkyl or M; provided that **R₉** and **R₁₃** are neither hydrogen nor fluorine.

Or **R₉**, **R₁₀**, **R₁₁**, **R₁₂** and **R₁₃** for example independently of each other are hydrogen, phenyl, halogen, C₁-C₄haloalkyl, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉, C₁-C₂₀alkyl or C₁-C₂₀alkyl which is interrupted by one or more O, S, or NR₂₁, provided that **R₉** and **R₁₃** are neither hydrogen nor fluorine.

[0069] Or **R₉**, **R₁₀**, **R₁₁**, **R₁₂** and **R₁₃** for example independently of each other are hydrogen, OR₁₆, SR₁₇, NR₁₈R₁₉ or C₁-C₂₀alkyl, provided that **R₉** and **R₁₃** are no hydrogen.

Or **R₉**, **R₁₀**, **R₁₁**, **R₁₂** and **R₁₃** for example independently of each other are hydrogen, OR₁₆, NR₁₈R₁₉ or C₁-C₂₀alkyl, provided that **R₉** and **R₁₃** are neither hydrogen nor fluorine.

R₁₀ and **R₁₂** for example in particular are hydrogen and **R₉**, **R₁₁** and **R₁₃** independently of each other are, hydrogen, halogen, OR₁₆, SR₁₇, NR₁₈R₁₉ or C₂-C₂₀alkyl which is interrupted by one or more O, S or NR₂₁, wherein the interrupted C₂-C₂₀alkyl is unsubstituted or substituted by one or more halogen, OR₁₆, COOR₁₆, SR₁₇, CONR₁₈R₁₉; or **R₉**, **R₁₁** and **R₁₃** independently of each other are C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, OR₁₆, SR₁₇, COOR₁₆, CONR₁₈R₁₉, NR₁₈R₁₉, phenyl, C₃-C₈-cycloalkyl, C₃-C₂₀heteroaryl or M; provided that **R₉** and **R₁₃** are neither hydrogen nor fluorine.

Or **R₁₀** and **R₁₂** for example in particular are hydrogen and **R₉**, **R₁₁** and **R₁₃** independently of each other are hydrogen, OR₁₆, SR₁₇, NR₁₈R₁₉ or C₂-C₂₀alkyl which is interrupted by one or more O or NR₂₁, wherein the interrupted C₂-C₂₀alkyl is unsubstituted or substituted by one or more halogen, OR₁₆, COOR₁₆ or CONR₁₈R₁₉; or **R₉**, **R₁₁** and **R₁₃** independently of each other are C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, OR₁₆, SR₁₇, COOR₁₆, CONR₁₈R₁₉, NR₁₈R₁₉, phenyl, C₃-C₈-cycloalkyl or M; provided that **R₉** and **R₁₃** are no hydrogen.

Or **R₁₀** and **R₁₂** for example in particular are hydrogen and **R₉**, **R₁₁** and **R₁₃** independently of each other are, OR₁₆, SR₁₇, NR₁₈R₁₉ or C₂-C₂₀alkyl which is interrupted by one or more O, S or NR₂₁, wherein the interrupted C₂-C₂₀alkyl is unsubstituted or substituted by one or more halogen, OR₁₆, COOR₁₆, SR₁₇, CONR₁₈R₁₉; or **R₉**, **R₁₁** and **R₁₃** independ-


ently of each other are C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, OR₁₆, SR₁₇, COOR₁₆, CONR₁₈R₁₉, NR₁₈R₁₉, phenyl, C₃-C₈-cycloalkyl, C₃-C₂₀heteroaryl or M.

Or **R**₁₀ and **R**₁₂ for example in particular are hydrogen and **R**₉, **R**₁₁ and **R**₁₃ independently of each other are hydrogen, phenyl, halogen, C₁-C₄haloalkyl, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉, C₁-C₂₀alkyl or C₁-C₂₀alkyl which is interrupted by one or more O, S, or NR₂₁, provided that **R**₉ and **R**₁₃ are neither hydrogen nor fluorine.

In particular **R**₁₀ and **R**₁₂ are hydrogen and **R**₉, **R**₁₁ and **R**₁₃ independently of each other are hydrogen or C₁-C₂₀alkyl, provided that **R**₉ and **R**₁₃ are no hydrogen.


Preferably **R**₁₀ and **R**₁₂ are hydrogen and **R**₉, **R**₁₁ and **R**₁₃ are C₁-C₂₀alkyl.

[0070] **R**₁₄ is for example C₆-C₂₀aryl or C₃-C₂₀heteroaryl each of which is unsubstituted or substituted by one or more phenyl, C₁-C₄haloalkyl, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉, PO(OC_kH_{2k+1})₂, SO-C₁-C₁₀alkyl, SO₂-C₁-C₁₀alkyl, M,



or by C₂-C₂₀alkyl which is interrupted by one or more O, CO, S, C(O)O, OC(O), phenylene, naphthylene or by NR₂₁, or each of which C₆-C₂₀aryl or C₃-C₂₀heteroaryl is substituted by one or more C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, COOR₁₆, CONR₁₈R₁₉, phenyl, C₃-C₈cycloalkyl, C₃-C₂₀heteroaryl, C₆-C₂₀aryloxycarbonyl, C₃-C₂₀heteroaryloxycarbonyl, OR₁₆, SR₁₇, NR₁₈R₁₉ or by M.

Or **R**₁₄ is for example C₆-C₂₀aryl, in particular phenyl or naphthyl, or C₃-C₂₀heteroaryl each of which C₆-C₂₀aryl or C₃-C₂₀heteroaryl is unsubstituted or substituted by one or more phenyl, C₁-C₄haloalkyl, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉, M,



or by C₂-C₂₀alkyl which is interrupted by one or more O, CO, S, C(O)O, OC(O), phenylene, naphthylene or by NR₂₁, or each of which C₆-C₂₀aryl or C₃-C₂₀heteroaryl is substituted by one or more C₁-C₂₀alkyl which is unsubstituted or substituted by one or more OR₁₆, SR₁₇, NR₁₈R₁₉ or by M.

Or **R**₁₄ is for example C₆-C₂₀aryl, in particular phenyl or naphthyl, each of which is unsubstituted or substituted by one or more OR₁₆, SR₁₇, NR₁₈R₁₉, or each of which is substituted by one or more C₁-C₂₀alkyl.

Or **R**₁₄ is for example C₆-C₂₀aryl, in particular phenyl or naphthyl, preferably phenyl, each of which is unsubstituted or substituted by SR₁₇ or OR₁₆, in particular by OR₁₆.

[0071] **R**₁₅ is hydrogen, C₃-C₈cycloalkyl, C₂-C₅alkenyl, C₁-C₂₀alkyl or phenyl.

[0072] **R'**₁₄ has one of the meanings as given for **R**₁₄ or is C₁-C₂₀alkyl; including the examples and preferences as given above.

R'₁₅ has one of the meanings as given for **R**₁₅; including the examples and preferences as given above.

[0073] **R''**₁₄ for example is C₁-C₂₀alkyl which is unsubstituted or substituted by phenyl or by phenyl which is substituted by one or more halogen or C₁-C₂₀alkyl; or **R''**₁₄ is C₂-C₂₀alkyl which is interrupted by one or more O, CO, S, C(O)O, OC(O), phenylene or NR₂₁; or **R''**₁₄ is CN, CONR₁₈R₁₉, NO₂, C₁-C₄haloalkyl, S(O)_m-C₁-C₆alkyl, S(O)_m-phenyl; or **R''**₁₄ is SO₂O-phenyl, C₆-C₂₀aryl which is unsubstituted or substituted by one or more phenyl, halogen, C₁-C₄haloalkyl, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉, PO(OC_kH_{2k+1})₂, SO-C₁-C₁₀alkyl, SO₂-C₁-C₁₀alkyl, or by C₂-C₂₀alkyl which is interrupted by one or more O, CO, S, C(O)O, OC(O), phenylene, naphthylene or by NR₂₁, or each of which is substituted by one or more C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, COOR₁₆, CONR₁₈R₁₉, phenyl, C₃-C₈cycloalkyl, C₃-C₂₀heteroaryl, C₆-C₂₀aryloxycarbonyl, C₃-C₂₀heteroaryloxycarbonyl, OR₁₆, SR₁₇ or by NR₁₈R₁₉.

Or **R''**₁₄ for example is C₁-C₂₀alkyl which is unsubstituted or substituted by phenyl; or **R''**₁₄ is C₂-C₂₀alkyl which is interrupted by one or more O, CO, S, C(O)O, OC(O), phenylene or NR₂₁; or **R''**₁₄ is C₆-C₂₀aryl, in particular phenyl or naphthyl, each of which is unsubstituted or substituted by one or more OR₁₆, SR₁₇, NR₁₈R₁₉, or each of which is substituted by one or more C₁-C₂₀alkyl.


In particular **R''**₁₄ is C₁-C₂₀alkyl which is unsubstituted or substituted by phenyl; preferably **R''**₁₄ is C₁-C₂₀alkyl.

[0074] **M** is of the formula (X), (Y) or (Z) as defined above; in particular **M** is of the formula (X) or (Z), especially (X).

[0075] **R**₁₆ for example is hydrogen, phenyl-C₁-C₃alkyl, C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, OH, SH, CN, OCH₂CH₂(CO)O(C₁-C₄alkyl), O(CO)-(C₁-C₄alkyl), O(CO)-phenyl, (CO)OH, (CO)O(C₁-C₄alkyl), C₃-C₂₀cycloalkyl, O(C₁-C₂₀arylene)-M, or by C₃-C₂₀cycloalkyl which is interrupted by one or more O; or **R**₁₆ is C₂-C₂₀alkyl which is interrupted by one or more O, S or NR₂₁; or **R**₁₆ is C₁-C₈alkanoyl, C₂-C₁₂alkenyl, C₃-C₆alkenyl or C₃-C₂₀cycloalkyl; or **R**₁₆ is C₁-C₈alkyl-C₃-C₁₀cycloalkyl which is uninterrupted or interrupted by one or more O; or **R**₁₆ is benzoyl; or **R**₁₆ is phenyl, naphthyl or C₃-C₂₀heteroaryl, in particular phenyl, each of which phenyl,


naphthyl or C₃-C₂₀heteroaryl is unsubstituted or substituted by one or more halogen, OH, C₁-C₁₂alkyl, C₁-C₁₂alkoxy, CN, NO₂, phenoxy, C₁-C₁₂alkylsulfanyl, phenylsulfanyl, N(C₁-C₁₂alkyl)₂, diphenylamino or

5



Or **R**₁₆ for example is phenyl-C₁-C₃alkyl, C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, OH, SH, CN, C₃-C₂₀cycloalkyl, O(C₁-C₂₀arylene)-M, or by C₃-C₂₀cycloalkyl which is interrupted by one or more O; or **R**₁₆ is C₂-C₂₀alkyl which is interrupted by one or more O, S or NR₂₁; or **R**₁₆ is phenyl or naphthyl, in particular phenyl, each of which is unsubstituted or substituted by one or more halogen, OH, C₁-C₁₂alkyl, C₁-C₁₂alkoxy, CN, NO₂, N(C₁-C₁₂alkyl)₂, diphenylamino or

15




[0076] In particular **R**₁₆ is C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, O(C₁-C₄alkyl), O(CO)-(C₁-C₄alkyl), or O(C₁-C₂₀arylene)-M.

20 In particular **R**₁₆ is C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, O(C₁-C₄alkyl) or O(CO)-(C₁-C₄alkyl). Preferably **R**₁₆ is C₁-C₂₀alkyl.


[0077] **R**₁₇ for example is C₂-C₁₂alkenyl, C₃-C₂₀cycloalkyl, phenyl-C₁-C₃alkyl or C₁-C₂₀alkyl; or **R**₁₇ is C₂-C₂₀alkyl which is interrupted by one or more O, S, CO, NR₂₁ or COOR₁₆; or **R**₁₇ is phenyl, naphthyl or C₃-C₂₀heteroaryl, in particular phenyl, each of which is unsubstituted or substituted by one or more halogen, C₁-C₁₂alkyl, C₁-C₄haloalkyl, C₁-C₁₂alkoxy, CN, NO₂, phenyl-C₁-C₃alkyloxy, phenoxy, C₁-C₁₂alkylsulfanyl, phenylsulfanyl, N(C₁-C₁₂alkyl)₂, diphenylamino, (CO)O(C₁-C₈alkyl), (CO)-C₁-C₈alkyl, (CO)N(C₁-C₈alkyl)₂ or

30



Or **R**₁₇ for example is C₂-C₁₂alkenyl, C₃-C₂₀cycloalkyl, phenyl-C₁-C₃alkyl or C₁-C₂₀alkyl; or **R**₁₇ is C₂-C₂₀alkyl which is interrupted by one or more O, S, CO, NR₂₁ or COOR₁₆; or **R**₁₇ is phenyl or naphthyl, in particular phenyl, each of which is unsubstituted or substituted by one or more halogen, C₁-C₁₂alkyl or


35



40 In particular **R**₁₇ is C₁-C₂₀alkyl which is unsubstituted or substituted by COOR₁₆.

[0078] **R**₁₈ and **R**₁₉ for example are independently of each other are hydrogen, C₁-C₂₀alkyl, C₂-C₄hydroxyalkyl, C₂-C₁₀alkoxyalkyl, C₂-C₅alkenyl, C₃-C₂₀cycloalkyl, phenyl-C₁-C₃alkyl, C₁-C₈alkanoyl, C₁-C₈alkanoyloxy, C₃-C₁₂alkenoyl or benzoyl; or **R**₁₈ and **R**₁₉ are phenyl, naphthyl or C₃-C₂₀heteroaryl, in particular phenyl, each of which is unsubstituted or substituted by one or more halogen, C₁-C₄haloalkyl, C₁-C₂₀alkoxy, C₁-C₁₂alkyl, benzoyl or C₁-C₁₂alkoxy; or **R**₁₈ and **R**₁₉ together with the N-atom to which they are attached form a 5- or 6-membered saturated or unsaturated ring which is uninterrupted or is interrupted by O or NR₂₁; or **R**₁₈ and **R**₁₉ together with the N-atom to which they are attached form a group

50




55

[0079] Or **R**₁₈ and **R**₁₉ for example are independently of each other are hydrogen, C₁-C₂₀alkyl or C₂-C₄hydroxyalkyl; or are phenyl which is unsubstituted or substituted by one or more halogen or C₁-C₁₂alkyl; or **R**₁₈ and **R**₁₉ together with the N-atom to which they are attached form a morpholino ring; or **R**₁₈ and **R**₁₉ together with the N-atom to which they


are attached form a group

5



10 In particular **R₁₈** and **R₁₉** together with the N-atom to which they are attached form a group


15



In particular **R₁₈** and **R₁₉** together with the N-atom to which they are attached form a morpholino ring.

20 **[0080]** **R₂₀** is for example C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, OR₁₆, SR₁₇, COOR₁₆, CONR₁₈R₁₉, NR₁₈R₁₉ or M; or is C₂-C₂₀alkyl which is interrupted by one or more O, CO, C(O)O, OC(O) phenylene or NR₂₁, wherein the interrupted C₂-C₂₀alkyl is unsubstituted or substituted by one or more halogen, OR₁₆, SR₁₇, COOR₁₆, CONR₁₈R₁₉, NR₁₈R₁₉ or M; or is phenyl, naphthyl or C₃-C₂₀heteroaryl, in particular thienyl, each of which phenyl, naphthyl or C₃-C₂₀heteroaryl is unsubstituted or substituted by one or more halogen, C₁-C₄haloalkyl, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉, M,

25




30

or by C₂-C₂₀alkyl which is interrupted by one or more O, S, or NR₂₁, or each of which is substituted by one or more C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, COOR₁₆, phenyl, C₃-C₈cycloalkyl, OR₁₆, SR₁₇ or NR₁₈R₁₉.

35

Or **R₂₀** is for example C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, OR₁₆, SR₁₇, NR₁₈R₁₉, or M; or is C₂-C₂₀alkyl which is interrupted by one or more O, CO, C(O)O, OC(O), phenylene or NR₂₁, wherein the interrupted C₁-C₂₀alkyl is unsubstituted or substituted by one or more halogen, OR₁₆, COOR₁₆, NR₁₈R₁₉ or M; or is phenyl, naphthyl or C₃-C₂₀heteroaryl, in particular thienyl, each of which phenyl, naphthyl or C₃-C₂₀heteroaryl is unsubstituted or substituted by one or more halogen, C₁-C₄haloalkyl, CN, NO₂, OR₁₆, NR₁₈R₁₉,

40




45

or by C₁-C₂₀alkyl which is interrupted by one or more O, S, or NR₂₁, or each of which is substituted by one or more C₁-C₂₀alkyl.


Or **R₂₀** is for example C₁-C₂₀alkyl which is unsubstituted or substituted by one or more NR₁₈R₁₉; or is C₂-C₂₀alkyl which is interrupted by one or more C(O)O, OC(O) or phenylene, wherein the interrupted C₁-C₂₀alkyl is unsubstituted or substituted by NR₁₈R₁₉; or is phenyl, naphthyl or C₃-C₂₀heteroaryl, in particular thienyl, each of which phenyl, naphthyl or C₃-C₂₀heteroaryl is unsubstituted or substituted by

50



55

Or **R₂₀** is for example unsubstituted C₁-C₂₀alkyl or C₂-C₂₀alkyl which is interrupted by one or more C(O)O, OC(O) and which interrupted C₂-C₂₀alkyl is substituted by NR₁₈R₁₉, or **R₂₀** is phenyl or thienyl, both of which are unsubstituted or substituted by



5 Or **R₂₀** is for example C₁-C₂₀alkyl, phenyl or C₃-C₂₀heteroaryl, in particular thienyl, each of which is unsubstituted or substituted by



Preferably **R₂₀** is C₁-C₂₀alkyl, phenyl, or phenyl which is substituted by




In particular **R₂₀** is C₁-C₂₀alkyl.

20 **[0081]** **R₂₁** for example is hydrogen, C₁-C₂₀alkyl, C₁-C₄haloalkyl, (CO)_{R₄₁}, C₂-C₂₀alkyl which is interrupted by one or more O, CO, C(O)O or OC(CO), or is phenyl-C₁-C₄alkyl, C₃-C₈cycloalkyl; or **R₂₁** is phenyl or naphthyl both of which are unsubstituted or substituted by one or more C₁-C₂₀alkyl, halogen, C₁-C₄haloalkyl, OR₁₆, SR₁₇, NR₁₈R₁₉ or



Or **R₂₁** for example is C₁-C₂₀alkyl, C₁-C₄haloalkyl, phenyl-C₁-C₄alkyl, C₃-C₈cycloalkyl or phenyl which is unsubstituted or substituted by one or more C₁-C₂₀alkyl. In particular **R₂₁** is C₁-C₂₀alkyl.

30 **[0082]** **R₂₂, R₂₃, R₂₄, R₂₅, R₂₆ or R₂₇** for example independently of each other are hydrogen, COR₄₁ or



35 or one of **R₂₂, R₂₃ or R₂₄** and one of **R₂₅, R₂₆ or R₂₇** together with X₃ and the phenyl rings to which they are attached form a heteroaromatic ring system.

Or **R₂₂, R₂₃, R₂₄, R₂₅, R₂₆ or R₂₇** for example independently of each other are hydrogen, NO₂ or



or one of **R₂₂, R₂₃ or R₂₄** and one of **R₂₅, R₂₆ or R₂₇** together with X₃ and the phenyl rings to which they are attached form a heteroaromatic ring system.

45 Or **R₂₂, R₂₃, R₂₄, R₂₅, R₂₆ or R₂₇** for example independently of each other are hydrogen or one of **R₂₂, R₂₃ or R₂₄** and one of **R₂₅, R₂₆ or R₂₇** together with X₃ and the phenyl rings to which they are attached form a heteroaromatic ring system.


Or **R₂₂, R₂₃, R₂₄, R₂₅, R₂₆ or R₂₇** for example independently of each other are hydrogen, COR₄₁, NO₂ or



[0083] **R₃₁ and R₃₂** for example independently of each other are C₁-C₂₀alkyl; or **R₃₁ and R₃₂** together with N-atom to which they are attached form a morpholino ring.

55 **[0084]** **R₃₃, R₃₄, R₃₅, R₃₆, R₃₇, R₃₈, R₃₉ and R₄₀** for example independently of each other are hydrogen,

EP 2 847 167 B9



5 NO₂, COR₁₆, C₁-C₂₀alkyl, C₁-C₄haloalkyl, OR₁₆, SR₁₇, NR₁₈R₁₉, halogen, CN, phenyl or C₃-C₂₀cycloalkyl; or R₃₅ and R₃₆ or R₃₇ and R₃₈ or both, R₃₅ and R₃₆ and R₃₇ and R₃₈ are



Or R₃₃, R₃₄, R₃₅, R₃₆, R₃₇, R₃₈, R₃₉ and R₄₀ for example independently of each other are hydrogen,



NO₂ or COR₁₆; or R₃₅ and R₃₆ or R₃₇ and R₃₈ or both, R₃₅ and R₃₆ and R₃₇ and R₃₈ are



Or R₃₃, R₃₄, R₃₅, R₃₆, R₃₇, R₃₈, R₃₉ and R₄₀ for example independently of each other are hydrogen,




30 NO₂ or COR₁₆; or R₃₅ and R₃₆ or R₃₇ and R₃₈ or both, are




Or for example R₃₃, R₃₅, R₃₆, R₃₇, R₃₈, R₃₉ and R₄₀ for example independently of each other are hydrogen or



and R₃₄ is NO₂ or COR₁₆; or R₃₅ and R₃₆ or R₃₆ and R₃₇ are




In particular R₃₃, R₃₄, R₃₅, R₃₆, R₃₇, R₃₈, R₃₉ and R₄₀ for example independently of each other are hydrogen or




Preferably R₃₃, R₃₄, R₃₅, R₃₆, R₃₈, R₃₉ and R₄₀ are hydrogen and R₃₇ is




[0085] R_{41} for example is C_6-C_{20} aryl, in particular phenyl, or C_3-C_{20} heteroaryl each of which is unsubstituted or substituted by one or more phenyl, C_1-C_4 haloalkyl, OR_{16} , SR_{17} , $NR_{18}R_{19}$ or by C_2-C_{20} alkyl which is interrupted by one or more O, or each of which C_6-C_{20} aryl or C_3-C_{20} heteroaryl is substituted by one or more C_1-C_{20} alkyl which is unsubstituted or substituted by one or more $COOR_{16}$, $CONR_{18}R_{19}$, phenyl, C_3-C_8 cycloalkyl, C_6-C_{20} aryloxy carbonyl, OR_{16} , SR_{17} or $NR_{18}R_{19}$; or R_{41} is



hydrogen, OH, C_1-C_{20} alkyl, C_1-C_4 haloalkyl, C_2-C_{20} alkyl which is interrupted by one or more O, CO or NR_{21} , or R_{41} is C_3-C_{20} cycloalkyl which is uninterrupted or is interrupted by O, S, CO or NR_{21} . Or R_{41} for example is phenyl which is unsubstituted or substituted by one or more OR_{16} , SR_{17} , $NR_{18}R_{19}$ or by C_1-C_{20} alkyl; or R_{41} is



hydrogen, OH, C_1-C_{20} alkyl, C_1-C_4 haloalkyl, C_2-C_{20} alkyl which is interrupted by one or more O, CO or NR_{21} , or R_{41} is C_3-C_{20} cycloalkyl which is uninterrupted or is interrupted by O, S, CO or NR_{21} . Or R_{41} for example is




hydrogen, OH, C_1-C_{20} alkyl, C_1-C_4 haloalkyl, C_2-C_{20} alkyl which is interrupted by one or more O, CO or NR_{21} , or R_{41} is C_3-C_{20} cycloalkyl which is uninterrupted or is interrupted by O, S, CO or NR_{21} . Or R_{41} for example is hydrogen, OH, C_1-C_{20} alkyl, C_1-C_4 haloalkyl, C_2-C_{20} alkyl which is interrupted by one or more O, CO or NR_{21} , or R_{41} is C_3-C_{20} cycloalkyl which is uninterrupted or is interrupted by O, S, CO or NR_{21} . In particular R_{41} is phenyl which is substituted by C_1-C_{20} alkyl.

n is an integer 1-20, for example 1-12, 1-10, 1-8, 1-4, 1-3 or 1 or 2.

m is an integer 1 or 2; or for example is an integer 1 or for example is an integer 2.

k is an integer 1-10, for example 1-8, 1-4, or 1 or 2.

Z is



[0086] Interesting are compounds of the formula I as defined above, wherein


R_1 , R_2 , R_3 , R_4 , R_5 and R_6 independently of each other are hydrogen, OR_{16} , or C_1-C_{20} alkyl which is unsubstituted or substituted by one or more halogen, OR_{16} , $COOR_{16}$, $CONR_{18}R_{19}$, $NR_{18}R_{19}$;

R_9 , R_{10} , R_{11} , R_{12} and R_{13} independently of each other are hydrogen, halogen, OR_{16} , SR_{17} , $NR_{18}R_{19}$ or C_1-C_{20} alkyl which is interrupted by one or more O, S, NR_{21} , or independently each of which R_9 , R_{10} , R_{11} , R_{12} and R_{13} is C_1-C_{20} alkyl

which is unsubstituted or substituted by one or more halogen, OR₁₆, SR₁₇, COOR₁₆, CONR₁₈R₁₉, NR₁₈R₁₉, phenyl, C₃-C₈-cycloalkyl or C₃-C₂₀heteroaryl;


provided that R₉ and R₁₃ is neither hydrogen nor fluorine;

R₁₄ is C₆-C₂₀aryl or C₃-C₂₀heteroaryl each of which is unsubstituted or substituted by one or more phenyl, halogen, C₁-C₄haloalkyl, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉, PO(OC_kH_{2k+1})₂, SO-C₁-C₁₀alkyl, SO₂-C₁-C₁₀alkyl, M,




or by C₂-C₂₀alkyl which is interrupted by one or more O, CO, S, C(O)O, OC(O), phenylene, naphthylene or by NR₂₁, or each of which is substituted by one or more C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, COOR₁₆, CONR₁₈R₁₉, phenyl, C₃-C₈cycloalkyl, C₃-C₂₀heteroaryl, C₆-C₂₀aryloxycarbonyl, C₃-C₂₀heteroaryloxycarbonyl, OR₁₆, SR₁₇, NR₁₈R₁₉ or by M;

M is



or



R''₁₄ is C₁-C₂₀alkyl which is unsubstituted or substituted by phenyl or by phenyl which is substituted by halogen, C₁-C₂₀alkyl, C₁-C₄haloalkyl, OR₁₆, SR₁₇ or by NR₁₇R₁₉;

or R''₁₄ is C₂-C₂₀alkyl which is interrupted by one or more O, CO, S, C(O)O, OC(O), phenylene, naphthylene or NR₂₁, wherein the interrupted C₂-C₂₀alkyl is unsubstituted or substituted by one or more halogen, OR₁₆, COOR₁₆, CONR₁₈R₁₉, phenyl, or by phenyl which is substituted by OR₁₆, SR₁₇ or NR₁₈R₁₉;

or R''₁₄ is CN, CONR₁₈R₁₉, NO₂, C₁-C₄haloalkyl;

R₁₅ is C₁-C₂₀alkyl or phenyl;

k is an integer 1-10;

R'₁₄ has one of the meanings as given for R₁₄;

R'₁₅ has one of the meanings as given for R₁₅;

X₁ is O, CO, S or a direct bond;


X₃ is O, S or NR'₂₀;

R₁₆ is hydrogen, phenyl-C₁-C₃alkyl, C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, OCH₂CH₂CN, OCH₂CH₂(CO)O(C₁-C₄alkyl), O(CO)-(C₁-C₄alkyl), O(CO)-(C₂-C₄)alkenyl, O(CO)-phenyl, (CO)OH, (CO)O(C₁-C₄alkyl), C₃-C₂₀cycloalkyl, SO₂-(C₁-C₄haloalkyl), O(C₁-C₄haloalkyl), O(C₁-C₂₀arylene)-M or by C₃-C₂₀cycloalkyl which is interrupted by one or more O;

or R₁₆ is C₂-C₂₀alkyl which is interrupted by one or more O, S or NR₂₁;

R₁₇ is methyl substituted by COOR₁₆;


or R₁₇ is phenyl unsubstituted or substituted by one or more C₁-C₁₂alkyl, C₁-C₁₂alkoxy,



R₁₈ and R₁₉ independently of each other are hydrogen, phenyl, C₁-C₂₀alkyl, C₁-C₈alkanoyl or C₁-C₈alkanoyloxy; or R₁₈ and R₁₉ together with the N-atom to which they are attached form a heteroaromatic ring system which is unsub-


stituted or substituted by

5



or R_{18} and R_{19} together with the N-atom to which they are attached form a group

10




15

R_{20} is hydrogen, $\text{C}_1\text{-C}_4$ haloalkyl, or $\text{C}_1\text{-C}_{20}$ alkyl which is unsubstituted or substituted by one or more halogen, OR_{16} , SR_{17} , COOR_{16} , $\text{CONR}_{17}\text{R}_{18}$, $\text{NR}_{17}\text{R}_{18}$, $\text{PO}(\text{OC}_k\text{H}_{2k+1})_2$ or M; or R_{20} is $\text{C}_2\text{-C}_{20}$ alkyl of which is interrupted by one or more O, CO, $\text{C}(\text{O})\text{O}$, $\text{OC}(\text{O})$ or NR_{21} , wherein the interrupted $\text{C}_2\text{-C}_{20}$ alkyl is unsubstituted or substituted by one or more halogen, OR_{16} , SR_{17} , COOR_{16} , $\text{CONR}_{18}\text{R}_{19}$, $\text{NR}_{18}\text{R}_{19}$ or M;

20

or R_{20} is $\text{C}_6\text{-C}_{20}$ aryl or $\text{C}_3\text{-C}_{20}$ heteroaryl each of which are unsubstituted or substituted by one or more halogen, $\text{C}_1\text{-C}_4$ haloalkyl, OR_{16} , SR_{17} , $\text{NR}_{18}\text{R}_{19}$, or

25




or by $\text{C}_2\text{-C}_{20}$ alkyl which is interrupted by one or more O, S or NR_{21} , or each of which $\text{C}_6\text{-C}_{20}$ aryl or $\text{C}_3\text{-C}_{20}$ heteroaryl is substituted by one or more $\text{C}_1\text{-C}_{20}$ alkyl which is unsubstituted or substituted by one or more halogen, COOR_{16} , $\text{CONR}_{18}\text{R}_{19}$, phenyl, $\text{C}_3\text{-C}_8$ cycloalkyl, $\text{C}_3\text{-C}_{20}$ heteroaryl, $\text{C}_6\text{-C}_{20}$ aryloxy carbonyl, $\text{C}_3\text{-C}_{20}$ heteroaryloxy carbonyl, OR_{16} , SR_{17} or $\text{NR}_{18}\text{R}_{19}$;

30

R_{21} is hydrogen, $\text{C}_1\text{-C}_{20}$ alkyl or $\text{C}_2\text{-C}_{20}$ alkyl which is interrupted by one or more O or CO;


or R_{21} is phenyl or naphthyl both of which are unsubstituted or substituted by one or more $\text{C}_1\text{-C}_{20}$ alkyl, halogen, $\text{C}_1\text{-C}_4$ haloalkyl, OR_{16} , SR_{17} , $\text{NR}_{18}\text{R}_{19}$, COR_{41} or

35




R_{22} , R_{23} , R_{24} , R_{25} , R_{26} , or R_{27} independently of each other is hydrogen, COR_{41} , NO_2 or

40




or one of R_{22} and R_{23} , R_{24} and R_{25} , or R_{26} and R_{27} is

50



or one of R_{22} , R_{23} or R_{24} and one of R_{25} , R_{26} or R_{27} together with X_3 and the phenyl rings to which they are attached form a heteroaromatic ring system which is unsubstituted or substituted by one or more $\text{C}_1\text{-C}_{20}$ alkyl, $\text{C}_1\text{-C}_{20}$ alkoxy, OR_{16} , SR_{17} , $\text{NR}_{18}\text{R}_{19}$, COR_{41} ,


55



NO₂ or phenyl;


R₂₈ is C₆-C₂₀aryl or C₃-C₂₀heteroaryl each of which is unsubstituted or substituted by one or more phenyl, halogen, C₁-C₄haloalkyl, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉ or by C₁-C₂₀alkyl which is interrupted by one or more O, S, or NR₂₁, or each of which C₆-C₂₀aryl or C₃-C₂₀heteroaryl is substituted by one or more C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, COOR₁₆, CONR₁₈R₁₉, phenyl, C₃-C₈cycloalkyl, C₃-C₂₀heteroaryl, C₆-C₂₀aryloxycarbonyl, C₃-C₂₀heteroaryloxycarbonyl, OR₁₆, SR₁₇ or NR₁₈R₁₉;

R₃₃, R₃₄, R₃₅, R₃₆, R₃₇, R₃₈, R₃₉ and **R₄₀** independently of each other are hydrogen,




NO₂, COR₄₁, C₁-C₂₀alkyl, C₁-C₄haloalkyl, OR₁₆, SR₁₇, NR₁₈R₁₉, halogen, CN, phenyl or C₃-C₂₀cycloalkyl which is uninterrupted or is interrupted by one or more O, S, CO or NR₂₁;

or **R₃₅** and **R₃₆** or **R₃₇** and **R₃₈** or both, **R₃₅** and **R₃₆** and **R₃₇** and **R₃₈** are



R₄₁ is C₆-C₂₀aryl or C₃-C₂₀heteroaryl each of which is unsubstituted or substituted by one or more phenyl, halogen, C₁-C₄haloalkyl, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉ or by C₁-C₂₀alkyl which is interrupted by one or more O, S, or NR₂₁, or each of which C₆-C₂₀aryl or C₃-C₂₀heteroaryl is substituted by one or more C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, COOR₁₆, CONR₁₈R₁₉, phenyl, C₃-C₈cycloalkyl, C₃-C₂₀heteroaryl, C₆-C₂₀aryloxycarbonyl, C₃-C₂₀heteroaryloxycarbonyl, OR₁₆, SR₁₇ or NR₁₈R₁₉;

or **R₄₁** is



or **R₄₁** is hydrogen, OH, C₁-C₂₀alkyl, C₁-C₄haloalkyl, C₂-C₂₀alkyl which is interrupted by one or more O, CO or by NR₂₁, or is C₃-C₂₀cycloalkyl which is uninterrupted or is interrupted by O, S, CO or NR₂₁.

[0087] Further interesting are compounds of the formula I as defined above, wherein **R₉**, **R₁₁** and **R₁₃** are methyl and **R₁₀** and **R₁₂** are hydrogen.


[0088] Interesting are compounds of the formula I according to claim 1, wherein

R₁, **R₂**, **R₃**, **R₄**, **R₅** and **R₆** are hydrogen;

R₉, **R₁₀**, **R₁₁**, **R₁₂** and **R₁₃** independently of each other are hydrogen, or C₁-C₂₀alkyl; **provided that** **R₉** and **R₁₃** are neither hydrogen nor fluorine;

R₁₄ is C₆-C₂₀aryl which is unsubstituted or substituted by OR₁₆, or by C₁-C₂₀alkyl which is unsubstituted or substituted by SR₁₇;

M is



R₁₅ is C₁-C₂₀alkyl;

R'₁₄ is C₁-C₂₀alkyl or C₆-C₂₀aryl;

R'₁₅ is C₁-C₂₀alkyl;

X₁ is a direct bond;


X₃ is NR₂₀;

R₁₆ is C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, or O(C₁-C₂₀arylene)-M;

EP 2 847 167 B9

R₁₇ is C₁-C₂₀alkyl which is unsubstituted or substituted by COOR₁₆;
R₁₈ and **R₁₉** together with the N-atom to which they are attached form a group


5



10


R₂₀ is C₁-C₂₀alkyl;
 or **R₂₀** is C₂-C₂₀alkyl of which is interrupted by one or more C(O)O or OC(O) wherein the interrupted C₂-C₂₀alkyl is unsubstituted or substituted by NR₁₈R₁₉;
 or **R₂₀** is C₆-C₂₀aryl or C₃-C₂₀heteroaryl each of which is unsubstituted or substituted by

15




R'₂₀ is C₁-C₂₀alkyl;
R₂₂, **R₂₃**, **R₂₄**, **R₂₅**, **R₂₆** or **R₂₇** independently of each other are hydrogen, or **R₂₂** and **R₂₅** together with **X₃** and the phenyl rings to which they are attached form a heteroaromatic ring system;
R₂₈ is C₆-C₂₀aryl which is unsubstituted or substituted by C₁-C₂₀alkyl;
R₃₃, **R₃₄**, **R₃₅**, **R₃₆**, **R₃₇**, **R₃₈**, **R₃₉** and **R₄₀** independently of each other are hydrogen,

25



or COR₄₁;
R₄₁ is C₆-C₂₀aryl which is unsubstituted or substituted by C₁-C₂₀alkyl.
[0089] Of interest are compounds of the formula I as described above, wherein **Z** is

35




40

R₁, **R₂**, **R₃**, **R₄**, **R₅** and **R₆** are hydrogen;
R₁₀ and **R₁₂** are hydrogen;
R₁₁ is hydrogen, OR₁₆ or C₁-C₂₀alkyl;
R₉ and **R₁₃** independently of each other are OR₁₆ or C₁-C₂₀alkyl;
R₁₄ is C₆-C₂₀aryl which is unsubstituted or substituted by one or more NO₂, SR₁₇, NR₁₈R₁₉ or C₁-C₂₀alkyl;
M is

45

50



G is -COR₂₈;
R₁₅ is C₁-C₂₀alkyl;
R'₁₄ has one of the meanings as given for **R₁₄**;
R'₁₅ has one of the meanings as given for **R₁₅**;
R₁₆ is C₁-C₂₀alkyl, which is unsubstituted or substituted by one or more halogen, OH, O(C₁-C₄alkyl), O(CO)-(C₁-C₄alkyl)

55

or O(C₁-C₂₀arylene)-M,


or R₁₆ is C₁-C₈alkanoyl;

R₁₇ is COOR₁₆;

R₁₈ and R₁₉ independently of each other are C₁-C₂₀alkyl,

5 or R₁₈ and R₁₉ together with the N-atom to which they are attached form a 5- or 6-membered saturated or unsaturated ring which is uninterrupted or is interrupted by O, or R₁₈ and R₁₉ together with the N-atom to which they are attached form a group

10




15

R₂₀ is C₁-C₂₀alkyl or C₂-C₂₀alkyl of which is interrupted by one or more O, wherein the interrupted C₂-C₂₀alkyl is unsubstituted or substituted by NR₁₈R₁₉;

or R₂₀ is C₆-C₂₀aryl which is substituted by

20



R₂₂, R₂₃, R₂₅ and R₂₆ are hydrogen,


25 R₂₄ and R₂₇ together with X₃ and the phenyl rings to which they are attached form a heteroaromatic ring system;

R₂₈ is C₆-C₂₀aryl which is unsubstituted or substituted by C₁-C₂₀alkyl;

R₃₃, R₃₅, R₃₆, R₃₇, R₃₈ and R₄₀ independently of each other are hydrogen;

R₃₄ is

30




R₃₉ is COR₄₁;

35 R₄₁ is C₆-C₂₀aryl which is unsubstituted or substituted by C₁-C₂₀alkyl.

[0090] Preferred are compounds of the formula I as defined above, wherein

Z is

40



45 R₁, R₂, R₃, R₄, R₅ and R₆ are hydrogen;

R₁₀ and R₁₂ are hydrogen;

R₁₁ is hydrogen, OR₁₆ or C₁-C₂₀alkyl;


R₉ and R₁₃ independently of each other are OR₁₆ or C₁-C₂₀alkyl;

R₁₄ is C₆-C₂₀aryl which is unsubstituted or substituted by one or more NO₂, OR₁₆, NR₁₈R₁₉ or C₁-C₂₀alkyl which

50 C₁-C₂₀alkyl is unsubstituted or substituted by SR₁₇;

M is

55



G is -COR₂₈;

R''₁₄ is C₁-C₂₀alkyl or C₆-C₂₀aryl which C₆-C₂₀aryl is unsubstituted or substituted by C₁-C₂₀alkyl;

R₁₅ is C₁-C₂₀alkyl;

R'₁₄ is C₁-C₂₀alkyl;

5 **R'₁₅** is C₁-C₂₀alkyl;

X₃ together with **R₂₄** and **R₂₇** and the phenyl rings to which they are attached forms a heteroaromatic ring system;

R₁₆ is C₁-C₂₀alkyl, which is unsubstituted or substituted by one or more halogen, OH, O(C₁-C₄alkyl), O(CO)-(C₁-C₄alkyl) or O(C₁-C₂₀arylene)-M;

10 or **R₁₆** is C₂-C₂₀alkyl which is interrupted by one or more O, which interrupted C₂-C₂₀alkyl is substituted by O-C₆-C₂₀arylene-M, in which O-C₆-C₂₀arylene-M, the arylene is unsubstituted or substituted by O(C₁-C₆alkyl);

or **R₁₆** is C₁-C₈alkanoyl;

R₁₇ is C₁-C₂₀alkyl which is unsubstituted or substituted by COOR₁₆;

R₁₈ and **R₁₉** independently of each other are C₁-C₂₀alkyl,

15 or **R₁₈** and **R₁₉** together with the N-atom to which they are attached form a 5- or 6-membered saturated or unsaturated ring which is uninterrupted or is interrupted by O, or **R₁₈** and **R₁₉** together with the N-atom to which they are attached form a group


20



25 **R₂₀** is C₁-C₂₀alkyl or C₂-C₂₀alkyl of which is interrupted by one or more O, wherein the interrupted C₂-C₂₀alkyl is unsubstituted or substituted by NR₁₈R₁₉;

or **R₂₀** is C₆-C₂₀aryl which is substituted by

30



R₂₂, **R₂₃**, **R₂₅** and **R₂₆** are hydrogen,


R₂₄ and **R₂₇** together with **X₃** and the phenyl rings to which they are attached form a heteroaromatic ring system;

35 **R₂₈** is C₆-C₂₀aryl which is unsubstituted or substituted by C₁-C₂₀alkyl;

R₃₃, **R₃₅**, **R₃₆**, **R₃₇**, **R₃₈** and **R₄₀** independently of each other are hydrogen;

R₃₄ is

40




R₃₉ is COR₄₁;

R₄₁ is C₆-C₂₀aryl which is unsubstituted or substituted by C₁-C₂₀alkyl.

45 **[0091]** Other interesting compounds are compounds of the formula I as described above, wherein

Z is

50




R₁, **R₂**, **R₃**, **R₄**, **R₅** and **R₆** are hydrogen;

55 **R₁₀**, **R₁₁** and **R₁₂** independently of each other are hydrogen, OR₁₆ or C₁-C₂₀alkyl;

R₉ and **R₁₃** independently of each other are OR₁₆ or C₁-C₂₀alkyl;

R₁₄ is C₆-C₂₀aryl which is unsubstituted or substituted by one or more NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉ or C₁-C₂₀alkyl;

M is



5

R''₁₄ is C₆-C₂₀aryl which is unsubstituted or substituted by C₁-C₂₀alkyl;

R₁₅ is C₁-C₂₀alkyl;

10 **X₃** is NR'₂₀;

R₁₆ is C₁-C₂₀alkyl, which is unsubstituted or substituted by one or more halogen, OH, O(C₁-C₄alkyl), O(CO)-(C₁-C₄alkyl), or **R₁₆** is C₂-C₂₀alkyl which is interrupted by one or more O, which interrupted C₂-C₂₀alkyl is unsubstituted or substituted by O-C₆-C₂₀arylene-M, in which O-C₆-C₂₀arylene-M, the arylene is unsubstituted or substituted by one or more O(C₁-C₆alkyl);

15 **R₁₇** is C₁-C₂₀alkyl which is unsubstituted or substituted by COOR₁₆;

R₁₈ and **R₁₉** independently of each other are C₁-C₂₀alkyl,

or **R₁₈** and **R₁₉** together with the N-atom to which they are attached form a 5- or 6-membered saturated or unsaturated ring which is uninterrupted or is interrupted by O,

R₂₀ and **R'₂₀** are C₁-C₂₀alkyl;

20 **R₂₂**, **R₂₃**, **R₂₄**, **R₂₅**, **R₂₆** or **R₂₇** independently of each other are hydrogen, or one of **R₂₂**, **R₂₃** or **R₂₄** and one of **R₂₅**, **R₂₆** or **R₂₇** together with **X₃** and the phenyl rings to which they are attached form a heteroaromatic ring system.

[0092] Additionally preferred are compounds of the formula I according to claim 1, wherein

R₁, **R₂**, **R₃**, **R₄**, **R₅** and **R₆** are hydrogen;

R₉, **R₁₁** and **R₁₃** are C₁-C₂₀alkyl;

25 **R₁₀** and **R₁₂** are hydrogen;

R₁₄ is C₆-C₂₀aryl which is unsubstituted or substituted by C₁-C₂₀alkyl which is unsubstituted or substituted by SR₁₇;

R₁₅ is C₁-C₂₀alkyl;

R₁₆ is C₁-C₂₀alkyl;

R₁₇ is C₁-C₂₀alkyl which is unsubstituted or substituted by COOR₁₆; and

30 **R₂₀** is C₁-C₂₀alkyl.

[0093] Preferred are compounds of the formula I as defined above, wherein

R''₁₄ is C₁-C₂₀alkyl or C₆-C₂₀aryl which is substituted by C₁-C₂₀alkyl;

R₁₆ is C₁-C₂₀alkyl, which is unsubstituted or substituted by one or more halogen, OH, O(C₁-C₄alkyl), O(CO)-(C₁-C₄alkyl) or O(C₁-C₂₀arylene)-M;

35 or **R₁₆** is C₂-C₂₀alkyl which is interrupted by one or more O, which interrupted C₂-C₂₀alkyl is substituted by O-C₆-C₂₀arylene-M, in which O-C₆-C₂₀arylene-M, the arylene is substituted by O(C₁-C₆alkyl);

or **R₁₆** is C₁-C₈alkanoyl;


R₁₇ is C₁-C₂₀alkyl which is substituted by COOR₁₆;

R₁₈ and **R₁₉** independently of each other are C₁-C₂₀alkyl,

40 or **R₁₈** and **R₁₉** together with the N-atom to which they are attached form a 6-membered saturated ring which is uninterrupted or is interrupted by O,

or **R₁₈** and **R₁₉** together with the N-atom to which they are attached form a group

45




50

R₂₀ is C₁-C₂₀alkyl or C₂-C₂₀alkyl of which is interrupted by one or more O, wherein the interrupted C₂-C₂₀alkyl is substituted by NR₁₈R₁₉;

or **R₂₀** is C₆-C₂₀aryl which is substituted by

55



R₂₄ and **R₂₇** together with **X₃** and the phenyl rings to which they are attached form a carbazolyl ring system;

R₂₈ is C₆-C₂₀aryl which is substituted by C₁-C₂₀alkyl;

R₄₁ is C₆-C₂₀aryl which is substituted by C₁-C₂₀alkyl.

[0094] The compounds of the formula I are suitable as radical photoinitiators.

Accordingly, subject of the invention is the use of a compound of the formula I as defined above for the photopolymerization of a composition comprising at least one ethylenically unsaturated photopolymerizable compound.

[0095] Another subject of the present invention therefore is a photopolymerizable composition comprising

(a) at least one ethylenically unsaturated photopolymerizable compound and

(b) as photoinitiator, at least one compound of the formula I as defined above.

[0096] The composition may comprise additionally to the photoinitiator (b) at least one further photoinitiator (c), and/or other additives (d).

The composition may comprise additionally to the photoinitiator (b) at least one further photoinitiator (c) or other additives (d) or both, at least one further photoinitiator (c) and other additives (d).

[0097] The unsaturated compounds (a) may include one or more olefinic double bonds. They may be of low (monomeric) or high (oligomeric) molecular mass. Examples of monomers containing a double bond are alkyl, hydroxyalkyl, cycloalkyl (which optionally interrupted by O) or amino acrylates, or alkyl, hydroxyalkyl, cycloalkyl (which optionally interrupted by O) or amino methacrylates, for example methyl, ethyl, butyl, 2-ethylhexyl or 2-hydroxyethyl acrylate, tetrahydrofurfuryl acrylate, isobornyl acrylate, methyl methacrylate, cyclohexyl methacrylate or ethyl methacrylate. Silicone acrylates are also advantageous. Other examples are acrylonitrile, acrylamide, methacrylamide, N-substituted (meth)acrylamides, vinyl esters such as vinyl acetate, vinyl ethers such as isobutyl vinyl ether, styrene, alkyl- and halostyrenes, N-vinylpyrrolidone, vinyl chloride or vinylidene chloride.

Examples of monomers containing two or more double bonds are the diacrylates of ethylene glycol, propylene glycol, neopentyl glycol, hexamethylene glycol or of bisphenol A, and 4,4'-bis(2-acryloxyethoxy)diphenylpropane, trimethylolpropane triacrylate, pentaerythritol triacrylate or tetraacrylate, vinyl acrylate, divinylbenzene, divinyl succinate, diallyl phthalate, triallyl phosphate, triallyl isocyanurate or tris(2-acryloylethyl) isocyanurate.

Examples of polyunsaturated compounds of relatively high molecular mass (oligomers) are acrylated epoxy resins, polyesters containing acrylate-, vinyl ether- or epoxy-groups, and also polyurethanes and polyethers. Further examples of unsaturated oligomers are unsaturated polyester resins, which are usually prepared from maleic acid, phthalic acid and one or more diols and have molecular weights of from about 500 to 3000. In addition it is also possible to employ vinyl ether monomers and oligomers, and also maleate-terminated oligomers with polyester, polyurethane, polyether, polyvinyl ether and epoxy main chains. Of particular suitability are combinations of oligomers which carry vinyl ether groups and of polymers as described in WO 90/01512. However, copolymers of vinyl ether and maleic acid-functionalized monomers are also suitable. Unsaturated oligomers of this kind can also be referred to as prepolymers.

[0098] Particularly suitable examples are esters of ethylenically unsaturated carboxylic acids and polyols or polyepoxides, and polymers having ethylenically unsaturated groups in the chain or in side groups, for example unsaturated polyesters, polyamides and polyurethanes and copolymers thereof, polymers and copolymers containing (meth)acrylic groups in side chains, and also mixtures of one or more such polymers.

Examples of unsaturated carboxylic acids are acrylic acid, methacrylic acid, crotonic acid, itaconic acid, cinnamic acid, and unsaturated fatty acids such as linolenic acid or oleic acid. Acrylic and methacrylic acid are preferred.

Suitable polyols are aromatic and, in particular, aliphatic and cycloaliphatic polyols. Examples of aromatic polyols are hydroquinone, 4,4'-dihydroxydiphenyl, 2,2-di(4-hydroxyphenyl)propane, and also novolaks and resols. Examples of polyepoxides are those based on the abovementioned polyols, especially the aromatic polyols, and epichlorohydrin.

Other suitable polyols are polymers and copolymers containing hydroxyl groups in the polymer chain or in side groups, examples being polyvinyl alcohol and copolymers thereof or polyhydroxyalkyl methacrylates or copolymers thereof. Further polyols which are suitable are oligoesters having hydroxyl end groups.

Examples of aliphatic and cycloaliphatic polyols are alkylenediols having preferably 2 to 12 C atoms, such as ethylene glycol, 1,2- or 1,3-propanediol, 1,2-, 1,3- or 1,4-butanediol, pentanediol, hexanediol, octanediol, dodecanediol, diethylene glycol, triethylene glycol, polyethylene glycols having molecular weights of preferably from 200 to 1500, 1,3-cyclopentanediol, 1,2-, 1,3- or 1,4-cyclohexanediol, 1,4-dihydroxymethylcyclohexane, glycerol, tris(β -hydroxyethyl)amine, trimethylolpropane, trimethylolpropane, pentaerythritol, dipentaerythritol and sorbitol.

[0099] The polyols may be partially or completely esterified with one carboxylic acid or with different unsaturated carboxylic acids, and in partial esters the free hydroxyl groups may be modified, for example etherified or esterified with other carboxylic acids. Examples of esters are:

trimethylolpropane triacrylate, trimethylolpropane trimethacrylate, trimethylolpropane trimethacrylate, tetramethylene glycol dimethacrylate, triethylene glycol dimethacrylate, tetraethylene glycol diacrylate, pentaerythritol diacrylate, pentaerythritol triacrylate, pentaerythritol tetraacrylate, dipentaerythritol diacrylate, dipentaer-

ythritol triacrylate, dipentaerythritol tetraacrylate, dipentaerythritol pentaacrylate, dipentaerythritol hexaacrylate, tripentaerythritol octaacrylate, pentaerythritol dimethacrylate, pentaerythritol trimethacrylate, dipentaerythritol dimethacrylate, dipentaerythritol tetramethacrylate, tripentaerythritol octamethacrylate, pentaerythritol diitaconate, dipentaerythritol trisitaconate, dipentaerythritol pentaitaconate, dipentaerythritol hexaitaconate, ethylene glycol diacrylate, 1,3-butanediol diacrylate, 1,3-butanediol dimethacrylate, 1,4-butanediol diitaconate, sorbitol triacrylate, sorbitol tetraacrylate, pentaerythritol-modified triacrylate, sorbitol tetra methacrylate, sorbitol pentaacrylate, sorbitol hexaacrylate, oligoester acrylates and methacrylates, glycerol diacrylate and triacrylate, 1,4-cyclohexane diacrylate, bisacrylates and bismethacrylates of polyethylene glycol with a molecular weight of from 200 to 1500, or mixtures thereof.

[0100] Also suitable as components (a) are the amides of identical or different, unsaturated carboxylic acids with aromatic, cycloaliphatic and aliphatic polyamines having preferably 2 to 6, especially 2 to 4, amino groups. Examples of such polyamines are ethylenediamine, 1,2- or 1,3-propylenediamine, 1,2-, 1,3- or 1,4-butylenediamine, 1,5-pentylendiamine, 1,6-hexylendiamine, octylendiamine, dodecylendiamine, 1,4-diaminocyclohexane, isophoronediamine, phenylenediamine, bisphenylenediamine, di- β -aminoethyl ether, diethylenetriamine, triethylenetetramine, di(β -aminoethoxy)- or di(β -aminopropoxy)ethane. Other suitable polyamines are polymers and copolymers, preferably with additional amino groups in the side chain, and oligoamides having amino end groups. Examples of such unsaturated amides are methylenebisacrylamide, 1,6-hexamethylenebisacrylamide, diethylenetriaminetrimethacrylamide, bis(methacrylamidopropoxy)ethane, β -methacrylamidoethyl methacrylate and N[(β -hydroxyethoxy)-ethyl]acrylamide.

[0101] Suitable unsaturated polyesters and polyamides are derived, for example, from maleic acid and from diols or diamines. Some of the maleic acid can be replaced by other dicarboxylic acids. They can be used together with ethylenically unsaturated comonomers, for example styrene. The polyesters and polyamides may also be derived from dicarboxylic acids and from ethylenically unsaturated diols or diamines, especially from those with relatively long chains of, for example 6 to 20 C atoms. Examples of polyurethanes are those composed of saturated or unsaturated diisocyanates and of unsaturated or, respectively, saturated diols.

Polymers with (meth)acrylate groups in the side chain are likewise known. They may, for example, be reaction products of epoxy resins based on novolaks with (meth)acrylic acid, or may be homo- or copolymers of vinyl alcohol or hydroxyalkyl derivatives thereof which are esterified with (meth)acrylic acid, or may be homo- and copolymers of (meth)acrylates which are esterified with hydroxyalkyl (meth)acrylates.

Other suitable polymers with acrylate or methacrylate groups in the side chains are, for example, solvent soluble or alkaline soluble polyimide precursors, for example poly(amic acid ester) compounds, having the photopolymerizable side groups either attached to the backbone or to the ester groups in the molecule, i.e. according to EP 624826. Such oligomers or polymers can be formulated with the new photoinitiators and optionally reactive diluents, like polyfunctional (meth)acrylates in order to prepare highly sensitive polyimide precursor resists.

[0102] The photopolymerizable compounds can be used alone or in any desired mixtures. It is preferred to use mixtures of polyol (meth)acrylates.

[0103] Examples of the component (a) are also polymers or oligomers having at least two ethylenically unsaturated groups and at least one carboxyl function within the molecule structure, such as a resin obtained by the reaction of a saturated or unsaturated polybasic acid anhydride with a product of the reaction of an epoxy compound and an unsaturated monocarboxylic acid, for example, photosensitive compounds as described in JP 6-1638 and JP 10301276 and commercial products such as EB9696, UCB Chemicals; KAYARAD TCR1025, Nippon Kayaku Co.,LTD., or an addition product formed between a carboxyl group-containing resin and an unsaturated compound having an α,β -unsaturated double bond and an epoxy group (for example, ACA200M, Daicel Industries, Ltd.).

[0104] As diluent, a mono- or multi-functional ethylenically unsaturated compound, or mixtures of several of said compounds, can be included in the above composition up to 70 % by weight based on the solid portion of the composition.

[0105] Subject of the invention also is a photopolymerizable composition as described above, wherein the component (a) is a resin obtained by the reaction of a saturated or unsaturated polybasic acid anhydride with a product of the reaction of an epoxy resin and an unsaturated monocarboxylic acid.

Such components are for example described in JP06-1938, JP08-278629, JP08-278630, JP10-301276, JP2001-40022, JP10-221843, JP11-231523, JP2002-206014-A or JP2006-53569-A, the disclosure of which hereby is incorporated by reference.

The unsaturated compounds (a) can also be used as a mixture with non-photopolymerizable, film-forming components. These may, for example, be physically drying polymers or solutions thereof in organic solvents, for instance nitrocellulose or cellulose acetobutyrate. They may also, however, be chemically and/or thermally curable (heat-curable) resins, examples being polyisocyanates, polyepoxides and melamine resins, as well as polyimide precursors. The use of heat-curable resins at the same time is important for use in systems known as hybrid systems, which in a first stage are photopolymerized and in a second stage are crosslinked by means of thermal aftertreatment.

[0106] The invention also provides compositions comprising as component (a) at least one ethylenically unsaturated photopolymerizable compound which is emulsified or dissolved in water.

Many variants of such radiation-curable aqueous prepolymer dispersions are commercially available. A prepolymer

dispersion is understood as being a dispersion of water and at least one prepolymer dispersed therein. The concentration of water in these systems is, for example, from 5 to 80% by weight, in particular from 30 to 60% by weight. The concentration of the radiation-curable prepolymer or prepolymer mixture is, for example, from 95 to 20% by weight, in particular from 70 to 40% by weight. In these compositions the sum of the percentages given for water and prepolymer is in each case

100, with auxiliaries and additives being added in varying quantities depending on the intended use.

The radiation-curable, film-forming prepolymers which are dispersed in water and are often also dissolved are aqueous prepolymer dispersions of mono- or polyfunctional, ethylenically unsaturated prepolymers which are known per se, can be initiated by free radicals and have for example a content of from 0.01 to 1.0 mol of polymerizable double bonds per 100 g of prepolymer and an average molecular weight of, for example, at least 400, in particular from 500 to 10'000. Prepolymers with higher molecular weights, however, may also be considered depending on the intended application. Use is made, for example, of polyesters containing polymerizable C-C double bonds and having an acid number of not more than 10, of polyethers containing polymerizable C-C double bonds, of hydroxyl-containing reaction products of a polyepoxide, containing at least two epoxide groups per molecule, with at least one α,β -ethylenically unsaturated carboxylic acid, of polyurethane (meth)acrylates and of acrylic copolymers which contain α,β -ethylenically unsaturated acrylic radicals, as are described in EP 12339. Mixtures of these prepolymers can likewise be used. Also suitable are the polymerizable prepolymers described in EP 33896, which are thioether adducts of polymerizable prepolymers having an average molecular weight of at least 600, a carboxyl group content of from 0.2 to 15% and a content of from 0.01 to 0.8 mol of polymerizable C-C double bonds per 100 g of prepolymer. Other suitable aqueous dispersions, based on specific alkyl (meth)acrylate polymers, are described in EP 41125, and suitable waterdispersible, radiation-curable prepolymers of urethane acrylates can be found in DE 2936039. Further additives which may be included in these radiation-curable aqueous prepolymer dispersions are dispersion auxiliaries, emulsifiers, antioxidants, e.g. 2,2-thiobis(4-methyl-6-*t*-butylphenol) or 2,6-di-*t*-butylphenol, light stabilizers, dyes, pigments, fillers, such as glass or alumina, for example talc, gypsum, silicic acid, rutile, carbon black, zinc oxide, iron oxides, reaction accelerators, levelling agents, lubricants, wetting agents, thickeners, flattening agents, antifoams and other auxiliaries customary in paint technology. Suitable dispersion auxiliaries are water-soluble organic compounds which are of high molecular mass and contain polar groups, examples being polyvinyl alcohols, polyvinylpyrrolidone or cellulose ethers. Emulsifiers which can be used are nonionic emulsifiers and, if desired, ionic emulsifiers as well.

[0107] It is of course also possible to add other known photoinitiators (c), for example mixtures with camphor quinone; benzophenone, benzophenone derivatives, such as for example given below as sensitizers; ketal compounds, as for example benzildimethylketal (Irgacure® 651); acetophenone, acetophenone derivatives, for example α -hydroxy-cycloalkyl phenyl ketones or α -hydroxyalkyl phenyl ketones, such as for example 2-hydroxy-2-methyl-1-phenyl-propanone (Darocur® 1173), 1-hydroxy-cyclohexyl-phenyl-ketone (Irgacure® 184), 1-(4-dodecylbenzoyl)-1-hydroxy-1-methyl-ethane, 1-(4-isopropylbenzoyl)-1-hydroxy-1-methyl-ethane, 1-[4-(2-hydroxyethoxy)-phenyl]-2-hydroxy-2-methyl-1-propan-1-one (Irgacure®2959); 2-hydroxy-1-[4-[4-(2-hydroxy-2-methyl-propionyl)-benzyl]-phenyl]-2-methyl-propan-1-one (Irgacure®127); 2-hydroxy-1-[4-[4-(2-hydroxy-2-methyl-propionyl)-phenoxy]-phenyl]-2-methyl-propan-1-one; 1-[4-(benzoyl-phenyl-thia)phenyl]-2-methyl-2-(*p*-tolylsulfonyl)-propane-1-one (Esacure® 1001M); oligomeric α -hydroxyalkyl phenyl ketones e.g. Esacure®ONE, Esacure®KIP 100; dialkoxyacetophenones, α -aminoacetophenones, e.g. (4-methylthiobenzoyl)-1-methyl-1-morpholinoethane (Irgacure® 907), (4-morpholinobenzoyl)-1-benzyl-1-dimethylaminopropane (Irgacure® 369), (4-morpholinobenzoyl)-1-(4-methylbenzyl)-1-dimethylaminopropane (Irgacure® 379), (4-(2-hydroxyethyl)aminobenzoyl)-1-benzyl-1-dimethylaminopropane), (3,4-dimethoxybenzoyl)-1-benzyl-1-dimethylaminopropane; 4-*aroyl*-1,3-dioxolanes, benzoin alkyl ethers, phenylglyoxalic esters and derivatives thereof, e.g. methyl α -oxo benzeneacetate, oxo-phenyl-acetic acid 2-(2-hydroxy-ethoxy)-ethyl ester, dimeric phenylglyoxalic esters, e.g. oxo-phenyl-acetic acid 1-methyl-2-[2-(2-oxo-2-phenyl-acetoxy)-propoxy]-ethyl ester (Irgacure® 754); other oximeesters, e.g. 1,2-octanedione 1-[4-(phenylthio)phenyl]-2-(*O*-benzoyloxime) (Irgacure® OXE01), ethanone 1-[9-ethyl-6-(2-methylbenzoyl)-9H-carbazol-3-yl]-1-(*O*-acetyloxime) (Irgacure® OXE02), 9H-thioxanthene-2-carboxaldehyde 9-oxo-2-(*O*-acetyloxime), peresters, e.g. benzophenone tetracarboxylic peresters as described for example in EP 126541, monoacyl phosphine oxides, e.g. (2,4,6-trimethylbenzoyl)diphenylphosphine oxide (Darocur® TPO), ethyl (2,4,6-trimethylbenzoyl phenyl) phosphinic acid ester; bisacylphosphine oxides, e.g. bis(2,6-dimethoxy-benzoyl)-(2,4,4-trimethyl-pentyl)phosphine oxide, bis(2,4,6-trimethylbenzoyl)-phenylphosphine oxide (Irgacure® 819), bis(2,4,6-trimethylbenzoyl)-2,4-dipentoxylphenylphosphine oxide, trisacylphosphine oxides, halomethyltriazines, e.g. 2-[2-(4-methoxy-phenyl)-vinyl]-4,6-bis-trichloromethyl-[1,3,5]triazine, 2-(4-methoxy-phenyl)-4,6-bis-trichloromethyl-[1,3,5]-triazene, 2-(3,4-dimethoxy-phenyl)-4,6-bis-trichloromethyl-[1,3,5]triazine, 2-methyl-4,6-bis-trichloromethyl-[1,3,5]triazine, hexaarylbisimidazole / coinitiators systems, e.g. ortho-chlorohexaphenyl-bisimidazole combined with 2-mercaptobenzthiazole, ferrocenium compounds, or titanocenes, e.g. bis(cyclopentadienyl)-bis(2,6-difluoro-3-pyrrylphenyl)titanium (Irgacure®784).

Further, borate compounds can be used as coinitiators. The Darocur® and Irgacure® compounds are available from BASF SE; Esacure is available from Lamberti SPA.

Where the novel photoinitiator systems are employed in hybrid systems, use is made, in addition to the novel free-radical hardeners, of cationic photoinitiators, of peroxide compounds, such as benzoyl peroxide (other suitable peroxides are

described in US 4950581 column 19, lines 17-25), of aromatic sulfonium-, phosphonium- or iodonium salts as described for example in US4950581, column 18, line 60 to column 19, line 10 or cyclopentadienylarene-iron(II) complex salts, for example $(\eta^6\text{-iso-propylbenzene})(\eta^5\text{-cyclopentadienyl})\text{iron(II) hexafluorophosphate}$, as well as oxime sulfonic acid esters, as are, for example described in EP780729. Also pyridinium and (iso)quinolinium salts as described e.g. in EP497531 and EP441232 may be used in combination with the new photoinitiators.

The new photoinitiators, either alone or in mixtures with other known photoinitiators and sensitizers, can be used also in the form of a dispersion or emulsion in water or aqueous solutions. In case the compounds are used in emulsions or dispersions conveniently customary dispersants or emulsifiers are added to prepare a stable emulsion or dispersion. Corresponding suitable additives are known to the person skilled in the art.

The photopolymerizable compositions generally comprise 0.05 to 25 % by weight, preferably 0.01 to 10 % by weight, in particular 0.01 to 5 % by weight of the photoinitiator, based on the solid composition. The amount refers to the sum of all photoinitiators added, if mixtures of initiators are employed. Accordingly, the amount either refers to the photoinitiator (b) or the photoinitiators (b)+(c).

[0108] In addition to the photoinitiator the photopolymerizable mixtures may include various additives (d). Examples of these are thermal inhibitors, which are intended to prevent premature polymerization, examples being hydroquinone, hydroquinone derivatives, p-methoxyphenol, β -naphthol or sterically hindered phenols, such as 2,6-di-tert-butyl-p-cresol. In order to increase the stability on storage in the dark it is possible, for example, to use copper compounds, such as copper naphthenate, stearate or octoate, phosphorus compounds, for example triphenylphosphine, tributylphosphine, triethyl phosphite, triphenyl phosphite or tribenzyl phosphite, quaternary ammonium compounds, for example tetramethylammonium chloride or trimethylbenzylammonium chloride, or hydroxylamine derivatives, for example N-diethylhydroxylamine. To exclude atmospheric oxygen during the polymerization it is possible to add paraffin or similar wax-like substances which, being of inadequate solubility in the polymer, migrate to the surface in the beginning of polymerization and form a transparent surface layer which prevents the ingress of air. It is also possible to apply an oxygen-impermeable layer on top of the coating, for example poly(vinylalcohol-co-vinylacetate). Light stabilizers which can be added in a small quantity are UV absorbers, for example those of the hydroxyphenylbenzotriazole, hydroxyphenyl-benzophenone, oxalamide or hydroxyphenyl-s-triazine type. These compounds can be used individually or in mixtures, with or without sterically hindered amines (HALS). Examples of such UV absorbers and light stabilisers are disclosed in WO 04/074328, page 12, line 9 to page 14, line 23, said disclosure hereby is incorporated by reference.

[0109] To accelerate the photopolymerization it is possible to add amines as component (d), for example triethanolamine, N-methyldiethanolamine, ethyl-p-dimethylaminobenzoate, 2-(dimethylamino)ethyl benzoate, 2-ethylhexyl-p-dimethylaminobenzoate, octyl-para-N,N-dimethylaminobenzoate, N-(2-hydroxyethyl)-N-methyl-para-toluidine or Michler's ketone. The action of the amines can be intensified by the addition of aromatic ketones of the benzophenone type. Examples of amines which can be used as oxygen scavengers are substituted N,N-dialkylanilines, as are described in EP339841. Other accelerators, coinitiators and autoxidizers are thiols, thioethers, disulfides, phosphonium salts, phosphine oxides or phosphines, as described, for example, in EP438123, in GB2180358 and in JP Kokai Hei 6-68309. It is further possible to add chain transfer agents which are customary in the art to the compositions according to the invention as component (d). Examples are mercaptans, amines and benzothiazol.

Photopolymerization can also be accelerated by adding further photosensitizers or coinitiators (as component (d)) which shift or broaden the spectral sensitivity. These are, in particular, aromatic compounds, for example benzophenone and derivatives thereof, thioxanthone and derivatives thereof, anthraquinone and derivatives thereof, coumarin and phenothiazine and derivatives thereof, and also 3-(aroylmethylene)thiazolines, rhodanine, camphorquinone, but also eosine, rhodamine, erythrosine, xanthene, thioxanthene, acridine, e.g. 9-phenylacridine, 1,7-bis(9-acridinyl)heptane, 1,5-bis(9-acridinyl)pentane, cyanine and merocyanine dyes. Examples of suitable sensitizer compounds (d) are disclosed in WO 06/008251, page 36, line 30 to page 38, line 8, the disclosure of which is hereby incorporated by reference.

[0110] A photopolymerizable composition, comprising as further additive (d) a photosensitizer compound selected from the group consisting of benzophenone and its derivatives, thioxanthone and its derivatives, anthraquinone and its derivatives, or coumarin and its derivatives is preferred.

Examples of benzophenone derivatives, thioxanthone derivatives, anthraquinone derivatives and coumarin derivatives are benzophenone, 4-phenyl benzophenone, 4-methoxy benzophenone, 4,4'-dimethoxy benzophenone, 4,4'-dimethyl benzophenone, 4,4'-dichlorobenzophenone, 4,4'-bis(dimethylamino)benzophenone, 4,4'-bis(diethylamino)benzophenone, 4,4'-bis(methylethylamino)benzophenone, 4,4'-bis(p-isopropylphenoxy)benzophenone, 4-methyl benzophenone, 2,4,6-trimethylbenzophenone, 4-(4-methylthiophenyl)-benzophenone, 3,3'-dimethyl-4-methoxy benzophenone, methyl-2-benzoylbenzoate, 4-(2-hydroxyethylthio)-benzophenone, 4-(4-tolylthio)benzophenone, 1-[4-(4-benzoyl-phenyl)sulfonyl]-phenyl]-2-methyl-2-(toluene-4-sulfonyl)-propan-1-one, 4-benzoyl-N,N,N-trimethylbenzenemethanaminium chloride, 2-hydroxy-3-(4-benzoyl-phenoxy)-N,N,N-trimethyl-1-propanaminium chloride monohydrate, 4-(13-acryloyl-1,4,7,10,13-pentaoxatridecyl)-benzophenone, 4-benzoyl-N,N-dimethyl-N-[2-(1-oxo-2-propenyl)oxy]ethyl-benzenemethanaminium chloride; thioxanthone, 2-isopropylthioxanthone, 2-chlorothioxanthone, 1-chloro-4-propoxythioxanthone, 2-dodecylthioxanthone, 2,4-diethylthioxanthone, 2,4-dimethylthioxanthone, 1-methoxycarbonylthioxanthone, 2-

ethoxycarbonylthioxanthone, 3-(2-methoxyethoxycarbonyl)-thioxanthone, 4-butoxy-arynylthioxanthone, 3-butoxycarbonyl-7-methylthioxanthone, 1-cyano-3chlorothioxanthone, 1-ethoxycarbonyl-3-chlorothioxanthone, 1-ethoxycarbonyl-3-ethoxythioxanthone, 1-ethoxycarbonyl-3-aminothioxanthone, 1-ethoxycarbonyl-3-phenylsulfurylthioxanthone, 3,4-di-[2-(2-methoxyethoxy)ethoxycarbonyl]-thioxanthone, 1,3-dimethyl-2-hydroxy-9Hthioxanthone-9-one 2-ethylhexylether, 1-ethoxycarbonyl-3-(1-methyl-1-morpholinothyl)-thioxanthone, 2-methyl-6-dimethoxymethyl-thioxanthone, 2-methyl-6-(1,1-dimethoxyethyl)-thioxanthone, 2-morpholinomethylthioxanthone, 2-methyl-6-morpholinoethylthioxanthone, N-allylthioxanthone-3,4-dicarboximide, N-octylthioxanthone-3,4-dicarboximide, N-(1,1,3,3-tetramethylbutyl)-thioxanthone-3,4-dicarboximide, 1-phenoxythioanone, 6-ethoxycarbonyl-2methoxythioxanthone, 6-ethoxycarbonyl-2-methylthioxanthone, thioxanthone-2-carboxylic acid polyethyleneglycol ester, 2-hydroxy-3-(3,4-dimethyl-9-oxo-9H-thioxanthone-2-ylxy)-N,N,N-trimethyl-1-propanaminium chloride, couarin 1, Coumarin 2, Coumarin 6, Coumarin 7, Coumarin 30, Coumarin 102, Coumarin 106, Coumarin 138, Coumarin 152, Coumarin 153, Coumarin 307, Coumarin 314, Coumarin 314T, Coumarin 334, Coumarin 337, Coumarin 500, 3-benzoyl coumarin, 3-benzoyl-7-methoxycoumarin, 3-benzoyl-5,7-dimethoxycoumarin, 3-benzoyl-5,7-dipropoxycoumarin, 3-benzoyl-6,8-dichlorocoumarin, 3-benzoyl-6-chloro-coumarin, 3,3'-carbonyl-bis[5,7-di(propoxy)coumarin], 3,3'-carbonyl-bis(7-methoxycoumarin), 3,3'-carbonyl-bis(7-diethylaminocoumarin), 3-isobutyroylcoumarin, 3-benzoyl-5,7-dimethoxy-coumarin, 3-benzoyl-5,7-diethoxy-coumarin, 3-benzoyl-5,7-dibutoxycoumarin, 3-benzoyl-5,7-di(methoxyethoxy)-coumarin, 3-benzoyl-5,7-di(allyloxy)coumarin, 3-benzoyl-7-dimethylaminocoumarin, 3-benzoyl-7-diethylaminocoumarin, 3-isobutyroyl-7-dimethylaminocoumarin, 5,7-dimethoxy-3-(1-naphthoyl)-coumarin, 5,7-diethoxy-3-(1-naphthoyl)-coumarin, 3-benzoylbenzo[f]coumarin, 7-diethylamino-3-thienoylcoumarin, 3-(4-cyanobenzoyl)-5,7-dimethoxycoumarin, 3-(4-cyanobenzoyl)-5,7-dipropoxycoumarin, 7-dimethylamino-3-phenylcoumarin, 7-diethylamino-3-phenylcoumarin, the coumarin derivatives disclosed in JP 09-179299-A and JP 09-325209-A, for example 7-[[4-chloro-6-(diethylamino)-S-triazine-2-yl]amino]-3-phenylcoumarin, 9,10-anthraquinone and anthracene.

The curing process can be assisted by adding photosensitizers, in particular, in compositions which are pigmented (for example with titanium dioxide), and also by adding a component which under thermal conditions forms free radicals, for example an azo compound such as 2,2'-azobis(4-methoxy-2,4-dimethylvaleronitrile), a triazene, diazo sulfide, pentazadiene or a peroxy compound, for instance a hydroperoxide or peroxy carbonate, for example t-butyl hydroperoxide, as described for example in EP245639. The compositions according to the invention may comprise as further additive (d) a photoreducible dye, e.g., xanthene-, benzoxanthene-, benzothioxanthene, thiazine-, pyronine-, porphyrine- or acridine dyes, and/or trihalogenmethyl compounds which can be cleaved by irradiation. Similar compositions are for example described in EP445624.

Further additives known in the art may be added as component (d), as for example flow improvers, adhesion promoters, such as vinyltrimethoxysilane, vinyltriethoxysilane vinyltris(2-methoxyethoxy)silane, N-(2-aminoethyl)-3-aminopropylmethyltrimethoxysilane, N-(2-aminoethyl)3-aminopropyltrimethoxysilane, 3-aminopropyltriethoxysilane, 3-glycidoxypropyltrimethoxysilane, 3-glycidoxypropylmethyltrimethoxysilane, 2-(3,4-epoxycyclohexyl)ethyltrimethoxysilane, 3-chloropropylmethyltrimethoxysilane, 3-chloropropyltrimethoxysilane, 3-methacryloxypropyltrimethoxysilane and 3-mercapto-propyltrimethoxysilane. Surfactants, optical brighteners, pigments, dyes, wetting agents, levelling assistants, dispersants, aggregation preventers, antioxidants or fillers are further examples for additives (d).

In order to cure thick and pigmented coatings it is appropriate to add glass microspheres or pulverized glass fibres, as described for example in US 5013768.

Further suitable components (d) are, as already mentioned above, surfactants and dispersants and other components, in particular to support the application of pigments or colorants in the formulation.

It is preferred to apply a surface treatment to the pigments in order to make the pigment easy to disperse and to stabilize the resultant pigment dispersion. The surface treatment reagents are, for example, surfactants, polymeric dispersants, general texture improving agents, pigment derivatives and mixtures thereof. It is especially preferred when the colorant composition according to the invention comprises at least one polymeric dispersant and/or at least pigment derivative. Suitable surfactants include anionic surfactants such as alkylbenzene- or alkylnaphthalene-sulfonates, alkylsulfosuccinates or naphthalene formaldehyde sulfonates; cationic surfactants including, for example, quaternary salts such as benzyl tributyl ammonium chloride; or nonionic or amphoteric surfactants such as polyoxyethylene surfactants and alkyl- or amidopropyl betaines, respectively.

Illustrative examples of the surfactant include polyoxyethylene alkyl ethers such as polyoxyethylene lauryl ether, polyoxyethylene stearyl ether and polyoxyethylene oleyl ether; polyoxyethylene alkylphenyl ethers such as polyoxyethylene octylphenyl ether and polyoxyethylene nonylphenyl ether; polyethylene glycol diesters such as polyethylene glycol dilaurate and polyethylene glycol distearate; sorbitan fatty acid esters; fatty acid modified polyesters; tertiary amine modified polyurethanes; polyethyleneimines; those available under the trade names of KP (a product of Shin-Etsu Chemical Co., Ltd), Polyflow (a product of KYOEISHA CHEMICAL Co., Ltd), F-Top (a product of Tochem Products Co., Ltd), MEGAFAC (a product of Dainippon Ink & Chemicals, Inc.), Fluorad (a product of Sumitomo 3M Ltd), Asahi Guard and Surfion (products of Asahi Glass Co., Ltd); and the like.

These surfactants may be used alone or in admixture of two or more.

The surfactant is generally used in an amount of 50 parts or less by weight, preferably 0 to 30 parts by weight, based on 100 parts by weight of the colorant composition.

[0111] Polymeric dispersants include high molecular weight polymers with pigment affinic groups. Examples are: statistical co-polymers comprised from, for instance, styrene derivatives, (meth)acrylates and (meth)acrylamides, and such statistical co-polymers modified by post modification; block co-polymers and/or comb polymers comprised from, for instance, styrene derivatives, (meth)acrylates and (meth)acrylamides, and such block co-polymers and/or comb polymers modified by post modification; polyethylenimines, which for instance is crafted with polyesters; polyamines, which for instance is crafted with polyesters; and many kinds of (modified) polyurethanes.

Polymeric dispersants may also be employed. Suitable polymeric dispersants are, for example, BYK's DISPERBYK® 101, 115, 130, 140, 160, 161, 162, 163, 164, 166, 168, 169, 170, 171, 180, 182, 2000, 2001, 2009, 2020, 2025, 2050, 2070, 2090, 2091, 2095, 2096, 2150, 2163, 2164, BASFs EFKAO 4008, 4009, 4010, 4015, 4020, 4046, 4047, 4050, 4055, 4060, 4061, 4080, 4300, 4310, 4320, 4330, 4340, 4400, 4401, 4402, 4403, 4406, 4500, 4510, 4520, 4530, 4540, 4550, 4560, 4570, 4580, 4585, 4590, 4800, Ajinomoto Fine Techno's Ajisper PB®711, 821, 822, 823, 824, 827, 881, Lubrizol's SOLSPERSE® 1320, 13940, 17000, 20000, 21000, 24000, 26000, 27000, 28000, 31845, 32000, 32500, 32550, 32600, 33500, 34750, 36000, 36600, 37500, 38500, 39000, 41000, 41090, 44000, 53095, Kawaken Fine Chemicals' Hinoact KF-1300M, T-6000, T-8000, T-8000E, T-9050, Kusumoto Chemicals' Disparlon PW-36, DA-325, DA-375, DA-7301, Kyoheisha Chemical's Flowlen DOPA-15B, DOPA-15BHFS, DOPA-17HF, DOPA-22, DOPA-33, G-600, G-700, G-820, G-900, NC-500, KDG-2400 and combinations thereof.

It is preferred to use EFKA® 4046, 4047, 4060, 4061, 4300, 4310, 4320, 4330, 4340, 4585, DISPERBYK® 161, 162, 163, 164, 165, 166, 168, 169, 170, 2000, 2001, 2020, 2050, 2090, 2091, 2095, 2096, 2105, 2150, 2163, 2164, PB®711, 821, 822, 823, 824, 827, 881, SOLSPERSE® 24000, 31845, 32500, 32550, 32600, 33500, 34750, 36000, 36600, 37500, 39000, 41090, 44000, 53095, Hinoact T-6000, T-8000E, Disparlon PW-36, DA-7301, and combinations thereof as dispersant.

[0112] Suitable texture improving agents are, for example, fatty acids such as stearic acid or behenic acid, and fatty amines such as laurylamine and stearylamine. In addition, fatty alcohols or ethoxylated fatty alcohols polyols such as aliphatic 1,2-diols or epoxidized soy bean oil, waxes, resin acids and resin acid salts may be used for this purpose.

[0113] Suitable pigment dispersants are, for example, copper phthalocyanine derivatives such as BASF's EFKA® 6745, Lubrizol's SOLSPERSE® 5000, 12000, BYK's SYNERGIST 2100 and azo derivatives such as EFKA® 6750, SOLSPERSE® 22000 and SYNERGIST 2105.

The above mentioned dispersants and surfactants for pigments are for example employed in compositions of the present invention which are used as resist formulations, in particular in color filter formulations.

[0114] Subject of the invention also is a photopolymerizable composition as described above as further additive (d) comprising a dispersant or a mixture of dispersants as well as a photopolymerizable composition as described above as further additive (d) comprising a pigment or a mixture of pigments or a mixture of one or more pigments with one or more dyes.

Suitable pigments and dyes, in particular for color filter applications are described below.

[0115] The choice of additive(s) (d) is made depending on the field of application and on properties required for this field. The additives described above are customary in the art and accordingly are added in amounts which are usual in the respective application.

Binders (e) as well can be added to the novel compositions. This is particularly expedient when the photopolymerizable compounds are liquid or viscous substances. The quantity of binder may, for example, be 2-98 %, preferably 5-95 % and especially 20-90 %, by weight relative to the overall solids content. The choice of binder is made depending on the field of application and on properties required for this field, such as the capacity for development in aqueous and organic solvent systems, adhesion to substrates and sensitivity to oxygen.

Examples of suitable binders are polymers having a molecular weight of about 2'000 to 2'000'000, preferably 3'000 to 1'000'000. Examples of alkali developable binders are acrylic polymer having carboxylic acid function as a pendant group, such as conventionally known copolymers obtained by copolymerizing an ethylenic unsaturated carboxylic acid such as (meth)acrylic acid, 2-carboxyethyl (meth)acrylic acid, 2-carboxypropyl (meth)acrylic acid itaconic acid, crotonic acid, maleic acid, fumaric acid and ω -carboxypolycaprolactone mono(meth)acrylate, with one or more monomers selected from esters of (meth)acrylic acid, such as methyl (meth)acrylate, ethyl (meth)acrylate, propyl (meth)acrylate, butyl (meth)acrylate, benzyl (meth)acrylate, 2-ethylhexyl (meth)acrylate, hydroxyethyl (meth)acrylate, hydroxypropyl (meth)acrylate, glycerol mono(meth)acrylate, tricyclo[5.2.1.0^{2,6}]decan-8-yl (meth)acrylate, glycidyl (meth)acrylate, 2-methylglycidyl (meth)acrylate, 3,4-epoxybutyl (meth)acrylate, 6,7-epoxyheptyl (meth)acrylate; vinyl aromatic compounds, such as styrene, α -methylstyrene, vinyltoluene, p-chlorostyrene, vinylbenzyl glycidyl ether; amide type unsaturated compounds, (meth)acrylamide diacetone acrylamide, N-methylolacrylamide, N-butoxymethacrylamide; and polyolefin type compounds, such as butadiene, isoprene, chloroprene and the like; methacrylonitrile, methyl isopropenyl ketone, mono-2-[(meth)acryloyloxy]ethyl succinate, N-phenylmaleimide, maleic anhydride, vinyl acetate, vinyl propionate, vinyl pivalate, polystyrene macromonomer, or polymethyl (meth)acrylate macromonomer. Examples of copolymers

are copolymers of acrylates and methacrylates with acrylic acid or methacrylic acid and with styrene or substituted styrene, phenolic resins, for example novolak, (poly)hydroxystyrene, and copolymers of hydroxystyrene with alkyl acrylates, acrylic acid and/or methacrylic acid. Preferable examples of copolymers are copolymers of methyl methacrylate/methacrylic acid, co-polymers of benzyl methacrylate/methacrylic acid, copolymers of methyl methacrylate/ethyl acrylate/methacrylic acid, copolymers of benzyl methacrylate/methacrylic acid/styrene, copolymers of benzyl methacrylate/methacrylic acid/hydroxyethyl methacrylate, copolymers of methyl methacrylate/butyl methacrylate/ methacrylic acid/styrene, copolymers of methyl methacrylate/benzyl methacrylate/methacrylic acid/hydroxyphenyl methacrylate. Examples of solvent developable binder polymers are poly(alkyl methacrylates), poly(alkyl acrylates), poly(benzylmethacrylate-co-hydroxyethylmethacrylate-co-methacrylic acid), poly(benzylmethacrylate-co-methacrylic acid); cellulose esters and cellulose ethers, such as cellulose acetate, cellulose acetobutyrate, methylcellulose, ethylcellulose; polyvinylbutyral, polyvinylformal, cyclized rubber, polyethers such as polyethylene oxide, polypropylene oxide and polytetrahydrofuran; polystyrene, polycarbonate, polyurethane, chlorinated polyolefins, polyvinyl chloride, vinyl chloride/vinylidene copolymers, copolymers of vinylidene chloride with acrylonitrile, methyl methacrylate and vinyl acetate, polyvinyl acetate, copoly(ethylene/vinyl acetate), polymers such as polycaprolactam and poly(hexamethylene adipamide), and polyesters such as poly(ethylene glycol terephthalate) and poly(hexamethylene glycol succinate) and polyimide binder resins. The polyimide binder resin in the present invention can either be a solvent soluble polyimide or a polyimide precursor, for example, a poly(amic acid).

[0116] Preferred is a photopolymerizable composition, comprising as binder polymer (e), a copolymer of methacrylate and methacrylic acid.

Interesting further are polymeric binder components as described e.g. in JP 10-171119-A, in particular for use in color filters.

Subject of the invention further is a photopolymerizable composition as described above, wherein the component (a) is a resin obtained by the reaction of a saturated or unsaturated polybasic acid anhydride with a product of the reaction of an epoxy resin and an unsaturated monocarboxylic acid.

[0117] The photopolymerizable compositions can be used for various purposes, for example as printing ink, e.g. screen printing inks, inks for offset- or flexo printing, as a clear finish, as a white or colored finish, for example for wood or metal, as powder coating, as a coating material, inter alia for paper, wood, metal or plastic, as a daylight-curable coating for the marking of buildings and roadmarking, for photographic reproduction techniques, for holographic recording materials, for image recording techniques or to produce printing plates which can be developed with organic solvents or with aqueous alkalis, for producing masks for screen printing, as dental filling compositions, as adhesives, as pressure-sensitive adhesives, as laminating resins, as etch resists, solder resists, electroplating resists, or permanent resists, both liquid and dry films, as photostructurable dielectric, for printed circuit boards and electronic circuits, as resists to manufacture color filters for a variety of display applications or to generate structures in the manufacturing process of plasma-display panels and electroluminescence displays, (as for example described in US5853446, EP863534, JP 09-244230-A, JP10-62980-A, JP08-171863-A, US5840465, EP855731, JP05-271576-A, JP 05-67405-A) for the production of holographic data storage (HDS) material, for the production of optical switches, optical lattices (interference lattice), light circuits, for producing three-dimensional articles by mass curing (UV curing in transparent moulds) or by the stereolithography technique, as is described, for example, in US4575330, to produce composite materials (for example styrenic polyesters, which may, if desired, contain glass fibres and/or other fibres and other auxiliaries) and other thick-layered compositions, for coating or sealing electronic components and integrated circuits, or as coatings for optical fibres, or for producing optical lenses, e.g. contact lenses or Fresnel lenses. The compositions according to the invention are further suitable for the production of medical equipment, auxiliaries or implants. Further, the compositions according to the invention are suitable for the preparation of gels with thermotropic properties, as for example described in DE19700064 and EP678534.

[0118] The novel photoinitiators may additionally be employed as initiators for emulsion polymerizations, pearl polymerizations or suspension polymerizations, as polymerization initiators for fixing ordered states of liquid-crystalline monomers and oligomers, or as initiators for fixing dyes on organic materials.

[0119] In coating materials, use is frequently made of mixtures of a prepolymer with polyunsaturated monomers, which may additionally include a monounsaturated monomer as well. It is the prepolymer here which primarily dictates the properties of the coating film, and by varying it the skilled worker is able to influence the properties of the cured film. The polyunsaturated monomer functions as a crosslinking agent which renders the film insoluble. The monounsaturated monomer functions as a reactive diluent, which is used to reduce the viscosity without the need to employ a solvent. Unsaturated polyester resins are usually used in two-component systems together with a monounsaturated monomer, preferably with styrene. For photoresists, specific one-component systems are often used, for example polymaleimides, polychalcones or polyimides, as described in DE 2308830.

[0120] The novel photoinitiators can also be used for the polymerization of radiation-curable powder coatings. The powder coatings can be based on solid resins and monomers containing reactive double bonds, for example maleates, vinyl ethers, acrylates, acrylamides and mixtures thereof. A free-radically UV-curable powder coating can be formulated

by mixing unsaturated polyester resins with solid acrylamides (for example methyl methacrylamidoglycolate) and a novel free-radical photoinitiator, such formulations being as described, for example, in the paper "Radiation Curing of Powder Coating", Conference Proceedings, Radtech Europe 1993 by M. Wittig and Th. Gohmann. The powder coatings can also contain binders, as are described, for example, in DE 4228514 and in EP 636669. Free-radically UV-curable powder coatings can also be formulated by mixing unsaturated polyester resins with solid acrylates, methacrylates or vinyl ethers and with a novel photoinitiator (or photoinitiator mixture). The powder coatings may also comprise binders as are described, for example, in DE 4228514 and in EP 636669. The UV-curable powder coatings may additionally comprise white or coloured pigments. For example, preferably rutile titanium dioxide can be employed in concentrations of up to 50% by weight in order to give a cured powder coating of good hiding power. The procedure normally comprises electrostatic or tribostatic spraying of the powder onto the substrate, for example metal or wood, melting of the powder by heating, and, after a smooth film has formed, radiation-curing of the coating with ultraviolet and/or visible light, using for example medium-pressure mercury lamps, metal halide lamps or xenon lamps. A particular advantage of the radiation-curable powder coatings over their heat-curable counterparts is that the flow time after melting the powder particles can be delayed in order to ensure the formation of a smooth, high-gloss coating. In contrast to heat-curable systems, radiation-curable powder coatings can be formulated to melt at lower temperatures without the unwanted effect of shortening their lifetime. For this reason, they are also suitable as coatings for heat-sensitive substrates, for example wood or plastics. In addition to the novel photoinitiator systems, the powder coating formulations may also include UV absorbers. Appropriate examples are listed above in sections 1.-8.

[0121] The novel photocurable compositions are suitable, for example, as coating materials for substrates of all kinds, for example wood, textiles, paper, ceramics, glass, plastics such as polyesters, polyethylene terephthalate, polyolefins or cellulose acetate, especially in the form of films, and also metals such as Al, Cu, Ni, Fe, Zn, Mg or Co and GaAs, Si or SiO₂ to which it is intended to apply a protective layer or, by means of imagewise exposure, to generate an image.

[0122] The novel radiation-sensitive compositions further find application as negative resists, having a very high sensitivity to light and being able to be developed in an aqueous alkaline medium without swelling. They are suitable for the production of printing forms for relief printing, planographic printing, photogravure or of screen printing forms, for the production of relief copies, for example for the production of texts in braille, for the production of stamps, for use in chemical milling or as a microresist in the production of integrated circuits. The compositions further may be used as photopatternable dielectric layer or coating, encapsulating material and isolating coating in the production of computer chips, printed boards and other electric or electronic components. The possible layer supports, and the processing conditions of the coating substrates, are just as varied.

[0123] The novel composition also relates to a photosensitive thermosetting resin composition and a method of forming a solder resist pattern by the use thereof, and more particularly relates to a novel photosensitive thermosetting resin composition useful as materials for the production of printed circuit boards, the precision fabrication of metallic articles, the etching of glass and stone articles, the relief of plastic articles, and the preparation of printing plates and particularly useful as a solder resist for printed circuit boards and to a method of forming a solder resist pattern by the steps of exposing a layer of the resin composition selectively to an actinic ray through a photomask having a pattern and developing the unexposed part of the layer.

[0124] The solder resist is a substance which is used during the soldering of a given part to a printed circuit board for the purpose of preventing molten solder from adhering to irrelevant portions and protecting circuits. It is, therefore, required to possess such properties as high adhesion, insulation resistance, resistance to soldering temperature, resistance to solvents, resistance to alkalis, resistance to acids, and resistance to plating.

[0125] Because the photocurable compositions according to the invention have a good thermal stability and are sufficiently resistant to inhibition by oxygen, they are particularly suitable for the production of color filters or color mosaic systems, such as described, for example, in EP 320 264. Color filters usually are employed in the manufacturing of flat panel displays such as LCD's, PDP(plasma panel display), EL (electroluminescence) display, and projection systems, image sensors, CCD (charge coupled device), and CMOS (complementary metal oxide semiconductor) sensors for scanner, digital camera and video camera.

[0126] The color filters usually are prepared by forming red, green and blue pixels and a black matrix on a glass substrate. In these processes photocurable compositions according to the invention can be employed. A particularly preferred method of use comprises adding of the coloring matters, dyes and pigments of red, green and blue colors to the light-sensitive resin composition of the present invention, coating of the substrate with the composition, drying of the coating with a short heat treatment, patternwise exposure of the coating to actinic radiation and subsequent development of the pattern in an aqueous alkaline developer solution and optionally a heat treatment. Thus, by subsequently applying a red, green and blue pigmented coating, in any desired order, on top of each other with this process a color filter layer with red, green and blue color pixels can be produced.

[0127] The development is carried out by washing out the areas which were not polymerized with a suitable alkali developing solution. This process is repeated to form the image having plural colors.

[0128] In the light-sensitive resin composition of the present invention, with a process in which at least one or more

picture elements are formed on a transparent substrate and then an exposure is given from a side of the transparent substrate, on which the above picture elements are not formed, the above picture elements can be utilized as a light-shielding mask. In this case, for example, in the case where an overall exposure is given, a position adjustment of a mask gets unnecessary and a concern on a position slippage thereof is removed. And, it is possible to cure all of the part on which the above picture elements are not formed. Further, in this case, it is possible as well to develop and

remove a part of the portion on which the above picture elements are not formed by using partially a light-shielding mask. **[0129]** Since in either case, no gap is formed between the picture elements which are formed formerly and those which are formed later, the composition of the present invention is suitable for, for example, a forming material for a color filter. To be concrete, the coloring matters, dyes and pigments of red, green and blue colors are added to the light-sensitive resin composition of the present invention, and the processes for forming an image are repeated to form the picture elements of red, green and blue colors. Then, the light-sensitive resin composition to which, for example, the black coloring materials, dyes and pigments are added is provided on an overall face. An overall exposure (or a partial exposure via a light-shielding mask) can be provided thereon to form the picture elements of a black color all over the spaces (or all but a partial region of the light-shielding mask) between the picture elements of red, green and blue colors.

[0130] In addition to a process in which the light-sensitive resin composition is coated on a substrate and dried, the light-sensitive resin composition of the present invention can be used as well for a layer transfer material. That is, the light-sensitive resin composition is layer-wise provided directly on a temporary support, preferably on a polyethylene terephthalate film, or on a polyethylene terephthalate film on which an oxygen-shielding layer and a peeling layer or the peeling layer and the oxygen-shielding layer are provided. Usually, a removable cover sheet made of a synthetic resin is laminated thereon for a protection in handling. Further, there can be applied as well a layer structure in which an alkali soluble thermoplastic resin layer and an intermediate layer are provided on a temporary support and further a light-sensitive resin composition layer is provided thereon (JP 5-173320-A).

[0131] The above cover sheet is removed in use and the light-sensitive resin composition layer is laminated on a permanent support. Subsequently, peeling is carried out between those layer and a temporary support when an oxygen-shielding layer and a peeling layer are provided, between the peeling layer and the oxygen-shielding layer when the peeling layer and the oxygen-shielding layer are provided, and between the temporary support and the light-sensitive resin composition layer when either the peeling layer or the oxygen-shielding layer is not provided, and the temporary support is removed.

[0132] A metal support, glass, ceramics, and a synthetic resin film can be used as a support for a color filter. Glass and a synthetic resin film which is transparent and have an excellent dimension stability is particularly preferred.

[0133] The thickness of the light-sensitive resin composition layer is usually 0.1 to 50 micrometers, in particular 0.5 to 5 micrometers.

[0134] A diluted aqueous solution of an alkaline substance can be used as a developing solution for the light-sensitive resin composition of the present invention if the composition contains alkali soluble resin or alkali soluble monomers or oligomers, and further a developer solution prepared by adding a small amount of a water-miscible organic solvent thereto is included as well.

[0135] Examples of suitable alkaline materials include alkali metal hydroxides (for example, sodium hydroxide and potassium hydroxide), alkali metal carbonates (for example, sodium carbonate and potassium carbonate), alkali metal bicarbonates (for example, sodium bicarbonate and potassium bicarbonate), alkali metal silicates (for example, sodium silicate and potassium silicate), alkali metal metasilicates (for example, sodium metasilicate and potassium metasilicate), triethanolamine, diethanolamine, monoethanolamine, morpholine, tetraalkylammonium hydroxides (for example, tetramethylammonium hydroxide), or trisodium phosphate. The concentration of the alkaline substance is 0.01 to 30 weight %, and pH is preferably 8 to 14.

Suitable organic solvents which are miscible with water include methanol, ethanol, 2-propanol, 1-propanol, butanol, diacetone alcohol, ethylene glycol monomethyl ether, ethylene glycol monoethyl ether, ethylene glycol mono-n-butyl ether, diethyleneglycol dimethyl ether, propyleneglycol monomethyl ether acetate, ethyl-3-ethoxypropionate, methyl-3-methoxypropionate, n-butyl acetate, benzyl alcohol, acetone, methyl ethyl ketone, cyclopentanone, cyclohexanone, 2-heptanone, 2-pentanone, epsilon-caprolactone, gamma-butyrolactone, dimethylformamide, dimethylacetamide, hexamethylphosphoramide, ethyl lactate, methyl lactate, epsilon-caprolactam, and N-methyl-pyrrolidinone. The concentration of the organic solvent which is miscible with water is 0.1 to 30 weight %.

[0136] Further, a surface active agent can be added. The concentration of the surface active agent is preferably 0.001 to 10 weight %. Such additives are known in the art.

[0137] The light sensitive resin composition of the present invention can also be developed with organic solvents, including blends of two or more solvents, not containing alkaline compounds. Suitable solvents include methanol, ethanol, 2-propanol, 1-propanol, butanol, diacetone alcohol, ethylene glycol monomethyl ether, ethylene glycol monoethyl ether, ethylene glycol mono-n-butyl ether, diethyleneglycol dimethyl ether, propyleneglycol monomethyl ether acetate, ethyl-3-ethoxypropionate, methyl-3-methoxypropionate, n-butyl acetate, benzyl alcohol, acetone, methyl ethyl ketone, cyclopentanone, cyclohexanone, 2-heptanone, 2-pentanone, epsilon-caprolactone, gamma-butyrolactone, dimethylforma-

amide, dimethylacetamide, hexamethylphosphoramide, ethyl lactate, methyl lactate, epsilon-caprolactam, and N-methylpyrrolidinone. Optionally, water can be added to these solvents up to a level at which still a clear solution is obtained and at which sufficient solubility of the unexposed areas of the light sensitive composition is maintained.

[0138] The developer solution can be used in all forms known to the person skilled in the art, for example in form of a bath solution, puddle, or a spraying solution. In order to remove the non-cured portion of the light-sensitive resin composition layer, there can be combined the methods such as rubbing with a rotary brush and rubbing with a wet sponge. Usually, the temperature of the developing solution is preferably at and around room temperature to 40°C. The developing time is changeable according to the specific kind of the light-sensitive resin composition, the alkalinity and temperature of the developing solution, and the kind and concentration of the organic solvent in the case where it is added. Usually, it is 10 seconds to 2 minutes. It is possible to put a rinsing step after the development processing.

[0139] A final heat treatment is preferably carried out after the development processing. Accordingly, a support having a layer which is photopolymerized by exposing (hereinafter referred to as a photocured layer) is heated in an electric furnace and a drier, or the photocured layer is irradiated with an infrared lamp or heated on a hot plate. The heating temperature and time depend on the composition used and the thickness of the formed layer. In general, heating is preferably applied at about 120°C to about 250°C, for about 5 to about 60 minutes.

[0140] The pigment which can be comprised in the composition according to the present invention, including a pigmented color filter resist composition, is preferably a processed pigment, for example a powdery or pasty product prepared by finely dispersing a pigment into at least one resin selected from the group consisting of acrylic resin, vinyl chloride-vinyl acetate copolymer, maleic acid resin and ethyl cellulose resin.

The red pigment comprises, for example, an anthraquinone type pigment alone, a diketopyrrolopyrrole type pigment alone, a mixture of them or a mixture consisting of at least one of them and a disazo type yellow pigment or an isoindoline type yellow pigment, in particular C. I. Pigment Red 177 alone, C. I. Pigment Red 254 alone, a mixture of C. I. Pigment Red 177 and C. I. Pigment Red 254 or a mixture consisting of at least one member of C. I. Pigment Red 177 and C. I. Pigment Red 254, and C. I. Pigment Yellow 83 or C. I. Pigment Yellow 139 ("C.I." refers to the Color Index, known to the person skilled in the art and publicly available).

Further suitable examples for the pigment are C.I. Pigment Red 9, 97, 105, 122, 123, 144, 149, 168, 176, 179, 180, 185, 202, 207, 209, 214, 222, 242, 244, 255, 264, 272 and C.I. Pigment Yellow 12, 13, 14, 17, 20, 24, 31, 53, 55, 93, 95, 109, 110, 128, 129, 138, 139, 150, 153, 154, 155, 166, 168, 185, 199, 213 and C.I. Pigment Orange 43. Examples of the dyes for red color are C. I. Solvent Red 25, 27, 30, 35, 49, 83, 89, 100, 122, 138, 149, 150, 160, 179, 218, 230, C. I. Direct Red 20, 37, 39, 44, and C. I. Acid Red 6, 8, 9, 13, 14, 18, 26, 27, 51, 52, 87, 88, 89, 92, 94, 97, 111, 114, 115, 134, 145, 151, 154, 180, 183, 184, 186, 198, C. I. Basic Red 12, 13, C. I. Disperse Red 5, 7, 13, 17 and 58. The Red dyes can be used in combination with yellow and/or orange dyes. The green pigment comprises for instance a halogenated phthalocyanine type pigment alone or its mixture with a disazo type yellow pigment, an quinophthalone type yellow pigment or a metal complex, in particular C. I. Pigment Green 7 alone, C. I. Pigment Green 36 alone, or a mixture consisting of at least one member of C. I. Pigment Green 7, C. I. Pigment Green 36 and C. I. Pigment Yellow 83, C. I. Pigment Yellow 138 or C. I. Pigment Yellow 150. Other suitable green pigments are C.I. Pigment Green 15, 25 and 37. Examples for suitable green dyes are C. I. Acid Green 3, 9, 16, C. I. Basic Green 1 and 4.

Examples for suitable blue pigments are phthalocyanine type pigments, used either alone or in combination with an dioxazine type violet pigment, for instance, C. I. Pigment Blue 15:6 alone, a combination of C. I. Pigment Blue 15:6 and C. I. Pigment Violet 23. Further examples for blue pigments are such of C. I. Pigment Blue 15:3, 15:4, 16, 22, 28 and 60. Other suitable pigments are C. I. Pigment Violet 14, 19, 23, 29, 32, 37, 177 and C. I. Orange 73.

Examples for suitable blue dyes are C. I. Solvent Blue 25, 49, 68, 78, 94, C. I. Direct Blue 25, 86, 90, 108, C. I. Acid Blue 1, 7, 9, 15, 103, 104, 158, 161, C. I. Basic Blue 1, 3, 9, 25, and C. I. Disperse Blue 198.

The pigment of the photopolymeric composition for black matrix preferably comprises at least one member selected from the group consisting of carbon black, titanium black and iron oxide. However, a mixture of other pigments which, in total, give the black appearance, can also be used. For example, also C. I. Pigment Black 1, 7 and 31 can be used alone or in combination.

Other examples of the dyes used for color filter are C. I. Solvent Yellow 2, 5, 14, 15, 16, 19, 21, 33, 56, 62, 77, 83, 93, 162, 104, 105, 114, 129, 130, 162, C. I. Disperse Yellow 3, 4, 7, 31, 54, 61, 201, C. I. Direct Yellow 1, 11, 12, 28, C. I. Acid Yellow 1, 3, 11, 17, 23, 38, 40, 42, 76, 98, C. I. Basic Yellow 1, C. I. Solvent Violet 13, 33, 45, 46, C. I. Disperse Violet 22, 24, 26, 28, C. I. Acid Violet 49, C. I. Basic Violet 2, 7, 10, C. I. Solvent Orange 1, 2, 5, 6, 37, 45, 62, 99, C. I. Acid Orange 1, 7, 8, 10, 20, 24, 28, 33, 56, 74, C. I. Direct Orange 1, C. I. Disperse Orange 5, C. I. Direct Brown 6, 58, 95, 101, 173, C. I. Acid Brown 14, C. I. Solvent Black 3, 5, 7, 27, 28, 29, 35, 45 and 46.

[0141] In some special cases of manufacturing color filters, complementary colors, yellow, magenta, cyan and optionally green, are used instead of red, green and blue. As yellow for this type of color filters, the abovementioned yellow pigments and dyes can be employed. Examples of the colorants suitable for magenta color are C. I. Pigment Red 122, 144, 146, 169, 177, C. I. Pigment Violet 19 and 23. Examples of cyan color are aluminum phthalocyanine pigments, titanium phthalocyanine pigments, cobalt phthalocyanine pigments, and tin phthalocyanine pigments.

based on novolacs with (meth)acrylic acid.

Polyethers obtained from the reaction of the abovementioned polyols or polyepoxides with the unsaturated compounds with a hydroxy group such as 2-hydroxyethyl (meth)acrylate, vinyl alcohol can also be used as component (a).


5 Other examples for suitable components (a) are unsaturated urethanes derived from a polyisocyanate and an unsaturated compound having a hydroxy group or from a polyisocyanate, a polyol and an unsaturated compound having a hydroxy group.

10 Other examples are polyesters, polyamides, or polyurethanes having ethylenically unsaturated groups in the chain. Suitable unsaturated polyesters and polyamides are also derived, for example, from maleic acid and diols or diamines. Some of the maleic acid can be replaced by other dicarboxylic acids. The polyesters and polyamides may also be derived from dicarboxylic acids and ethylenically unsaturated diols or diamines, especially from those with relatively long chains of, for example 6 to 20 C atoms. Examples of polyurethanes are those composed of saturated or unsaturated diisocyanates and of unsaturated or, respectively, saturated diols.


15 Other suitable polymers with acrylate or methacrylate groups in the side chains are, for example, solvent soluble or alkaline soluble polyimide precursors, for example poly(amic acid ester) compounds, having the photopolymerizable side groups either attached to the backbone or to the ester groups in the molecule, i.e. according to EP 624826. Such oligomers or polymers can be formulated optionally with reactive diluents, like polyfunctional (meth)acrylates in order to prepare highly sensitive polyimide precursor resists.

20 Further examples of the component (a) are also polymers or oligomers having at least one carboxyl function and at least two ethylenically unsaturated groups within the molecular structure, such as a resin obtained by the reaction of a saturated or unsaturated polybasic acid anhydride with a product of the reaction of phenol or cresol novolac epoxy resin and an unsaturated monocarboxylic acid, for example, commercial products such as EB9696, UCB Chemicals; KAYARAD TCR1025, Nippon Kayaku Co., LTD. Examples of the polybasic acid anhydride are maleic anhydride, succinic anhydride, itaconic anhydride, phthalic anhydride, tetrahydrophthalic anhydride, hexahydrophthalic anhydride, methyltetrahydrophthalic anhydride, glutaric anhydride, glutaconic anhydride, citraconic anhydride, diglycolic anhydride, iminodiacetic anhydride, 1,1-cyclopentanediacetic anhydride, 3,3-dimethylglutaric anhydride, 3-ethyl-3-methylglutaric anhydride, 2-phenylglutaric anhydride, homophthalic anhydride, trimellitic anhydride, chlorendic anhydride, pyromellitic dianhydride, benzophenone tetracarboxylic acid dianhydride, biphenyl tetracarboxylic acid dianhydride, and biphenylether tetracarboxylic acid dianhydride.

30 Other examples are the products from the polycondensation reaction and/or addition reaction of the compound of formula (XIV) with one or more abovementioned polybasic acid anhydrides.



40 wherein Y_{10} is



R_{200} is hydrogen or methyl,

50 R_{300} and R_{400} independently of each other are hydrogen, methyl, Cl, or Br, M_{20} is substituted or unsubstituted alkylene having 1 to 10 carbon atoms, x is 0 to 5, and y is 1 to 10. Examples of such compounds as component (a) are described in JP2002-206014A, JP2004-69754A, JP2004-302245A, JP2005-77451A, JP2005-316449A, JP2005-338328A and JP3754065B2.








Polymers or oligomers as abovementioned have for example a molecular weight of about 1'000 to 1'000'000, preferably 2'000 to 200'000 and an acid value of about 10 to 200 mg KOH/g, preferably 20 to 180 mg KOH/g.

55 A preferred photopolymerizable composition comprises as component (a) a compound having at least two ethylenically unsaturated bonds and at least one carboxylic acid group in the molecule, in particular a reaction product obtained by adding an epoxy group containing unsaturated compound to a part of the carboxyl groups of a carboxylic acid group containing polymer or a reaction product of the compound shown below with one or more polybasic acid anhydrides. Further preferred components (a) comprise a compound obtained from the reaction of a compound of the formula XIV

with one or more polybasic acid anhydrides.

Further examples are reaction products obtained by adding an epoxy group containing unsaturated compound to a part of the carboxyl groups of a carboxylic acid group containing polymer. As the carboxylic acid containing polymer, the abovementioned binder polymers which are resulting from the reaction of an unsaturated carboxylic acid compound with one or more polymerizable compounds, for example, copolymers of (meth)acrylic acid, benzyl (meth)acrylate, styrene and 2-hydroxyethyl (meth)acrylate, copolymers of (meth)acrylic acid, styrene and α -methystyrene, copolymers of (meth)acrylic acid, N-phenylmaleimide, styrene and benzyl (meth)acrylate, copolymers of (meth)acrylic acid and styrene, copolymers of (meth)acrylic acid and benzyl (meth)acrylate, copolymers of tetrahydrofurfuryl (meth)acrylate, styrene and (meth)acrylic acid, and the like.

Examples of the unsaturated compounds having an epoxy group are given below in the formula (V-1) - (V-15);



wherein R_{50} is hydrogen or methyl group, M_{30} is substituted or unsubstituted alkylene having 1 to 10 carbon atoms.

[0148] Among these compounds, compounds having alicyclic epoxy groups are particularly preferred, because these compounds have a high reactivity with carboxyl group-containing resins, accordingly the reaction time can be shortened. These compounds further do not cause gelation in the process of reaction and make it possible to carry out the reaction stably. On the other hand, glycidyl acrylate and glycidyl methacrylate are advantageous from the viewpoint of sensitivity and heat resistance because they have a low molecular weight and can give a high conversion of esterification. Concrete

examples of the abovementioned compounds are, for example a reaction product of a copolymer of styrene, α -methyl styrene and acrylic acid or a copolymer of methyl methacrylate and acrylic acid with 3,4-epoxycyclohexylmethyl (meth)acrylate.

[0149] Unsaturated compounds having a hydroxy group such as 2-hydroxyethyl (meth)acrylate and glycerol mono(meth)acrylate can be used instead of the above mentioned epoxy group containing unsaturated compounds as the reactant for carboxylic acid group containing polymers.

Other examples are half esters of anhydride containing polymers, for example reaction products of a copolymer of maleic anhydride and one or more other polymerizable compounds with (meth)acrylates having an alcoholic hydroxy group such as 2-hydroxyethyl (meth)acrylate or having an epoxy group for example such as the compounds described in the formula (V-1) - (V-15).

Reaction products of polymers having alcoholic hydroxy groups such as copolymers of 2-hydroxyethyl (meth)acrylate, (meth)acrylic acid, benzy methacrylate and styrene, with (meth)acrylic acid or (meth)acryl chloride can also be used as component (a).

Other examples are reaction products of a polyester with terminal unsaturated groups, which is obtained from the reaction of a dibasic acid anhydride and a compound having at least two epoxy groups followed by further reaction with an unsaturated compound, with a polybasic acid anhydride.

Further examples are resins obtained by the reaction of a saturated or unsaturated polybasic acid anhydride with a reaction product obtained by adding epoxy group containing (meth)acrylic compound to all of the carboxyl groups of a carboxylic acid containing polymer as mentioned above.

[0150] The photopolymerizable compounds can be used alone or in any desired mixtures.

[0151] In a color filter resist composition the whole amount of the monomers contained in the photopolymerizable composition is preferably 5 to 80 % by weight, in particular 10 to 70 % by weight based on the whole solid contents of the composition, i.e. the amount of all components without the solvent(s).

[0152] As the binder used in the color filter resist composition, which is soluble in an alkaline aqueous solution and insoluble in water, for example, a homopolymer of a polymerizable compound having one or more acid groups and one or more polymerizable unsaturated bonds in the molecule, or a copolymer of two or more kinds thereof, and a copolymer of one or more polymerizable compounds having one or more unsaturated bonds copolymerizable with these compounds and containing no acid group, can be used. Such compounds can be obtained by copolymerizing one or more kinds of a low molecular compound having one or more acid groups and one or more polymerizable unsaturated bonds in the molecule with one or more polymerizable compounds having one or more unsaturated bonds copolymerizable with these compounds and containing no acid group. Examples of acids groups are, a -COOH group, a -SO₃H group, a -SO₂NHCO-group, a phenolic hydroxy group, a -SO₂NH- group, and a -CO-NH-CO-group. Among those, a high molecular compound having a -COOH group is particularly preferred.

[0153] Preferably, the organic polymer binder in the color filter resist composition comprises an alkali soluble copolymer comprising, as addition polymerizable monomer units, at least an unsaturated organic acid compound such as acrylic acid, methacrylic acid and the like. It is preferred to use as a further co-monomer for the polymer binder an unsaturated organic acid ester compound such as methyl acrylate, ethyl (meth)acrylate, benzyl (meth)acrylate, styrene and the like to balance properties such as alkaline solubility, adhesion rigidity, chemical resistance etc..

The organic polymer binder can either be a random co-polymer or a block-co-polymer, for example, such as described in US 5368976.

[0154] Examples of the polymerizable compounds having one or more -COOH groups and one or more polymerizable unsaturated bonds in a molecule are (meth)acrylic acid, 2-carboxyethyl (meth)acrylic acid, 2-carboxypropyl (meth)acrylic acid, crotonic acid, cinnamic acid, mono[2-(meth)acryloyloxyethyl] succinate, mono[2-(meth)acryloyloxyethyl] adipate, mono[2-(meth)acryloyloxyethyl] phthalate, mono[2-(meth)acryloyloxyethyl] hexahydrophthalate, mono[2-(meth)acryloyloxyethyl] maleate, mono[2-(meth)acryloyloxypropyl] succinate, mono[2-(meth)acryloyloxypropyl] adipate, mono[2-(meth)acryloyloxypropyl] phthalate, mono[2-(meth)acryloyloxypropyl] hexahydrophthalate, mono[2-(meth)acryloyloxypropyl] maleate, mono[2-(meth)acryloyloxybutyl] succinate, mono[2-(meth)acryloyloxybutyl] adipate, mono[2-(meth)acryloyloxybutyl] phthalate, mono[2-(meth)acryloyloxybutyl] hexahydrophthalate, mono[2-(meth)acryloyloxybutyl] maleate, 3-(alkylcarbamoyl)acrylic acid, α -chloroacrylic acid, maleic acid, monoesterified maleic acid, fumaric acid, itaconic acid, citraconic acid, mesaconic acid, maleic anhydride, and ω -carboxypolycaprolactone mono(meth)acrylate.



Vinylbenzenesulfonic acid and 2-(meth)acrylamide-2-methylpropanesulfonic acid are examples of the polymerizable compounds having one or more -SO₃H groups and one or more polymerizable unsaturated bonds.

N-methylsulfonyl (meth)acrylamide, N-ethylsulfonyl (meth)acrylamide, N-phenylsulfonyl (meth)acrylamide, and N-(p-methylphenylsulfonyl) (meth)acrylamide are examples of the polymerizable compounds having one or more -SO₂NHCO-groups and one or more polymerizable unsaturated bonds.

Examples of polymerizable compounds having one or more phenolic hydroxy groups and one or more polymerizable unsaturated bonds in a molecule include hydroxyphenyl (meth)acrylamide, dihydroxyphenyl (meth)acrylamide, hydrox-

yphenyl-carbonyloxyethyl (meth)acrylate, hydroxyphenyloxyethyl (meth)acrylate, hydroxyphenylthioethyl (meth)acrylate, dihydroxyphenylcarbonyloxyethyl (meth)acrylate, dihydroxyphenyloxyethyl (meth)acrylate, and dihydroxyphenylthioethyl (meth)acrylate.

[0155] Examples of the polymerizable compounds having one or more $-\text{SO}_2\text{NH}-$ groups and one or more polymerizable unsaturated bonds in the molecule include compounds represented by formula (a) or (b):



wherein Y_{100} and Y_{200} each represents $-\text{COO}-$, $-\text{CONA}_{700}-$, or a single bond; A_{100} and A_{400} each represents H or CH_3 ; A_{200} and A_{500} each represents $\text{C}_1\text{-C}_{12}$ alkylene optionally having a substituent, cycloalkylene, arylene, or aralkylene, or $\text{C}_2\text{-C}_{12}$ alkylene into which an ether group and a thioether group are inserted, cycloalkylene, arylene, or aralkylene; A_{300} and A_{600} each represents H, $\text{C}_1\text{-C}_{12}$ alkyl optionally having a substituent, a cycloalkyl group, an aryl group, or an aralkyl group; and A_{700} represents H, $\text{C}_1\text{-C}_{12}$ alkyl optionally having a substituent, a cycloalkyl group, an aryl group, or an aralkyl group.

[0156] The polymerizable compounds having one or more $-\text{CO-NH-CO}-$ group and one or more polymerizable unsaturated bond include maleimide and N-acryloyl-acrylamide. These polymerizable compounds become the high molecular compounds comprising a $-\text{CO-NH-CO}-$ group, in which a ring is formed together with a primary chain by polymerization. Further, a methacrylic acid derivative and an acrylic acid derivative each having a $-\text{CO-NH-CO}-$ group can be used as well. Such methacrylic acid derivatives and the acrylic acid derivatives include, for example, a methacrylamide derivative such as N-acetylmethacrylamide, N-propionylmethacrylamide, N-butanoylmethacrylamide, N-pentanoylmethacrylamide, N-decanoylmethacrylamide, N-dodecanoylmethacrylamide, N-benzoylmethacrylamide, N-(p-methylbenzoyl)methacrylamide, N-(p-chlorobenzoyl)methacrylamide, N-(naphthyl-carbonyl)methacrylamide, N-(phenylacetyl)-methacrylamide, and 4-methacryloylaminophthalimide, and an acrylamide derivative having the same substituent as these. These polymerizable compounds polymerize to be compounds having a $-\text{CO-NH-CO}-$ group in a side chain.

[0157] Examples of polymerizable compounds having one or more polymerizable unsaturated bond and containing no acid group include a compound having a polymerizable unsaturated bond, selected from esters of (meth)acrylic acid, such as methyl (meth)acrylate, ethyl (meth)acrylate, propyl (meth)acrylate, butyl (meth)acrylate, tetrahydrofurfuryl (meth)acrylate, benzyl (meth)acrylate, 2-ethylhexyl (meth)acrylate, hydroxyethyl (meth)acrylate, hydroxypropyl (meth)acrylate, hydroxybutyl (meth)acrylate, glycerol mono(meth)acrylate, dihydroxypropyl (meth)acrylate, allyl (meth)acrylate, cyclohexyl (meth)acrylate, phenyl (meth)acrylate, methoxyphenyl (meth)acrylate, methoxyethyl (meth)acrylate, phenoxyethyl (meth)acrylate, methoxydiethyleneglycol (meth)acrylate, methoxytriethyleneglycol (meth)acrylate, methoxypropyl (meth)acrylate, methoxydipropyleneglycol (meth)acrylate, isobornyl meth(acrylate), dicyclopentadienyl (meth)acrylate, 2-hydroxy-3-phenoxypropyl (meth)acrylate, tricyclo[5.2.1.0^{2,6}]decan-8-yl (meth)acrylate, aminoethyl (meth)acrylate, N, N-dimethylaminoethyl (meth)acrylate, aminopropyl (meth)acrylate, N, N-dimethylaminopropyl (meth)acrylate, glycidyl (meth)acrylate, 2-methylglycidyl (meth)acrylate, 3,4-epoxybutyl (meth)acrylate, 6,7-epoxy-heptyl (meth)acrylate; vinyl aromatic compounds, such as styrene, α -methylstyrene, vinyltoluene, p-chlorostyrene, polychlorostyrene, fluorostyrene, bromostyrene, ethoxymethyl styrene, methoxystyrene, 4-methoxy-3-methylstyrene, dimethoxystyrene, vinylbenzyl methyl ether, vinylbenzyl glycidyl ether, indene, 1-methylindene; vinyl or allyl esters, such as vinyl acetate, vinyl propionate, vinyl butylate, vinyl pivalate, vinyl benzoate, vinyl trimethylacetate, vinyl diethylacetate, vinyl barate, vinyl caproate, vinyl chloroacetate, vinyl dichloroacetate, vinyl methoxyacetate, vinyl butoxyacetate, vinyl phenylacetate, vinyl acetate, vinyl acetoacetate, vinyl lactate, vinyl phenylbutylate, vinyl cyclohexylcarboxylate, vinyl salicylate, vinyl chlorobenzoate, vinyl tetrachlorobenzoate, vinyl naphthoate, allyl acetate, allyl propionate, allyl butylate, allyl pivalate, allyl benzoate, allyl caproate, allyl stearate, allyl acetoacetate, allyl lactate; vinyl or allyl ethers, such as vinyl methyl ether, vinyl ethyl ether, vinyl hexyl ether, vinyl octyl ether, vinyl ethylhexyl ether, vinyl methoxyethyl ether, vinyl ethoxyethyl ether, vinyl chloroethyl ether, vinyl hydroxyethyl ether, vinyl ethylbutyl ether, vinyl hydroxyethoxyethyl ether, vinyl dimethylaminoethyl ether, vinyl diethylaminoethyl ether, vinyl butylaminoethyl ether, vinyl benzyl ether, vinyl tetrahydrofurfuryl ether, vinyl phenyl ether, vinyl tolyl ether, vinyl chlorophenyl ether, vinyl chloroethyl ether, vinyl dichlorophenyl ether, vinyl naphthyl ether, vinyl anthryl ether, allyl glycidyl ether; amide type unsaturated compounds, such as (meth)acrylamide, N, N-dimethyl (meth)acrylamide, N, N-diethyl (meth)acrylamide, N, N-dibutyl (meth)acrylamide, N, N-diethylhexyl (meth)acrylamide, N, N-dicyclohexyl (meth)acrylamide, N, N-diphenyl (meth)acrylamide, N-methyl-N-phenyl (meth)acrylamide, N-hydroxyethyl-N-methyl (meth)acrylamide, N-methyl (meth)acrylamide, N-ethyl (meth)acrylamide, N-propyl (meth)acrylamide, N-butyl (meth)acrylamide, N-hydroxyethyl (meth)acrylamide, N-heptyl (meth)acrylamide, N-octyl (meth)acrylamide, N-ethylhexyl (meth)acrylamide, N-hydroxyethyl (meth)acrylamide-cyclohexyl, N-benzyl (meth)acrylamide, N-phenyl (meth)acrylamide, N-tolyl (meth)acrylamide, N-hydroxyphenyl (meth)acrylamide, N-naphthyl (meth)acrylamide, N-phenylsulfonyl (meth)acrylamide, N-methylphenylsulfonyl (meth)acrylamide and N-(meth)acryloylmorpholine, diacetone acrylamide, N-methylol acrylamide, N-butoxyacrylamide; polyolefin

type compounds, such as butadiene, isoprene, chloroprene and the like; (meth)acrylonitrile, methyl isopropenyl ketone, maleimide, N-phenylmaleimide, N-methylphenylmaleimide, N-methoxyphenylmaleimide, N-cyclohexylmaleimide, N-alkylmaleimide, maleic anhydride, polystyrene macromonomer, polymethyl (meth)acrylate macromonomer, polybutyl (meth)acrylate macromonomer; crotonates, such as butyl crotonate, hexyl crotonate, glycerine monocrotonate; and itaconates, such as dimethyl itaconate, diethyl itaconate, dibutyl itaconate; and maleates or fumarates, such as dimethyl maleate, dibutyl fumarate.

[0158] Preferable examples of copolymers are copolymers of methyl (meth)acrylate and (meth)acrylic acid, copolymers of benzyl (meth)acrylate and (meth)acrylic acid, copolymers of methyl (meth)acrylate/, ethyl (meth)acrylate and (meth)acrylic acid, copolymers of benzyl (meth)acrylate, (meth)acrylic acid and styrene, copolymers of benzyl (meth)acrylate, (meth)acrylic acid and 2-hydroxyethyl (meth)acrylate, copolymers of methyl (meth)acrylate/, butyl (meth)acrylate, (meth)acrylic acid and styrene, copolymers of methyl (meth)acrylate, benzyl (meth)acrylate, (meth)acrylic acid and hydroxyphenyl (meth)acrylate, copolymers of methyl (meth)acrylate, (meth)acrylic acid and polymethyl (meth)acrylate macromonomer, copolymers of benzyl (meth)acrylate, (meth)acrylic acid and polymethyl (meth)acrylate macromonomer, copolymers of tetrahydrofurfuryl (meth)acrylate, styrene and (meth)acrylic acid, copolymers of methyl (meth)acrylate, (meth)acrylic acid and polystyrene macromonomer, copolymers of benzyl (meth)acrylate, (meth)acrylic acid and polystyrene macromonomer, copolymers of benzyl (meth)acrylate, (meth)acrylic acid, 2-hydroxyethyl (meth)acrylate and polystyrene macromonomer, copolymers of benzyl (meth)acrylate, (meth)acrylic acid, 2-hydroxypropyl (meth)acrylate and polystyrene macromonomer, copolymers of benzyl (meth)acrylate, (meth)acrylic acid, 2-hydroxy-3-phenoxypropyl (meth)acrylate and polymethyl (meth)acrylate macromonomer, copolymers of methyl (meth)acrylate, (meth)acrylic acid, 2-hydroxyethyl (meth)acrylate and polystyrene macromonomer, copolymers of benzyl (meth)acrylate, (meth)acrylic acid, 2-hydroxyethyl (meth)acrylate and polymethyl (meth)acrylate macromonomer, copolymers of N-phenylmaleimide, benzyl (meth)acrylate, (meth)acrylic acid and styrene, copolymers of benzyl (meth)acrylate, (meth)acrylic acid, N-phenylmaleimide, mono-[2-(meth)acryloyloxyethyl] succinate and styrene, copolymers of allyl (meth)acrylate, (meth)acrylic acid, N-phenylmaleimide, mono-[2-(meth)acryloyloxyethyl] succinate and styrene, copolymers of benzyl (meth)acrylate, (meth)acrylic acid, N-phenylmaleimide, glycerol mono(meth)-acrylate and styrene, copolymers of benzyl (meth)acrylate, ω -carboxypolycaprolactone mono(meth)acrylate, (meth)acrylic acid, N-phenylmaleimide, glycerol mono(meth)-acrylate and styrene, and copolymers of benzyl (meth)acrylate, (meth)acrylic acid, N-cyclohexylmaleimide and styrene.

There can be used as well hydroxystyrene homo- or co-polymers or a novolak type phenol resin, for example, poly(hydroxystyrene) and poly(hydroxystyrene-co-vinylcyclohexanol), a novolak resin, a cresol novolak resin, and a halogenated phenol novolak resin. More specifically, it includes, for example, the methacrylic acid copolymers, the acrylic acid copolymers, the itaconic acid copolymers, the crotonic acid co-polymers, the maleic anhydride co-polymers, for example, with styrene as a co-monomer, and maleic acid copolymers, and partially esterified maleic acid copolymers each described in, for example, JP 59-44615-B4 (the term "JP-B4" as used herein refers to an examined Japanese patent publication), JP 54-34327-B4, JP 58-12577-B4, and JP 54-25957-B4, JP 59-53836-A, JP 59-71048-A, JP 60-159743-A, JP 60-258539-A, JP 1-152449-A, JP 2-199403-A, and JP 2-199404-A, and which copolymers can be further reacted with an amine, as e.g. disclosed in US5650263; further, a cellulose derivative having a carboxyl group on a side chain can be used, and particularly preferred are copolymers of benzyl (meth)acrylate and (meth)acrylic acid and copolymers of benzyl (meth)acrylate, (meth)acrylic acid and other monomers, for example as described in US 4139391, JP 59-44615-B4, JP 60-159743-A and JP 60-258539-A.

[0159] With respect to those having carboxylic acid groups among the above organic binder polymers, it is possible to react some or all of the carboxylic acid groups with glycidyl(meth)acrylate or an epoxy(meth)acrylate to obtain photopolymerizable organic binder polymers for the purpose of improving the photosensitivity, coating film strength, the coating solvent and chemical resistance and the adhesion to the substrate. Examples are disclosed in, JP 50-34443-B4 and JP 50-34444-B4, US5153095, by T. Kudo et al. in J. Appl. Phys., Vol. 37 (1998), p. 3594-3603, US5677385, and US5650233.

[0160] The weight-average molecular weight of the binders is preferably 500 to 1'000'000, e.g. 3'000 to 1'000'000, more preferably 5'000 to 400'000.

[0161] These compounds may be used singly or as a mixture of two or more kinds. The content of the binder in the light-sensitive resin composition is preferably 10 to 95 weight %, more preferably 15 to 90 weight % based on the whole solid matters.

[0162] Further, in the color filter the total solid component of each color may contain an ionic impurity-scavenger, e.g. an organic compound having an epoxy group. The concentration of the ionic impurity scavenger in the total solid component generally is in the range from 0.1% by weight to 10% by weight.

Examples of color filters, especially with respect to the above described combinations of pigments and ionic impurity scavenger are given in EP 320264. It is understood, that the photoinitiators according to the present invention, i.e. the compounds of the formula I in the color filter formulations described in EP 320264 can replace the triazine initiator compounds.

[0163] The compositions according to this invention can comprise additionally a crosslinking agent which is activated

by an acid, for example as described in JP 10-221843A, and a compound which generates acid thermally or by actinic radiation and which activates a crosslinking reaction.

The compositions according to this invention can also comprise latent pigments which are transformed into finely dispersed pigments during the heat treatment of the latent pigment containing photosensitive pattern or coating. The heat treatment can be performed after exposure or after development of the latent pigment-containing photoimageable layer. Such latent pigments are soluble pigment precursors which can be transformed into insoluble pigments by means of chemical, thermal, photolytic or radiation induced methods as described, for example, in US5879855. This transformation of such latent pigments can be enhanced by adding a compound which generates acid at actinic exposure or by adding an acidic compound to the composition. Therefore, a color filter resist can also be prepared, which comprises a latent pigment in a composition according to this invention.

[0164] Examples for color filter resists, the composition of such resists and the processing conditions are given by T. Kudo et al., Jpn. J. Appl. Phys. Vol. 37 (1998) 3594; T. Kudo et al., J. Photopolym. Sci. Technol. Vol 9 (1996) 109; K. Kobayashi, Solid State Technol. Nov. 1992, p. S15-S18; US5368976; US5800952; US5882843; US5879855; US5866298; US5863678; JP 06-230212A; EP320264; JP 09-269410A; JP 10-221843A; JP 01-090516A; JP 10-171119A, US5821016, US5847015, US5882843, US5719008, EP881541, or EP902327.

The photoinitiators of the present invention can be used in color filter resists, for example, such as those given as examples above, or can partially or fully replace the known photoinitiators in such resists. It is understood by a person skilled in the art that the use of the new photoinitiators of the present invention is not limited to the specific binder resins, crosslinkers and formulations of the color filter resist examples given hereinbefore but can be used in conjunction with any radically polymerizable component in combination with a dye or color pigment or latent pigment to form a photosensitive color filter ink or color filter resist.

[0165] Accordingly, subject of the invention also is a color filter prepared by providing red, green and blue (RGB) colour elements and, optionally a black matrix, all comprising a photosensitive resin and a pigment on a transparent substrate and providing a transparent electrode either on the surface of the substrate or on the surface of the color filter layer, wherein said photosensitive resin comprises a polyfunctional acrylate monomer, an organic polymer binder and a photopolymerization initiator of formula I as described above. The monomer and binder components, as well as suitable pigments are as described above. In the manufacture of color filters the transparent electrode layer can either be applied on the surface of the transparent substrate or can be provided on the surface of the red, green and blue picture elements and the black matrix. The transparent substrate is for example a glass substrate which can additionally have an electrode layer on its surface.

[0166] It is preferred to apply a black matrix between the color areas of different color in order to improve the contrast of a color filter.

[0167] The photosensitive compositions of the present invention, as already stated above, are also suitable for the preparation of the black matrix of color filters. Said black matrix composition for example comprises a photoinitiator compound of the formula I of the present invention, an organic binder, in particular an organic binder, which is an epoxy acrylate resin having a carboxyl group, a black coloring material, a polymer dispersant, in particular a polymer dispersant containing a basic functional group.

The person skilled in the art is familiar with such formulations. Examples of suitable black matrix compositions and the components (other than the photoinitiator) as described above are given in JP Patent No. 3754065, the disclosure of which hereby is incorporated by reference.

[0168] Instead of forming a black matrix using a photosensitive composition and patterning the black photosensitive composition photolithographically by patternwise exposure (i.e. through a suitable mask) to form the black pattern separating the red green and blue coloured areas on the transparent substrate it is alternatively possible to use an inorganic black matrix. Such inorganic black matrix can be formed from deposited (i.e. sputtered) metal (i.e. chromium) film on the transparent substrate by a suitable imaging process, for example utilizing photolithographic patterning by means of an etch resist, etching the inorganic layer in the areas not protected by the etch resist and then removing the remaining etch resist.

[0169] There are different methods known how and at which step in the color filter manufacturing process the black matrix can be applied. It can either be applied directly on the transparent substrate prior to formation of the red, green and blue (RGB) colour filter as already mentioned above, or it can be applied after the RGB colour filter is formed on the substrate.

[0170] In a different embodiment of a color filter for a liquid crystal display, according to US626796, the black matrix can also be applied on the substrate opposite to the RGB color filter element-carrying substrate, which is separated from the former by a liquid crystal layer.

[0171] If the transparent electrode layer is deposited after applying the RGB color filter elements and -optionally - the black matrix, an additional overcoat film as a protective layer can be applied on the color filter layer prior to deposition of the electrode layer, for example, as described in US 5650263.

[0172] To form an overcoat layer of a color filter, photosensitive resin or thermosetting resin compositions are employed. The photosensitive composition of the present invention can also be used to form such overcoat layers, because a cured film of the composition is excellent in flatness, hardness, chemical and thermal resistance, transparency especially in a visible region, adhesion to a substrate, and suitability for forming a transparent conductive film, e.g., an ITO film, thereon. In the production of a protective layer, there has been a demand that unnecessary parts of the protective layer, for example on scribing lines for cutting the substrate and on bonding pads of solid image sensors should be removed from the substrate as described in JP57-42009A, JP1-130103A and JP1-134306A. In this regard, it is difficult to selectively form a protective layer with good precision using the above-mentioned thermosetting resins. The photosensitive composition, however, allows to easily remove the unnecessary parts of the protective layer by photolithography.

[0173] It is obvious to those skilled in the art, that the photosensitive compositions of the present invention can be used for generating red, green and blue color pixels and a black matrix, for the manufacture of a color filter, regardless of the above described differences in processing, regardless, of additional layers which can be applied and regardless of differences in the design of the color filter. The use of a composition according to the present invention to form colored elements shall not be regarded as limited by different designs and manufacturing processes of such color filters.

[0174] The photo-sensitive composition of the present invention can suitably be used for forming a color filter but will not be limited to this application. It is useful as well for a recording material, a resist material, a protective layer, a dielectric layer, in display applications and display elements, a paint, and a printing ink.

[0175] The photosensitive compositions according to the invention are also suitable for manufacturing interlayer insulating layers or dielectric layers in a liquid crystal display, and more particularly in a reflection type liquid crystal display including an active matrix type display having a thin film transistor (TFT) as a switching device, and a passive matrix type without a switching device.

In recent years, liquid crystal displays have, for example, been widely used for pocket-type TV sets and terminal devices for communication by virtue of its small thickness and light weight. A reflection type liquid crystal display without necessity of using a back light is in particular in demand because it is ultra-thin and light-weight, and it can significantly reduce power consumption. However, even if a back light is removed out of a presently available transmission type color liquid crystal display and a light reflection plate is added to a lower surface of the display, it would cause a problem in that the efficiency of utilizing lights is low, and it is not possible to have practical brightness. As a solution to this problem, there have been suggested various reflection type liquid crystal displays for enhancing an efficiency of utilizing lights. For instance, a certain reflection type liquid crystal display is designed to include a pixel electrode having reflection function. The reflection type liquid crystal display includes an insulating substrate and an opposing substrate spaced away from the insulating substrate. A space between the substrates is filled with liquid crystals. A gate electrode is formed on the insulating substrate, and both the gate electrode and the insulating substrate are covered with a gate insulating film. A semiconductor layer is then formed on the gate insulating film above the gate electrode. A source electrode and a drain electrode are also formed on the gate insulating film in contact with the semiconductor layer. The source electrode, the drain electrode, the semiconductor layer, and the gate electrode cooperate with one another to thereby constitute a bottom gate type TFT as a switching device.

An interlayer insulating film is formed covering the source electrode, the drain electrode, the semiconductor layer, and the gate insulating film therewith. A contact hole is formed throughout the interlayer insulating film on the drain electrode. A pixel electrode made of aluminum is formed on both the interlayer insulating film and an inner sidewall of the contact hole. The drain electrode of the TFT is eventually in contact with the pixel electrode through the interlayer insulating film. The interlayer insulating layer is generally designed to have a roughened surface by which the pixel electrode acts as a reflection plate which diffuses lights to get a wider angle for viewing (angle of visibility).

[0176] The reflection type liquid crystal display remarkably enhances an efficiency of using lights by virtue that the pixel electrode acts as a light reflection plate.

In the above-mentioned reflection type liquid crystal display, the interlayer insulating film is designed to have projections and recesses by photolithography. To form and control a fine shape of the projections and recesses in micrometer order for surface roughness and to form contact holes, photolithography methods using positive and negative photoresists are used. For these resists the compositions according to the invention are especially suitable.

[0177] The photosensitive compositions according to the invention can further be used for manufacturing spacers, which control a cell gap of the liquid crystal part in liquid crystal display panels. Since the properties of light transmitted or reflected through the liquid crystal layer in a liquid crystal display are dependent on the cell gap, the thickness accuracy and uniformity over the pixel array are critical parameters for the performance of the liquid crystal display unit. In a liquid crystal cell, the spacing between the substrates in the cell is maintained constant by sparsely distributing glass or polymer spheres about several micrometers in diameter as spacers between the substrates. The spacers are thus held between the substrates to maintain the distance between the substrates at a constant value. The distance is determined by the diameter of the spacers. The spacers assure the minimum spacing between the substrates; i.e., they prevent a decrease in distance between the substrates. However, they cannot prevent the substrates from being separated apart from each other, i.e. the increase in distance between the substrates. Additionally, this method of using spacer beads has problems

of the uniformity in the diameter of spacer beads and difficulty in the even dispersion of spacer beads on the panel, as well as nonuniform orientation and decrease in brightness and/or optical aperture depending on the location of spacers on pixel array region. Liquid crystal displays having a large image display area have recently been attracting much attention. However, the increase in the area of a liquid crystal cell generally produces the distortion of the substrates constituting the cell. The layer structure of the liquid crystal tends to be destroyed due to the deformation of the substrate. Thus, even when spacers are used for maintaining the spacing between the substrates constant, a liquid crystal display having a large image display area is unfeasible because the display experiences disturbances. Instead of the above spacer sphere dispersion method, a method of forming columns in the cell gap as spacers has been proposed. In this method, columns of a resin are formed as spacers in the region between the pixel array region and the counter electrode to form a prescribed cell gap. Photosensitive materials having adhesive properties with photolithography are commonly used, for instance, in the manufacturing process of color filters. This method is advantageous compared with the conventional method using spacer beads in the points that location, number and height of the spacers may be controlled freely. In recent years, as the spread of the touch panel type liquid crystal displays such as mobile audio players and handheld game platforms, the mechanical stress to liquid crystal panel tends to grow. The demand for spacer that controls the cell gap to raise mechanical strength becomes strong thus the multi-spacer method is used. According to the multi-spacer method, when cell gap narrows by pressure from the outside, adding to main-spacer that controls the cell gap normally lower sub-spacer supports the cell gap against external stress. The multi-spacer can follow the contraction of liquid crystal at low temperature conditions by main-spacer and prevent to generate bubbles inside the liquid crystal.

The multi-spacer which contains main-spacer and sub-spacer is formed in the same step using, for example, a halftone mask as described in JPA-2011065133. The photo-sensitive compositions according to the invention are eligible for manufacturing process using halftone mask.

In a color liquid crystal display panel, such spacers are formed in the nonimaging area under black matrix of color filter elements. Therefore, the spacers formed using photo-sensitive compositions do not decrease brightness and optical aperture. Photosensitive compositions for producing protective layer with spacers for color filters are disclosed in JP 2000-81701A and dry film type photoresists for spacer materials are also disclosed in JP 11-174459A and JP 11-174464A. As described in the documents, the photosensitive compositions, liquid and dry film photoresists, are comprising at least an alkaline or acid soluble binder polymer, a radically polymerizable monomer, and a radical initiator. In some cases, thermally crosslinkable components such as epoxide and carboxylic acid may additionally be included.

The steps to form spacers using a photosensitive composition are as follows:

a photosensitive composition is applied to the substrate, for instance a color filter panel and after the substrate is prebaked, it is exposed to light through a mask. Then, the substrate is developed with a developer and patterned to form the desired spacers.

When the composition contains some thermosetting components, usually a postbaking is carried out to thermally cure the composition.

The photocurable compositions according to the invention are suitable for producing spacers for liquid crystal displays (as described above) because of their high sensitivity.

[0178] The photosensitive compositions according to the invention are also suitable for manufacturing microlens arrays used in liquid crystal display panels, image sensors and the like.

Microlenses are microscopic passive optical components that fit on active optoelectronic devices such as detectors, displays, and light emitting devices (light-emitting diodes, transversal and vertical cavity lasers) to improve their optical input or output quality. The areas of applications are wide and cover areas such as telecommunications, information technology, audio-visual services, solar cells, detectors, solid-state light sources, and optical interconnects.

Present optical systems use a variety of techniques to obtain efficient coupling between microlenses and microoptical devices.

The microlens arrays are used for condensing illuminating light on the picture element regions of a nonluminescent display device, such as a liquid crystal display devices, to increase the brightness of the display, for condensing incident light or as a means for forming an image on the photoelectric conversion regions of a line image sensor used for example in facsimiles and the like to improve the sensitivity of these devices, and for forming an image to be printed on a photosensitive means used in liquid crystal printers or light emitting diode (LED) printers.

The most common application is their use to improve the efficiency of photodetector arrays of a solid-state image sensing device such as a charge coupled device (CCD). In a detector array, the collection of as much light as possible in each detector element or pixel is wanted. If a microlens is put on top of each pixel, the lens collects incoming light and focuses it onto an active area that is smaller than the size of the lens.

According to the prior-art, microlens arrays can be produced by a variety of methods; for each of them compositions according to the present invention may be employed.

(1) A method for obtaining convex lenses wherein a pattern of the lenses in a planar configuration is drawn on a

thermoplastic resin by a conventional photolithographic technique or the like, and then the thermoplastic resin is heated to a temperature above the softening point of the resin to have flowability, thereby causing a sag in the pattern edge (so called "reflowing") (see, e.g., JP 60-38989A, JP 60-165623A, JP 61-67003A, and JP 2000-39503A). In this method, when the thermoplastic resin used is photosensitive, a pattern of the lenses can be obtained by exposure of this resin to light.

(2) A method for forming a plastic or glass material by the use of a mold or a stamper. As lens material, a photocurable resin and a thermosetting resin can be used in this method (see, e.g., WO99/38035).

(3) A method for forming convex lenses on the basis of a phenomenon in which when a photosensitive resin is exposed to light in a desired pattern by the use of an aligner, unreacted monomers move from the unexposed regions to the exposed regions, resulting in a swell of the exposed regions (see, e.g., Journal of the Research Group in Microoptics Japanese Society of Applied Physics, Colloquium in Optics, Vol. 5, No. 2, pp. 118-123 (1987) and Vol. 6, No. 2, pp. 87-92(1988)).

On the upper surface of a supporting substrate, a photosensitive resin layer is formed. Thereafter, with the use of a separate shading mask, the upper surface of the photo-sensitive resin layer is illuminated with light from a mercury lamp or the like, so that the photosensitive resin layer is exposed to the light. As a result, the exposed portions of the photosensitive resin layer swell into the shape of convex lenses to form the light condensing layer having a plurality of microlens.

(4) A method for obtaining convex lenses wherein a photosensitive resin is exposed to light by a proximity exposure technique in which a photomask is not brought into contact with the resin, to cause a blur at the pattern edge, so that the amount of photochemical reaction products is distributed depending upon the degree of blurring at the pattern edge (see, e.g., JP 61-153602A).

(5) A method for generating a lens effect wherein a photosensitive resin is exposed to light with a particular intensity distribution to form a distribution pattern of refractive index depending upon the light intensity (see, e.g., JP 60-72927A and JP 60-166946A). The photosensitive compositions according to the invention can be used in any one of the above-mentioned methods to form microlens arrays using photocurable resin compositions.

[0179] A particular class of techniques concentrates on forming microlenses in thermoplastic resins like photoresist. An example is published by Popovic et al. in the reference SPIE 898, pp.23-25 (1988). The technique, named reflow technique, comprises the steps of defining the lenses' footprint in a thermoplastic resin, e.g. by photolithography in a photosensitive resin like a photoresist, and subsequently heating this material above its reflow temperature. The surface tension draws the island of photoresist into a spherical cap with a volume equal to the original island before the reflow. This cap is a plano-convex microlens. Advantages of the technique are, amongst others, the simplicity, the reproducibility, and the possibility of integration directly on top of a light-emitting or light-detecting optoelectronic device.

In some cases, an overcoat layer is formed on the patterned lens units with a rectangular shape prior to reflowing to avoid a sagging of the island of the resin in the middle without reflow into a spherical cap in the reflow step. The overcoat acts as a permanent protective layer. The coating layer is also made of a photosensitive composition. Microlens arrays can also be fabricated by the use of a mold or a stamper as, for example, disclosed in EP0932256. A process of manufacturing the planar microlens array is as follows: a release agent is coated on a shaping surface of a stamper on which convex portions are densely arranged, and a photocurable synthetic resin material having a high refractive index is set on the shaping surface of the stamper. Next, the base glass plate is pushed onto the synthetic resin material, thereby spreading the synthetic resin material, and the synthetic resin material is cured by irradiating with ultraviolet radiation or by heating and is shaped to form the convex microlenses. Thereafter the stamper is peeled off. Then, a photocurable synthetic resin material having a low refractive index is additionally coated onto the convex microlenses as an adhesive layer and a glass substrate which is made into a cover glass plate is pushed onto the synthetic resin material, thereby spreading the same. The synthetic resin material is then cured and finally the planar microlens array is formed.

As disclosed in US5969867, a similar method using a mold is applied for the production of a prism sheet, which is used as a part of backlight units for color liquid crystal display panels to enhance the brightness. A prism sheet forming a prism row on one side is mounted on the light-emitting surface of the backlight. For fabricating a prism sheet, an active energy ray-curable composition is cast and spread in a lens mold which is made of metal, glass or resin and forms the lens shape of the prism row, etc., after which a transparent substrate sheet is placed onto it and active energy rays from an active energy ray-emitting source are irradiated through the sheet for curing. The prepared lens sheet is then released from the lens mold to obtain the lens sheet.

The active energy ray-curable composition used to form the lens section must have a variety of properties, including adhesion to the transparent substrate, and suitable optical characteristics.

Lenses at least with some photoresists in the prior art are not desirable for some applications since the optical transmittance in the blue end of the optical spectrum is poor. Because the photocurable compositions according to the invention have low yellowing properties, both thermally and photochemically, they are suitable for the production of microlens

arrays as described above.

[0180] The novel radiation-sensitive compositions are also suitable for photo-lithographic steps used in the production process of plasma display panels (PDP), particularly for the imaging forming process of barrier rib, phosphor layer and electrodes.

[0181] The PDP is a planar display for displaying images and information by virtue of the emission of light by gas discharge. By the construction of panel and the method of operation, it is known in two types, i.e. DC (direct current) type and AC (alternating current) type.

By way of example, the principle of the DC type color PDP will be briefly explained. In the DC type color PDP, the space intervening between two transparent substrates (generally glass plates) is divided into numerous minute cells by latticed barrier ribs interposed between the transparent substrates. In the individual cells a discharge gas, such as He or Xe, is sealed. On the rear wall of each cell there is a phosphor layer which, on being excited by the ultraviolet light generated by the discharge of the discharge gas, emits visible light of three primary colors. On the inner faces of the two substrates, electrodes are disposed as opposed to each other across the relevant cells. Generally, the cathodes are formed of a film of transparent electroconductive material such as NESA glass. When a high voltage is applied between these electrodes formed on the fore wall and the rear wall, the discharge gas which is sealed in the cells induces plasma discharge and, by virtue of the ultraviolet light radiated consequently, incites the fluorescent elements of red, blue, and green colors to emit lights and effect the display of an image. In the full-color display system, three fluorescent elements severally of the three primary colors of red, blue, and green mentioned above jointly form one picture element.

The cells in the DC type PDP are divided by the component barrier ribs of a lattice, whereas those in the AC type PDP are divided by the barrier ribs which are arranged parallel to each other on the faces of the substrates. In either case, the cells are divided by barrier ribs. These barrier ribs are intended to confine the luminous discharge within a fixed area to preclude false discharge or cross talk between adjacent discharge cells and ensure ideal display.

[0182] The compositions according to the invention also find application for the production of one- or more-layered materials for the image recording or image reproduction (copies, reprography), which may be mono- or polychromatic. Furthermore the materials are suitable for color proofing systems. In this technology formulations containing microcapsules can be applied and for the image production the radiation curing can be followed by a thermal treatment. Such systems and technologies and their applications are for example disclosed in US5376459.

[0183] The compounds of the formula I are also suitable as photoinitiators in the holographic data storage application. Said photoinitiators generate radicals and initiate polymerization of monomer upon irradiation with blue laser radiation, suitable for holographic data storage. The wavelength range of the blue laser is 390-420 nm, preferably 400-410 nm and particularly 405 nm. Holographic storage systems (holographic recording media) are for example used to record and to retrieve a large amount of data with fast access time. The photoinitiators of the invention are for example in particular suitable for systems as described for example in WO 03/021358.

The holographic data storage system is preferably comprised of a matrix network of low-refractive index matrix precursors and high-refractive index photopolymerizable monomers.

The matrix precursor and photoactive monomer can be selected such that (a) the reaction by which the matrix precursor is polymerized during the cure is independent from the reaction by which the photoactive monomer will be polymerized during writing of a pattern, e.g. data, and (b) the matrix polymer and the polymer resulting from polymerization of the photoactive monomer (the photopolymer) are compatible with each other. The matrix is considered to be formed when the photorecording material, i.e. the matrix material plus the photoactive monomer, photoinitiator and/or additives, exhibits an elastic modulus of at least about 10^5 Pa, generally about 10^5 Pa to about 10^9 Pa.

The media matrix is formed by in-situ polymerization which yields as cross-linked network in the presence of the photopolymerizable monomers which remain "dissolved" and unreacted. The matrix containing un-reacted, photopolymerizable monomers can also be formed by other means, for example by using a solid-resin matrix material in which the photoreactive, liquid monomer is homogeneously distributed. Then, monochromatic exposure generates the holographic pattern, which according to the light intensity distribution, polymerizes the photoreactive monomers in the solid pre-formed matrix. The unreacted monomers (where light intensity was at a minimum) diffuse through the matrix, producing a modulation of the refractive index that is determined by the difference between the refractive indices of the monomer and the matrix and by the relative volume fraction of the monomer. The thickness of the recording layer is in the range of several micrometers up to a thickness of one millimeter. Because of such thick holographic data storage layers it is required that the photoinitiator combines high photoreactivity with low absorbance, in order to render the layer transparent at the laser wavelength to assure that the extent of photopolymerization is as little as possible dependent on the exposure depth into the recording layer.

[0184] It was found that the photoinitiators of the present invention combine high reactivity with low absorbance at 405 nm and are suitable for this application. Dyes and sensitizers can also be added to the formulations. Suitable dyes and sensitizers for blue laser radiation are for example coumarines, xanthenes, thioxanthenes, see list above.

In particular relevant are thioxanthenes, coumarins and benzophenones as mentioned under items 1., 2. and 3. in the list given above.

It was found that the photoinitiators allow photopolymerization of monomers in thick layers, such as required for holographic data storage, with high sensitivity and yield recording layers which are sensitive to blue laser radiation. The photoinitiators, when applied at a concentration of 2-8 wt% in the photosensitive layer of 20 micron thickness yield an absorbance of the layer which comprises the photoinitiator, of less than 0.4, preferably less than 0.2 at the laser wavelength.

The photoinitiators are in particular suitable for the preparation of optical articles (for example optical waveguides) or holographic recording media e.g. comprising a polymer and an organic photoinitiator as described above, having a maximum absorption at a UV wavelength in the range of 340-450 nm, wherein the refractive index contrast adjusted sensitivity is greater than $3 \times 10^{-6} \Delta n / (mJ/cm^2)$. For example, the polymer is formed by polymerizing a material comprising component 1 and component 2, wherein component 1 comprises a NCO-terminated pre-polymer and component 2 comprises a polyol. Component 1 is, for example, diphenylmethane diisocyanate, toluene diisocyanate, hexamethylene diisocyanate, a derivative of hexamethylene diisocyanate, a methylenebis(cyclohexyl)isocyanate, a derivative of methylenebis(cyclohexyl)isocyanate. Component 2 is for example a polyol of propylene oxide. Preferably, the photoactive monomer is an acrylate monomer. In such media the shrinkage induced by writing is usually less than 0.25%.

[0185] Photocuring further is of great importance for printings, since the drying time of the ink is a critical factor for the production rate of graphic products, and should be in the order of fractions of seconds. UV-curable inks are particularly important for screen printing and offset inks.

[0186] As already mentioned above, the novel mixtures are highly suitable also for producing printing plates. This application uses, for example, mixtures of soluble linear polyamides or styrene/butadiene and/or styrene/isoprene rubber, polyacrylates or polymethyl methacrylates containing carboxyl groups, polyvinyl alcohols or urethane acrylates with photopolymerizable monomers, for example acrylamides and/or methacrylamides, or acrylates and/or methacrylates, and a photoinitiator. Films and plates of these systems (wet or dry) are exposed over the negative (or positive) of the printed original, and the uncured parts are subsequently washed out using an appropriate solvent or aqueous solutions. Another field where photocuring is employed is the coating of metals, in the case, for example, of the coating of metal plates and tubes, cans or bottle caps, and the photocuring of polymer coatings, for example of floor or wall coverings based on PVC. Examples of the photocuring of paper coatings are the colourless varnishing of labels, record sleeves and book covers.

[0187] Also of interest is the use of the novel photoinitiators for curing shaped articles made from composite compositions. The composite compound consists of a self-supporting matrix material, for example a glass fibre fabric, or alternatively, for example, plant fibres [cf. K.-P. Mieck, T. Reussmann in *Kunststoffe* 85 (1995), 366-370], which is impregnated with the photocuring formulation. Shaped parts comprising composite compounds, when produced using the novel compounds, attain a high level of mechanical stability and resistance. The novel compounds can also be employed as photocuring agents in moulding, impregnating and coating compositions as are described, for example, in EP7086. Examples of such compositions are gel coat resins, which are subject to stringent requirements regarding curing activity and yellowing resistance, and fibre-reinforced mouldings, for example, light diffusing panels which are planar or have lengthwise or crosswise corrugation. Techniques for producing such mouldings, such as hand lay-up, spray lay-up, centrifugal casting or filament winding, are described, for example, by P.H. Selden in "Glasfaserverstärkte Kunststoffe", page 610, Springer Verlag Berlin-Heidelberg-New York 1967. Examples of articles which can be produced by these techniques are boats, fibre board or chipboard panels with a double-sided coating of glass fibre-reinforced plastic, pipes, containers, etc. Further examples of moulding, impregnating and coating compositions are UP resin gel coats for mouldings containing glass fibres (GRP), such as corrugated sheets and paper laminates. Paper laminates may be based on urea resins or melamine resins. Prior to production of the laminate, the gel coat is produced on a support (for example a film). The novel photocurable compositions can also be used for casting resins or for embedding articles, for example electronic components, etc..

[0188] The compositions and compounds according to the invention can be used for the production of holographies, waveguides, optical switches wherein advantage is taken of the development of a difference in the index of refraction between irradiated and unirradiated areas.

[0189] The use of photocurable compositions for imaging techniques and for the optical production of information carriers is also important. In such applications, as already described above, the layer (wet or dry) applied to the support is irradiated imagewise, e.g. through a photomask, with UV or visible light, and the unexposed areas of the layer are removed by treatment with a developer. Application of the photocurable layer to metal can also be carried out by electrodeposition. The exposed areas are polymeric through crosslinking and are therefore insoluble and remain on the support. Appropriate colouration produces visible images. Where the support is a metallized layer, the metal can, following exposure and development, be etched away at the unexposed areas or reinforced by electroplating. In this way it is possible to produce electronic circuits and photoresists. When used in image-forming materials the novel photoinitiators provide excellent performance in generating so called printout images, whereby a color change is induced due to irradiation. To form such printout images different dyes and/or their leuco form are used and examples for such print out image systems can be found e.g. in WO96/41240, EP706091, EP511403, US3579339 and US4622286.

[0190] The novel photoinitiator is also suitable for a photopatternable composition for forming a dielectric layer of a multilayer layer circuit board produced by a sequential build-up process.

[0191] The invention, as described above, provides compositions, as well as a process, for producing pigmented and nonpigmented paints and varnishes, powder coatings, printing inks, printing plates, adhesives, pressure sensitive adhesives, dental compositions, gel coats, photoresists for electronics, etch resists, both liquid and dry films, solder resists, resists to manufacture color filters for a variety of display applications (a color filter resist contains pigments, pigments and dyes (i.e. hybrid systems) or dyes alone), resists to generate structures in the manufacturing processes of plasma-display panels (e.g. barrier rib, phosphor layer, electrode), electroluminescence displays and LCD (e.g. interlayer insulating layers, spacers, multi-spacers, microlens arrays), for encapsulating electrical and electronic components, for producing magnetic recording materials, micromechanical parts, waveguides, optical switches, plating masks, colour proofing systems, glass fibre cable coatings, screen printing stencils, three-dimensional objects by means of stereolithography, image recording materials for holographic recordings (e.g. for holographic data storage (HDS)), microelectronic circuits, decolorizing materials, formulations containing microcapsules, photoresist materials for a UV and visible laser direct imaging system and for forming dielectric layers in a sequential build-up layer of a printed circuit board; wherein the process comprises irradiating a composition as described above with electromagnetic radiation in the range from 150 to 600 nm, or with electron beam or with X-rays.

[0192] Substrates used for photographic information recordings include, for example, films of polyester, cellulose acetate or polymer-coated papers; substrates for offset printing forms are specially treated aluminium, substrates for producing printed circuits are copper-clad laminates, and substrates for producing integrated circuits are, for example, silicon wafers. The layer thickness of the photosensitive layer for photographic materials and offset printing forms is generally from about 0.5 μm to 10 μm , while for printed circuits it is from 0.1 μm to about 100 μm . Following the coating of the substrates, the solvent is removed, generally by drying, to leave a coat of the photoresist on the substrate.

[0193] Coating of the substrates can be carried out by applying to the substrate a liquid composition, a solution or a suspension. The choice of solvents and the concentration depend principally on the type of composition and on the coating technique. The solvent should be inert, i.e. it should not undergo a chemical reaction with the components and should be able to be removed again, after coating, in the course of drying. Examples of suitable solvents are ketones, ethers and esters, such as methyl ethyl ketone, isobutyl methyl ketone, cyclopentanone, cyclohexanone, N-methylpyrrolidone, dioxane, tetrahydrofuran, 2-methoxyethanol, 2-ethoxyethanol, 1-methoxy-2-propanol, 1,2-dimethoxyethane, ethyl acetate, n-butyl acetate, ethyl 3-ethoxypropionate, 2-methoxypropylacetate, methyl-3-methoxypropionate, 2-heptanone, 2-pentanone, and ethyl lactate. The solution is applied uniformly to a substrate by means of known coating techniques, for example by spin coating, dip coating, knife coating, curtain coating, brushing, spraying, especially by electrostatic spraying, and reverse-roll coating, and also by means of electrophoretic deposition. It is also possible to apply the photosensitive layer to a temporary, flexible support and then to coat the final substrate, for example a copper-clad circuit board, or a glass substrate by transferring the layer via lamination.

The quantity applied (coat thickness) and the nature of the substrate (layer support) are dependent on the desired field of application. The range of coat thicknesses generally comprises values from about 0.1 μm to more than 100 μm , for example 0.1 μm to 1 cm, preferably 0.5 μm to 1000 μm .

[0194] Following the coating of the substrates, the solvent is removed, generally by drying, to leave an essentially dry resist film of the photoresist on the substrate.

[0195] The photosensitivity of the novel compositions can extend in general from about 150 nm to 600 nm, for example 190-600 nm, (UV-vis region). Suitable radiation is present, for example, in sunlight or light from artificial light sources. Consequently, a large number of very different types of light sources are employed. Both point sources and arrays ("lamp carpets") are suitable. Examples are carbon arc lamps, xenon arc lamps, low-, medium-, high- and super high- pressure mercury lamps, possibly with metal halide dopes (metal-halogen lamps), microwave-stimulated metal vapour lamps, excimer lamps, superactinic fluorescent tubes, fluorescent lamps, argon incandescent lamps, electronic flashlights, photographic flood lamps, light emitting diodes (LED), electron beams and X-rays. The distance between the lamp and the substrate to be exposed in accordance with the invention may vary depending on the intended application and the type and output of lamp, and may be, for example, from 2 cm to 150 cm. Laser light sources, for example excimer lasers, such as F_2 excimer lasers at 157 nm exposure, KrF excimer lasers for exposure at 248 nm and ArF excimer lasers for exposure at 193 nm are also suitable. Lasers in the visible region can also be employed.

[0196] The term "imagewise" exposure includes both, exposure through a photomask comprising a predetermined pattern, for example a slide, a chromium mask, a stencil mask or a reticle, as well as exposure by means of a laser or light beam, which for example is moved under computer control over the surface of the coated substrate and in this way produces an image. Suitable UV laser exposure systems for the purpose are, for example, provided by Etec and Orbotech (DP-100™ DIRECT IMAGING SYSTEM). Other examples of laser light sources are, for example excimer lasers, such as F_2 excimer lasers at 157 nm exposure, KrF excimer lasers for exposure at 248 nm and ArF excimer lasers for exposure at 193 nm. Further suitable are solid state UV lasers (e.g. Gemini from ManiaBarco, DI-2050 from PENTAX) and violet laser diodes with 405 nm output (DI-2080, DI-PDP from PENTAX). Lasers in the visible region can also be employed.

And the computer-controlled irradiation can also be achieved by electron beams. It is also possible to use masks made of liquid crystals that can be addressed pixel by pixel to generate digital images, as is, for example, described by A. Bertsch, J.Y. Jezequel, J.C. Andre in *Journal of Photochemistry and Photobiology A: Chemistry* 1997, 107, p. 275-281 and by K.-P. Nicolay in *Offset Printing* 1997, 6, p. 34-37. Following the imagewise exposure of the material and prior to development, it may be advantageous to carry out thermal treatment for a short time. After the development a thermal post bake can be performed to harden the composition and to remove all traces of solvents. The temperatures employed are generally 50-250°C, preferably 80-220°C; the duration of the thermal treatment is in general between 0.25 and 60 minutes.

[0197] The photocurable composition may additionally be used in a process for producing printing plates or photoresists as is described, for example, in DE4013358. In such a process the composition is exposed for a short time to visible light with a wavelength of at least 400 nm, without a mask, prior to, simultaneously with or following imagewise irradiation. After the exposure and, if implemented, thermal treatment, the unexposed areas of the photosensitive coating are removed with a developer in a manner known per se.

[0198] As already mentioned, the novel compositions can be developed by aqueous alkalis or organic solvents. Particularly suitable aqueous-alkaline developer solutions are aqueous solutions of tetraalkylammonium hydroxides or of alkali metal silicates, phosphates, hydroxides and carbonates. Minor quantities of wetting agents and/or organic solvents may also be added, if desired, to these solutions. Examples of typical organic solvents, which may be added to the developer liquids in small quantities, are cyclohexanone, 2-ethoxyethanol, toluene, acetone and mixtures of such solvents. Depending on the substrate also solvents, e.g. organic solvents, can be used as developer, or, as mentioned above mixtures of aqueous alkalis with such solvents. Particularly useful solvents for solvent development include methanol, ethanol, 2-propanol, 1-propanol, butanol, diacetone alcohol, ethylene glycol monomethyl ether, ethylene glycol monoethyl ether, ethylene glycol mono-n-butyl ether, diethyleneglycol dimethyl ether, propyleneglycol monomethyl ether acetate, ethyl-3-ethoxypropionate, methyl-3-methoxypropionate, n-butyl acetate, benzyl alcohol, acetone, methyl ethyl ketone, cyclopentanone, cyclohexanone, 2-heptanone, 2-pentanone, epsilon-caprolactone, gamma-butyrolactone, dimethylformamide, dimethylacetamide, hexamethylphosphoramide, ethyl lactate, methyl lactate, epsilon-caprolactam, and N-methyl-pyrrolidinone. Optionally, water can be added to these solvents up to a level at which still a clear solution is obtained and at which sufficient solubility of the unexposed areas of the light sensitive composition is maintained.

[0199] The invention therefore also provides a process for the photopolymerization of compounds containing ethylenically unsaturated double bonds, i.e. monomeric, oligomeric or polymeric compounds containing at least one ethylenically unsaturated double bond, which comprises adding to these compounds at least one photoinitiator of the formula I as described above and irradiating the resulting composition with electromagnetic radiation, in particular light of the wavelength 150 to 600 nm, in particular 190-600 nm, with electron beam, or with X-rays.

In other words, adding to these compounds compounds containing ethylenically unsaturated double bonds at least one photoinitiator of the formula I as described above and irradiating the resulting composition with electromagnetic radiation, in particular light of the wavelength 150 to 600 nm, in particular 190-600 nm, with electron beam, or with X-rays.

[0200] The invention further provides a coated substrate which is coated on at least one surface with a composition as described above, and describes a process for the photographic production of relief images, in which a coated substrate is subjected to imagewise exposure and then the unexposed portions are removed with a developer. Imagewise exposure may be effected by irradiating through a mask or by means of a laser or electron beam as already described above. Of particular advantage in this context is the laser beam exposure already mentioned above.

[0201] The compounds of the invention have a good thermal stability, low volatility, good storage stability and high solubility, and are also suitable for photopolymerisations in the presence of air (oxygen). Further, they cause only low yellowing in the compositions after photopolymerization.


[0202] The examples which follow illustrate the invention in more detail, without restricting the scope said examples only. Parts and percentages are, as in the remainder of the description and in the claims, by weight, unless stated otherwise. Where alkyl radicals having more than three carbon atoms are referred to in the examples without any mention of specific isomers, the n-isomers are meant in each case.

Example 1 Synthesis of [9-(2-ethyl-hexyl)-6-(acetoxymino-o-tolyl-methyl)-9H-carbazol-3-yl]-(2,4,6-trimethyl-phenyl)-methanone

1.a Synthesis of [9-(2-ethyl-hexyl)-6-(2-methyl-benzoyl)-9H-carbazol-3-yl]-(2,4,6-trimethyl-phenyl)-methanone

[0203]

EP 2 847 167 B9




5

10 **[0204]** To 9-(2-ethyl-hexyl)-9H-carbazole (1.40 g; 5.00 mmol) in CH_2Cl_2 (50 mL) are added 2,4,6-trimethylbenzoyl chloride (0.91 g; 5.00 mmol) and AlCl_3 (0.69 g; 5.15 mmol) at 0°C . After stirring for 3 h at 0°C , AlCl_3 (0.69 g; 5.15 mmol) and *o*-toluoyl chloride (0.80 g; 5.15 mmol) are added at 0°C , and the mixture is stirred at room temperature overnight. The reaction mixture is poured into ice-water, and the crude product is extracted twice with CH_2Cl_2 . The combined organic layer is washed with H_2O and brine, dried over MgSO_4 , and concentrated and dried in vacuo to give a beige solid as a crude product (2.08 g). The product is used for the next reaction without further purification. The structure is confirmed by $^1\text{H-NMR}$ spectrum (CDCl_3). δ [ppm]: 0.81 (t, 3H), 0.92 (t, 3H), 1.21-1.42 (m, 8H), 2.05 (m, 1H), 2.13 (s, 6H), 2.34 (s, 3H), 4.20 (m, 2H), 6.94 (s, 2H), 7.27-7.37 (m, 4H), 7.41-7.45 (m, 3H), 7.98-8.02 (m, 2H), 8.56 (br, 1H), 8.57 (s, 1H).

20 1.b Synthesis of [9-(2-ethyl-hexyl)-6-(hydroxyimino-*o*-tolyl-methyl)-9H-carbazol-3-yl]-(2,4,6-trimethyl-phenyl)-methanone

[0205]



25


30

35 **[0206]** To [9-(2-ethyl-hexyl)-6-(2-methyl-benzoyl)-9H-carbazol-3-yl]-(2,4,6-trimethyl-phenyl)-methanone (2.00 g; 3.78 mmol) in pyridine (10 mL) are added hydroxylammonium chloride (0.52 g; 7.55 mmol) at 120°C , and then the mixture is stirred at 120°C overnight. After it is cooled at room temperature, the reaction mixture is poured into water, and the crude product is extracted twice with CH_2Cl_2 . The combined organic layer is washed with water and brine and dried over MgSO_4 . After CH_2Cl_2 is removed by concentration, the crude product is recrystallized with a mixed solvent of CH_2Cl_2 (2 mL) and *n*-hexane (10 mL) to give a beige solid. It is collected by filtration, and washed with *n*-hexane, and then it is dried to give a beige solid (0.66 g; 31%). The product is composed of an isomeric mixture, and the structure is confirmed by $^1\text{H-NMR}$ spectrum (CDCl_3). δ [ppm]: 0.82 (m), 1.25 (m), 2.02 (m), 2.12 (s), 2.25 (s), 2.36 (s), 4.20 (m), 6.92 (s), 7.20 (d), 7.33-7.745 (m), 7.65 (br), 7.89 (br), 8.16 (s), 8.55 (br).

40

45 1.c Synthesis of [9-(2-Ethyl-hexyl)-6-(acetoxyimino-*o*-tolyl-methyl)-9H-carbazol-3-yl]-(2,4,6-trimethyl-phenyl)-methanone

[0207]



50













55

[0208] To [9-(2-ethyl-hexyl)-6-(hydroxyimino-o-tolyl-methyl)-9H-carbazol-3-yl]-(2,4,6-trimethylphenyl)-methanone in AcOEt (ethyl acetate) (5 mL) are added triethylamine (0.36 g; 3.54 mmol) and acetyl chloride (0.28 g; 3.54 mmol) at 0 °C. Then the mixture is stirred at 0 °C for 1 h. The reaction mixture is poured into ice-water, and the crude product is extracted with AcOEt. The combined organic layer is washed with H₂O and brine, dried over MgSO₄, and concentrated and dried in vacuo to give a yellow resin as a crude product. The crude product is composed of an isomeric mixture according to ¹H-NMR spectrum. The crude product is purified by column chromatography on silica gel eluting with a mixed solvent of CH₂Cl₂ and *n*-hexane (4:1) to obtain a pale yellow solid (0.49 g, 69%). The structure is confirmed by ¹H-NMR spectrum (CDCl₃). δ [ppm]: 0.82 (t, 3H), 0.92 (t, 3H), 2.02 (m, 1H), 2.06 (s, 3H), 2.12 (s, 6H), 2.19 (s, 3H), 2.36 (s, 3H), 4.20 (m, 2H), 6.93 (s, 2H), 7.14 (dd, 1H), 7.30-7.43 (m, 5H), 7.71 (br, 1H), 8.00 (br, 1H), 8.32 (br, 1H), 8.52 (br, 1H).



















Examples 2-11

[0209] In case of the compounds of example 2-5, the corresponding di-ketone intermediates are prepared according to the procedure as described in example 1.a with the corresponding aryl chloride using 9-(2-ethyl-hexyl)-9H-carbazole or 9-ethyl-9H-carbazole as a starting material, and then the oxime and the oxime ester are prepared according to the procedures as disclosed in examples 1.b and 1.c. In case of the compound of example 6, the corresponding di-ketone is prepared by reaction of [6-(2-chloromethylbenzoyl)-9-ethyl-9H-carbazol-3-yl]-(2,4,6-trimethyl-phenyl)-methanone with ethyl mercaptoacetate, and then the oxime and the oxime ester are prepared according to the procedures as disclosed in examples 1.b and 1.c. The corresponding diketone intermediates of the compounds of examples 7-11 are prepared by reacting mono- or difluorinated diketone intermediate with the corresponding nucleophiles. Then, the oxime and the oxime ester are prepared according to the procedures as disclosed in examples 1.b and 1.c. The compounds of the examples 2, 3, 5, 6, 7, 9 and 11 are obtained as an isomeric mixture, but the compounds of the other examples are obtained as a single component.

Table 1

Example	Ar ₁	Ar ₂	R	¹ H-NMR δ [ppm]
2				1.48 (t, 3H), 2.12 (s, 6H), 2.18 (s, 3H), 2.36 (s, 3H), 4.38 (q, 2H), 6.93 (s, 2H), 7.13 (d, 1H), 7.28-7.45 (m, 5H), 7.73 (br, 1H), 7.99 (br, 1H), 8.34 (br, 1H), 8.52 (br, 1H)
3				0.80-0.98(m), 1.18-1.48(m), 2.01(s), 2.05(m), 2.16(s), 2.18(s), 2.22(s), 3.72 (s), 4.17(m), 6.67(d), 7.14(d), 7.20-7.44 (m), 7.59(d), 7.66(d), 7.97(d), 8.05(d), 8.21(s), 8.33(s), 8.54(s), 8.61(s)
4				0.78-0.96(m), 1.18-1.45(m), 2.03(m), 2.10(s), 2.12(s), 2.35(s), 4.19(m), 6.93 (s), 7.37-7.44(m), 7.56(d), 7.68(br), 8.00 (br), 8.24(br), 8.40(d), 8.52(br)
5				0.82-0.98(m), 1.20-1.48(m), 2.05(s), 2.06(s), 2.13(s), 2.16(s), 2.23(s), 2.36(s), 4.22(m), 6.93(s), 7.15(d), 7.23-7.45(m), 7.46-7.59(m), 7.95(br), 8.20(s), 8.41(br), 8.56(br)


(continued)

Example	Ar ₁	Ar ₂	R	¹ H-NMR δ [ppm]
6				1.21 (t), 1.46 (t), 2.05 (s), 2.12 (s), 2.36 (s), 3.06 (d), 3.71 (d), 4.09 (q), 4.40 (m), 6.93 (s), 7.20 (d), 7.36-7.42 (m), 7.50 (t), 7.61 (d), 7.73 (br), 8.00 (br), 8.22 (s), 8.35 (br), 8.52 (br)
7				0.81-1.02(m), 1.10-1.52(m), 2.04(m), 2.08(s), 2.12(s), 2.16(s), 2.35(s), 3.24 (m), 3.32(m), 3.86(m), 3.89(m), 4.19(m), 4.22(m), 6.84(d), 6.92(s), 6.96(d), 6.96 (d), 7.34-7.54(m), 7.74(br), 7.98(s), 8.04 (br), 8.25(s), 8.48(br)
8				1.46(t), 2.08(s), 2.12(s), 2.36(s), 3.18(s), 3.48(t), 3.50(s), 3.81(t), 4.04(t), 4.21(t), 4.38(q), 6.60(d), 6.67(s), 6.93(s), 7.04 (d), 7.36(d), 7.40(d), 7.74(br), 8.04(br), 8.33(s), 8.50(br)
9				1.48(t), 2.12(s), 2.19(s), 2.36(s), 4.11(t), 4.42(q), 5.03(m), 6.88(d), 6.93(s), 7.18 (t), 7.41(d), 7.48(d), 7.49(d), 7.61(d), 7.72(d), 7.93(br), 8.08(s), 8.55(br)
10				1.46(t), 2.07(s), 2.09(s), 2.12(s), 2.36(s), 4.38-4.45(m), 6.93(s), 7.07(d), 7.20(d), 7.38(d), 7.53(m), 7.78(br), 7.96(br), 8.25 (br), 8.55(br)
11				1.44(t), 2.06(s), 2.11(s), 2.19(s), 2.36(s), 3.90(t), 4.20-4.50(m), 6.93(s), 7.07(d), 7.20(d), 7.30-7.56(m), 7.60(d), 7.63(d), 7.82(br), 8.12(br), 8.25(br), 8.56(br)

Example 12 [1-[4-[3-[N-acetoxy-C-phenyl-carbonimidoyl]-6-(2,4,6-trimethylbenzoyl)carbazol-9-yl]phenyl]ethylideneamino]acetate

12.a 1-(4-carbazol-9-ylphenyl)ethanone


[0210]



[0211] To carbazole (5.02g; 30.0 mmol) in DMSO (50 mL) is added 4-fluoroacetophenone (3.45 g; 25.0 mmol) and K₂CO₃ (10.4 g; 75.2 mmol), and the mixture is stirred at 135°C overnight. The mixture is poured into water to afford a precipitate, which is isolated by filtration and washed with water. The crude product thus obtained is further purified by recrystallization from TBME (tert-butyl methyl ether), giving the product as a light brown solid. The structure is confirmed by the ¹H-NMR spectrum (CDCl₃). δ [ppm]: 2.71 (s), 7.32 (d), 7.41-7.50 (m), 7.72 (d), 8.15 (d), 8.21 (d).

12.b 1-[4-[3-benzoyl-6-(2,4,6-trimethylbenzoyl)carbazol-9-yl]phenyl]ethanone


[0212]



5
10
15 **[0213]** To 1-(4-carbazol-9-ylphenyl)ethanone (5.73 g; 20.0 mmol) in CH_2Cl_2 (50 mL) are added 2,4,6-trimethylbenzoyl chloride (3.84g; 21.0 mmol) and AlCl_3 (5.60 g, 42.0 mmol) at 0 °C. After stirring overnight at room temperature, AlCl_3 (2.80 g, 21.0 mmol) and benzoyl chloride (2.95 g, 21.0 mmol) are added at 0 °C, and the mixture is stirred at room temperature overnight. The reaction mixture is poured into ice-water, and the crude product is extracted twice with CH_2Cl_2 . The combined organic layer is washed with water and brine, dried over MgSO_4 . After CH_2Cl_2 is removed by concentration, the crude product is purified by column chromatography on silica gel eluting with a mixed solvent of CH_2Cl_2 and *n*-hexane (1:1) to obtain a pale white solid (2.25 g, 21%). The structure is confirmed by $^1\text{H-NMR}$ spectrum (CDCl_3). δ [ppm]: 2.14 (s), 2.39 (s), 2.72 (s), 6.94 (s), 7.43-7.58 (m), 7.58-7.68 (m), 7.70- 7.80 (m), 7.82-7.89 (m), 7.97 (d), 8.02 (d), 8.11 (d), 8.26 (d), 8.28 (d), 8.60 (br), 8.64 (s).

25 **12.c** [9-[4-[N-hydroxy-C-methyl-carbonimidoyl]phenyl]-6-[N-hydroxy-C-phenyl-carbonimidoyl]carbazol-3-yl]-(2,4,6-trimethylphenyl)methanone

[0214]




30
35
40 **[0215]** To 1-[4-[3-benzoyl-6-(2,4,6-trimethylbenzoyl)carbazol-9-yl]phenyl]ethanone (1.10 g; 2.00 mmol) in pyridine (5 mL) is added hydroxylammonium chloride (0.81 g; 12.0 mmol) at 100 °C, and then the mixture is stirred at 100 °C overnight. After it is cooled at room temperature, the reaction mixture is poured into water, and the crude product is extracted twice with AcOEt (ethyl acetate). The combined organic layer is washed with water and brine and dried over MgSO_4 . After AcOEt is removed by concentration, the crude product is purified by column chromatography on silica gel eluting with a mixed solvent of AcOEt and *n*-hexane (1:2) to obtain a pale white solid (2.48 g, 22%). The product is composed of an isomeric mixture, and the structure is confirmed by $^1\text{H-NMR}$ spectrum (CDCl_3). δ [ppm]: 2.12 (s), 2.33 (s), 2.40 (s), 6.88 (s), 7.30-7.66 (m), 7.88 (d), 7.90 (d), 7.99 (br), 8.20 (s), 8.55 (br).

50 **12.d** [1-[4-[3-[N-acetoxy-C-phenyl-carbonimidoyl]-6-(2,4,6-trimethylbenzoyl)carbazol-9-yl]phenyl]ethylideneamino] acetate

[0216]

55




[0217] To [9-[4-[N-hydroxy-C-methyl-carbonimidoyl]phenyl]-6-[N-hydroxy-C-phenyl-carbonimidoyl]carbazol-3-yl]-(2,4,6-trimethylphenyl)methanone (0.24 g; 0.42 mmol) in AcOEt (5 mL) are added triethylamine (0.43 g; 4.24 mmol) and acetyl chloride (0.34 g; 4.24 mmol) at 0 °C. Then the mixture is stirred at 0 °C for 3 hours. The reaction mixture is poured into ice-water, and the crude product is extracted with AcOEt. The combined organic layer is washed with H₂O and brine, dried over MgSO₄, and concentrated. The crude product is purified by column chromatography on silica gel eluting with a mixed solvent of AcOEt and *n*-hexane (1:1) to obtain a pale yellow solid (0.28 g, 74%). The product is composed of an isomeric mixture, and the structure is confirmed by ¹H-NMR spectrum (CDCl₃). δ [ppm]: 2.11 (s), 2.13 (s), 2.31 (s), 2.32 (s), 2.35 (s), 2.36 (s), 2.50 (s), 2.51 (s), 6.93 (s), 6.94 (s), 7.31-7.54 (m), 7.58-7.69 (m), 7.98 (br), 8.01-8.08 (m), 8.41 (s), 8.55 (br).

Reference Example 13 [[2-[6-[2-[N-acetoxy-C-[9-ethyl-6-(2,4,6-trimethylbenzoyl)carbazol-3-yl]carbonimidoyl]phenoxy]-2,2,3,3,4,4,5,5-octafluoro-hexoxy]phenyl]-[9-ethyl-6-(2,4,6-trimethylbenzoyl)carbazol-3-yl]methylene]amino acetate

13.a [9-ethyl-6-(2,4,6-trimethylbenzoyl)carbazol-3-yl]-(2-fluorophenyl)methanone

[0218]




[0219] To 9-ethyl-9H-carbazole (8.50 g; 43.5 mmol) in CH₂Cl₂ (200 mL) are added 2,4,6-trimethylbenzoyl chloride (8.35g; 45.7 mmol) and AlCl₃ (6.37 g; 47.8 mmol) at 0 °C. After stirring for 20 minutes, AlCl₃ (6.53 g; 48.9 mmol) is added and 2-fluorobenzoyl chloride (7.26 g; 45.7 mmol) is added dropwise, and then the mixture is stirred at room temperature for 5 hours. The reaction mixture is poured into ice-water, and the crude product is extracted twice with CH₂Cl₂. The combined organic layer is washed with water and brine, dried over MgSO₄. After 100 mL of *n*-hexane is added there, CH₂Cl₂ is removed by concentration to give a white solid. It is collected by filtration, and washed with *n*-hexane, and then it is dried to give a white solid (17.82 g; 88%). The structure is confirmed by ¹H-NMR spectrum (CDCl₃). δ [ppm]: 1.49 (t), 2.13 (s), 2.38 (s), 4.42 (q), 6.94 (s), 7.21 (t), 7.32 (t), 7.44 (d), 7.46 (d), 7.53-7.62 (m), 8.25 (br), 8.04 (d), 8.56 (br), 8.60 (s); ¹⁹F-NMR spectrum (CDCl₃). δ [ppm]: -111.75.

13.b [2-[6-[2-[9-ethyl-6-(2,4,6-trimethylbenzoyl)carbazole-3-carbonyl]phenoxy]-2,2,3,3,4,4,5,5-octafluoro-hexoxy]phenyl]-[9-ethyl-6-(2,4,6-trimethylbenzoyl)-carbazol-3-yl]methanone

[0220]


EP 2 847 167 B9



[0221] To [9-ethyl-6-(2,4,6-trimethylbenzoyl)carbazol-3-yl]-(2-fluorophenyl)methanone (1.86 g; 4.01 mmol) in pyridine (10 mL) are added 2,2,3,3,4,4,5,5-octafluoro-1,6-hexanediol (0.47 g; 1.8 mmol) and sodium hydroxide (0.24 g; 6.0 mmol) at 80 °C. The mixture is stirred overnight. The reaction mixture is poured into ice-water, the crude product is extracted twice with AcOEt. The combined organic layer is washed with water and brine, dried over MgSO₄. After AcOEt is removed by concentration, the crude product is recrystallized with a mixed solvent of CH₂Cl₂ (2 mL) and *n*-hexane (10 mL) to give a beige solid. It is collected by filtration, and washed with *n*-hexane, and then it is dried to give a beige solid (0.44 g; 21%). The product is composed of an isomeric mixture, and the structure is confirmed by ¹H-NMR spectrum (CDCl₃). δ [ppm]: 1.42 (t), 2.10 (s), 2.37 (s), 4.22 (t), 4.35 (q), 6.92 (s), 7.19 (t), 7.34-7.50 (m), 7.92 (s), 7.94 (br), 8.50 (s), 8.51 (br).

13.c [9-ethyl-6-[C-[2-[6-[2-[C-[9-ethyl-6-(2,4,6-trimethylbenzoyl)carbazol-3-yl]-N-hydroxy-carbonimidoyl]phenoxy]-2,2,3,3,4,4,5,5-octafluoro-hexoxy]phenyl]-N-hydroxy-carbonimidoyl]carbazol-3-yl]-(2,4,6-trimethylphenyl)methanone


[0222]



[0223] To [2-[6-[2-[9-ethyl-6-(2,4,6-trimethylbenzoyl)carbazole-3-carbonyl]phenoxy]-2,2,3,3,4,4,5,5-octafluoro-hexoxy]phenyl]-[9-ethyl-6-(2,4,6-trimethylbenzoyl)carbazol-3-yl]methanone (0.44 g; 0.38 mmol) in pyridine (5 mL) are added hydroxylammonium chloride (0.16 g; 2.30 mmol) at 100 °C, and then the mixture is stirred at 100 °C overnight. After it is cooled at room temperature, the reaction mixture is poured into water, and the crude product is extracted twice with AcOEt (ethyl acetate). The combined organic layer is washed with water and brine and dried over MgSO₄. After AcOEt is removed by concentration, the crude product is purified by column chromatography on silica gel eluting with a mixed solvent of AcOEt and *n*-hexane (1:1) to obtain a pale white solid (0.28 g, 63%). The product is composed of an isomeric mixture, and the structure is confirmed by ¹H-NMR spectrum (CDCl₃). δ [ppm]: 1.23 (t), 2.11 (m), 2.32 (s), 2.35 (s), 4.32-4.64 (m), 6.91 (s), 7.06-7.42 (m), 7.42 (d), 7.46-7.56 (m), 7.75 (br), 7.80-7.91 (m), 7.93 (s), 8.00 (s), 8.37 (s), 8.63 (br).

13.d [[2-[6-[2-[N-acetoxy-C-[9-ethyl-6-(2,4,6-trimethylbenzoyl)carbazol-3-yl]carbonimidoyl]phenoxy]-2,2,3,3,4,4,5,5-octafluoro-hexoxy]phenyl]-[9-ethyl-6-(2,4,6-trimethylbenzoyl)carbazol-3-yl]methylene]amino acetate


[0224]



[0225] To [9-ethyl-6-[C-[2-[6-[2-[C-[9-ethyl-6-(2,4,6-trimethylbenzoyl)carbazol-3-yl]-N-hydroxycarbonimidoyl]phenoxy]-2,2,3,3,4,4,5,5-octafluoro-hexoxy]phenyl]-N-hydroxy-carbonimidoyl]carbazol-3-yl]-(2,4,6-trimethylphenyl)methanone (0.28 g; 0.24 mmol) in AcOEt (5 mL) are added triethylamine (0.24 g; 2.4 mmol) and acetyl chloride (0.19 g; 2.4 mmol) at 0 °C. Then the mixture is stirred at 0 °C for 4 hours. The reaction mixture is poured into ice-water, and the crude product is extracted with AcOEt. The combined organic layer is washed with H₂O and brine, dried over MgSO₄, and concentrated. The crude product is purified by column chromatography on silica gel eluting with a mixed solvent of AcOEt and *n*-hexane (1:1) to obtain a pale yellow solid (0.16 g, 54%). The product is composed of an isomeric mixture, and the structure is confirmed by ¹H-NMR spectrum (CDCl₃). δ [ppm]: 1.22(m), 2.01(s), 2.08(s), 2.11(s), 2.16(s), 2.34(s), 2.35(s), 4.05(t), 4.33(m), 6.80(m), 6.92(s), 6.98(m), 7.16(s), 7.28-7.54(m), 7.60(d), 7.64(d), 7.71(br), 7.95(br), 8.02(s), 8.28(br), 8.52(br).

Reference Example 14 [[2-[6-[2-[N-acetoxy-C-[9-ethyl-6-(2,4,6-trimethylbenzoyl)carbazol-3-yl]carbonimidoyl]phenoxy]hexoxy]phenyl]-[9-ethyl-6-(2,4,6-trimethylbenzoyl)carbazol-3-yl]methylene]amino acetate


[0226]



[0227] The corresponding dimer intermediate of diketone is prepared according to the procedure as disclosed in example 13.b with 1,6-hexanediol instead of 2,2,3,3,4,4,5,5-octafluoro-1,6-hexanediol, and then the oxime and oxime ester are prepared the same procedure as 13.c and 13.d respectively. The structure is confirmed by ¹H-NMR spectrum (CDCl₃). δ [ppm]: 0.78(m), 1.15(m), 1.39(t), 2.00(s), 2.10(s), 2.35(s), 3.60(m), 4.31(q), 6.85(d), 6.92(s), 7.03(t), 7.12(d), 7.28(d), 7.32-7.42(m), 7.65(br), 7.96(br), 8.30(br), 8.50(br).

Reference Example 15 [[4-[6-[4-[N-acetoxy-C-[9-ethyl-6-(2,4,6-trimethylbenzoyl)carbazol-3-yl]carbonimidoyl]phenoxy]-2,2,3,3,4,4,5,5-octafluoro-hexoxy]phenyl]-[9-ethyl-6-(2,4,6-trimethylbenzoyl)carbazol-3-yl]methylene]amino acetate

[0228]



[0229] The corresponding diketone intermediate is prepared according to the procedure as disclosed in example 13.a with 4-fluorobenzoyl chloride instead of 2-fluorobenzoyl chloride, and then the dimer of diketone, oxime and oxime ester are prepared the same procedure as 13.b, 13.c and 13.d respectively. The product is composed of an isomeric mixture,


EP 2 847 167 B9

and the structure is confirmed by $^1\text{H-NMR}$ spectrum (CDCl_3). δ [ppm]: 1.47(t), 1.52(t), 2.10(s), 2.12(s), 2.34(s), 3.38(t), 4.36-4.66(m), 6.90-6.98(m), 7.04-7.12(m), 7.14-7.48(m), 7.50(s), 7.60(d), 7.72(br), 8.01(s), 8.04(br), 8.28(br), 8.52(br).

Reference Example 16 [[9-[2-[2-[2-[3-[N-acetoxy-C-(o-tolyl)carbonimidoyl]-6-(2,4,6-trimethylbenzoyl)carbazol-9-yl]ethoxy]ethoxy]ethyl]-6-(2,4,6-trimethylbenzoyl)carbazol-3-yl]-(o-tolyl)methylene]amino acetate

16.a o-Tolyl-[6-(2,4,6-trimethylbenzoyl)-9H-carbazol-3-yl]methanone


[0230]



[0231] To 9-benzyl-9H-carbazole (2.50 g; 9.72 mmol) in CH_2Cl_2 (50 mL) are added 2,4,6-trimethylbenzoyl chloride (1.86g; 10.2 mmol) and AlCl_3 (1.48 g; 11.1 mmol) at 0°C . After stirring for 2 hours, AlCl_3 (1.55 g; 11.6 mmol) is added and o-toluoyl chloride (1.58 g; 10.2 mmol) is added dropwise, and then the mixture is stirred at room temperature overnight. To the mixture AlCl_3 (1.51 g; 11.3 mmol) is added, and the reaction mixture is stirred for 1 hour at 50°C . The reaction mixture is poured into ice-water, and the crude product is extracted twice with CH_2Cl_2 . The combined organic layer is washed with water and brine, dried over MgSO_4 . After CH_2Cl_2 is removed by concentration, the crude product is purified by column chromatography on silica gel eluting with CH_2Cl_2 to obtain a white solid (2.23 g, 53%). The structure is confirmed by $^1\text{H-NMR}$ spectrum (CDCl_3). δ [ppm]: 2.00 (s), 2.22 (s), 2.31 (s), 6.96 (s), 7.25 (t), 7.31 (d), 7.36 (d), 7.41 (t), 7.43 (t), 7.45 (t), 7.61 (t), 7.63 (d), 7.73 (br), 7.78 (d), 7.79 (d), 8.54 (s), 8.55 (s).

16.b [9-[2-[2-[2-[3-(2-methylbenzoyl)-6-(2,4,6-trimethylbenzoyl)carbazol-9-yl]ethoxy]-ethoxy]ethyl]-6-(2,4,6-trimethylbenzoyl)carbazol-3-yl]-(o-tolyl)methanone


[0232]



[0233] To o-Tolyl-[6-(2,4,6-trimethylbenzoyl)-9H-carbazol-3-yl]methanone (1.62 g; 3.76 mmol) in DMA (20 mL) are added triethylene glycol bis(p-toluenesulfonate) (0.90 g; 2.0 mmol) and potassium parbonate (1.11 g; 8.39 mmol). After stirring overnight at room temperature, the reaction mixture is poured into ice-water, and the crude product is extracted twice with AcOEt. The combined organic layer is washed with water and brine, dried over MgSO_4 . After AcOEt is removed by concentration, the crude product is purified by column chromatography on silica gel eluting with CH_2Cl_2 to obtain a white solid (1.60 g, 87%). The structure is confirmed by $^1\text{H-NMR}$ spectrum (CDCl_3). δ [ppm]: 2.01 (s), 2.24 (s), 2.33 (s), 3.33 (s), 3.72 (t), 4.37 (t), 6.92 (s), 7.16-7.44 (m), 7.86-8.04 (m), 8.50 (s), 8.53 (s).

16.c [6-[N-hydroxy-C-(o-tolyl)carbonimidoyl]-9-[2-[2-[2-[3-[N-hydroxy-C-(o-tolyl)carbonimidoyl]-6-(2,4,6-trimethylbenzoyl)carbazol-9-yl]ethoxy]ethoxy]ethyl]carbazol-3-yl]-(2,4,6-trimethylphenyl)methanone


[0234]



[0235] To [9-[2-[2-[2-[3-(2-methylbenzoyl)-6-(2,4,6-trimethylbenzoyl)carbazol-9-yl]ethoxy]ethoxy]ethyl]-6-(2,4,6-trimethylbenzoyl)carbazol-3-yl]-(o-tolyl)methanone (1.50 g; 1.53 mmol) in pyridine (10 mL) is added hydroxylammonium chloride (7.32 g; 12.0 mmol) at 120 °C, and then the mixture is stirred at 120 °C overnight. After it is cooled at room temperature, the reaction mixture is poured into water, and the crude product is extracted twice with AcOEt (ethyl acetate). The combined organic layer is washed with water and brine and dried over MgSO₄. After AcOEt is removed by concentration, the crude product is purified by column chromatography on silica gel eluting with a mixed solvent of CH₂Cl₂ and AcOEt (5:1) to obtain a white solid (0.50 g, 33%). The structure is confirmed by ¹H-NMR spectrum (CDCl₃). δ [ppm]: 2.07 (s), 2.21 (s), 2.35 (s), 3.33 (s), 3.68 (t), 4.32 (t), 6.90 (s), 7.15 (d), 7.26-7.40 (m), 7.69 (br), 7.87 (br), 8.07 (s), 8.53 (br).

16.d [9-[2-[2-[2-[3-[N-acetoxy-C-(o-tolyl)carbonimidoyl]-6-(2,4,6-trimethylbenzoyl)-carbazol-9-yl]ethoxy]ethoxy]ethyl]-6-(2,4,6-trimethylbenzoyl)carbazol-3-yl]-(o-tolyl)methylene]amino acetate

[0236]




[0237] To [6-[N-hydroxy-C-(o-tolyl)carbonimidoyl]-9-[2-[2-[2-[3-[N-hydroxy-C-(o-tolyl)carbonimidoyl]-6-(2,4,6-trimethylbenzoyl)carbazol-9-yl]ethoxy]ethoxy]ethyl]carbazol-3-yl]-(2,4,6-trimethylphenyl)methanone (0.50 g; 0.50 mmol) in THF (5 mL) are added triethylamine (0.20 g; 2.0 mmol) and acetyl chloride (0.15 g; 1.9 mmol) at 0 °C. Then the mixture is stirred at 0 °C for 1.5 hours. The reaction mixture is poured into ice-water, and the crude product is extracted with AcOEt. The combined organic layer is washed with H₂O and brine, dried over MgSO₄, and concentrated. The crude product is purified by column chromatography on silica gel eluting AcOEt to obtain a white solid (0.36 g, 67%). The structure is confirmed by ¹H-NMR spectrum (CDCl₃). δ [ppm]: 2.09 (s), 2.15 (s), 2.17 (s), 2.35 (s), 3.31 (s), 3.69 (t), 4.32 (t), 6.91 (s), 7.09 (d), 7.26-7.41 (m), 7.66 (br), 7.96 (br), 8.31 (br), 8.49 (br).

Reference Example 17 [[6-[2-[2-[2-[2-[6-[N-acetoxy-C-(o-tolyl)carbonimidoyl]-9-ethylcarbazole-3-carbonyl]-3-ethoxyphenoxy]ethoxy]ethoxy]ethoxy]-6-ethoxybenzoyl]-9-ethyl-carbazol-3-yl]-(o-tolyl)methylene]amino acetate

17.a ethyl 2-ethoxy-6-[2-[2-[2-(3-ethoxy-2-ethoxycarbonyl-phenoxy)ethoxy]-ethoxy]ethoxy]benzoate

[0238]




EP 2 847 167 B9

[0239] To ethyl 6-ethoxy-2-hydroxybenzoate (5.00 g; 23.8 mmol) in DMA (50 mL) are added triethylene glycol bis(p-toluenesulfonate) (5.48 g; 12.0 mmol) and potassium parbonate (9.86 g; 71.4 mmol). After stirring at 80 °C for 3 hours, the reaction mixture is poured into water, and the crude product is extracted twice with AcOEt. The combined organic layer is washed with water and brine, dried over MgSO₄. After AcOEt is removed by concentration and dried under vacuo, a white solid is obtained (2.62 g, 34%). The structure is confirmed by ¹H-NMR spectrum (CDCl₃). δ [ppm]: 1.30-1.39 (m), 3.68 (s), 3.81 (t), 4.04 (q), 4.14 (t), 4.36 (q), 6.53 (d), 7.22 (t)

17.b 2-[2-[2-[2-(2-carboxy-3-ethoxy-phenoxy)ethoxy]ethoxy]ethoxy]-6-ethoxybenzoic acid


[0240]



[0241] To ethyl 2-ethoxy-6-[2-[2-[2-(3-ethoxy-2-ethoxycarbonyl-phenoxy)ethoxy]ethoxy]ethoxy]benzoate (2.60 g; 4.89 mmol) in a mixed solvent of methanol (30 mL) and H₂O (60 mL) is added sodium hydroxide (4.08 g; 102 mmol). After stirring at 100 °C overnight, the reaction mixture is cooled at room temperature. The mixture is acidified with concentrated hydrochloric acid to pH= 3.0 and the crude product is extracted twice with AcOEt. The combined organic layer is washed with water and brine, dried over MgSO₄. After AcOEt is removed by concentration, the crude product is purified by column chromatography on silica gel eluting with AcOEt to obtain a white solid (0.83 g, 35%). The structure is confirmed by ¹H-NMR spectrum (CDCl₃). δ [ppm]: 1.44 (t), 3.88 (s), 3.91 (t), 4.09-4.20 (m), 6.53 (d), 6.59 (d), 7.28 (t).

17.c [6-[2-ethoxy-6-[2-[2-[2-(3-ethoxy-2-[9-ethyl-6-(2-methylbenzoyl)carbazole-3-carbonyl]phenoxy]ethoxy]ethoxy]ethoxy]benzoyl]-9-ethyl-carbazol-3-yl]-(o-tolyl)methanone

[0242]




[0243] To 2-[2-[2-[2-(2-carboxy-3-ethoxy-phenoxy)ethoxy]ethoxy]ethoxy]-6-ethoxy-benzoic acid (0.83 g; 1.7 mmol) in CH₂Cl₂ (10 mL) are added oxalyl chloride (0.68 g; 5.36 mmol) and 1 drop o DMF. After stirring for 2 hours, CH₂Cl₂ is removed by concentration, and the crude product is dried under vacuo. To 9-ethyl-9H-carbazol (0.68 g, 3.5 mmol) in CH₂Cl₂ are added AlCl₃ (0.51 g; 3.8 mmol) and o-toluoyl chloride (0.56 g; 3.6 mmol) at 0°C. After stirring for 1 hour, AlCl₃ (0.58 g; 4.3 mmol) and the acid chloride prepared above are added at 0°C, and then the mixture is stirred at room temperature for 3 hours. The reaction mixture is poured into ice-water, and the crude product is extracted twice with CH₂Cl₂. The combined organic layer is washed with water and brine, dried over MgSO₄. After CH₂Cl₂ is removed by concentration, the crude product is purified by column chromatography on silica gel eluting with a mixed solvent of CH₂Cl₂ and AcOEt (5:1) to obtain a white solid (1.04 g, 56%). The structure is confirmed by ¹H-NMR spectrum (CDCl₃). δ [ppm]: 1.13 (t), 1.43 (t), 2.31 (s), 2.93 (s), 3.30 (t), 3.88 (t), 4.00 (q), 4.35 (q), 6.54 (d), 6.63 (d), 7.24-7.44 (m), 7.94 (d), 7.97 (d), 8.53 (s).

17.d [2-ethoxy-6-[2-[2-[2-[3-ethoxy-2-[9-ethyl-6-[N-hydroxy-C-(o-tolyl)carbonimidoyl]carbazole-3-carbonyl]phenoxy]ethoxy]ethoxy]ethoxy]phenyl]-[9-ethyl-6-[N-hydroxy-C-(o-tolyl)carbonimidoyl]carbazol-3-yl]methanone

[0244]

5

10



15

20


[0245] To[6-[2-ethoxy-6-[2-[2-[2-[3-ethoxy-2-[9-ethyl-6-(2-methylbenzoyl)]carbazole-3-carbonyl]phenoxy]ethoxy]ethoxy]benzoyl]-9-ethyl-carbazol-3-yl]-(o-tolyl)methanone (1.03 g; 0.935 mmol) in pyridine (10 mL) is added hydroxylammonium chloride (0.41 g; 5.8 mmol) at 120 °C, and then the mixture is stirred at 120 °C overnight. After it is cooled at room temperature, the reaction mixture is poured into water, and the crude product is extracted twice with AcOEt (ethyl acetate). The combined organic layer is washed with water and brine and dried over MgSO₄. After AcOEt is removed by concentration, the crude product is purified by column chromatography on silica gel eluting with a mixed solvent of CH₂Cl₂ and AcOEt (3:1) to obtain a white solid (0.45 g, 44%). The structure is confirmed by ¹H-NMR spectrum (CDCl₃). δ [ppm]: 1.12 (t), 1.37 (t), 2.22 (s), 2.92 (s), 3.29 (t), 3.88 (t), 3.97 (q), 4.27 (q), 6.53 (d), 6.61 (d), 7.17 (d), 7.24-7.40 (m), 7.58 (d), 7.88 (d), 8.16 (s), 8.54 (s).

25

17.e [[6-[2-[2-[2-[2-[6-[N-acetoxy-C-(o-tolyl)carbonimidoyl]-9-ethyl-carbazole-3-carbonyl]-3-ethoxy-phenoxy]ethoxy]ethoxy]ethoxy]-6-ethoxy-benzoyl]-9-ethyl-carbazol-3-yl]-(o-tolyl)methylene]amino acetate

30

35



40

45

[0247] To[2-ethoxy-6-[2-[2-[2-[3-ethoxy-2-[9-ethyl-6-[N-hydroxy-C-(o-tolyl)carbonimidoyl]carbazole-3-carbonyl]phenoxy]ethoxy]ethoxy]ethoxy]phenyl]-[9-ethyl-6-[N-hydroxy-C-(o-tolyl)carbonimidoyl]carbazol-3-yl]methanone (0.42 g; 0.38 mmol) in THF (10 mL) are added triethylamine (0.12 g; 1.2 mmol) and acetyl chloride (0.15 g; 1.9 mmol) at 0 °C. Then the mixture is stirred at 0 °C for 2 hours. The reaction mixture is poured into ice-water, and the crude product is extracted with AcOEt. The combined organic layer is washed with H₂O and brine, dried over MgSO₄, and concentrated. The crude product is purified by column chromatography on silica gel eluting AcOEt to obtain a white solid (0.38 g, 84%). The structure is confirmed by ¹H-NMR spectrum (CDCl₃). δ [ppm]: 1.13 (t), 1.39 (t), 2.04 (s), 2.17 (s), 2.92 (s), 3.30 (t), 3.88 (t), 3.98 (q), 4.30 (q), 6.53 (d), 6.62 (d), 7.11 (d), 7.26-7.42 (m), 7.70 (d), 7.92 (d), 8.27 (s), 8.52 (s).

50

Application Examples

Example A1: Sensitivity tests

55

[0248] A photocurable composition for a sensitivity test is prepared by mixing the following components:

- | | | |
|------|--------------------|--|
| 11.0 | parts by weight of | REGAL® 400 pigment black (provided by CABOT), |
| 11.0 | parts by weight of | EFKA® 4046, dispersant for pigment provided by BASF), |
| 10.3 | parts by weight of | Ripoxy® SPC1000, alkaline soluble polymer (provided by SHOWA DENKO), |

EP 2 847 167 B9

(continued)

3.6	parts by weight of	dipentaerythritol penta-/hexa-acrylate ((DPHA), provided by SIGMA-ALDRICH)
1.0	parts by weight of	photoinitiator
48.5	parts by weight of	propylene glycol monomethyl ether acetate (PGMEA)
15.6	parts by weight of	cyclohexanone


[0249] All operations are carried out under yellow light. The compositions are applied to a glass plate using a spincoater. The solvent is removed by heating at 80°C for 10 minutes in a convection oven. The thickness of the dry film is approximately 1.2 μm. A stepwedge pattern mask with 9 linear steps and 9 logarithmic steps of different optical density (Edmund Optics, EIA GrayScale Pattern Slide) is placed on the resist directly. Exposure is carried out using a 250W super high pressure mercury lamp (USH-IO, USH-250BY) at a distance of 15 cm. A total exposure dose measured by an optical power meter (ORC UV Light Measure Model UV-M02 with UV-35 detector) on the glass filter is 500mJ/cm². After exposure, the exposed film is developed with an alkaline solution (5 % aqueous solution of DL-A4, YOKOHAMA OILS & FATS) for 10 seconds after break time at 28°C by using a spray type developer (AD-1200, MIKASA). Break time is the development time of the unexposed region. The necessary UV dose for full curing (i.e. the pattern is not dissolved with the alkaline solution) is calculated from the residual thickness of each step after development. The smaller the value of the dose, the more sensitive is the tested initiator. The results are listed in Table 2.

Table 2

photoinitiator of example	necessary UV dose for full curing
1	39 mJ/cm ²
2	32 mJ/cm ²
3	42 mJ/cm ²
4	37 mJ/cm ²
6	35 mJ/cm ²
7	37 mJ/cm ²
8	22 mJ/cm ²
9	39 mJ/cm ²
10	32 mJ/cm ²
11	33 mJ/cm ²
12	28 mJ/cm ²
13	15 mJ/cm ²
14	15 mJ/cm ²
15	29 mJ/cm ²
16	18 mJ/cm ²
17	19 mJ/cm ²


Claims

1. Compounds of the formula I



10 wherein

Z is



R₁, R₂, R₃, R₄, R₅ and **R₆** independently of each other are hydrogen, halogen, OR₁₆, SR₁₇, NR₁₈R₁₉, or C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, OR₁₆, COOR₁₆, CONR₁₈R₁₉ or NR₁₈R₁₉;


or **R₁, R₂, R₃, R₄, R₅** and **R₆** independently of each other are C₆-C₂₀aryl, or C₄-C₂₀heteroaryl, each of which is unsubstituted or substituted by one or more C₁-C₆alkyl, C₁-C₄haloalkyl or halogen;

R₉, R₁₀, R₁₁, R₁₂ and **R₁₃** independently of each other are hydrogen, halogen, OR₁₆, SR₁₇, NR₁₈R₁₉, CN, NO₂ or C₂-C₂₀alkyl which is interrupted by one or more O, S or NR₂₁, wherein the interrupted C₂-C₂₀alkyl is unsubstituted or substituted by one or more halogen, OR₁₆, COOR₁₆, SR₁₇, CONR₁₈R₁₉, C₆-C₂₀aryl, C₃-C₂₀heteroaryl or C₃-C₂₀cycloalkyl, C₃-C₂₀cycloalkyl interrupted by one or more O, S, NR₂₁;

or **R₉, R₁₀, R₁₁, R₁₂** and **R₁₃** independently of each other are C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, OR₁₆, SR₁₇, COOR₁₆, CONR₁₈R₁₉, NR₁₈R₁₉, phenyl, C₃-C₈-cycloalkyl, C₃-C₂₀heteroaryl or M;


provided that **R₉** and **R₁₃** are neither hydrogen nor fluorine;

R₁₄ is C₆-C₂₀aryl or C₃-C₂₀heteroaryl each of which is unsubstituted or substituted by one or more phenyl, halogen, C₁-C₄haloalkyl, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉, PO(OC_kH_{2k+1})₂, SO-C₁-C₁₀alkyl, SO₂-C₁-C₁₀alkyl, M,




or by C₂-C₂₀alkyl which is interrupted by one or more O, CO, S, C(O)O, OC(O), phenylene, naphthylene or by NR₂₁, or each of which C₆-C₂₀aryl or C₃-C₂₀heteroaryl is substituted by one or more C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, COOR₁₆, CONR₁₈R₁₉, phenyl, C₃-C₈cycloalkyl, C₃-C₂₀heteroaryl, C₆-C₂₀aryloxycarbonyl, C₃-C₂₀heteroaryloxycarbonyl, OR₁₆, SR₁₇, NR₁₈R₁₉ or by M;

M is



55 or



5

G is NO₂ or -COR₂₈;

R''₁₄ is C₁-C₂₀alkyl which is unsubstituted or substituted by phenyl or by phenyl which is substituted by one or

more halogen, C₁-C₂₀alkyl, C₁-C₄haloalkyl, OR₁₆, SR₁₇ or by NR₁₈R₁₉;
or **R''₁₄** is C₂-C₂₀alkyl which is interrupted by one or more O, CO, S, C(O)O, OC(O), phenylene, naphthylene
or NR₂₁, wherein the interrupted C₂-C₂₀alkyl is unsubstituted or substituted by one or more halogen, OR₁₆,
COOR₁₆, CONR₁₈R₁₉, phenyl or by phenyl which is substituted by OR₁₆, SR₁₇ or NR₁₈R₁₉;

or **R''₁₄** is CN, CONR₁₈R₁₉, NO₂, C₁-C₄haloalkyl, S(O)_m-C₁-C₆alkyl; S(O)_m-phenyl which is unsubstituted or
substituted by C₁-C₁₂alkyl or SO₂-C₁-C₆alkyl;

or **R''₁₄** is SO₂O-phenyl which is unsubstituted or substituted by C₁-C₁₂alkyl; or is diphenyl phosphinoyl or
di-(C₁-C₄alkoxy)-phosphinoyl;

or **R''₁₄** is C₆-C₂₀aryl or C₃-C₂₀heteroaryl each of which is unsubstituted or substituted by one or more phenyl,
halogen, C₁-C₄haloalkyl, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉, PO(OC_kH_{2k+1})₂, SO-C₁-C₁₀alkyl, SO₂-C₁-C₁₀alkyl,
or by C₂-C₂₀alkyl which is interrupted by one or more O, CO, S, C(O)O, OC(O), phenylene, naphthylene or by
NR₂₁, or each of which is substituted by one or more C₁-C₂₀alkyl which is unsubstituted or substituted by one
or more halogen, COOR₁₆, CONR₁₈R₁₉, phenyl, C₃-C₈cycloalkyl, C₃-C₂₀heteroaryl, C₆-C₂₀aryloxycarbonyl,
C₃-C₂₀heteroaryloxycarbonyl, OR₁₆, SR₁₇ or by NR₁₈R₁₉;

R₁₅ is hydrogen, C₃-C₈cycloalkyl, C₂-C₅alkenyl, C₁-C₂₀alkyl or phenyl;

k is an integer 1-10;

m is an integer 1 or 2;

R'₁₄ has one of the meanings as given for R₁₄ or is C₁-C₂₀alkyl;

R'₁₅ has one of the meanings as given for R₁₅;

X₁ is O, CO, S or a direct bond;

X₃ is O, S or NR'₂₀;

R₁₆ is hydrogen, phenyl-C₁-C₃alkyl, C₁-C₂₀alkyl, which is unsubstituted or substituted by one or more halogen,
OH, SH, CN, C₃-C₆alkenoxy, O(C₁-C₄alkyl), OCH₂CH₂CN, OCH₂CH₂(CO)O(C₁-C₄alkyl), O(CO)-(C₁-C₄alkyl),
O(CO)-(C₂-C₄)alkenyl, O(CO)-phenyl, (CO)OH, (CO)O(C₁-C₄alkyl), C₃-C₂₀cycloalkyl, SO₂-(C₁-C₄haloalkyl),
O(C₁-C₄haloalkyl), O(C₁-C₂₀arylene)-M, or by C₃-C₂₀cycloalkyl which is interrupted by one or more O;

or **R₁₆** is C₂-C₂₀alkyl which is interrupted by one or more O, S or NR₂₁, which interrupted C₂-C₂₀alkyl is unsub-
stituted or substituted by O-C₆-C₂₀arylene-M, in which O-C₆-C₂₀arylene-M, the arylene is unsubstituted or
substituted by one or more C₁-C₆alkyl or O(C₁-C₆alkyl);


or **R₁₆** is (CH₂CH₂O)_{n+1}H, (CH₂CH₂O)_n(CO)-(C₁-C₈alkyl), C₁-C₈alkanoyl, C₂-C₁₂alkenyl, C₃-C₆alkenoyl, or
C₃-C₂₀cycloalkyl which is uninterrupted or interrupted by one or more O, S, CO or NR₂₁;

or **R₁₆** is C₁-C₈alkyl-C₃-C₁₀cycloalkyl which is uninterrupted or interrupted by one or more O;

or **R₁₆** is benzoyl which is unsubstituted or substituted by one or more C₁-C₆alkyl, halogen, OH, or C₁-C₃alkoxy;

or **R₁₆** is phenyl, naphthyl or C₃-C₂₀heteroaryl, each of which is unsubstituted or substituted by one or more
halogen, OH, C₁-C₁₂alkyl, C₁-C₁₂alkoxy, CN, NO₂, phenyl-C₁-C₃alkyloxy, phenoxy, C₁-C₁₂alkylsulfanyl, phe-
nylsulfanyl, N(C₁-C₁₂alkyl)₂, diphenylamino or

45



n is 1-20;

R₁₇ is hydrogen, C₂-C₁₂alkenyl, C₃-C₂₀cycloalkyl or phenyl-C₁-C₃alkyl, wherein the C₂-C₁₂alkenyl,
C₃-C₂₀cycloalkyl or phenyl-C₁-C₃alkyl is uninterrupted or interrupted by one or more O, S, CO or NR₂₁;

or **R₁₇** is C₁-C₂₀alkyl which is unsubstituted or substituted by one or more OH, SH, CN, C₃-C₆alkenoxy,
OCH₂CH₂CN, OCH₂CH₂(CO)O(C₁-C₄alkyl), O(CO)-(C₂-C₄)alkenyl, O(CO)-(C₁-C₄alkyl), O(CO)-phenyl,
COOR₁₆ or S-C₆-C₂₀arylene-M;

or **R₁₇** is C₁-C₂₀alkyl which is unsubstituted or substituted by one or more OH, SH, CN, C₃-C₆alkenoxy,
OCH₂CH₂CN, OCH₂CH₂(CO)O(C₁-C₄alkyl), O(CO)-(C₂-C₄)alkenyl, O(CO)-(C₁-C₄alkyl), O(CO)-phenyl or
COOR₁₆;

or **R₁₇** is C₁-C₂₀alkyl which is unsubstituted or substituted by one or more OH, SH, CN, C₃-C₆alkenoxy,
OCH₂CH₂CN, OCH₂CH₂(CO)O(C₁-C₄alkyl), O(CO)-(C₂-C₄)alkenyl, O(CO)-(C₁-C₄alkyl), O(CO)-phenyl or
COOR₁₆;

or **R₁₇** is C₁-C₂₀alkyl which is unsubstituted or substituted by one or more OH, SH, CN, C₃-C₆alkenoxy,
OCH₂CH₂CN, OCH₂CH₂(CO)O(C₁-C₄alkyl), O(CO)-(C₂-C₄)alkenyl, O(CO)-(C₁-C₄alkyl), O(CO)-phenyl or
COOR₁₆;


or **R₁₇** is C₁-C₂₀alkyl which is unsubstituted or substituted by one or more OH, SH, CN, C₃-C₆alkenoxy,
OCH₂CH₂CN, OCH₂CH₂(CO)O(C₁-C₄alkyl), O(CO)-(C₂-C₄)alkenyl, O(CO)-(C₁-C₄alkyl), O(CO)-phenyl or
COOR₁₆;

or R₁₇ is C₂-C₂₀alkyl which is interrupted by one or more O, S, CO or NR₂₁, which interrupted C₂-C₂₀alkyl is unsubstituted or substituted by S-C₆-C₂₀arylene- M;

or R₁₇ is (CH₂CH₂O)_nH, (CH₂CH₂O)_n(CO)-(C₁-C₈alkyl), C₂-C₈alkanoyl or C₃-C₆alkenoyl;

or R₁₇ is benzoyl which is unsubstituted or substituted by one or more C₁-C₆alkyl, halogen, OH, C₁-C₄alkoxy or C₁-C₄alkylsulfanyl;


or R₁₇ is phenyl, naphthyl or C₃-C₂₀heteroaryl, each of which is unsubstituted or substituted by one or more halogen, C₁-C₁₂alkyl, C₁-C₄haloalkyl, C₁-C₁₂alkoxy, CN, NO₂, phenyl-C₁-C₃alkyloxy, phenoxy, C₁-C₁₂alkylsulfanyl, phenylsulfanyl, N(C₁-C₁₂alkyl)₂, diphenylamino, (CO)O(C₁-C₈alkyl), (CO)-C₁-C₈alkyl, (CO)N(C₁-C₈alkyl)₂ or



R₁₈ and R₁₉ independently of each other are hydrogen, C₁-C₂₀alkyl, C₂-C₄hydroxyalkyl, C₂-C₁₀alkoxyalkyl, C₂-C₅alkenyl, C₃-C₂₀cycloalkyl, phenyl-C₁-C₃alkyl, C₁-C₈alkanoyl, C₁-C₈alkanoyloxy, C₃-C₁₂alkenoyl, SO₂-(C₁-C₄haloalkyl) or benzoyl;


or R₁₈ and R₁₉ are phenyl, naphthyl or C₃-C₂₀heteroaryl, each of which is unsubstituted or substituted by one or more halogen, C₁-C₄haloalkyl, C₁-C₂₀alkoxy, C₁-C₁₂alkyl, benzoyl or C₁-C₁₂alkoxy;

or R₁₈ and R₁₉ together with the N-atom to which they are attached form a 5- or 6-membered saturated or unsaturated ring which is uninterrupted or is interrupted by O, S, or NR₂₁, and which 5- or 6-membered saturated or unsaturated ring is unsubstituted or substituted by one or more C₁-C₂₀alkyl, C₁-C₂₀alkoxy, =O, OR₁₆, SR₁₇, NR₃₁R₃₂, COR₄₁, NO₂, halogen, C₁-C₄-haloalkyl, CN, phenyl,



or by C₃-C₂₀cyclalkyl which is uninterrupted or is interrupted by one or more O, S, CO or NR₂₁;


or R₁₈ and R₁₉ together with the N-atom to which they are attached form a group



R₂₀ is hydrogen, COR₄₁ or C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, OR₁₆, SR₁₇, COOR₁₆, CONR₁₈R₁₉, NR₁₈R₁₉, PO(OC_kH_{2k+1})₂ or M;

or R₂₀ is C₂-C₂₀alkyl which is interrupted by one or more O, CO, C(O)O, OC(O) or NR₂₁, wherein the interrupted C₂-C₂₀alkyl is unsubstituted or substituted by one or more halogen, OR₁₆, SR₁₇, COOR₁₆, CONR₁₈R₁₉, NR₁₈R₁₉ or M;

or R₂₀ is C₆-C₂₀aryl or C₃-C₂₀heteroaryl each of which is unsubstituted or substituted by one or more phenyl, halogen, C₁-C₄haloalkyl, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉, M, Z,



or by C₁-C₂₀alkyl which is interrupted by one or more O, S or NR₂₁, or each of which C₆-C₂₀aryl or C₃-C₂₀heteroaryl is substituted by one or more C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, COOR₁₆, CONR₁₈R₁₉, phenyl, C₃-C₈cycloalkyl, C₃-C₂₀heteroaryl, C₆-C₂₀aryloxycarbonyl, C₃-C₂₀heteroaryloxycarbonyl, OR₁₆, SR₁₇ or NR₁₈R₁₉;


R₂₀ is hydrogen, COR₄₁ or C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, OR₁₆, SR₁₇, COOR₁₆, CONR₁₈R₁₉, NR₁₈R₁₉ or PO(OC_kH_{2k+1})₂;

or R₂₀ is C₂-C₂₀alkyl of which is interrupted by one or more O, CO, C(O)O, OC(O) or NR₂₁, wherein the interrupted C₂-C₂₀alkyl is unsubstituted or substituted by one or more halogen, OR₁₆, SR₁₇, COOR₁₆,

CONR₁₈R₁₉ or NR₁₈R₁₉;

or R'₂₀ is C₆-C₂₀aryl or C₃-C₂₀heteroaryl each of which is unsubstituted or substituted by one or more phenyl, halogen, C₁-C₄haloalkyl, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉,

5



10

or by C₁-C₂₀alkyl which is interrupted by one or more O, S or NR₂₁, or each of which C₆-C₂₀aryl or C₃-C₂₀heteroaryl is substituted by one or more C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, COOR₁₆, CONR₁₈R₁₉, phenyl, C₃-C₈cycloalkyl, C₃-C₂₀heteroaryl, C₆-C₂₀aryloxycarbonyl, C₃-C₂₀heteroaryloxycarbonyl, OR₁₆, SR₁₇ or NR₁₈R₁₉;


R₂₁ is hydrogen, C₁-C₂₀alkyl, C₁-C₄haloalkyl or C₂-C₂₀alkyl which is interrupted by one or more O, CO, C(O)O or OC(CO),

15

or R₂₁ is COR₄₁, phenyl-C₁-C₄alkyl or C₃-C₈cycloalkyl which is uninterrupted or is interrupted by one or more O or CO,


or R₂₁ is phenyl or naphthyl both of which are unsubstituted or substituted by one or more C₁-C₂₀alkyl, halogen, C₁-C₄haloalkyl, OR₁₆, SR₁₇, NR₁₈R₁₉ or

20



R₂₂, R₂₃, R₂₄, R₂₅, R₂₆ or R₂₇ independently of each other are hydrogen, COR₄₁, NO₂ or

25



30

or one of R₂₂, R₂₃ or R₂₄ and one of R₂₅, R₂₆ or R₂₇ together with X₃ and the phenyl rings to which they are attached form a heteroaromatic ring system;

R₂₈ is C₆-C₂₀aryl or C₃-C₂₀heteroaryl each of which is unsubstituted or substituted by one or more phenyl, halogen, C₁-C₄haloalkyl, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉ or by C₂-C₂₀alkyl which is interrupted by one or more O, S or NR₂₁, or each of which C₆-C₂₀aryl or C₃-C₂₀heteroaryl is substituted by one or more C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, COOR₁₆, CONR₁₈R₁₉, phenyl, C₃-C₈cycloalkyl, C₃-C₂₀heteroaryl, C₆-C₂₀aryloxycarbonyl, C₃-C₂₀heteroaryloxycarbonyl, OR₁₆, SR₁₇ or NR₁₈R₁₉;


35

R₃₁ and R₃₂ independently of each other are hydrogen, C₁-C₂₀alkyl, C₁-C₄haloalkyl, C₃-C₁₀cycloalkyl or phenyl; or R₃₁ and R₃₂ together with N-atom to which they are attached form a 5- or 6-membered saturated or unsaturated ring, which is uninterrupted or is interrupted by O, S or NR₂₁, and which 5- or 6-membered saturated or unsaturated ring is not condensed or to which 5- or 6-membered saturated or unsaturated ring a benzene ring is condensed;

40

R₃₃, R₃₄, R₃₅, R₃₆, R₃₇, R₃₈, R₃₉ and R₄₀ independently of each other are hydrogen,

45




NO₂, COR₄₁, C₁-C₂₀alkyl, C₁-C₄haloalkyl, OR₁₆, SR₁₇, NR₁₈R₁₉, halogen, CN, phenyl or C₃-C₂₀cycloalkyl which is uninterrupted or is interrupted by one or more O, S, CO or NR₂₁;

50

or R₃₅ and R₃₆ or R₃₇ and R₃₈ or both, R₃₅ and R₃₆ and R₃₇ and R₃₈ are

55




and

R₄₁ is C₆-C₂₀aryl or C₃-C₂₀heteroaryl each of which is unsubstituted or substituted by one or more phenyl, halogen, C₁-C₄haloalkyl, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉ or by C₂-C₂₀alkyl which is interrupted by one or more

EP 2 847 167 B9

O, S or NR₂₁, or each of which C₆-C₂₀aryl or C₃-C₂₀heteroaryl is substituted by one or more C₁-C₂₀alkyl which is unsubstituted or substituted by one or more halogen, COOR₁₆, CONR₁₈R₁₉, phenyl, C₃-C₈cycloalkyl, C₃-C₂₀heteroaryl, C₆-C₂₀aryloxycarbonyl, C₃-C₂₀heteroaryloxycarbonyl, OR₁₆, SR₁₇ or NR₁₈R₁₉; or R₄₁ is

5



10


or R₄₁ is hydrogen, OH, C₁-C₂₀alkyl, C₁-C₄haloalkyl, C₂-C₂₀alkyl which is interrupted by one or more O, CO or NR₂₁, or R₄₁ is C₃-C₂₀cycloalkyl which is uninterrupted or is interrupted by O, S, CO or NR₂₁.

15

2. Compounds of the formula I according to claim 1, wherein

Z is

20



25

R₁, R₂, R₃, R₄, R₅ and R₆ are hydrogen;

R₁₀ and R₁₂ are hydrogen;

R₁₁ is hydrogen, OR₁₆ or C₁-C₂₀alkyl;


R₉ and R₁₃ independently of each other are OR₁₆ or C₁-C₂₀alkyl;

30

R₁₄ is C₆-C₂₀aryl which is unsubstituted or substituted by one or more NO₂, OR₁₆, NR₁₈R₁₉ or C₁-C₂₀alkyl which C₁-C₂₀alkyl is unsubstituted or substituted by SR₁₇;

M is

35



40

G is -COR₂₈;

R¹⁴ is C₁-C₂₀alkyl or C₆-C₂₀aryl which C₆-C₂₀aryl is unsubstituted or substituted by C₁-C₂₀alkyl;

R₁₅ is C₁-C₂₀alkyl;

R¹⁴ is C₁-C₂₀alkyl;

45

R¹⁵ is C₁-C₂₀alkyl;

X₃ together with R₂₄ and R₂₇ and the phenyl rings to which they are attached forms a heteroaromatic ring system;

R₁₆ is C₁-C₂₀alkyl, which is unsubstituted or substituted by one or more halogen, OH, O(C₁-C₄alkyl), O(CO)-(C₁-C₄alkyl) or O(C₁-C₂₀arylene)-M;

50

or R₁₆ is C₂-C₂₀alkyl which is interrupted by one or more O, which interrupted C₂-C₂₀alkyl is substituted by O-C₆-C₂₀arylene-M, in which O-C₆-C₂₀arylene-M, the arylene is unsubstituted or substituted by O(C₁-C₆alkyl);

or R₁₆ is C₁-C₈alkanoyl;

R₁₇ is C₁-C₂₀alkyl which is unsubstituted or substituted by COOR₁₆;


R₁₈ and R₁₉ independently of each other are C₁-C₂₀alkyl,

55

or R₁₈ and R₁₉ together with the N-atom to which they are attached form a 5- or 6-membered saturated or unsaturated ring which is uninterrupted or is interrupted by O, or R₁₈ and R₁₉ together with the N-atom to which they are attached form a group



R₂₀ is C₁-C₂₀alkyl or C₂-C₂₀alkyl of which is interrupted by one or more O, wherein the interrupted C₂-C₂₀alkyl is unsubstituted or substituted by NR₁₈R₁₉;
 or **R**₂₀ is C₆-C₂₀aryl which is substituted by




R₂₂, **R**₂₃, **R**₂₅ and **R**₂₆ are hydrogen,

R₂₄ and **R**₂₇ together with X₃ and the phenyl rings to which they are attached form a heteroaromatic ring system;

R₂₈ is C₆-C₂₀aryl which is unsubstituted or substituted by C₁-C₂₀alkyl;

R₃₃, **R**₃₅, **R**₃₆, **R**₃₇, **R**₃₈ and **R**₄₀ independently of each other are hydrogen;

R₃₄ is



R₃₉ is COR₄₁;

R₄₁ is C₆-C₂₀aryl which is unsubstituted or substituted by C₁-C₂₀alkyl.

3. Compounds of the formula I according to claim 2, wherein

R'₁₄ is C₁-C₂₀alkyl or C₆-C₂₀aryl which is substituted by C₁-C₂₀alkyl;

R₁₆ is C₁-C₂₀alkyl, which is unsubstituted or substituted by one or more halogen, OH, O(C₁-C₄alkyl), O(CO)-(C₁-C₄alkyl) or O(C₁-C₂₀arylene)-M;

or **R**₁₆ is C₂-C₂₀alkyl which is interrupted by one or more O, which interrupted C₂-C₂₀alkyl is substituted by O-C₆-C₂₀arylene-M, in which O-C₆-C₂₀arylene-M, the arylene is substituted by O(C₁-C₆alkyl);


or **R**₁₆ is C₁-C₈alkanoyl;

R₁₇ is C₁-C₂₀alkyl which is substituted by COOR₁₆;

R₁₈ and **R**₁₉ independently of each other are C₁-C₂₀alkyl,


or **R**₁₈ and **R**₁₉ together with the N-atom to which they are attached form a 6-membered saturated ring which is uninterrupted or is interrupted by O,

or **R**₁₈ and **R**₁₉ together with the N-atom to which they are attached form a group



R₂₀ is C₁-C₂₀alkyl or C₂-C₂₀alkyl of which is interrupted by one or more O, wherein the interrupted C₂-C₂₀alkyl is substituted by NR₁₈R₁₉;

or **R**₂₀ is C₆-C₂₀aryl which is substituted by



R₂₄ and **R**₂₇ together with X₃ and the phenyl rings to which they are attached form a carbazoyl ring system;

R₂₈ is C₆-C₂₀aryl which is substituted by C₁-C₂₀alkyl;

R_{41} is C_6-C_{20} aryl which is substituted by C_1-C_{20} alkyl.

4. A photopolymerizable composition comprising

- (a) at least one ethylenically unsaturated photopolymerizable compound and
 (b) as photoinitiator, at least one compound of the formula I as defined in claim 1.

5. A photopolymerizable composition according to claim 4, wherein the component (a) is a resin obtained by the reaction of a saturated or unsaturated polybasic acid anhydride with a product of the reaction of an epoxy resin and an unsaturated monocarboxylic acid.

6. A photopolymerizable composition according to claim 4, additionally to the photoinitiator (b) comprising at least one further photoinitiator (c), and/or other additives (d).

7. A photopolymerizable composition according to claim 6 as further additive (d) comprising a pigment or a mixture of pigments or a mixture of one or more pigments with one or more dyes.


8. A photopolymerizable composition according to claim 7 as further additive (d) comprising a dispersant or a mixture of dispersants.

9. A photopolymerizable composition according to anyone of claims 4-8, comprising 0.05 to 25 % by weight of the photoinitiator (b), or the photoinitiators (b) and (c), based on the composition.



10. A photopolymerizable composition according to anyone of claims 4-9 as further additive (d) comprising a photosensitizer, in particular a compound selected from the group consisting of benzophenone, benzophenone derivatives, thioxanthone, thioxanthone derivatives, anthraquinone, anthraquinone derivatives, coumarin and coumarine derivatives.

11. A photopolymerizable composition according to anyone of claims 4-10 additionally comprising a binder polymer (e), in particular a copolymer of methacrylate and methacrylic acid.

12. A process for the preparation of a compound of the formula I according to claim 1 by reacting the corresponding oxime compound of formula IA



wherein Z , Q , R_1 , R_2 , R_3 , R_4 , R_5 , R_6 , R_{20} , and R_{14} are as defined in claim 1, with an acyl halide of the formula 2 or an anhydride of the formula 3




wherein Hal is a halogen, in particular Cl, and R_{15} is as defined in claim 1, in the presence of a base or a mixture of bases.

13. A process for the photopolymerization of compounds containing ethylenically unsaturated double bonds, which comprises irradiating a composition according to anyone of claims 4-11 with electromagnetic radiation in the range from 150 to 600 nm, or with electron beam or with X-rays.

14. A color filter prepared by providing red, green and blue picture elements and optionally a black matrix, all comprising a photosensitive resin and a pigment on a transparent substrate and providing a transparent electrode either on the surface of the substrate or on the surface of the color filter layer, wherein said photosensitive resin comprises a polyfunctional acrylate monomer, an organic polymer binder and a photopolymerization initiator of formula I as defined in claim 1.

15. Compounds of the formula IA



wherein Z, R₁, R₂, R₃, R₄, R₅, R₆, R₂₀, and R₁₄ are as defined in claim 1.

16. A coated substrate which is coated on at least one surface with a composition according to claim 4.


17. A process for the photographic production of relief images, in which a coated substrate according to claim 16 is subjected to imagewise exposure and then the unexposed portions are removed with a developer.

18. Use of a compound of the formula I according to claim 1 for the photopolymerization of a composition comprising at least one ethylenically unsaturated photopolymerizable compound.

19. Process according to claim 13 for producing pigmented and nonpigmented paints and varnishes, powder coatings, printing inks, printing plates, adhesives, dental compositions, gel coats, photoresists, for encapsulating electrical and electronic components, for producing magnetic recording materials, micromechanical parts, waveguides, optical switches, plating masks, colour proofing systems, glass fibre cable coatings, screen printing stencils, three-dimensional objects by means of stereolithography, image recording materials for holographic recordings, microelectronic circuits, decolorizing materials, formulations containing microcapsules.


Patentansprüche

1. Verbindungen der Formel I



worin

Z



5

ist

R₁, R₂, R₃, R₄, R₅ und R₆ unabhängig voneinander Wasserstoff, Halogen, OR₁₆, SR₁₇, NR₁₈R₁₉ oder C₁-C₂₀-Alkyl sind, das unsubstituiert oder mit einem oder mehreren Halogen, OR₁₆, COOR₁₆, CONR₁₈R₁₉ oder NR₁₈R₁₉ substituiert ist;

oder R₁, R₂, R₃, R₄, R₅ und R₆ unabhängig voneinander C₆-C₂₀-Aryl oder C₄-C₂₀-Heteroaryl sind, wobei jeder von ihnen unsubstituiert oder mit einem oder mehreren C₁-C₆-Alkyl, C₁-C₄-Halogenalkyl oder Halogen substituiert ist;


R₉, R₁₀, R₁₁, R₁₂ und R₁₃ unabhängig voneinander Wasserstoff, Halogen, OR₁₆, SR₁₇, NR₁₈R₁₉, CN, NO₂ oder C₂-C₂₀-Alkyl sind, das durch ein oder mehrere O, S oder NR₂₁ unterbrochen ist, wobei das unterbrochene C₂-C₂₀-Alkyl unsubstituiert oder mit einem oder mehreren Halogen, OR₁₆, COOR₁₆, SR₁₇, CONR₁₈R₁₉, C₆-C₂₀-Aryl, C₃-C₂₀-Heteroaryl oder C₃-C₂₀-Cycloalkyl, C₃-C₂₀-Cycloalkyl, unterbrochen durch ein oder mehrere O, S, NR₂₁, substituiert ist;

oder R₉, R₁₀, R₁₁, R₁₂ und R₁₃ unabhängig voneinander C₁-C₂₀-Alkyl sind, das unsubstituiert oder mit einem oder mehreren Halogen, OR₁₆, SR₁₇, COOR₁₆, CONR₁₈R₁₉, NR₁₈R₁₉, Phenyl, C₃-C₈-Cycloalkyl, C₃-C₂₀-Heteroaryl oder M substituiert ist;

mit der Maßgabe, dass R₉ und R₁₃ weder Wasserstoff noch Fluor sind;

R₁₄ C₆-C₂₀-Aryl oder C₃-C₂₀-Heteroaryl ist, wobei jeder von ihnen unsubstituiert oder mit einem oder mehreren Phenyl, Halogen, C₁-C₄-Halogenalkyl, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉, PO(OC_kH_{2k+1})₂, SO-C₁-C₁₀-Alkyl, SO₂-C₁-C₁₀-Alkyl, M,

25




30

oder mit C₂-C₂₀-Alkyl substituiert ist, das durch ein oder mehrere O, CO, S, C(O)O, O(CO), Phenylen, Naphthylen oder durch NR₂₁ unterbrochen ist, oder jeder von dem C₆-C₂₀-Aryl oder C₃-C₂₀-Heteroaryl mit einem oder mehreren C₁-C₂₀-Alkyl substituiert ist, das unsubstituiert oder mit einem oder mehreren Halogen, COOR₁₆, CONR₁₈R₁₉, Phenyl, C₃-C₈-Cycloalkyl, C₃-C₂₀-Heteroaryl, C₆-C₂₀-Aryloxycarbonyl, C₃-C₂₀-Heteroaryloxycarbonyl, OR₁₆, SR₁₇, NR₁₈R₁₉ oder mit M substituiert ist;

35

M


40



45

oder

50



55

ist;

G NO₂ oder -COR₂₈ ist;

R''₁₄ C₁-C₂₀-Alkyl ist, das unsubstituiert oder mit Phenyl oder mit Phenyl substituiert ist, das mit einem oder mehreren Halogen, C₁-C₂₀-Alkyl, C₁-C₄-Halogenalkyl, OR₁₆, SR₁₇ oder mit NR₁₈R₁₉ substituiert ist;

oder R''₁₄ C₂-C₂₀-Alkyl ist, das durch ein oder mehrere O, CO, S, C(O)O, OC(O), Phenylen, Naphthylen oder

NR₂₁ unterbrochen ist, wobei das unterbrochene C₂-C₂₀-Alkyl unsubstituiert oder mit einem oder mehreren Halogen, OR₁₆, COOR₁₆, CONR₁₈R₁₉, Phenyl oder mit Phenyl substituiert ist, das mit OR₁₆, SR₁₇ oder NR₁₈R₁₉ substituiert ist;

oder R¹⁴ CN, CONR₁₈R₁₉, NO₂, C₁-C₄-Halogenalkyl, S(O)_m-C₁-C₆-Alkyl; S(O)_m-Phenyl ist, das unsubstituiert oder mit C₁-C₁₂-Alkyl oder SO₂-C₁-C₆-Alkyl substituiert ist;

oder R¹⁴ SO₂O-Phenyl ist, das unsubstituiert oder mit C₁-C₁₂-Alkyl substituiert ist; oder Diphenylphosphinoyl oder Di-(C₁-C₄-alkoxy)-phosphinoyl ist;

oder R¹⁴ C₆-C₂₀-Aryl oder C₃-C₂₀-Heteroaryl ist, wobei jeder von ihnen unsubstituiert oder mit einem oder mehreren Phenyl, Halogen, C₁-C₄-Halogenalkyl, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉, PO(OC_kH_{2k+1})₂, SO-C₁-C₁₀-Alkyl, SO₂-C₁-C₁₀-Alkyl oder mit C₂-C₂₀-Alkyl substituiert ist, das durch ein oder mehrere O, CO, S, C(O)O, OC(O), Phenylen, Naphthylen oder durch NR₂₁ unterbrochen ist, oder jeder von ihnen mit einem oder mehreren C₁-C₂₀-Alkyl substituiert ist, das unsubstituiert oder mit einem oder mehreren Halogen, COOR₁₆, CONR₁₈R₁₉, Phenyl, C₃-C₈-Cycloalkyl, C₃-C₂₀-Heteroaryl, C₆-C₂₀-Aryloxycarbonyl, C₃-C₂₀-Heteroaryloxycarbonyl, OR₁₆, SR₁₇ oder mit NR₁₈R₁₉ substituiert ist;

R₁₅ Wasserstoff, C₃-C₈-Cycloalkyl, C₂-C₅-Alkenyl, C₁-C₂₀-Alkyl oder Phenyl ist;

k eine ganze Zahl 1-10 ist;

m eine ganze Zahl 1 oder 2 ist;

R¹⁴ eine der für R₁₄ angegebenen Bedeutungen aufweist oder C₁-C₂₀-Alkyl ist;

R¹⁵ eine der für R₁₅ angegebenen Bedeutungen aufweist;

X₁ O, CO, S oder eine direkte Bindung ist;

X₃ O, S oder NR₂₀ ist;

R₁₆ Wasserstoff, Phenyl-C₁-C₃-alkyl, C₁-C₂₀-Alkyl ist, das unsubstituiert oder mit einem oder mehreren Halogen, OH, SH, CN, C₃-C₆-Alkenoxy, O(C₁-C₄-Alkyl), OCH₂CH₂CN, OCH₂CH₂(CO)O(C₁-C₄-Alkyl), O(CO)-(C₁-C₄-Alkyl), O(CO)-(C₂-C₄)-Alkenyl, O(CO)-Phenyl, (CO)OH, (CO)O(C₁-C₄-Alkyl), C₃-C₂₀-Cycloalkyl, SO₂-(C₁-C₄-Halogenalkyl), O(C₁-C₄-Halogenalkyl), O(C₁-C₂₀-Arylen)-M oder mit C₃-C₂₀-Cycloalkyl substituiert ist, das durch ein oder mehrere O unterbrochen ist;


oder R₁₆ C₂-C₂₀-Alkyl ist, das durch ein oder mehrere O, S oder NR₂₁ unterbrochen ist, wobei das unterbrochene C₂-C₂₀-Alkyl unsubstituiert oder mit O-C₆-C₂₀-Arylen-M substituiert ist, wobei in dem O-C₆-C₂₀-Arylen-M das Arylen unsubstituiert oder mit einem oder mehreren C₁-C₆-Alkyl oder O(C₁-C₆-Alkyl) substituiert ist;

oder R₁₆ (CH₂CH₂O)_{n+1}H, (CH₂CH₂O)_n(CO)-(C₁-C₈-Alkyl), C₁-C₈-Alkanoyl, C₂-C₁₂-Alkenyl, C₃-C₆-Alkenoyl oder C₃-C₂₀-Cycloalkyl ist, das nicht unterbrochen oder durch ein oder mehrere O, S, CO oder NR₂₁ unterbrochen ist;

oder R₁₆ C₁-C₈-Alkyl-C₃-C₁₀-cycloalkyl ist, das nicht unterbrochen oder durch ein oder mehrere O unterbrochen ist;

oder R₁₆ Benzoyl ist, das unsubstituiert oder mit einem oder mehreren C₁-C₆-Alkyl, Halogen, OH oder C₁-C₃-Alkoxo substituiert ist;

oder R₁₆ Phenyl, Naphthyl oder C₃-C₂₀-Heteroaryl ist, wobei jeder von ihnen unsubstituiert oder mit einem oder mehreren Halogen, OH, C₁-C₁₂-Alkyl, C₁-C₁₂-Alkoxy, CN, NO₂, Phenyl-C₁-C₃-alkyloxy, Phenoxy, C₁-C₁₂-Alkylsulfanyl, Phenylsulfanyl, N(C₁-C₁₂-Alkyl)₂, Diphenylamino oder



substituiert ist;

n 1-20 ist;


R₁₇ Wasserstoff, C₂-C₁₂-Alkenyl, C₃-C₂₀-Cycloalkyl oder Phenyl-C₁-C₃-alkyl ist, wobei das C₂-C₁₂-Alkenyl, C₃-C₂₀-Cycloalkyl oder Phenyl-C₁-C₃-alkyl nicht unterbrochen oder durch ein oder mehrere O, S, CO oder NR₂₁ unterbrochen ist;

oder R₁₇ C₁-C₂₀-Alkyl ist, das unsubstituiert oder mit einem oder mehreren OH, SH, CN, C₃-C₆-Alkenoxy, OCH₂CH₂CN, OCH₂CH₂(CO)O(C₁-C₄-Alkyl), O(CO)-(C₂-C₄)-Alkenyl, O(CO)-(C₁-C₄-Alkyl), O(CO)-Phenyl, COOR₁₆ oder S-C₆-C₂₀-Arylen-M substituiert ist;

oder R₁₇ C₁-C₂₀-Alkyl ist, das unsubstituiert oder mit einem oder mehreren OH, SH, CN, C₃-C₆-Alkenoxy, OCH₂CH₂CN, OCH₂CH₂(CO)O(C₁-C₄-Alkyl), O(CO)-(C₂-C₄)-Alkenyl, O(CO)-(C₁-C₄-Alkyl), O(CO)-Phenyl oder COOR₁₆ substituiert ist;

oder R₁₇ C₂-C₂₀-Alkyl ist, das durch ein oder mehrere O, S, CO oder NR₂₁ unterbrochen ist, wobei das unterbrochene C₂-C₂₀-Alkyl unsubstituiert oder mit S-C₆-C₂₀-Arylen-M substituiert ist;

oder R_{17} $(CH_2CH_2O)_nH$, $(CH_2CH_2O)_n(CO)-(C_1-C_8-Alkyl)$, $C_2-C_8-Alkanoyl$ oder $C_3-C_6-Alkenoyl$ ist;
 oder R_{17} Benzoyl ist, das unsubstituiert oder mit einem oder mehreren $C_1-C_6-Alkyl$, Halogen, OH, $C_1-C_4-Alkoxy$
 oder $C_1-C_4-Alkylsulfanyl$ substituiert ist;
 oder R_{17} Phenyl, Naphthyl oder C_3-C_{20} -Heteroaryl ist, wobei jeder von ihnen unsubstituiert oder mit einem oder
 mehreren Halogen, $C_1-C_{12}-Alkyl$, $C_1-C_4-Halogenalkyl$, $C_1-C_{12}-Alkoxy$, CN, NO_2 , Phenyl- C_1-C_3 -alkoxy, Phen-
 oxy, $C_1-C_{12}-Alkylsulfanyl$, Phenylsulfanyl, $N(C_1-C_{12}-Alkyl)_2$, Diphenylamino, $(CO)O(C_1-C_8-Alkyl)$,
 $(CO)-C_1-C_8-Alkyl$, $(CO)N(C_1-C_8-Alkyl)_2$ oder




substituiert ist;

R_{18} und R_{19} unabhängig voneinander Wasserstoff, $C_1-C_{20}-Alkyl$, $C_2-C_4-Hydroxyalkyl$, $C_2-C_{10}-Alkoxyalkyl$,
 $C_2-C_5-Alkenyl$, $C_3-C_{20}-Cycloalkyl$, Phenyl- C_1-C_3 -alkyl, $C_1-C_8-Alkanoyl$, $C_1-C_8-Alkanoyloxy$, $C_3-C_{12}-Alkenoyl$,
 $SO_2-(C_1-C_4-Halogenalkyl)$ oder Benzoyl sind;


oder R_{18} und R_{19} Phenyl, Naphthyl oder C_3-C_{20} -Heteroaryl sind, wobei jeder von ihnen unsubstituiert oder mit
 einem oder mehreren Halogen, $C_1-C_4-Halogenalkyl$, $C_1-C_{20}-Alkoxy$, $C_1-C_{12}-Alkyl$, Benzoyl oder $C_1-C_{12}-Alkoxy$
 substituiert ist;

oder R_{18} und R_{19} zusammen mit dem N-Atom, an das sie gebunden sind, einen 5- oder 6-gliedrigen gesättigten
 oder ungesättigten Ring bilden, der nicht unterbrochen ist oder durch O, S oder NR_{21} unterbrochen ist, und der
 5- oder 6-gliedrige gesättigte oder ungesättigte Ring unsubstituiert oder mit einem oder mehreren $C_1-C_{20}-Alkyl$,
 $C_1-C_{20}-Alkoxy$, =O, OR_{16} , SR_{17} , $NR_{31}R_{32}$, COR_{41} , NO_2 , Halogen, $C_1-C_4-Halogenalkyl$, CN, Phenyl,



oder mit $C_3-C_{20}-Cycloalkyl$ substituiert ist, das nicht unterbrochen ist oder durch ein oder mehrere O, S, CO
 oder NR_{21} unterbrochen ist;

oder R_{18} und R_{19} zusammen mit dem N-Atom, an das sie gebunden sind, eine Gruppe




bilden;

R_{20} Wasserstoff, COR_{41} oder $C_1-C_{20}-Alkyl$ ist, das unsubstituiert oder mit einem oder mehreren Halogen, OR_{16} ,
 SR_{17} , $COOR_{16}$, $CONR_{18}R_{19}$, $NR_{18}R_{19}$, $PO(OC_kH_{2k+1})_2$ oder M substituiert ist;


oder R_{20} $C_2-C_{20}-Alkyl$ ist, das durch ein oder mehrere O, CO, $C(O)O$, $OC(O)$ oder NR_{21} unterbrochen ist, wobei
 das unterbrochene $C_2-C_{20}-Alkyl$ unsubstituiert oder mit einem oder mehreren Halogen, OR_{16} , SR_{17} , $COOR_{16}$,
 $CONR_{18}R_{19}$, $NR_{18}R_{19}$ oder M substituiert ist;

oder R_{20} $C_6-C_{20}-Aryl$ oder C_3-C_{20} -Heteroaryl ist, wobei jeder von ihnen unsubstituiert oder mit einem oder
 mehreren Phenyl, Halogen, $C_1-C_4-Halogenalkyl$, CN, NO_2 , OR_{16} , SR_{17} , $NR_{18}R_{19}$, M, Z,




oder mit $C_1-C_{20}-Alkyl$ substituiert ist, das durch ein oder mehrere O, S oder NR_{21} unterbrochen ist, oder jeder
 von ihnen $C_6-C_{20}-Aryl$ oder C_3-C_{20} -Heteroaryl mit einem oder mehreren $C_1-C_{20}-Alkyl$ substituiert ist, das un-
 substituiert oder mit einem oder mehreren Halogen, $COOR_{16}$, $CONR_{18}R_{19}$, Phenyl, $C_3-C_8-Cycloalkyl$,
 C_3-C_{20} -Heteroaryl, $C_6-C_{20}-Aryloxycarbonyl$, C_3-C_{20} -Heteroaryloxycarbonyl, OR_{16} , SR_{17} oder $NR_{18}R_{19}$ substi-
 tuiert ist;

R'₂₀ Wasserstoff, COR₄₁ oder C₁-C₂₀-Alkyl ist, das unsubstituiert oder mit einem oder mehreren Halogen, OR₁₆, SR₁₇, COOR₁₆, CONR₁₈R₁₉, NR₁₈R₁₉ oder PO(OC_kH_{2k+1})₂ substituiert ist;
 oder R'₂₀ C₂-C₂₀-Alkyl ist, das durch ein oder mehrere O, CO, C(O)O, OC(O) oder NR₂₁ unterbrochen ist, wobei
 das unterbrochene C₂-C₂₀-Alkyl unsubstituiert oder mit einem oder mehreren Halogen, OR₁₆, SR₁₇, COOR₁₆,
 CONR₁₈R₁₉ oder NR₁₈R₁₉ substituiert ist;
 oder R'₂₀ C₆-C₂₀-Aryl oder C₃-C₂₀-Heteroaryl ist, wobei jeder von ihnen unsubstituiert oder mit einem oder
 mehreren Phenyl, Halogen, C₁-C₄-Halogenalkyl, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉,




oder mit C₁-C₂₀-Alkyl substituiert ist, das durch ein oder mehrere O, S oder NR₂₁ unterbrochen ist, oder jeder
 von ihnen C₆-C₂₀-Aryl oder C₃-C₂₀-Heteroaryl mit einem oder mehreren C₁-C₂₀-Alkyl substituiert ist, das un-
 substituiert oder mit einem oder mehreren Halogen, COOR₁₆, CONR₁₈R₁₉, Phenyl, C₃-C₈-Cycloalkyl,
 C₃-C₂₀-Heteroaryl, C₆-C₂₀-Aryloxycarbonyl, C₃-C₂₀-Heteroaryloxycarbonyl, OR₁₆, SR₁₇ oder NR₁₈R₁₉ substi-
 tuiert ist;

R₂₁ Wasserstoff, C₁-C₂₀-Alkyl, C₁-C₄-Halogenalkyl oder C₂-C₂₀-Alkyl ist, das durch ein oder mehrere O, CO,
 C(O)O oder OC(CO) unterbrochen ist,
 oder R₂₁ COR₄₁, Phenyl-C₁-C₄-alkyl oder C₃-C₈-Cycloalkyl ist, das nicht unterbrochen ist oder durch ein oder
 mehrere O oder CO unterbrochen ist,
 oder R₂₁ Phenyl oder Naphthyl ist, wobei beide von ihnen unsubstituiert oder mit einem oder mehreren C₁-C₂₀-Al-
 kyl, Halogen, C₁-C₄-Halogenalkyl, OR₁₆, SR₁₇, NR₁₈R₁₉ oder



substituiert sind;

R₂₂, R₂₃, R₂₄, R₂₅, R₂₆ oder **R₂₇** unabhängig voneinander Wasserstoff, COR₄₁, NO₂ oder




sind oder einer von R₂₂, R₂₃ oder R₂₄ und einer von R₂₅, R₂₆ oder R₂₇ zusammen mit X₃ und den Phenyl-
 Ringen, an das sie gebunden sind, ein heteroaromatisches Ring-System bilden;

R₂₈ C₆-C₂₀-Aryl oder C₃-C₂₀-Heteroaryl ist, wobei jeder von ihnen unsubstituiert oder mit einem oder mehreren
 Phenyl, Halogen, C₁-C₄-Halogenalkyl, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉ oder mit C₂-C₂₀-Alkyl substituiert ist,
 das durch ein oder mehrere O, S oder NR₂₁ unterbrochen ist, oder jeder von ihnen C₆-C₂₀-Aryl oder
 C₃-C₂₀-Heteroaryl mit einem oder mehreren C₁-C₂₀-Alkyl substituiert ist, das unsubstituiert oder mit einem oder
 mehreren Halogen, COOR₁₆, CONR₁₈R₁₉, Phenyl, C₃-C₈-Cycloalkyl, C₃-C₂₀-Heteroaryl,
 C₆-C₂₀-Aryloxycarbonyl, C₃-C₂₀-Heteroaryloxycarbonyl, OR₁₆, SR₁₇ oder NR₁₈R₁₉ substituiert ist;

R₃₁ und **R₃₂** unabhängig voneinander Wasserstoff, C₁-C₂₀-Alkyl, C₁-C₄-Halogenalkyl, C₃-C₁₀-Cycloalkyl oder
 Phenyl sind;

oder R₃₁ und R₃₂ zusammen mit dem N-Atom, an das sie gebunden sind, einen 5- oder 6-gliedrigen gesättigten
 oder ungesättigten Ring bilden, der nicht unterbrochen ist oder durch O, S oder NR₂₁ unterbrochen ist, und der
 5- oder 6-gliedrige gesättigte oder ungesättigte Ring nicht kondensiert ist oder an den 5- oder 6-gliedrigen
 gesättigten oder ungesättigten Ring ein Benzol-Ring kondensiert ist;


R₃₃, R₃₄, R₃₅, R₃₆, R₃₇, R₃₈, R₃₉ und **R₄₀** unabhängig voneinander Wasserstoff,



NO₂, COR₄₁, C₁-C₂₀-Alkyl, C₁-C₄-Halogenalkyl, OR₁₆, SR₁₇, NR₁₈R₁₉, Halogen, CN, Phenyl oder C₃-C₂₀-Cy-

cloalkyl sind, das nicht unterbrochen ist oder durch ein oder mehrere O, S, CO oder NR₂₁ unterbrochen ist; oder R₃₅ und R₃₆ oder R₃₇ und R₃₈ oder sowohl R₃₅ und R₃₆ als auch R₃₇ und R₃₈

5




sind und

10

R₄₁ C₆-C₂₀-Aryl oder C₃-C₂₀-Heteroaryl ist, wobei jeder von ihnen unsubstituiert oder mit einem oder mehreren Phenyl, Halogen, C₁-C₄-Halogenalkyl, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉ oder mit C₂-C₂₀-Alkyl substituiert ist, das durch ein oder mehrere O, S oder NR₂₁ unterbrochen ist, oder jeder von ihnen C₆-C₂₀-Aryl oder C₃-C₂₀-Heteroaryl mit einem oder mehreren C₁-C₂₀-Alkyl substituiert ist, das unsubstituiert oder mit einem oder mehreren Halogen, COOR₁₆, CONR₁₈R₁₉, Phenyl, C₃-C₈-Cycloalkyl, C₃-C₂₀-Heteroaryl, C₆-C₂₀-Aryloxycarbonyl, C₃-C₂₀-Heteroaryloxycarbonyl, OR₁₆, SR₁₇ oder NR₁₈R₁₉ substituiert ist; oder R₄₁

15

20



25

ist;


oder R₄₁ Wasserstoff, OH, C₁-C₂₀-Alkyl, C₁-C₄-Halogenalkyl, C₂-C₂₀-Alkyl ist, das durch ein oder mehrere O, CO oder NR₂₁ unterbrochen ist, oder R₄₁ C₃-C₂₀-Cycloalkyl ist, das nicht unterbrochen ist oder durch O, S, CO oder NR₂₁ unterbrochen ist.

30

2. Verbindungen der Formel I nach Anspruch 1, wobei

Z

35



40

ist;

R₁, R₂, R₃, R₄, R₅ und R₆ Wasserstoff sind;

R₁₀ und R₁₂ Wasserstoff sind;

R₁₁ Wasserstoff, OR₁₆ oder C₁-C₂₀-Alkyl ist;


R₉ und R₁₃ unabhängig voneinander OR₁₆ oder C₁-C₂₀-Alkyl sind;

45

R₁₄ C₆-C₂₀-Aryl ist, das unsubstituiert oder mit einem oder mehreren NO₂, OR₁₆, NR₁₈R₁₉ oder C₁-C₂₀-Alkyl substituiert ist, das C₁-C₂₀-Alkyl unsubstituiert oder mit SR₁₇ substituiert ist;

M

50



55

ist;

G -COR₂₈ ist;

R''₁₄ C₁-C₂₀-Alkyl oder C₆-C₂₀-Aryl ist, wobei das C₆-C₂₀-Aryl unsubstituiert oder mit C₁-C₂₀-Alkyl substituiert ist;

R₁₅ C₁-C₂₀-Alkyl ist;

R'₁₄ C₁-C₂₀-Alkyl ist;

R'₁₅ C₁-C₂₀-Alkyl ist;

X₃ zusammen mit **R₂₄** und **R₂₇** und den Phenyl-Ringen, an die sie gebunden sind, ein heteroaromatisches Ring-System bilden;

R₁₆ C₁-C₂₀-Alkyl ist, das unsubstituiert oder mit einem oder mehreren Halogen, OH, O(C₁-C₄-Alkyl), O(CO)-(C₁-C₄-Alkyl) oder O(C₁-C₂₀-Arylen)-M substituiert ist;

oder **R₁₆** C₂-C₂₀-Alkyl ist, das durch ein oder mehrere O unterbrochen ist, das unterbrochene C₂-C₂₀-Alkyl mit O-C₆-C₂₀-Arylen-M substituiert ist, in dem O-C₆-C₂₀-Arylen-M das Arylen unsubstituiert oder mit O(C₁-C₆-Alkyl) substituiert ist;


oder **R₁₆** C₁-C₈-Alkanoyl ist;

R₁₇ C₁-C₂₀-Alkyl ist, das unsubstituiert oder mit COOR₁₆ substituiert ist;

R₁₈ und **R₁₉** unabhängig voneinander C₁-C₂₀-Alkyl sind,

oder **R₁₈** und **R₁₉** zusammen mit dem N-Atom, an das sie gebunden sind, einen 5- oder 6-gliedrigen gesättigten oder ungesättigten Ring bilden, der nicht unterbrochen ist oder durch O unterbrochen ist,


oder **R₁₈** und **R₁₉** zusammen mit dem N-Atom, an das sie gebunden sind, eine Gruppe



bilden;

R₂₀ C₁-C₂₀-Alkyl oder C₂-C₂₀-Alkyl ist, das durch ein oder mehrere O unterbrochen ist, wobei das unterbrochene C₂-C₂₀-Alkyl unsubstituiert oder mit NR₁₈R₁₉ substituiert ist;

oder **R₂₀** C₆-C₂₀-Aryl ist, das mit



substituiert ist;


R₂₂, **R₂₃**, **R₂₅** und **R₂₆** Wasserstoff sind,

R₂₄ und **R₂₇** zusammen mit **X₃** und den Phenyl-Ringen, an die sie gebunden sind, ein heteroaromatisches Ring-System bilden;

R₂₈ C₆-C₂₀-Aryl ist, das unsubstituiert oder mit C₁-C₂₀-Alkyl substituiert ist;

R₃₃, **R₃₅**, **R₃₆**, **R₃₇**, **R₃₈** und **R₄₀** unabhängig voneinander Wasserstoff sind;

R₃₄



ist;

R₃₉ COR₄₁ ist;

R₄₁ C₆-C₂₀-Aryl ist, das unsubstituiert oder mit C₁-C₂₀-Alkyl substituiert ist.

3. Verbindungen der Formel I nach Anspruch 2, wobei

R''₁₄ C₁-C₂₀-Alkyl oder C₆-C₂₀-Aryl ist, das mit C₁-C₂₀-Alkyl substituiert ist;

R₁₆ C₁-C₂₀-Alkyl ist, das unsubstituiert oder mit einem oder mehreren Halogen, OH, O(C₁-C₄-Alkyl), O(CO)-(C₁-C₄-Alkyl) oder O(C₁-C₂₀-Arylen)-M substituiert ist;


oder **R₁₆** C₂-C₂₀-Alkyl ist, das durch ein oder mehrere O unterbrochen ist, wobei das unterbrochene C₂-C₂₀-Alkyl mit O-C₆-C₂₀-Arylen-M substituiert ist, in dem O-C₆-C₂₀-Arylen-M das Arylen mit O(C₁-C₆-Alkyl) substituiert ist;

oder **R₁₆** C₁-C₈-Alkanoyl ist;

R₁₇ C₁-C₂₀-Alkyl ist, das mit COOR₁₆ substituiert ist;

R₁₈ und **R₁₉** unabhängig voneinander C₁-C₂₀-Alkyl sind,
 oder **R₁₈** und **R₁₉** zusammen mit dem N-Atom, an das sie gebunden sind, einen 6-gliedrigen gesättigten Ring bilden,
 der nicht unterbrochen ist oder durch O unterbrochen ist,
 oder **R₁₈** und **R₁₉** zusammen mit dem N-Atom, an das sie gebunden sind, eine Gruppe

5




10

bilden;

R₂₀ C₁-C₂₀-Alkyl oder C₂-C₂₀-Alkyl ist, das durch ein oder mehrere O unterbrochen ist, wobei das unterbrochene C₂-C₂₀-Alkyl mit NR₁₈R₁₉ substituiert ist;
 oder **R₂₀** C₆-C₂₀-Aryl ist, das mit

20



substituiert ist;

R₂₄ und **R₂₇** zusammen mit X₃ und den Phenyl-Ringen, an die sie gebunden sind, ein Carbazolyl-Ring-System bilden;
R₂₈ C₆-C₂₀-Aryl ist, das mit C₁-C₂₀-Alkyl substituiert ist;
R₄₁ C₆-C₂₀-Aryl ist, das mit C₁-C₂₀-Alkyl substituiert ist.

25

4. Photopolymerisierbare Zusammensetzung, umfassend

30

- (a) mindestens eine ethylenisch ungesättigte photopolymerisierbare Verbindung und
- (b) als Photostarter mindestens eine Verbindung der Formel I, wie in Anspruch 1 definiert.

5. Photopolymerisierbare Zusammensetzung nach Anspruch 4, wobei die Komponente (a) ein durch die Reaktion von einem gesättigten oder ungesättigten mehrbasigen Säureanhydrid mit einem Produkt der Reaktion von einem Epoxid-Harz und einer ungesättigten Monocarbonsäure erhaltenes Harz ist.

35

6. Photopolymerisierbare Zusammensetzung nach Anspruch 4, zusätzlich zu dem Photostarter (b), umfassend mindestens einen weiteren Photostarter (c) und/oder andere Additive (d).

40

7. Photopolymerisierbare Zusammensetzung nach Anspruch 6 als weiteres Additiv (d), umfassend ein Pigment oder ein Gemisch von Pigmenten oder ein Gemisch von einem oder mehreren Pigmenten mit einem oder mehreren Farbstoffen.

45

8. Photopolymerisierbare Zusammensetzung nach Anspruch 7 als weiteres Additiv (d), umfassend ein Dispersionsmittel oder ein Gemisch von Dispersionsmitteln.

9. Photopolymerisierbare Zusammensetzung nach einem von Ansprüchen 4-8, umfassend 0,05 bis 25 Gewichts-% des Photostarters (b) oder der Photostarter (b) und (c), basierend auf der Zusammensetzung.


50

10. Photopolymerisierbare Zusammensetzung nach einem von Ansprüchen 4-9 als weiteres Additiv (d), umfassend einen Photosensibilisator, insbesondere eine Verbindung, ausgewählt aus der Gruppe, bestehend aus Benzophenon, Benzophenon-Derivaten, Thioxanthon, Thioxanthon-Derivaten, Anthrachinon, Anthrachinon-Derivaten, Cumarin und Cumarin-Derivaten.



55

11. Photopolymerisierbare Zusammensetzung nach einem von Ansprüchen 4-10, zusätzlich umfassend ein Bindemittel-Polymer (e), insbesondere ein Copolymer von Methacrylat und Methacrylsäure.

12. Verfahren zur Herstellung einer Verbindung der Formel I nach Anspruch 1 durch Umsetzen der entsprechenden Oxim-Verbindung der Formel IA



15 worin **Z, Q, R₁, R₂, R₃, R₄, R₅, R₆, R₂₀** und **R₁₄** wie in Anspruch 1 definiert sind, mit einem Acyl-halogenid der Formel 2 oder einem Anhydrid der Formel 3




25 wobei **Hal** ein Halogen, insbesondere Cl, ist und **R₁₅** wie in Anspruch 1 definiert ist, in Gegenwart einer Base oder eines Gemisches von Basen.

- 30 13. Verfahren zur Photopolymerisation von Verbindungen, die ethylenisch ungesättigte Doppel-Bindungen enthalten, das Bestrahlen einer Zusammensetzung nach einem der Ansprüche 4-11 mit elektromagnetischer Strahlung im Bereich von 150 bis 600 nm oder mit Elektronenstrahl oder mit Röntgenstrahlen umfasst.

- 35 14. Farb-Filter, hergestellt durch Bereitstellen roter, grüner und blauer Bild-Elemente und gegebenenfalls einer schwarzen Matrix, alle umfassend ein lichtempfindliches Harz und ein Pigment auf einem transparenten Substrat und Bereitstellen einer transparenten Elektrode entweder auf der Oberfläche des Substrats oder auf der Oberfläche der Farb-Filter-Schicht, wobei das lichtempfindliche Harz ein polyfunktionelles Acrylat-Monomer, ein organisches Polymer-Bindemittel und einen Photopolymerisations-Starter der Formel I, wie in Anspruch 1 definiert, umfasst.

15. Verbindungen der Formel IA



50 worin **Z, R₁, R₂, R₃, R₄, R₅, R₆, R₂₀** und **R₁₄** wie in Anspruch 1 definiert sind.

16. Beschichtetes Substrat, das auf mindestens einer Oberfläche mit einer Zusammensetzung nach Anspruch 4 beschichtet ist.


- 55 17. Verfahren zur photographischen Herstellung von Relief-Bildern, in dem ein beschichtetes Substrat nach Anspruch 16 bildmäßiger Belichtung unterzogen wird und dann die nicht exponierten Abschnitte mit einem Entwickler entfernt werden.

18. Utilisation d'une Verbindung der Formel I nach Anspruch 1 zur Photopolymerisation einer Zusammensetzung, umfassend mindestens eine ethylenisch ungesättigte photopolymerisierbare Verbindung.

19. Verfahren nach Anspruch 13 zum Erzeugen von pigmentierten und nicht-pigmentierten Anstrichen und Lacken, Pulver-Beschichtungen, Druck-Farben, Druck-Platten, Klebstoffen, dentalen Zusammensetzungen, Gel-Beschichtungen, Photoresists, zum Einkapseln elektrischer und elektronischer Komponenten, zum Herstellen magnetischer Aufzeichnungs-Materialien, mikromechanischer Teile, Wellenleitern, optischen Schaltern, Plattierungs-Masken, Farb-Prüf-Systemen, Glas-Faser-Kabel-Beschichtungen, Sieb-Druck-Schablonen, drei-dimensionalen Gegenständen mit Hilfe von Stereolithographie, Bild-Aufzeichnungs-Materialien für holographische Aufzeichnungen, mikroelektronischen Schaltkreisen, entfärbenden Materialien, Mikrokapseln enthaltenden Formulierungen.


Revendications

1. Composés de formule I



dans lesquels

Z est



R₁, R₂, R₃, R₄, R₅ et R₆, indépendamment les uns des autres, sont hydrogène, halogène, OR₁₆, SR₁₇, NR₁₈R₁₉, ou alkyle en C₁-C₂₀ qui est non substitué ou substitué par un ou plusieurs groupes halogène, OR₁₆, COOR₁₆, CONR₁₈R₁₉ ou NR₁₈R₁₉ ;


ou R₁, R₂, R₃, R₄, R₅ et R₆, indépendamment les uns des autres, sont aryle en C₆-C₂₀, ou hétéroaryle en C₄-C₂₀, dont chacun est non substitué ou substitué par un ou plusieurs alkyle en C₁-C₆, halogénoalkyle en C₁-C₄ ou halogène ;

R₉, R₁₀, R₁₁, R₁₂ et R₁₃, indépendamment les uns des autres, sont hydrogène, halogène, OR₁₆, SR₁₇, NR₁₈R₁₉, CN, NO₂ ou alkyle en C₂-C₂₀ qui est interrompu par un ou plusieurs groupes O, S ou NR₂₁, où l'alkyle en C₂-C₂₀ interrompu est non substitué ou substitué par un ou plusieurs groupes halogène, OR₁₆, COOR₁₆, SR₁₇, CONR₁₈R₁₉, aryle en C₆-C₂₀, hétéroaryle en C₃-C₂₀ ou cycloalkyle en C₃-C₂₀, cycloalkyle en C₃-C₂₀ interrompu par un ou plusieurs groupes O, S, NR₂₁ ;


ou R₉, R₁₀, R₁₁, R₁₂ et R₁₃, indépendamment les uns des autres, sont alkyle en C₁-C₂₀ qui est non substitué ou substitué par un ou plusieurs groupes halogène, OR₁₆, SR₁₇, COOR₁₆, CONR₁₈R₁₉, NR₁₈R₁₉, phényle, cycloalkyle en C₃-C₈, hétéroaryle en C₃-C₂₀ ou M ;

à condition que R₉ et R₁₃ ne soient ni hydrogène, ni fluor ;


R₁₄ est aryle en C₆-C₂₀ ou hétéroaryle en C₃-C₂₀ dont chacun est non substitué ou substitué par un ou plusieurs groupes phényle, halogène, halogénoalkyle en C₁-C₄, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉, PO(OC_kH_{2k+1})₂, SO-(alkyle en C₁-C₁₀), SO₂-(alkyle en C₁-C₁₀), M,



ou par alkyle en C₂-C₂₀ qui est interrompu par un ou plusieurs groupes O, CO, S, C(O)O, OC(O), phénylène, naphtylène ou par NR₂₁, ou chacun desdits aryle en C₆-C₂₀ ou hétéroaryle en C₃-C₂₀ est substitué par un ou plusieurs groupes alkyle en C₁-C₂₀ qui sont non substitués ou substitués par un ou plusieurs groupes halogène, COOR₁₆, CONR₁₈R₁₉, phényle, cycloalkyle en C₃-C₈, hétéroaryle en C₃-C₂₀, aryloxy-carbonyle en C₆-C₂₀, hétéroaryloxy-carbonyle en C₃-C₂₀, OR₁₆, SR₁₇, NR₁₈R₁₉ ou par M ;
M est



ou



G est NO₂ ou-COR₂₈ ;

R''₁₄ est alkyle en C₁-C₂₀ qui est non substitué ou substitué par phényle ou par phényle qui est substitué par un ou plusieurs groupes halogène, alkyle en C₁-C₂₀, halogénoalkyle en C₁-C₄, OR₁₆, SR₁₇ ou par NR₁₈R₁₉ ;
ou R''₁₄ est alkyle en C₂-C₂₀ qui est interrompu par un ou plusieurs groupes O, CO, S, C(O)O, OC(O), phénylène, naphtylène ou NR₂₁, où l'alkyle en C₂-C₂₀ interrompu est non substitué ou substitué par un ou plusieurs groupes halogène, OR₁₆, COOR₁₆, CONR₁₈R₁₉, phényle ou par phényle qui est substitué par OR₁₆, SR₁₇ ou NR₁₈R₁₉ ;
ou R''₁₄ est CN, CONR₁₈R₁₉, NO₂, halogénoalkyle en C₁-C₄, S(O)_m-(alkyle en C₁-C₆), S(O)_m-phényle qui est non substitué ou substitué par alkyle en C₁-C₁₂ ou SO₂-(alkyle en C₁-C₆) ;
ou R''₁₄ est SO₂O-phényle qui est non substitué ou substitué par alkyle en C₁-C₁₂ ; ou est diphenyl-phosphinoyl ou di-(alcoxy en C₁-C₄)-phosphinoyl ;

ou R''₁₄ est aryle en C₆-C₂₀ ou hétéroaryle en C₃-C₂₀ dont chacun est non substitué ou substitué par un ou plusieurs groupes phényle, halogène, halogénoalkyle en C₁-C₄, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉, PO(OC_kH_{2k+1})₂, SO-(alkyle en C₁-C₁₀), SO₂-(alkyle en C₁-C₁₀), ou par alkyle en C₂-C₂₀ qui est interrompu par un ou plusieurs groupes O, CO, S, C(O)O, OC(O), phénylène, naphtylène ou par NR₂₁, ou dont chacun est substitué par un ou plusieurs groupes alkyle en C₁-C₂₀ qui sont non substitués ou substitués par un ou plusieurs groupes halogène, COOR₁₆, CONR₁₈R₁₉, phényle, cycloalkyle en C₃-C₈, hétéroaryle en C₃-C₂₀, aryloxy-carbonyle en C₆-C₂₀, hétéroaryloxy-carbonyle en C₃-C₂₀, OR₁₆, SR₁₇ ou par NR₁₈R₁₉ ;

R₁₅ est hydrogène, cycloalkyle en C₃-C₈, alcényle en C₂-C₅, alkyle en C₁-C₂₀ ou phényle ;

k est un entier de 1 à 10 ;

m est un entier de 1 ou 2 ;

R'₁₄ a une des significations données pour R₁₄ ou est alkyle en C₁-C₂₀ ;

R'₁₅ a une des significations données pour R₁₅ ;

X₁ est O, CO, S ou une liaison directe ;

X₃ est O, S ou NR'₂₀ ;

R₁₆ est hydrogène, phényl- (alkyle en C₁-C₃), alkyle en C₁-C₂₀, qui est non substitué ou substitué par un ou plusieurs groupes halogène, OH, SH, CN, alcénoxy en C₃-C₆, O(alkyle en C₁-C₄), OCH₂CH₂CN, OCH₂CH₂(CO)O(alkyle en C₁-C₄), O(CO)-(alkyle en C₁-C₄), O(CO)-(alcényle en C₂-C₄), O(CO)-phényle, (CO)OH, (CO)O(alkyle en C₁-C₄), cycloalkyle en C₃-C₂₀, SO₂-(halogénoalkyle en C₁-C₄), O(halogénoalkyle en C₁-C₄), O(arylène en C₁-C₂₀)-M, ou par cycloalkyle en C₃-C₂₀ qui est interrompu par un ou plusieurs groupes O ;


ou R₁₆ est alkyle en C₂-C₂₀ qui est interrompu par un ou plusieurs groupes O, S ou NR₂₁, ledit alkyle en C₂-C₂₀ interrompu étant non substitué ou substitué par O-(arylène en C₆-C₂₀)-M, où, dans ledit O-(arylène en C₆-C₂₀)-M, l'arylène est non substitué ou substitué par un ou plusieurs groupes alkyle en C₁-C₆ ou O(alkyle en C₁-C₆) ;
ou R₁₆ est (CH₂CH₂O)_{n+1}H, (CH₂CH₂O)_n(CO)-(alkyle en C₁-C₈), alcanoyl en C₁-C₈, alcényle en C₂-C₁₂, alcényle en C₃-C₈, ou cycloalkyle en C₃-C₂₀ qui est ininterrompu ou interrompu par un ou plusieurs groupes

O, S, CO ou NR₂₁ ;

ou R₁₆ est (alkyle en C₁-C₈)-(cycloalkyle en C₃-C₁₀) qui est ininterrompu ou interrompu par un ou plusieurs groupes O ;

ou R₁₆ est benzoyle qui est non substitué ou substitué par un ou plusieurs groupes alkyle en C₁-C₆, halogène, OH ou alcoxy en C₁-C₃ ;

ou R₁₆ est phényle, naphthyle ou hétéroaryle en C₃-C₂₀, dont chacun est non substitué ou substitué par un ou plusieurs groupes halogène, OH, alkyle en C₁-C₁₂, alcoxy en C₁-C₁₂, CN, NO₂, phényl- (alkyloxy en C₁-C₃), phénoxy, alkylsulfanyle en C₁-C₁₂, phénylsulfanyle, N(alkyle en C₁-C₁₂)₂, diphenylamino ou



n est 1 à 20 ;

R₁₇ est hydrogène, alcényle en C₂-C₁₂, cycloalkyle en C₃-C₂₀ ou phényl-(alkyle en C₁-C₃), où l'alcényle en C₂-C₁₂, cycloalkyle en C₃-C₂₀ ou phényl- (alkyle en C₁-C₃) est ininterrompu ou interrompu par un ou plusieurs groupes O, S, CO ou NR₂₁ ;


ou R₁₇ est alkyle en C₁-C₂₀ qui est non substitué ou substitué par un ou plusieurs groupes OH, SH, CN, alcénoxy en C₃-C₆, OCH₂CH₂CN, OCH₂CH₂(CO)O(alkyle en C₁-C₄), O(CO)-(alcényle en C₂-C₄), O(CO)-(alkyle en C₁-C₄), O(CO)-phényle, COOR₁₆ ou S-(arylène en C₆-C₂₀)-M ;

ou R₁₇ est alkyle en C₁-C₂₀ qui est non substitué ou substitué par un ou plusieurs groupes OH, SH, CN, alcénoxy en C₃-C₆, OCH₂CH₂CN, OCH₂CH₂(CO)O(alkyle en C₁-C₄), O(CO)-(alcényle en C₂-C₄), O(CO)-(alkyle en C₁-C₄), O(CO)-phényle ou COOR₁₆ ;

ou R₁₇ est alkyle en C₂-C₂₀ qui est interrompu par un ou plusieurs groupes O, S, CO ou NR₂₁, ledit alkyle en C₂-C₂₀ interrompu étant non substitué ou substitué par S-(arylène en C₆-C₂₀)-M ; ou R₁₇ est (CH₂CH₂O)_nH, (CH₂CH₂O)_n(CO)-(alkyle en C₁-C₈), alcanoyle en C₂-C₈ ou alcénoyle en C₃-C₈ ;

ou R₁₇ est benzoyle qui est non substitué ou substitué par un ou plusieurs groupes alkyle en C₁-C₆, halogène, OH, alcoxy en C₁-C₄ ou alkylsulfanyle en C₁-C₄ ;


ou R₁₇ est phényle, naphthyle ou hétéroaryle en C₃-C₂₀, dont chacun est non substitué ou substitué par un ou plusieurs groupes halogène, alkyle en C₁-C₁₂, halogénoalkyle en C₁-C₄, alcoxy en C₁-C₁₂, CN, NO₂, phényl- (alkyloxy en C₁-C₃), phénoxy, alkylsulfanyle en C₁-C₁₂, phénylsulfanyle, N(alkyle en C₁-C₁₂)₂, diphenylamino, (CO)O(alkyle en C₁-C₈), (CO)-(alkyle en C₁-C₈), (CO)N(alkyle en C₁-C₈)₂ ou



R₁₈ et R₁₉, indépendamment l'un de l'autre, sont hydrogène, alkyle en C₁-C₂₀, hydroxyalkyle en C₂-C₄, alcoxyalkyle en C₂-C₁₀, alcényle en C₂-C₅, cycloalkyle en C₃-C₂₀, phényl-(alkyle en C₁-C₃), alcanoyle en C₁-C₈, alcanoyloxy en C₁-C₈, alcénoyle en C₃-C₁₂, SO₂-(halogénoalkyle en C₁-C₄) ou benzoyle ;


ou R₁₈ et R₁₉ sont phényle, naphthyle ou hétéroaryle en C₃-C₂₀, dont chacun est non substitué ou substitué par un ou plusieurs groupes halogène, halogénoalkyle en C₁-C₄, alcoxy en C₁-C₂₀, alkyle en C₁-C₁₂, benzoyle ou alcoxy en C₁-C₁₂ ;

ou R₁₈ et R₁₉, conjointement avec l'atome N auquel ils sont liés, forment un cycle saturé ou insaturé de 5 ou 6 chaînons qui est ininterrompu ou est interrompu par O, S ou NR₂₁, et ledit cycle saturé ou insaturé de 5 ou 6 chaînons est non substitué ou substitué par un ou plusieurs groupes alkyle en C₁-C₂₀, alcoxy en C₁-C₂₀, =O, OR₁₆, SR₁₇, NR₃₁R₃₂, COR₄₁, NO₂, halogène, halogénoalkyle en C₁-C₄, CN, phényle,



ou par cycloalkyle en C₃-C₂₀ qui est ininterrompu ou est interrompu par un ou plusieurs groupes O, S, CO ou NR₂₁ ;

ou R₁₈ et R₁₉, conjointement avec l'atome N auquel ils sont liés, forment un groupe




5

10

15

R_{20} est hydrogène, COR_{41} ou alkyle en C_1-C_{20} qui est non substitué ou substitué par un ou plusieurs groupes halogène, OR_{16} , SR_{17} , $COOR_{16}$, $CONR_{18}R_{19}$, $NR_{18}R_{19}$, $PO(OC_kH_{2k+1})_2$ ou M ;
ou R_{20} est alkyle en C_2-C_{20} qui est interrompu par un ou plusieurs groupes O , CO , $C(O)O$, $OC(O)$ ou NR_{21} , où l'alkyle en C_2-C_{20} interrompu est non substitué ou substitué par un ou plusieurs groupes halogène, OR_{16} , SR_{17} , $COOR_{16}$, $CONR_{18}R_{19}$, $NR_{18}R_{19}$ ou M ;
ou R_{20} est aryle en C_6-C_{20} ou hétéroaryle en C_3-C_{20} dont chacun est non substitué ou substitué par un ou plusieurs groupes phényle, halogène, halogénoalkyle en C_1-C_4 , CN , NO_2 , OR_{16} , SR_{17} , $NR_{18}R_{19}$, M , Z ,




20

25

30

ou par alkyle en C_1-C_{20} qui est interrompu par un ou plusieurs groupes O , S ou NR_{21} , ou chacun desdits aryle en C_6-C_{20} ou hétéroaryle en C_3-C_{20} est substitué par un ou plusieurs groupes alkyle en C_1-C_{20} qui sont non substitués ou substitués par un ou plusieurs groupes halogène, $COOR_{16}$, $CONR_{18}R_{19}$, phényle, cycloalkyle en C_3-C_8 , hétéroaryle en C_3-C_{20} , aryloxy-carbonyle en C_6-C_{20} , hétéroaryloxy-carbonyle en C_3-C_{20} , OR_{16} , SR_{17} ou $NR_{18}R_{19}$;
 R'_{20} est hydrogène, COR_{41} ou alkyle en C_1-C_{20} qui sont non substitués ou substitués par un ou plusieurs groupes halogène, OR_{16} , SR_{17} , $COOR_{16}$, $CONR_{18}R_{19}$, $NR_{18}R_{19}$ ou $PO(OC_kH_{2k+1})_2$;
ou R'_{20} est alkyle en C_2-C_{20} qui est interrompu par un ou plusieurs groupes O , CO , $C(O)O$, $OC(O)$ ou NR_{21} , où l'alkyle en C_2-C_{20} interrompu est non substitué ou substitué par un ou plusieurs groupes halogène, OR_{16} , SR_{17} , $COOR_{16}$, $CONR_{18}R_{19}$ ou $NR_{18}R_{19}$;
ou R'_{20} est aryle en C_6-C_{20} ou hétéroaryle en C_3-C_{20} dont chacun est non substitué ou substitué par un ou plusieurs groupes phényle, halogène, halogénoalkyle en C_1-C_4 , CN , NO_2 , OR_{16} , SR_{17} , $NR_{18}R_{19}$,

35




40

45


ou par alkyle en C_1-C_{20} qui est interrompu par un ou plusieurs groupes O , S ou NR_{21} , ou chacun desdits aryle en C_6-C_{20} ou hétéroaryle en C_3-C_{20} est substitué par un ou plusieurs groupes alkyle en C_1-C_{20} qui est non substitué ou substitué par un ou plusieurs groupes halogène, $COOR_{16}$, $CONR_{18}R_{19}$, phényle, cycloalkyle en C_3-C_8 , hétéroaryle en C_3-C_{20} , aryloxy-carbonyle en C_6-C_{20} , hétéroaryloxy-carbonyle en C_3-C_{20} , OR_{16} , SR_{17} ou $NR_{18}R_{19}$;
 R_{21} est hydrogène, alkyle en C_1-C_{20} , halogénoalkyle en C_1-C_4 ou alkyle en C_2-C_{20} qui est interrompu par un ou plusieurs groupes O , CO , $C(O)O$ ou $OC(CO)$,
ou R_{21} est COR_{41} , phényl- (alkyle en C_1-C_4) ou cycloalkyle en C_3-C_8 qui est ininterrompu ou est interrompu par un ou plusieurs groupes O ou CO ,
ou R_{21} est phényle ou naphyle dont tous deux sont non substitués ou substitués par un ou plusieurs groupes alkyle en C_1-C_{20} , halogène, halogénoalkyle en C_1-C_4 , OR_{16} , SR_{17} , $NR_{18}R_{19}$ ou

50



R_{22} , R_{23} , R_{24} , R_{25} , R_{26} ou R_{27} , indépendamment les uns des autres, sont hydrogène, COR_{41} , NO_2 ou

55




EP 2 847 167 B9

ou l'un de R₂₂, R₂₃ ou R₂₄ et l'un de R₂₅, R₂₆ ou R₂₇, conjointement avec X₃ et les cycles phényle auxquels ils sont liés, forment un système cyclique hétéroaromatique ; R₂₈ est aryle en C₆-C₂₀ ou hétéroaryle en C₃-C₂₀ dont chacun est non substitué ou substitué par un ou plusieurs groupes phényle, halogène, halogénoalkyle en C₁-C₄, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉ ou par alkyle en C₂-C₂₀ qui est interrompu par un ou plusieurs groupes O, S ou NR₂₁, ou chacun desdits aryle en C₆-C₂₀ ou hétéroaryle en C₃-C₂₀ est substitué par un ou plusieurs groupes alkyle en C₁-C₂₀ qui est non substitué ou substitué par un ou plusieurs groupes halogène, COOR₁₆, CONR₁₈R₁₉, phényle, cycloalkyle en C₃-C₈, hétéroaryle en C₃-C₂₀, aryloxy-carbonyle en C₆-C₂₀, hétéroaryloxy-carbonyle en C₃-C₂₀, OR₁₆, SR₁₇ ou NR₁₈R₁₉ ;


R₃₁ et R₃₂, indépendamment l'un de l'autre, sont hydrogène, alkyle en C₁-C₂₀, halogénoalkyle en C₁-C₄, cycloalkyle en C₃-C₁₀ ou phényle ;

ou R₃₁ et R₃₂, conjointement avec l'atome N auquel ils sont liés, forment un cycle saturé ou insaturé de 5 ou 6 chaîons, qui est ininterrompu ou est interrompu par O, S ou NR₂₁, et ledit cycle saturé ou insaturé de 5 ou 6 chaîons n'est pas condensé ou un cycle benzénique est condensé avec le cycle saturé ou insaturé de 5 ou 6 chaîons ;

R₃₃, R₃₄, R₃₅, R₃₆, R₃₇, R₃₈, R₃₉ et R₄₀, indépendamment les uns des autres, sont hydrogène,




NO₂, COR₄₁, alkyle en C₁-C₂₀, halogénoalkyle en C₁-C₄, OR₁₆, SR₁₇, NR₁₈R₁₉, halogène, CN, phényle ou cycloalkyle en C₃-C₂₀ qui est ininterrompu ou est interrompu par un ou plusieurs groupes O, S, CO ou NR₂₁ ; ou R₃₅ et R₃₆ ou R₃₇ et R₃₈ ou les deux, R₃₅ et R₃₆ et R₃₇ et R₃₈ sont



et

R₄₁ est aryle en C₆-C₂₀ ou hétéroaryle en C₃-C₂₀ dont chacun est non substitué ou substitué par un ou plusieurs groupes phényle, halogène, halogénoalkyle en C₁-C₄, CN, NO₂, OR₁₆, SR₁₇, NR₁₈R₁₉ ou par alkyle en C₂-C₂₀ qui est interrompu par un ou plusieurs groupes O, S ou NR₂₁, ou chacun desdits aryle en C₆-C₂₀ ou hétéroaryle en C₃-C₂₀ est substitué par un ou plusieurs groupes alkyle en C₁-C₂₀ qui sont non substitués ou substitués par un ou plusieurs groupes halogène, COOR₁₆, CONR₁₈R₁₉, phényle, cycloalkyle en C₃-C₈, hétéroaryle en C₃-C₂₀, aryloxy-carbonyle en C₆-C₂₀, hétéroaryloxy-carbonyle en C₃-C₂₀, OR₁₆, SR₁₇ ou NR₁₈R₁₉ ;


ou R₄₁ est



ou R₄₁ est hydrogène, OH, alkyle en C₁-C₂₀, halogénoalkyle en C₁-C₄, alkyle en C₂-C₂₀ qui est interrompu par un ou plusieurs groupes O, CO ou NR₂₁, ou R₄₁ est cycloalkyle en C₃-C₂₀ qui est ininterrompu ou est interrompu par O, S, CO ou NR₂₁.

2. Composés de formule I selon la revendication 1, dans lesquels

Z est



EP 2 847 167 B9

R₁, R₂, R₃, R₄, R₅ et R₆ sont hydrogène ;


R₁₀ et R₁₂ sont hydrogène ;

R₁₁ est hydrogène, OR₁₆ ou alkyle en C₁-C₂₀ ;

R₉ et R₁₃, indépendamment l'un de l'autre, sont OR₁₆ ou alkyle en C₁-C₂₀ ;

R₁₄ est aryle en C₆-C₂₀ qui est non substitué ou substitué par un ou plusieurs groupes NO₂, OR₁₆, NR₁₈R₁₉ ou alkyle en C₁-C₂₀, ledit alkyle en C₁-C₂₀ est non substitué ou substitué par SR₁₇ ;

M est



G est -COR₂₈ ;

R'₁₄ est alkyle en C₁-C₂₀ ou aryle en C₆-C₂₀, ledit aryle en C₆-C₂₀ étant non substitué ou substitué par alkyle en C₁-C₂₀ ;

R₁₅ est alkyle en C₁-C₂₀ ;

R'₁₄ est alkyle en C₁-C₂₀ ;

R'₁₅ est alkyle en C₁-C₂₀ ;

X₃, conjointement avec R₂₄ et R₂₇ et les cycles phényle auxquels ils sont liés, forme un système de cycle hétéroaromatique ;

R₁₆ est alkyle en C₁-C₂₀, qui est non substitué ou substitué par un ou plusieurs groupes halogène, OH, O(alkyle en C₁-C₄), O(CO)-(alkyle en C₁-C₄) ou O(arylène en C₁-C₂₀)-M ;


ou R₁₆ est alkyle en C₂-C₂₀ qui est interrompu par un ou plusieurs groupes O, ledit alkyle en C₂-C₂₀ interrompu étant substitué par O-(arylène en C₆-C₂₀)-M, où, dans ledit O-(arylène en C₆-C₂₀)-M, l'arylène est non substitué ou substitué par O(alkyle en C₁-C₆) ;

ou R₁₆ est alcanoyle en C₁-C₈ ;

R₁₇ est alkyle en C₁-C₂₀ qui est non substitué ou substitué par COOR₁₆ ;


R₁₈ et R₁₉, indépendamment l'un de l'autre, sont alkyle en C₁-C₂₀,

ou R₁₈ et R₁₉, conjointement avec l'atome N auquel ils sont liés, forment un cycle saturé ou insaturé de 5 ou 6 chaînons qui est ininterrompu ou est interrompu par O, ou R₁₈ et R₁₉, conjointement avec l'atome N auquel ils sont liés, forment un groupe



R₂₀ est alkyle en C₁-C₂₀ ou alkyle en C₂-C₂₀ qui est interrompu par un ou plusieurs groupes O, où l'alkyle en C₂-C₂₀ interrompu est non substitué ou substitué par NR₁₈R₁₉ ;

ou R₂₀ est aryle en C₆-C₂₀ qui est substitué par




R₂₂, R₂₃, R₂₅ et R₂₆ sont hydrogène,

R₂₄ et R₂₇, conjointement avec X₃ et les cycles phényle auxquels ils sont liés, forment un système de cycle hétéroaromatique ;

R₂₈ est aryle en C₆-C₂₀ qui est non substitué ou substitué par alkyle en C₁-C₂₀ ;

R₃₃, R₃₃, R₃₆, R₃₇, R₃₈ et R₄₀, indépendamment les uns des autres, sont hydrogène ;


R₃₄ est




5 R₃₉ est COR₄₁ ;
R₄₁ est aryle en C₆-C₂₀ qui est non substitué ou substitué par alkyle en C₁-C₂₀.

3. Composés de formule I selon la revendication 2, dans lesquels

10 R'₁₄ est alkyle en C₁-C₂₀ ou aryle en C₆-C₂₀ qui est substitué par alkyle en C₁-C₂₀ ;
R₁₆ est alkyle en C₁-C₂₀, qui est non substitué ou substitué par un ou plusieurs groupes halogène, OH, O(alkyle en C₁-C₄), O(CO)-(alkyle en C₁-C₄) ou O(arylène en C₁-C₂₀)-M ;
ou R₁₆ est alkyle en C₂-C₂₀ qui est interrompu par un ou plusieurs groupes O, ledit alkyle en C₂-C₂₀ interrompu étant substitué par O-(arylène en C₆-C₂₀)-M, où, dans ledit O-(arylène en C₆-C₂₀)-M, l'arylène est substitué par O(alkyle en C₁-C₆) ;
15 ou R₁₆ est alcanoylé en C₁-C₈ ;
R₁₇ est alkyle en C₁-C₂₀ qui est substitué par COOR₁₆ ;
R₁₈ et R₁₉, indépendamment l'un de l'autre, sont alkyle en C₁-C₂₀,
ou R₁₈ et R₁₉, conjointement avec l'atome N auquel ils sont liés, forment un cycle saturé de 6 chaînons qui est ininterrompu ou est interrompu par O,
20 ou R₁₈ et R₁₉, conjointement avec l'atome N auquel ils sont liés, forment un groupe



25 R₂₀ est alkyle en C₁-C₂₀ ou alkyle en C₂-C₂₀ qui est interrompu par un ou plusieurs groupes O, où l'alkyle en C₂-C₂₀ interrompu est substitué par NR₁₈R₁₉ ;
ou R₂₀ est aryle en C₆-C₂₀ qui est substitué par



35 R₂₄ et R₂₇, conjointement avec X₃ et les cycles phényle auxquels ils sont liés, forment un système de cycle carbazolylyle ;
R₂₈ est aryle en C₆-C₂₀ qui est substitué par alkyle en C₁-C₂₀ ;
40 R₄₁ est aryle en C₆-C₂₀ qui est substitué par alkyle en C₁-C₂₀.

4. Composition photopolymérisable comprenant

45 (a) au moins un composé photopolymérisable éthyléniquement insaturé et
(b) en tant que photo-initiateur, au moins un composé de formule I tel que défini dans la revendication 1.

5. Composition photopolymérisable selon la revendication 4, dans laquelle le composant (a) est une résine obtenue par la réaction d'un anhydride d'acide polybasique saturé ou insaturé avec un produit de la réaction d'une résine époxy et d'un acide monocarboxylique insaturé.


6. Composition photopolymérisable selon la revendication 4, comprenant, en plus du photo-initiateur (b), au moins un photo-initiateur supplémentaire (c), et/ou d'autres additifs (d).

7. Composition photopolymérisable selon la revendication 6 en tant qu'additif supplémentaire (d) comprenant un pigment ou un mélange de pigments ou un mélange d'un ou plusieurs pigments avec un ou plusieurs colorants.



8. Composition photopolymérisable selon la revendication 7 en tant qu'additif supplémentaire (d) comprenant un dispersant ou un mélange de dispersants.

EP 2 847 167 B9

9. Composition photopolymérisable selon l'une quelconque des revendications 4 à 8, comprenant 0,05 à 25 % en poids du photo-initiateur (b), ou des photo-initiateurs (b) et (c), sur la base de la composition.
10. Composition photopolymérisable selon l'une quelconque des revendications 4 à 9 en tant qu'additif supplémentaire (d) comprenant un photosensibilisateur, en particulier un composé choisi dans le groupe constitué des benzophénone, dérivés de benzophénone, thioxanthone, dérivés de thioxanthone, anthraquinone, dérivés d'anthraquinone, coumarine et dérivés de coumarine.
11. Composition photopolymérisable selon l'une quelconque des revendications 4 à 10 comprenant en outre un polymère liant (e), en particulier un copolymère de méthacrylate et d'acide méthacrylique.
12. Procédé de préparation d'un composé de formule I selon la revendication 1 par réaction du composé oxime correspondant de formule IA




dans laquelle Z, R₁, R₂, R₃, R₄, R₅, R₆, R₂₀ et R₁₄ sont tels que définis dans la revendication 1, avec un halogénure d'acyle de formule 2 ou un anhydride de formule 3



où Hal est un halogène, en particulier Cl, et R₁₅ est tel que défini dans la revendication 1, en présence d'une base ou un mélange de bases.

13. Procédé de photopolymérisation de composés contenant des doubles liaisons éthyléniquement insaturées, qui comprend l'irradiation d'une composition selon l'une quelconque des revendications 4 à 11 avec un rayonnement électromagnétique dans la plage de 150 à 600 nm, ou avec un faisceau d'électrons ou avec des rayons X.
14. Filtre coloré préparé par fourniture d'éléments d'image rouges, verts et bleus et facultativement une matrice noire, tous comprenant une résine photosensible et un pigment sur un substrat transparent et fourniture d'une électrode transparente sur la surface du substrat ou sur la surface de la couche de filtre coloré, dans lequel ladite résine photosensible comprend un monomère d'acrylate polyfonctionnel, un liant de polymère organique et un initiateur de photopolymérisation de formule I tel que défini dans la revendication 1.
15. Composés de formule IA



dans lesquels Z, R₁, R₂, R₃, R₄, R₅, R₆, R₂₀ et R₁₄ sont tels que définis dans la revendication 1.

16. Substrat revêtu qui est revêtu sur au moins une surface avec une composition selon la revendication 4.
17. Procédé de production photographique d'images en relief, dans lequel un substrat revêtu selon la revendication 16 est soumis à une exposition selon une image et ensuite, les parties non exposées sont éliminées avec un révélateur.
18. Utilisation d'un composé de formule I selon la revendication 1 pour la photopolymérisation d'une composition comprenant au moins un composé photopolymérisable éthyléniquement insaturé.
19. Procédé selon la revendication 13 pour produire des peintures et des vernis pigmentés et non pigmentés, des revêtements en poudre, des encres d'impression, des plaques d'impression, des adhésifs, des compositions dentaires, des couches de gel, des résines photosensibles, pour encapsuler des composants électriques et électroniques, pour produire des matériaux d'enregistrement magnétiques, des pièces de micromécanique, des guides d'ondes, des commutateurs optiques, des masques de placage, des systèmes d'épreuve couleur, des revêtements de câble en fibre de verre, des pochoirs de sérigraphie, des objets tridimensionnels au moyen de la stéréolithographie, des matériaux d'enregistrement d'image pour des enregistrements holographiques, des circuits microélectroniques, des matériaux décolorants, des formulations contenant des microcapsules.

5

10

15

20

25

30

35

40

45

50

55

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- WO 02100903 A [0001]
- JP 2006030809 A [0001]
- JP 2006162784 A [0001]
- JP 2009128419 A [0001]
- JP 2005099258 A [0001]
- WO 9001512 A [0097]
- EP 624826 A [0101] [0147]
- JP 6001638 A [0103]
- JP 10301276 B [0103]
- JP 6001938 A [0105]
- JP 8278629 A [0105]
- JP 8278630 A [0105]
- JP 10301276 A [0105]
- JP 2001040022 A [0105]
- JP 10221843 A [0105] [0163] [0164]
- JP 11231523 A [0105]
- JP 2002206014 A [0105] [0147]
- JP 2006053569 A [0105]
- EP 12339 A [0106]
- EP 33896 A [0106]
- EP 41125 A [0106]
- DE 2936039 [0106]
- EP 126541 A [0107]
- US 4950581 A [0107]
- EP 780729 A [0107]
- EP 497531 A [0107]
- EP 441232 A [0107]
- WO 04074328 A [0108]
- EP 339841 A [0109]
- EP 438123 A [0109]
- GB 2180358 A [0109]
- JP HEI668309 B [0109]
- WO 06008251 A [0109]
- JP 9179299 A [0110]
- JP 9325209 A [0110]
- EP 245639 A [0110]
- EP 445624 A [0110]
- US 5013768 A [0110]
- JP 10171119 A [0116] [0164]
- US 5853446 A [0117]
- EP 863534 A [0117]
- JP 9244230 A [0117]
- JP 10062980 A [0117]
- JP 8171863 A [0117]
- US 5840465 A [0117]
- EP 855731 A [0117]
- JP 5271576 A [0117]
- JP 5067405 A [0117]
- US 4575330 A [0117]
- DE 19700064 [0117]
- EP 678534 A [0117]
- DE 2308830 [0119]
- DE 4228514 [0120]
- EP 636669 A [0120]
- EP 320264 A [0125] [0162] [0164]
- JP 5173320 A [0130]
- JP 2004069754 A [0147]
- JP 2004302245 A [0147]
- JP 2005077451 A [0147]
- JP 2005316449 A [0147]
- JP 2005338328 A [0147]
- JP 3754065 B [0147] [0167]
- US 5368976 A [0153] [0164]
- JP 59044615 B [0158]
- JP 54034327 B [0158]
- JP 58012577 B [0158]
- JP 54025957 B [0158]
- JP 59053836 A [0158]
- JP 59071048 A [0158]
- JP 60159743 A [0158]
- JP 60258539 A [0158]
- JP 1152449 A [0158]
- JP 2199403 A [0158]
- JP 2199404 A [0158]
- US 5650263 A [0158] [0171]
- US 4139391 A [0158]
- JP 50034443 B [0159]
- JP 50034444 B [0159]
- US 5153095 A [0159]
- US 5677385 A [0159]
- US 5650233 A [0159]
- US 5879855 A [0163] [0164]
- US 5800952 A [0164]
- US 5882843 A [0164]
- US 5866298 A [0164]
- US 5863678 A [0164]
- JP 6230212 A [0164]
- JP 9269410 A [0164]
- JP 1090516 A [0164]
- US 5821016 A [0164]
- US 5847015 A [0164]
- US 5719008 A [0164]
- EP 881541 A [0164]
- EP 902327 A [0164]
- US 626796 A [0170]
- JP 57042009 A [0172]
- JP 1130103 A [0172]
- JP 1134306 A [0172]

EP 2 847 167 B9

- JP 2011065133 A [0177]
- JP 2000081701 A [0177]
- JP 11174459 A [0177]
- JP 11174464 A [0177]
- JP 60038989 A [0178]
- JP 60165623 A [0178]
- JP 61067003 A [0178]
- JP 2000039503 A [0178]
- WO 9938035 A [0178]
- JP 61153602 A [0178]
- JP 60072927 A [0178]
- JP 60166946 A [0178]
- EP 0932256 A [0179]
- US 5969867 A [0179]
- US 5376459 A [0182]
- WO 03021358 A [0183]
- EP 7086 A [0187]
- WO 9641240 A [0189]
- EP 706091 A [0189]
- EP 511403 A [0189]
- US 3579339 A [0189]
- US 4622286 A [0189]
- DE 4013358 [0197]

Non-patent literature cited in the description

- **J. MARCH.** Advanced Organic Chemistry. Wiley Interscience, 1992 [0062] [0063]
- **S.R. SANDLER ; W. KARO.** Organic functional group preparations. Academic Press, vol. 3 [0062]
- **M. WITTIG ; TH. GOHMANN.** Radiation Curing of Powder Coating. *Conference Proceedings, Radtech Europe*, 1993 [0120]
- **T. KUDO et al.** *J. Appl. Phys.*, 1998, vol. 37, 3594-3603 [0159]
- **T. KUDO et al.** *Jpn. J. Appl. Phys.*, 1998, vol. 37, 3594 [0164]
- **T. KUDO et al.** *J. Photopolym. Sci. Technol.*, 1996, vol. 9, 109 [0164]
- **K. KOBAYASHI.** *Solid State Technol.*, November 1992, S15-S18 [0164]
- Colloquium in Optics. *Journal of the Research Group in Microoptics Japanese Society of Applied Physics*, 1987, vol. 5 (2), 118-123 [0178]
- *JOURNAL OF THE RESEARCH GROUP IN MICRO-OPTICS JAPANESE SOCIETY OF APPLIED PHYSICS*, 1988, vol. 6 (2), 87-92 [0178]
- **POPOVIC et al.** *reference SPIE*, 1988, vol. 898, 23-25 [0179]
- **K.-P. MIECK ; T. REUSSMANN.** *Kunststoffe*, 1995, vol. 85, 366-370 [0187]
- **P.H. SELDEN.** *Glasfaserverstärkte Kunststoffe*. Springer Verlag, 1967, 610 [0187]
- **A. BERTSCH ; J.Y. JEZEQUEL ; J.C. ANDRE.** *Journal of Photochemistry and Photobiology A: Chemistry*, 1997, vol. 107, 275-281 [0196]
- **K.-P. NICOLAY.** *Offset Printing*, 1997, vol. 6, 34-37 [0196]