



(11) **EP 3 078 069 B9**

(12) **CORRECTED EUROPEAN PATENT SPECIFICATION**

(15) Correction information:
Corrected version no 1 (W1 B1)
Corrections, see
Claims EN 1, 3

(51) Int Cl.:
H01M 4/131 ^(2010.01) **H01M 4/505** ^(2010.01)
H01M 10/054 ^(2010.01) **H01M 4/50** ^(2010.01)
H01M 4/62 ^(2006.01) **H01M 10/0565** ^(2010.01)

(48) Corrigendum issued on:
19.05.2021 Bulletin 2021/20

(86) International application number:
PCT/US2014/068338

(45) Date of publication and mention
of the grant of the patent:
07.10.2020 Bulletin 2020/41

(87) International publication number:
WO 2015/084940 (11.06.2015 Gazette 2015/23)

(21) Application number: **14868257.8**

(22) Date of filing: **03.12.2014**

(54) **SOLID, IONICALLY CONDUCTING POLYMER MATERIAL, AND APPLICATIONS**
FESTES IONENLEITENDES POLYMERMATERIAL UND ANWENDUNGEN
MATÉRIAU POLYMÈRE SOLIDE À CONDUCTION IONIQUE, ET APPLICATIONS

(84) Designated Contracting States:
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB
GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO
PL PT RO RS SE SI SK SM TR

(30) Priority: **03.12.2013 US 201361911049 P**

(43) Date of publication of application:
12.10.2016 Bulletin 2016/41

(60) Divisional application:
20200120.2 / 3 813 157

(73) Proprietor: **Ionic Materials, Inc.**
Woburn, MA 01801 (US)

(72) Inventors:
• **ZIMMERMAN, Michael, A.**
No. Andover, MA 01845 (US)

• **GAVRILOV, Alexei, B.**
Woburn, MA 01801 (US)

(74) Representative: **Eisenführ Speiser**
Patentanwälte Rechtsanwälte PartGmbB
Postfach 10 60 78
28060 Bremen (DE)

(56) References cited:
JP-A- 2002 358 959 US-A- 4 720 910
US-A- 4 720 910 US-A- 4 925 751
US-A- 5 648 187 US-A1- 2002 177 043
US-A1- 2003 209 692 US-A1- 2004 229 118
US-A1- 2006 269 834 US-A1- 2008 090 138
US-A1- 2009 272 731 US-A1- 2011 281 159
US-A1- 2013 136 981 US-A1- 2014 377 621
US-B1- 6 183 914

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 3 078 069 B9

Description

BACKGROUND OF THE INVENTION

[0001] Batteries have become increasingly important in modern society, both in powering a multitude of portable electronic devices, as well as being key components in new green technologies. These new technologies offer the promise of removing the dependence on current energy sources such as coal, petroleum products, and natural gas which contribute to the production of by-product green-house gases. Furthermore, the ability to store energy in both stationary and mobile applications is critical to the success of new energy sources, and is likely to sharply increase the demand for all sizes of advanced batteries. Especially for batteries for large applications, a low base cost of the battery will be key to the introduction and overall success of these applications.

[0002] Conventional batteries have limitations, however. For example, lithium ion and other batteries generally employ a liquid electrolyte which is hazardous to humans and to the environment and which can be subject to fire or explosion. Liquid electrolyte batteries are hermetically sealed in a steel or other strong packaging material which adds to the weight and bulk of the packaged battery. Conventional liquid electrolyte suffers from the build-up of a solid interface layer at the electrode/electrolyte interface which causes eventual failure of the battery. Conventional lithium ion batteries also exhibit slow charge times and suffer from a limited number of recharges since the chemical reaction within the battery reaches completion and limits the rechargeability because of corrosion and dendrite formation. The liquid electrolyte also limits the maximum energy density which starts to break down at about 4.2 volts while often 4.8 volts and higher are required in the new industry applications. Conventional lithium ion batteries require a liquid electrolyte separator to allow ion flow but block electron flow, a vent to relieve pressure in the housing, and in addition, safety circuitry to minimize potentially dangerous over-currents and over-temperatures.

[0003] With respect to alkaline batteries which rely on the transport of OH⁻ ions to conduct electricity, the electrolyte becomes saturated with ions (e.g., zincate ions during discharge of Zn/MnO₂ batteries) at a certain point and eventually the anode becomes depleted of water. In rechargeable alkaline batteries, the reactions are reversed during charge. Formation of the same ions which saturated the electrolyte may hinder discharging, however. The cathode reaction results in the release of the OH⁻ ions. The formation of soluble low valent species (e.g., Mn species during discharge of Zn/MnO₂ batteries) can adversely affect the utilization of active material however. Although MnO₂ can theoretically experience 2-electron reduction with a theoretical capacity of 616 mAh/g, in practice a specific capacity close to theoretical 2-electron discharge has not been demonstrated. Crystalline structure rearrangement with formation of inactive phases and out-diffusion of soluble products limits cathode capacity.

[0004] US patent 7,972,726 describes the use of pentavalent bismuth metal oxides to enhance overall discharge performance of alkaline cells. Cathode containing 10% AgBiO₃ and 90% electrolytic MnO₂ was shown to deliver 351 mAh/g to 0.8V cut-off at 10 mA/g discharge rate, compared to 287 mAh/g for 100% MnO₂ and 200 mAh/g for 100% AgBiO₃. The 351 mAh/g specific capacity corresponds to 1.13 electron discharge of MnO₂ and represents the highest specific capacity delivered at practically useful discharge rates and voltage range. Bismuth- or lead-modified MnO₂ materials, disclosed in US 5,156,934 and US 5,660,953, were claimed to be capable of delivering about 80% of the theoretical 2-electron discharge capacity for many cycles. It was theorized in literature [Y. F. Yao, N. Gupta, H.S. Wroblowa, J. Electroanal. Chem., 223 (1987), 107; H.S. Wroblowa, N. Gupta, J. Electroanal. Chem., 238 (1987) 93; D.Y. Qu, L. Bai, C.G. Castledine, B.E. Conway, J. Electroanal. Chem., 365 (1994), 247] that bismuth or lead cations can stabilize crystalline structure of MnO₂ during discharge and/or allow for 2-electron reduction to proceed via heterogeneous mechanism involving soluble Mn²⁺ species. Containing said Mn²⁺ species seems to be the key for attaining high MnO₂ utilization and reversibility. In high carbon content (30-70%) cathodes per US 5,156,934 and US 5,660,953, the resulting highly porous structure was able to absorb soluble species. However, there is no data to suggest that a complete cell utilizing these cathodes was built or that this worked using a Zn anode.

[0005] Accordingly, polymer electrolyte which prevents 1) the dissolution of ions which would otherwise saturate the electrolyte and 2) the dissolution and transport of low-valent species, would improve utilization and rechargeability of alkaline batteries. In addition, it has been suggested [M. Minakshi, P. Singh, J. Solid State Electrochem, 16 (2012), 1487] that Li insertion can stabilize the MnO₂ structure upon reduction and enable rechargeability. A polymer engineered to conduct Li⁺ and OH⁻ ions, opens the possibility to tune MnO₂ discharge mechanism in favor of either proton or lithium insertion, which can serve as an additional tool to improve life cycle.

[0006] Further, while the battery technology for many advanced applications is Lithium Ion (Li-ion), increased demands for higher energy density, both in terms of volumetric (Wh/L) for portable devices, and gravimetric (Wh/kg) for electric vehicles and other large applications have shown the necessity for accessing technologies well beyond the current capabilities of Li-ion cells. One such promising technology is Li/sulfur batteries. A sulfur based cathode is enticing because of the high theoretical energy density (1672 mAh/g) which is ~ 10x better than the current Li-ion metal oxide cathode active materials. Sulfur is also exciting because it is a very abundant, low cost, environmentally friendly material, unlike many current Li-ion battery materials, such as LiCoO₂.

[0007] Recently, there has been a great amount of activity in Li/sulfur battery research, with advances in the capacity and cycle life of rechargeable Li/sulfur cells. Activity has included modifications to the cathode, anode, electrolyte and separator, all with the goal of reducing the polysulfide shuttle and thereby improving cell performance. Applications of this research to sulfur cathodes has focused in two main areas: 1) the use of engineered materials to surround and contain the sulfur and soluble lithiated products, for example see: U.S. Patent Application 2013/0065128, and 2) the use of conductive polymers which react with sulfur to produce a "sulfurized" composite cathode material. Examples of "sulfurized-polymer" include reaction products from high temperature exposure of sulfur with polyacrylonitrile (PAN) [see: Jeddi, K., et. al. J. Power Sources 2014, 245, 656-662 and Li, L., et. al. J. Power Sources 2014, 252, 107-112]. Other conductive polymer systems used in sulfur cathodes include polyvinylpyrrolidone (PVP) [see: Zheng, G., et. al. Nano Lett. 2013, 13, 1265-1270] and polypyrrole (PPY) [see: Ma, G., et. al. J. Power Sources 2014, 254, 353-359]. While these methods have met with various degrees of success in limiting the polysulfide shuttle mechanism, they all rely on the use of expensive materials which are not well suited to large scale manufacturing.

BRIEF SUMMARY OF THE INVENTION

[0008] A solid, ionically conducting polymer material is provided having very high ionic diffusivity and conductivity at room temperature and over a wide temperature range. The solid ionic polymer material is useful as a solid electrolyte for alkaline batteries and is also useful as a component to make electrodes for alkaline batteries. The material is not limited to battery applications but is more broadly applicable for other purposes such as alkaline fuel cells, supercapacitors, electrochromic devices, sensors and the like. The polymer material is non-flammable and self-extinguishes, which is especially attractive for applications which otherwise might be flammable. In addition the material is mechanically strong and can be manufactured using high volume polymer processing techniques and equipment which themselves are known in the art.

[0009] In one aspect of the invention the solid ionically conducting polymer material serves as an electrolyte to transmit OH⁻ ions in an alkaline battery. The alkaline battery may comprise various battery chemistries including, but not limited, Zn/MnO₂, Zn/Ni, Fe/Ni, Zn/AIR, Ni/Metal Hydride, Silver Oxide, Metal/Air and others known in the art. The zinc/manganese oxide (Zn/MnO₂) chemistry is the most widely used for consumer alkaline batteries.

[0010] A solid ionic polymer electrolyte for lithium ion batteries including the solid, ionically conducting polymer material is disclosed in co-pending United States Patent Application 13/861,170 filed April 11, 2013 and assigned to the same Assignee as the present invention.

[0011] In another aspect of the invention, the solid, ionically conducting polymer material is employed to form the cathode, electrolyte and anode of an alkaline battery. The three layers of the battery are solid and can be co-extruded to efficiently form the battery structure. The individual layers may also be or may alternatively be separately extruded or otherwise formed and layered together to form the battery structure.

[0012] The solid, ionically conducting polymer material includes a base polymer, a dopant and at least one compound including an ion source. The dopant includes an electron donor, an electron acceptor or an oxidant. In one embodiment for batteries with OH⁻ chemistry, the base polymer can be a polyphenylene sulfide, a polyether ether ketone also known as PEEK, or a liquid crystal polymer. In this embodiment, the dopant is an electron acceptor such as, for non-limiting examples, 2,3, dicloro-5,6-dicyano-1,4-benzoquinone, TCNE, sulfur trioxide or chloranil. Other dopants acting as electron acceptors or containing functional groups capable to accept electrons can be employed. The compound including an ion source includes compounds containing hydroxyl ions or materials chemically convertible to compounds containing hydroxyl ions including, but not limited to, hydroxides, oxides, salts or mixtures thereof, and more specifically Li₂O, Na₂O, MgO, CaO, ZnO, LiOH, KOH, NaOH, CaCl₂, AlCl₃, MgCl₂, LiTFSI (lithium bis-trifluoromethanesulfonimide), LiBOB (Lithium bis(oxalate)borate) or a mixture of the preceding two components.

[0013] The solid ionically conducting polymer material exhibits carbon 13 NMR (detection at 500 MHz) chemical shift peaks at about 172.5 ppm, 143.6 ppm, 127.7 ppm, and 115.3 ppm. A similar carbon 13 NMR scan of the electron acceptor shows chemical shift peaks at about 195 ppm, and 107.6 ppm in addition to the chemical shift peaks at about 172.5 ppm, 143.6 ppm, 127.7 ppm, and 115.3 ppm. In other words, the reaction between the base polymer and the electron acceptor appears to eliminate the chemical shift peaks at about 195 ppm, and 107.6 ppm. In addition, the ¹³C NMR spectrum of the solid ionically conducting polymer movement in the main peak (dominated by the aromatic carbon) in going from the base polymer to the solid ionically conducting polymer. The chemical shift of the dominant peak in the solid ionically conducting polymer is greater than the chemical shift of the dominant peak in the base polymer.

[0014] The material has crystallinity index of at least or greater than about 30%.

[0015] The compound including the ion source is in a range of 10 wt. % to 60 wt. % .

[0016] The dopant molar ratio is in the range of about 1-16.

[0017] The material has an ionic conductivity of at least 1x10⁻⁴ S/cm at room temperature of between 20 °C to 26 °C.

[0018] The material has a tensile strength in the range of 5-100 MPa, a Modulus of Elasticity in the range of 0.5-3.0 GPa, and Elongation in the range of 0.5-30%

[0019] The material has an OH⁻-diffusivity of greater than 10^{-11} cm²/S at room temperature of between 20 °C to 26 °C.

[0020] The batteries with OH⁻ chemistry may be rechargeable or non-rechargeable.

[0021] In another aspect, the invention provides a rechargeable alkaline battery including an anode; a cathode; and an electrolyte; wherein at least one of anode, the cathode and the electrolyte include a solid, ionically conducting polymer material.

[0022] In one embodiment of said battery, the battery comprises an anode; a cathode; and wherein at least one of the anode, and the cathode comprise a solid, ionically conducting polymer material. The battery can be rechargeable or primary. The battery further comprises an electrolyte, and the electrolyte can comprise the solid, ionically conducting polymer material. The battery can alternatively or additionally further comprise an electrolyte, and said electrolyte can be alkaline. As the solid, ionically conducting polymer can conduct a plurality of OH⁻ ions and has an OH⁻ diffusivity of greater than 10^{-11} cm²/sec at a temperature in a range of 20 °C to 26 °C it is particularly well suited for use on alkaline battery electrodes.

[0023] The solid, ionically conducting polymer material is formed from a reactant product comprising a base polymer, an electron acceptor, and a compound including a source of ions. The solid, ionically conducting polymer material can be used as an electrolyte in either the anode or cathode. If used in a battery the cathode of said battery can comprise an active material selected from the group comprising ferrate, iron oxide, cuprous oxide, iodate, cupric oxide, mercuric oxide, cobaltic oxide, manganese oxide, lead dioxide, silver oxide, oxygen, nickel oxyhydroxide, nickel dioxide, silver peroxide, permanganate, bromate, silver vanadium oxide, carbon monofluoride, iron disulfide, iodine, vanadium oxide, copper sulfide, sulfur or carbon and combinations thereof. The anode of said battery can comprise an active material selected from the group comprising lithium, magnesium, aluminum, zinc, chromium, iron, nickel, tin, lead, hydrogen, copper, silver, palladium, mercury, platinum or gold, and combinations thereof, and alloyed materials thereof.

[0024] In an alkaline battery where the cathode comprises manganese dioxide, and the anode comprises zinc. The manganese dioxide can take the form of a β -MnO₂ (pyrolusite), a ramsdellite, a γ -MnO₂, a ϵ -MnO₂, a λ -MnO₂, an electrolytic manganese dioxide (EMD), and a chemical manganese dioxide (CMD) and a combination of the proceeding forms. Further, at least one of the anode and cathode can comprise particles of active material and the solid, ionically conductive polymer material can encapsulate at least one particle of the active material or all of the active material. Such cathodes have shown specific capacity greater than 400 mAh/g, 450mAh/g, and 500mAh/g.

[0025] The battery can alternatively further comprise an electrically conductive additive and/or a functional additive in either the anode or cathode. The electrically conductive additive can be selected from the group comprising a carbon black, a natural graphite, a synthetic graphite, a graphene, a conductive polymer, a metal particle, and a combination of at least two of the preceding components. The functional additive can be selected from the group comprising bismuth, ZnO, MgO, CaO, SnO₂, Na₂SnO₃, and ZnSO₄.

[0026] The battery electrodes (anode or cathode) can composite structure which can be formed by a process such as injection molding, tube extrusion and compression molding. In one embodiment of making the solid, ionically conductive polymer material the base polymer is oxidatively doped in the presence of an ion source. The ion source is a compound including at least one hydroxyl group or convertible to a compound containing at least one hydroxyl group, or alternatively selected from the group consisting of a LiOH, a Li₂O or a mixture of the preceding two components. The base polymer is selected from the group comprising a liquid crystal polymer, a polyether ether ketone (PEEK), and a polyphenylene sulphide (PPS), or a semicrystalline polymer with a crystallinity index of greater than 30%, and combinations thereof. The electron acceptor which reacts with the base polymer in the presence of the ion source can be selected from the group comprising 2,3, dicloro-5,6-dicyano-1,4-benzoquinone, TCNE, sulfur trioxide or chloranil and combinations thereof. The method can additionally include a heating step to further the reaction. An electrochemically active material can be added to the mixing step and if so added is encapsulated by the reacted ionically conductive polymer. Such a battery with a MnO₂ cathode, zinc anode and an alkaline electrolyte wherein the alkaline battery is characterized by a flat discharge curve above 1 V, and having a voltage drop less than 0.3V between 5 and 95% depth of discharge.

[0027] The solid, ionically conductive polymer material can also be useful as a separator film, as it is electrically non-conductive, and ionically conductive. Therefore the solid, ionically conductive polymer material cast or otherwise rendered as a film can be used as a separator positioned between an anode and cathode. In addition, the solid, ionically conductive polymer material can be coated onto an electrode to function as a separator or alternatively to isolate the electrode or an electrode component from another battery component such as an aqueous electrolyte. The solid, ionically conductive polymer material enables ionic communication between such an isolated component despite it being physically separated, and electrically segmented from the rest of the battery component. The material can also comprise an aggregated or cast agglomeration of small particles of the solid, ionically conductive polymer material. Such an aggregation can take any shape but include an engineered porosity while possessing an engineered surface area. Fillers, such as hydrophobic materials can be mixed in the material to provide desirable physical properties such as low effective aqueous porosity. Catalysts can be added to the solid, ionically conductive polymer material to enable a combination of catalysis and ionic conductivity, such as required in an air electrode for a metal/air battery. Thus the solid, ionically conductive polymer material can include a low or very high surface area, and or a low or very high porosity. Shapes such as an annulus and

other moldable shapes can be engineering with desired physical properties with the ionic conductivity of the solid, ionically conductive polymer material are enabled by the invention.

BRIEF DESCRIPTION OF THE SEVERAL VIEWS OF THE DRAWINGS

[0028]

FIG. 1 exemplarily shows a resulting formula for the crystalline polymer of the present invention.
 FIG. 2 exemplarily illustrates a dynamic scanning calorimeter curve of a semicrystalline polymer.
 FIG. 3 exemplarily illustrates formulations which were investigated for use with the invention.
 FIG. 4 shows a schematic illustration of amorphous and crystalline polymers.
 FIG. 5 exemplarily illustrates a chemical diagram of 2,3-dicyano-5,6-dichlorodicyanoquinone (DDQ) as a typical electron acceptor dopant for use in the invention.
 FIG. 6 exemplarily illustrates a plot of the conductivity of the ionically conductive polymer according to the invention in comparison with a liquid electrolyte and a polyethylene oxide lithium salt compound.
 FIG. 7 exemplarily illustrates the mechanical properties of the ionically conducting film according to the invention.
 FIG. 8 exemplarily illustrates possible mechanisms of conduction of the solid electrolyte polymer according to the invention.
 FIG. 9 exemplarily shows a UL94 flammability test conducted on a polymer according to the invention.
 FIG. 10 exemplarily shows a plot of volts versus current of an ionically conductive polymer according to the invention versus lithium metal.
 FIG. 11 exemplarily illustrates a schematic of extruded ionically conductive electrolyte and electrode components according to the invention.
 FIG. 12 exemplarily illustrates the solid state battery according to the invention where electrode and electrolyte are bonded together.
 FIG. 13 exemplarily illustrates a final solid state battery according to the invention having a new and flexible form.
 FIG. 14 exemplarily illustrates a method of the invention including steps for manufacturing a solid state battery using an extruded polymer.
 FIG. 15 exemplarily illustrates the extrusion process according to the invention.
 FIG. 16 exemplarily illustrates a schematic representation of an embodiment according to the invention.
 FIG. 17 exemplarily illustrates an alkaline battery having three layers of the invention.
 FIG. 18 exemplarily illustrates a comparison of process steps for standard Li-ion cathode manufacturing with those for extrusion of the composite polymer-sulfur cathode of the invention.
 FIG. 19 exemplarily illustrates OH⁻ diffusivity at room temperature in a solid polymer electrolyte of the invention;
 FIG. 20 exemplarily illustrates lithium diffusivity at room temperature in a solid polymer electrolyte of the invention.
 FIG. 21 exemplarily illustrates voltage profile of cell of the invention per example 2 as a function of specific capacity of MnO₂ at 0.5 mA/cm² discharge rate.
 FIG. 22 exemplarily illustrates voltage profile of cell of the invention per example 3 as a function of specific capacity of MnO₂ at C/9 rate (35 mA/g).
 FIG. 23 exemplarily illustrates specific capacity of MnO₂ as a function of cycle number in the cells of the invention per example 4.
 FIG. 24 exemplarily illustrates discharge curve of coin cell of the invention per example 5 as a function of test time.
 FIG. 25 exemplarily illustrates voltage profile of the cell of the invention per example 6 as a function of test time.
 FIG. 26 exemplarily illustrates discharge curve of coin cells of the invention per example 7 as a function of discharge capacity.
 FIG. 27 exemplarily illustrates a potentiodynamic scan at 1 mV/s of anode of the present invention (curve A) and control Al foil (curve B) in ZnSO₄ electrolyte. Zn foil was used as counter electrode.
 FIG. 28 illustrates specific capacity of Duracell Coppertop AA cell under different constant current discharge rates
 FIG. 29 illustrates discharge curves for alkaline button cells at 10 mA/g rate per prior art.
 FIG. 30 exemplarily illustrates voltage profile of a cell of the invention per comparative example 12 at 35 mA/g constant current discharge as a function of specific capacity of MnO₂
 FIG. 31 exemplarily illustrates voltage profile of a cell of the invention per example 13 as a function of specific capacity of MnO₂.
 FIG. 32 exemplarily illustrates a voltage profile of cell of the invention per example 14 as a function of specific capacity of MnO₂ in comparison with a Duracell Coppertop cell.
 FIG. 33 exemplarily illustrates a voltage profile of a cell of the invention per example 15 as a function of specific capacity of MnO₂ in comparison with a Duracell Coppertop cell.
 FIG. 34 exemplarily illustrates a first discharge voltage curve for Li/Ionic polymer-sulfur cell of the present invention.

FIG. 35 exemplarily illustrates a discharge capacity curve plotted as a function of cycle number for Li/Ionic polymer-sulfur cell of the present invention.

FIG. 36 exemplarily illustrates a comparison of first discharge for literature example Li/Sulfur-CMK-3 with Li/Ionic polymer-sulfur of present invention.

FIG. 37 illustrates a charge/discharge voltage curves for a Li/sulfur-poly(pyridinopyridine) cell from the prior art.

DETAILED DESCRIPTION OF THE INVENTION

[0029] The invention comprises a solid, ionically conductive polymer material including a base polymer, a dopant, and at least one compound including an ion source. The polymer material has a capacity for ionic conduction over a wide temperature range including room temperature. It is believed that ion "hopping" occurs from a high density of atomic sites. Thus, the polymer material can function as a means for supplying ions and has significant material strength.

[0030] For the purposes of this application, the term "polymer" refers to a polymer having a crystalline or semi-crystalline structure. In some applications, the solid, ionically conductive polymer material can be molded into shapes which can be folded back on itself allowing for new physical formats depending on the application. The base polymer is selected depending upon the desired properties of the composition in relation to the desired application.

[0031] For purposes of the application, the term "dopant" refers to electron acceptors or oxidants or electron donors. The dopant is selected depending upon the desired properties of the composition in relation to the desired application.

[0032] Similarly, the compound including an ion source is selected depending upon the desired properties of the composition in relation to the desired application.

I. Li^+ chemistries

[0033] In one aspect, the invention relates to a solid polymer electrolyte including the solid, ionically conductive polymer material in a lithium ion battery.

[0034] In this aspect, the base polymer is characterized as having a crystallinity value of between 30% and 100%, and preferably between 50% and 100%. The base polymer has a glass transition temperature of above 80 °C, and preferably above 120 °C, and more preferably above 150 °C, and most preferably above 200 °C. The base polymer has a melting temperature of above 250 °C, and preferably above 280 °C, and more preferably above 320 °C. The molecular weight of the monomeric unit of the base polymer of the invention is in the 100-200 gm/mol range and can be greater than 200 gm/mol. FIG. 1 shows the molecular structure of an exemplary base polymer, wherein the monomeric unit of the base polymer has a molecular weight of 108.16 g/mol. FIG. 2 exemplarily illustrates a dynamic scanning calorimeter curve of an exemplary semicrystalline base polymer. FIG. 3 illustrates exemplary formulations for the solid, ionically conducting polymer material in this aspect of the invention where DDQ is the dopant. Typical materials that can be used for the base polymer include liquid crystal polymers and polyphenylene sulfide also known as PPS, or any semi-crystalline polymer with a crystallinity index greater than 30%, and preferably greater than 50%. In one embodiment, the invention uses a "crystalline or semi-crystalline polymer", exemplarily illustrated in FIG. 4, which typically is above a crystallinity value of 30%, and has a glass transition temperature above 200 °C, and a melting temperature above 250 °C.

[0035] In this aspect, the dopant is an electron acceptor, such as, for non-limiting examples, 2,3-dicyano-5,6-dichlorodicyanoquinone ($\text{C}_8\text{Cl}_2\text{N}_2\text{O}_2$) also known as DDQ, Tetracyanoethylene (C_6N_4) known as TCNE, and sulfur trioxide (SO_3). A preferred dopant is DDQ. FIG. 5 provides a chemical diagram of this preferred dopant. It is believed that the purpose of the electron acceptor is two-fold: to release ions for transport mobility, and to create polar high density sites within the polymer to allow for ionic conductivity. The electron acceptor can be "pre-mixed" with the initial ingredients and extruded without post-processing or alternatively, a doping procedure such as vapor doping can be used to add the electron acceptor to the composition after the material is created.

[0036] Typical compounds including an ion source for use in this aspect of the invention include, but are not limited to, Li_2O , LiOH , ZnO , TiO_2 , Al_3O_2 , and the like. The compounds containing appropriate ions which are in stable form can be modified after creation of the solid, polymer electrolytic film.

[0037] Other additives, such as carbon particles nanotubes and the like, can be added to the solid, polymer electrolyte including the solid, ionically conducting material to further enhance electrical conductivity or current density.

[0038] The novel solid polymer electrolyte enables a lighter weight and much safer architecture by eliminating the need for heavy and bulky metal hermetic packaging and protection circuitry. A novel solid polymer battery including the solid polymer electrolyte can be of smaller size, lighter weight and higher energy density than liquid electrolyte batteries of the same capacity. The novel solid polymer battery also benefits from less complex manufacturing processes, lower cost and reduced safety hazard, as the electrolyte material is non-flammable. The novel solid polymer battery is capable of cell voltages greater than 4.2 volts and is stable against higher and lower voltages. The novel solid polymer electrolyte can be formed into various shapes by extrusion (and co-extrusion), molding and other techniques such that different form factors can be provided for the battery. Particular shapes can be made to fit into differently shaped enclosures in

devices or equipment being powered. In addition, the novel solid polymer battery does not require a separator, as with liquid electrolyte batteries, between the electrolyte and electrodes. The weight of the novel solid polymer battery is substantially less than a battery of conventional construction having similar capacity. In some embodiments, the weight of the novel solid polymer battery can be less than half the weight of a conventional battery.

[0039] In another aspect of the invention, a solid polymer electrolyte including the solid, ionically conducting polymer material is in the form of an ionic polymer film. An electrode material is directly applied to each surface of the ionic polymer film and a foil charge collector or terminal is applied over each electrode surface. A light weight protective polymer covering can be applied over the terminals to complete the film based structure. The film based structure forms a thin film battery which is flexible and can be rolled or folded into intended shapes to suit installation requirements.

[0040] In yet another aspect of the invention, a solid polymer electrolyte including the solid, ionically conducting polymer material is in the form of an ionic polymer hollow monofilament. Electrode materials and charge collectors are directly applied (co-extruded) to each surface of the solid, ionically conductive polymer material and a terminal is applied at each electrode surface. A light weight protective polymer covering can be applied over the terminals to complete the structure. The structure forms a battery which is thin, flexible, and can be coiled into intended shapes to suit installation requirements, including very small applications.

[0041] In still another aspect of the invention, a solid polymer electrolyte including the solid, ionically conducting polymer material has a desired molded shape. Anode and cathode electrode materials can be disposed on respective opposite surfaces of the solid polymer electrolyte to form a cell unit. Electrical terminals can be provided on the anode and cathode electrodes of each cell unit for interconnection with other cell units to provide a multi cell battery or for connection to a utilization device.

[0042] In aspects of the invention relating to batteries, the electrode materials (cathode and anode) can be combined with a form of the novel solid, ionically conductive polymer material to further facilitate ionic movement between the two electrodes. This is analogous to a conventional liquid electrolyte soaked into each electrode material in a conventional lithium-ion battery.

[0043] Films of solid, ionically conducting polymer materials of the present invention have been extruded in thickness ranging upwards from 0.0076 mm (0.0003 inches). The ionic surface conductivity of the films has been measured using a standard test of AC-Electrochemical Impedance Spectroscopy (EIS) known to those of ordinary skill in the art. Samples of the solid, ionically conducting polymer material film were sandwiched between stainless steel blocking electrodes and placed in a test fixture. AC-impedance was recorded in the range from 800 KHz to 100 Hz using a Biologic VSP test system to determine the electrolyte conductivity. The results of the surface conductivity measurements are illustrated in FIG. 6. The conductivity of solid, ionically conductive polymer material film according to the invention (Δ) is compared with that of trifluoromethane sulfonate PEO (\square) and a liquid electrolyte made up of a Li salt solute and a EC:PC combination solvent using a Celgard separator (O). The conductivity of the solid, ionically conducting polymer material film according to the invention tracks the conductivity of the liquid electrolyte and far surpasses that of trifluoromethane sulfonate PEO at the lower temperatures. Further, unlike PEO electrolytes, the temperature dependence of the conductivity for inventive polymer material does not display a sharp increase above its glass transition temperature, associated with chain mobility, as described by Vogel-Tamman-Fulcher behavior activated by temperature. Therefore, segmental movement as the ion-conduction mechanism in the inventive polymer material is unlikely. Furthermore, this demonstrates that the inventive polymer material has similar ionic conductivity to liquid electrolytes.

[0044] FIG. 7 shows the mechanical properties of the solid, ionically conductive polymer material films of the invention. The mechanical properties were evaluated using the Institute for Interconnecting and Packaging Electronic Circuits IPC-TM-650 Test Methods Manual 2.4.18.3. In the tensile strength versus elongation curve of Fig. 7, the "ductile failure" mode indicates that the material can be very robust.

[0045] The solid, ionically conductive polymer material of the invention offers three key advantages in its polymer performance characteristics: (1) It has an expansive temperature range. In lab-scale testing, the crystalline polymer has shown high ionic conductivity both at room temperature and over a wide temperature range. (2) It is non-flammable. The polymer self-extinguishes, passing the UL-V0 Flammability Test. The ability to operate at room temperature and the non-flammable characteristics demonstrate a transformative safety improvement that eliminates expensive thermal management systems. (3) It offers low-cost bulk manufacturing. Rather than spraying the polymer onto electrodes, the polymer material can be extruded into a thin film via a roll-to-roll process, an industry standard for plastics manufacturing. After the film is extruded, it can be coated with the electrode and charge collector materials to build a battery "from the inside out." This enables thin, flexible form factors without the need for hermetic packaging, resulting in easy integration into vehicle and storage applications at low cost.

[0046] It is believed that the solid, ionically conducting polymer material of the present invention creates a new ionic conduction mechanism that provides a higher density of sites for ionic transport and allows the conducting material to maintain higher voltages without risk of thermal runaway or damage to ion transport sites from, for example, lithiation. This characteristic enables the solid, ionically conducting polymer material to be durable for anode materials and higher voltage cathode thin-film applications, resulting in higher energy densities for batteries which may be used in vehicle

and stationary storage applications. The ability to maintain high voltages within a solid, ionically conductive polymer material which is mechanically robust, chemical and moisture resistant, and nonflammable not only at room temperature, but over a wide range of temperatures, allows integration with high performance electrodes without costly thermal and safety mechanisms employed by the industry today.

[0047] Batteries employing the solid polymer electrolyte including the solid, ionically conductive polymer material of the invention are characterized by an energy density improvement over current commercially available electrolytes, as well as a performance range of -40°C to 150°C with minimal conductivity degradation. The solid polymer electrolyte can be extruded by a process that produces polymers of a thickness of 6 microns, which enables thin-film formats under commercial manufacturing conditions at batch scale. Further, such extrusion processes enables high throughput, low-cost manufacturing lines for the production of the solid polymer electrolyte, and the processes can be integrated into a variety of product lines, including lithium and zinc battery manufacture. Battery costs can be reduced by up to 50%.

[0048] In addition, the solid, ionically conductive polymer material is not limited to use in batteries, but can be used in any device or composition that includes an electrolyte material. For example, the novel solid, ionically conductive polymer material can be used in electrochromic devices, electrochemical sensors, supercapacitors and fuel cells. FIG. 8 shows possible mechanisms of conduction of the solid, ionically conducting polymer material in a solid polymer electrolyte aspect of the invention. Charge carrier complexes are set up in the polymer as a result of the doping process.

[0049] Flammability of the solid polymer electrolyte including the solid, ionically conductive polymer material of the invention was tested using a UL94 flame test. For a polymer to be rated UL94-V0, it must "self-extinguish" within 10 seconds and "not drip". The solid polymer electrolyte was tested for this property and it was determined that it self-extinguished with 2 seconds, did not drip, and therefore easily passed the V0 rating. FIG. 9 shows pictures of the result.

[0050] In addition to the properties of ionic conductivity, flame resistance, high temperature behavior, and good mechanical properties, it is preferable that the solid polymer electrolyte including the solid, ionically conductive polymer material of the invention is electrochemically stable at low and high potentials. The traditional test for the electrochemical stability is cyclic voltammetry, when working electrode potential is ramped linearly versus time. In this test, the polymer is sandwiched between a lithium metal anode and blocking stainless steel electrode. A voltage is applied and it is swept positively to a high value (greater than 4 volts vs. Li) for stability towards oxidation and negatively to a low value (0V vs. Li or less) for stability towards reduction. The current output is measured to determine if any significant reaction occurs at the electrode interface. High current output at high positive potential would signify oxidation reaction taking place, suggesting instability with cathode materials operating at these or more positive potentials (such as many metal oxides). High current output at low potentials would signify that a reduction reaction takes place, suggesting instability with anodes operating at these or more negative potentials (such as metal Li or lithiated carbon). FIG. 10 shows a plot of voltage versus current for a solid polymer electrolyte including the solid, ionically conductive polymer material according to the invention versus lithium metal. The study shows that the solid polymer electrolyte is stable up to about 4.4 volts. These results indicate that the solid polymer electrolyte could be stable with cathodes including LCO, LMO, NMC and similar cathodes, along with low voltage cathodes such as, for non-limiting examples iron phosphate and sulfur cathodes.

[0051] The solid polymer electrolyte including the solid, ionically conductive polymer material of the invention is able to achieve the following properties: A) high ionic conductivity at room temperature and over a wide temperature range (at least -10°C to $+60^{\circ}\text{C}$); B) non-flammability; C) extrudability into thin films allowing for reel-reel processing and a new way of manufacturing; D) compatibility with Lithium metal and other active materials. Accordingly, this invention allows for the fabrication of a true solid state battery. The invention allows for a new generation of batteries having the following properties:

- No safety issues;
- New form factors;
- Large increases in energy density; and
- large improvements in cost of energy storage.

[0052] FIGs. 11, 12 and 13 show several elements of the solid state battery including the solid, ionically conductive polymer material of the invention which are, respectively: A) an extruded electrolyte; B) extruded anodes and cathodes; and C) a final solid state battery allowing for new form factors and flexibility.

[0053] In other aspects, the invention provides methods for making Li batteries including the solid, ionically conducting polymer material of the invention. FIG. 14 shows a method of manufacturing a solid state lithium ion battery using an extruded solid, ionically conducting polymer material according to the invention. The material is compounded into pellets, and then extruded through a die to make films of variable thicknesses. The electrodes can be applied to the film using several techniques, such as sputtering or conventional casting in a slurry.




[0054] In yet another aspect, the invention provides a method of manufacturing of an ionic polymer film including the solid, ionically conductive polymer material of the invention which involves heating the film to a temperature around 295°C , and then casting the film onto a chill roll which solidifies the plastic. This extrusion method is shown in FIG. 15.

The resulting film can be very thin, in the range of 10 microns thick or less. FIG. 16 shows a schematic representation of the architecture of an embodiment according to the invention.

II. OH⁻ Chemistries




[0055] The invention also relates to a solid, ionically conducting polymer material which is engineered to transmit OH⁻ ions, thereby making it applicable for alkaline batteries. For the purposes of present invention, the term "alkaline battery or alkaline batteries" refers to a battery or batteries utilizing alkaline (OH⁻ containing) electrolyte. Such battery chemistries include, but not limited to, Zn/MnO₂, Zn/Ni, Fe/Ni, Zn/air, Al/air, Ni/metal hydride, silver oxide and others. Zn/MnO₂ chemistry is probably the most widely used and is the main choice for consumer batteries. Although many of the embodiments described herein are related to Zn/MnO₂ chemistry, a person of ordinary skill in the art would understand that the same principles are applicable broadly to other alkaline systems.

[0056] Alkaline batteries rely on the transport of OH⁻ ions to conduct electricity. In most cases, the OH⁻ ion is also a participant in the electrochemical process. For instance, during the discharge of a Zn/MnO₂ battery, the zinc anode releases 2 electrons and consumes OH⁻ ions:



[0057] During early stages of discharge of the battery, reaction (1) produces soluble zincate ions, which can be found in the separator and cathode [Linden's Handbook of Batteries, Fourth Edition]. At a certain point, the electrolyte will become saturated with zincates and the reaction product will change to insoluble Zn(OH)₂ (2). Eventually, the anode will become depleted of water and the zinc hydroxide dehydrates by equation (3). In rechargeable batteries, the reactions are reversed during charging of the battery. Formation of soluble zincate ions during the initial step of the Zn discharge may hinder recharging.

[0058] The cathode reaction involves a reduction of Mn⁴⁺ to Mn³⁺ by a proton insertion mechanism, resulting in the release of OH⁻ ions (4). The theoretical specific MnO₂ capacity for such 1-electron reduction is 308 mAh/g. Slow rate discharge to lower voltages may lead to further discharge of MnOOH as depicted by equation (5), which results in 410 mAh/g total specific capacity (1.33 e). In most prior art applications, the MnO₂ discharge is limited to the 1-electron process. Utilization of the active is further adversely affected by the formation of soluble low-valent Mn species.



[0059] Although MnO₂ can theoretically experience a 2-electron reduction according to equation (6) with a theoretical specific capacity of 616 mAh/g, in practice with prior art batteries, it is not demonstrated. The crystalline structure rearrangement with the formation of inactive phases, such as Hausmanite Mn₃O₄, and out-diffusion of soluble products are among the factors limiting cathode capacity.

[0060] US patent 7,972,726 describes the use of pentavalent bismuth metal oxides to enhance the overall discharge performance of alkaline cells. Cathode containing 10% AgBiO₃ and 90% electrolytic MnO₂ was shown to deliver 351 mAh/g to 0.8V cut-off at 10 mA/g discharge rate, compared to 287 mAh/g for 100% MnO₂ and 200 mAh/g for 100% AgBiO₃. The 351 mAh/g specific capacity corresponds to a 1.13 electron discharge of MnO₂ and represents the highest specific capacity delivered at practically useful discharge rates and voltage ranges.

[0061] In principle, reaction (4) can be reversible, opening the possibility for a rechargeable Zn/MnO₂ battery. In practice, the crystalline structure collapse and formation of soluble products allow only for shallow cycling.

[0062] Bismuth- or lead-modified MnO₂ materials, disclosed in US 5,156,934 and US 5,660,953, were claimed to be capable of delivering about 80% of the theoretical 2-electron discharge capacity for many cycles. It was theorized in literature [Y. F. Yao, N. Gupta, H.S. Wroblowa, J. Electroanal. Chem., 223 (1987), 107; H.S. Wroblowa, N. Gupta, J. Electroanal. Chem., 238 (1987) 93; D.Y. Qu, L. Bai, C.G. Castledine, B.E. Conway, J. Electroanal. Chem., 365 (1994), 247] that bismuth or lead cations can stabilize crystalline structure of MnO₂ during discharge and/or allow for reaction (6) to proceed via heterogeneous mechanism involving soluble Mn²⁺ species. Containing said Mn²⁺ species seems to be the key for attaining high MnO₂ utilization and reversibility. In high carbon content (30-70%) cathodes per US 5,156,934

and US 5,660,953, the resulting highly porous structure was able to absorb soluble species. However, there is no data to suggest that a complete cell utilizing these cathodes was built or that this worked using a Zn anode.

[0063] Thus, a polymer electrolyte which prevents dissolution and transport of low-valent manganese species and zincate ions, would be highly beneficial to improve MnO₂ utilization and achieve rechargeability of Zn/MnO₂ cells.

[0064] In addition to proton insertion, MnO₂ can undergo reduction by Li intercalation. It has been suggested [M. Minakshi, P. Singh, J. Solid State Electrochem, 16 (2012), 1487] that the Li insertion can stabilize MnO₂ structure upon reduction and enable rechargeability.

[0065] The solid, ionically conductive polymer material of the invention, engineered to conduct Li⁺ and OH⁻ ions, opens the possibility to tune MnO₂ discharge mechanism in favor of either proton or lithium insertion, which can serve as an additional tool to improve cycle life.

[0066] Accordingly, in one aspect, the invention provides a polymer material including a base polymer, a dopant and at least one compound including an ion source, wherein the polymer material is a solid, ionically conducting polymer material having mobility for OH⁻ ions. For the purposes of the application, the term "mobility for OH⁻ ions" refers to a diffusivity of greater than 10⁻¹¹ cm²/sec or a conductivity of 10⁻⁴ S/cm, at a room temperature of between 20 ° C and 26 ° C. The solid, ionically conducting polymer material is suitable for use in alkaline cells.

[0067] In different aspects, the invention provides an electrolyte including the solid, ionically conductive polymer material having mobility for OH⁻ ions, wherein the electrolyte is a solid polymer electrolyte for use in alkaline batteries; an electrode or electrodes including said solid polymer electrolyte; and/or a cell or cells including said electrode or electrodes.

[0068] In another aspect, the invention provides electrodes, cathodes and anodes including a solid polymer electrolyte for use in alkaline cells, wherein the solid polymer electrolyte includes a solid, ionically conducting polymer material having mobility for OH⁻ ions. In yet another aspect, the invention provides an electrolyte interposed between cathode and anode, where at least one of the electrolyte, cathode and anode includes the solid, ionically conductive polymer material having mobility for OH⁻ ions. In another aspect, the invention provides an alkaline battery including a cathode layer, an electrolyte layer and an anode layer, wherein at least one of the layers includes a solid, ionically conducting polymer material having mobility for OH⁻ ions. The latter aspect is exemplarily illustrated in FIG. 17.

[0069] The base polymer of the solid, ionically conducting polymer material having mobility for OH⁻ ions is a crystalline or semi-crystalline polymer, which typically has a crystallinity value between 30% and 100%, and preferably between 50% and 100%. The base polymer of this aspect of the invention has a glass transition temperature above 80 ° C, and preferably above 120 ° C, and more preferably above 150 ° C, and most preferably above 200 ° C. The base polymer has a melting temperature of above 250 ° C, and preferably above 280 ° C, and more preferably above 280 ° C, and most preferably above 300 ° C.

[0070] The dopant of the solid, ionically conducting polymer material having mobility for OH⁻ ions is an electron acceptor or oxidant. Typical dopants for use in this aspect of the invention are DDQ, TCNE, S₀₃, etc.

[0071] The compound including an ion source of the solid, ionically conducting polymer material having mobility for OH⁻ ions includes a salt, a hydroxide, an oxide or other material containing hydroxyl ions or convertible to such materials, including, but not limited to, LiOH, NaOH, KOH, Li₂O, LiNO₃, etc.

[0072] The solid, ionically conductive material having mobility for OH⁻ ions is characterized by a minimum conductivity of 1 x 10⁻⁴ S/cm at room temperature and/or a diffusivity of OH⁻ ions at room temperature of greater than 10⁻¹¹ cm²/sec.

[0073] The cathode of the present invention relating to OH⁻ chemistries includes MnO₂, NiOOH, Ag₂O, air (O₂) or similar active materials. MnO₂ is a preferred material and can be in the form of β-MnO₂ (pyrolusite), ramsdellite, γ-MnO₂, ε-MnO₂, λ-MnO₂ and other MnO₂ phases or mixtures thereof, including, but not limited to, EMD and CMD.

[0074] The cathode of the present invention relating to OH⁻ chemistries is prepared by mixing cathode active material with the components of the solid, ionically conducting polymer material of the invention including the base polymer, the dopant and a compound including a source of ions prior to formation of the solid, ionically conducting polymer material to form a mixture. Alternatively, the cathode active material is mixed with the solid, ionically conducting polymer material already formed.

[0075] The mixture is molded and/or extruded at temperatures between 180 °C and 350 °C, and preferably between 190 °C and 350 °C, and more preferably between 280 °C and 350 °C, and most preferably between 290 °C and 325 °C. The cathode active material can include various forms such as, for non-limiting examples, a powder form, a particle form, a fiber form, and/or a sheet form. The cathode of the present invention includes active material in an amount of between 10 w. % and 90 wt. %, and preferably in an amount of between 25 wt. % and 90 wt. %, and more preferably in an amount of between 50 wt. % and 90 wt. %, relative to the total cathode weight. The cathode can further include an electrically conductive additive, such as a carbon black component, a natural graphite component, a synthetic graphite component, a graphene component, a conductive polymer component, a metal particles component, and/or other like electrically conductive additives. The cathode can include the electrically conductive additives in an amount of between 0 wt. % and 25 wt. %, and preferably in an amount of between 10 wt. % and 15 wt. % relative to the total cathode weight. The cathode of the present invention relating to OH⁻ chemistries can further include one or more functional additives for improving performance. The cathode active material can be encapsulated by the solid, ionically conducting polymer

material of the invention.

[0076] The anode of the present invention relating to OH^- chemistries can include an active material of Zn, in the form of zinc powder, zinc flakes and other shapes, zinc sheets, and other shapes. All such forms of zinc can be alloyed to minimize zinc corrosion.

[0077] The anode of the present invention relating to OH^- chemistries is prepared by mixing anode active material with the components of the solid, ionically conducting polymer material of the invention including the base polymer, the dopant and a compound including a source of ions prior to formation of the solid, ionically conducting polymer material to form a mixture. Alternatively, the anode active material is mixed with the solid, ionically conducting polymer material already formed. The mixture is molded and/or extruded at temperatures between 180°C and 350°C . The anode of the present invention includes active material in an amount of between 10 wt. % and 90 wt. %, and preferably in an amount of between 25 wt. % and 90 wt. %, and more preferably in an amount of between 50 wt. % and 90 wt. %, relative to the total anode weight. The anode can further include an electrically conductive additive, such as a carbon black component, a natural graphite component, a synthetic graphite component, a graphene component, a conductive polymer component, a metal particles component, and/or other like electrically conductive additives. The anode can include the electrically conductive additives in an amount of between 0 wt. % and 25 wt. %, and preferably in an amount of between 10 wt. % and 15 wt. % relative to the total anode weight. The anode of the present invention relating to OH^- chemistries can further include one or more functional additives for improving performance. The anode active material can be encapsulated by the solid, ionically conducting polymer material of the invention.

[0078] In another aspect, the invention provides a Zn/MnO₂ battery including an electrolyte interposed between a MnO₂ cathode and a Zn anode. The electrolyte in this aspect can include the solid, ionically conducting material of the invention having mobility for OH^- ions or can include a traditional separator filled with liquid electrolyte. The cathode can include the solid, ionically conducting material having mobility for OH^- ions of the invention or can include a commercial MnO₂ cathode. The anode in this aspect can include the solid, ionically conducting material of the invention having mobility for OH^- ions or can include a Zn foil, a Zn mesh or a Zn anode manufactured by other methods. In the Zn/MnO₂ battery of the invention, the solid, electronically conducting polymer material of the invention having mobility for OH^- ions is included in at least one of the cathode, the anode and the electrolyte.

III. Polymer-MnO₂ composite cathode

[0079] The invention further relates to a polymer-MnO₂ composite cathode with a high specific capacity and a primary alkaline cell including the cathode. More specifically, the invention further relates to a polymer-MnO₂ composite cathode with a specific capacity close to theoretical 2-electron discharge and a primary alkaline cell comprising the cathode. The alkaline cell can be discharged at current densities comparable to that of commercial alkaline cells, while useful capacity is delivered to typical 0.8V voltage cut-off.

[0080] In different aspects, the invention features a cathode that is made of a MnO₂ active material including a plurality of active MnO₂ particles intermixed with a solid, ionically conductive polymer material including a base polymer, a dopant, and a compound including an ion source and a method of making said cathode. In other aspects, the invention features an electrochemical cell including a cathode, an anode and a separator disposed between the cathode and the anode, and a method for making said cathode. The cathode is made of a MnO₂ active material including a plurality of active MnO₂ particles intermixed with a solid, ionically conductive polymer material including a base polymer, a dopant, and a compound including an ion source. The cathode and the electrochemical cell of the present invention are characterized by flat discharge curves.

[0081] In the aspects of the invention related to the polymer-MnO₂ composite cathode, the base polymer can be a semicrystalline polymer. The base polymer can be selected from a group which consists of a conjugated polymer or a polymer which can easily be oxidized. Non-limiting examples of the base polymers used in this aspect of the invention include PPS, PPO, PEEK, PPA, etc.

[0082] In the aspects of the invention related to the polymer-MnO₂ composite cathode, the dopant is an electron acceptor or oxidant. Non-limiting examples of dopants are DDQ, tetracyanoethylene also known as TCNE, SO₃, ozone, transition metal oxides, including MnO₂, or any suitable electron acceptor, etc.

[0083] In the aspects of the invention related to the polymer-MnO₂ composite cathode, the compound including the ion source is a salt, a hydroxide, an oxide or other material containing hydroxyl ions or convertible to such materials, including, but not limited to, LiOH, NaOH, KOH, Li₂O, LiNO₃, etc.

[0084] In the aspects of the invention related to the polymer-MnO₂ composite cathode, the MnO₂ active material can be in the form of β -MnO₂ (pyrolusite), ramsdellite, γ -MnO₂, ϵ -MnO₂, λ -MnO₂ and other MnO₂ phases or mixtures thereof, including, but not limited to, EMD and CMD.

[0085] The cathode related to the polymer-MnO₂ composite cathode can be made prepared by mixing a plurality of active MnO₂ particles and a solid, ionically conducting polymer material including a base polymer, a dopant and a compound including an ion source, and heating the mixture to a specific temperature for a specific time. Said heating

can optionally be performed while applying pressure.

[0086] In one embodiment, the polymer-MnO₂ composite cathode of the present invention can be prepared by compression molding at a temperature of between 180 and 350 °C, and preferably between 190 °C and 350 °C, and more preferably between 280 °C and 350 °C, and most preferably between 290 °C and 325 °C. In other embodiments, the heating is optionally conducted at a pressure of between 150 - 2000 PSI, and preferably between 150-1000 PSI and more preferably between 150-500 PSI, and most preferably between 150-250 PSI. The MnO₂ active material can be in an amount of between 5 wt. % and 95 wt. % and preferably between 50 wt. % and 90 wt. % relative to the total weight of the composite cathode. The composite cathode can include a filler in the amount of between 5 wt. % and 50 wt. %, and preferably between 10 wt. % and 50 wt. %, and more preferably between 20 wt. % and 40 wt. %, and most preferably between 25 wt. % and 35 wt. % relative to the total weight of the composite cathode. The dopant can be added in the amount corresponding to a base polymer/dopant molar ratio between 2 and 10, and preferably between 2 and 8, and more preferably between 2 and 6, and most preferably between 3 and 5. The composite cathode can include an electrically conductive additive, such as a carbon black component, a natural and/or a synthetic graphite component, a graphene component, an electrically conductive polymer component, a metal particles component, and another component, wherein the electrically conductive component is in the amount of between 5 wt. % and 25 wt. %, and preferably between 15 wt. % and 25 wt. %, and more preferably between 18 wt. % and 22 wt. % relative to the total weight of the composite cathode. The MnO₂ active material in the composite cathode can be encapsulated by solid, ionically conducting polymer material of the invention.


[0087] In a preferred embodiment, the invention features an alkaline battery including said polymer-MnO₂ composite cathode and a Zn anode. The Zn anode can be in the form of slurry including Zn or Zn alloy powder, KOH, gelling agent and optionally other additives. The Zn anode can further include an electrically conductive additive, similar to the composite cathode.

[0088] The anode related to the polymer-MnO₂ composite of the invention can include Zn, Al, Fe, metal hydride alloys or similar materials. Zn and Al are preferred materials and can be in the form of pure metals or specially designed alloys. The separator can be a traditional non-woven separator used in alkaline batteries. Electrolyte is KOH, NaOH, LiOH etc. solution in water. Alkali concentration can be between 4 and 9 M. The Electrolyte can further contain an electronically conductive additive and/or a functional additive.

IV. Polymer-sulfur Cathode

[0089] In addition, the invention relates to a composite polymer-sulfur cathode. The composite polymer-sulfur cathode includes a sulfur component and a solid, ionically conducting polymer material including a base polymer, a dopant and a compound including a source of ions. The composite polymer-sulfur cathode is characterized as having a high specific capacity and a high capacity retention when employed in a secondary lithium or Li-ion sulfur cell. The composite cathode is characterized as having a specific capacity of greater than 200 milliamp-hr/gm, and preferably greater than 500 milliamp-hr/gm, and more preferably greater than 750 milliamp-hr/gm, and most preferably greater than 1000 milliamp-hr/gm. The composite cathode is characterized as having a retention of least 50% and preferably at least 80% for over 500 recharge/discharge cycles. The composite polymer-sulfur cathode of the present invention has direct application to low-cost, large-scale manufacturing enabled by the unique polymer used in this composite electrode. The composite polymer-sulfur cathode of the invention can provide high performance while simultaneously meeting the requirements for producing low-cost batteries.

[0090] Notably, sulfur cathodes reduce during discharge to create sequentially lower order polysulfides through the sequence illustrated in the following equation:



[0091] The intermediate polysulfides between Li₂S₈ and Li₂S₄ are soluble in liquid electrolytes. Thus, dissolved polysulfide particles are able to migrate (or "shuttle") across porous separators and react directly with the anode and cathode during cycling. The polysulfide shuttle produces parasitic reactions with the lithium anode and re-oxidation at the cathode, all causing capacity loss. Furthermore, aspects of this shuttle reaction are irreversible, leading to self-discharge and low cycle life that has, until now, plagued lithium sulfur batteries.

[0092] The present invention demonstrates a composite polymer-sulfur cathode including a sulfur component and a solid, ionically conducting polymer material. This cathode can be extruded into a flexible, thin film via a roll-to-roll process. Such thin films enable thin, flexible form factors which can be incorporated into novel flexible battery designs. As shown in the examples which follow, this composite polymer-sulfur cathode can include an electrically conductive addition such as, for example, an inexpensive carbon black component, such as Timcal C45, which is already in use for many commercial battery products. In addition to the exemplary carbon black component, the composite polymer-sulfur cathode can include other electrically conductive additives such as, for non-limiting examples, a carbon component including but

not limited to carbon fibers, a graphene component, a graphite component, metallic particles or other metal additives, and an electrically conductive polymer.

[0093] The engineering properties of the composite polymer-sulfur cathode allow the extrusion of the cathode into a wide range of possible thicknesses, which in turn provides important advantages in terms of flexibility in design in large-scale cathode manufacturing. The composite polymer-sulfur cathode can be extruded as thin as 5 microns and up to thicknesses greater than several 100 microns.

[0094] A comparison of the process steps necessary for producing standard lithium ion cathodes with those necessary to produce the inventive composite polymer-sulfur cathode is instructive relative to the inherent lower cost of the composite polymer-sulfur cathode manufacturing. FIG. 18 illustrates the process steps needed to manufacture a standard lithium ion cathode compared with the much simpler manufacturing of an extruded composite polymer-sulfur cathode of the invention. The extrusion process for the composite polymer-sulfur cathode is easily scaled-up to high volume manufacturing which provides a significant advantage over existing lithium ion battery, as well as a much lower capital expenditure for factory equipment.

[0095] In addition to extrusion, the composite polymer-sulfur cathode can be formed by injection molding, compression molding, or any other process involving heat, or other techniques known by those skilled in the art for engineering plastics.

[0096] The composite polymer-sulfur cathode includes a sulfur component and a solid, ionically conducting polymer material including a base polymer, a dopant and a compound including a source of ions, as discussed above.

[0097] The base polymer includes liquid crystal polymers and polyphenylene sulfide (PPS), or any semicrystalline polymer with a crystallinity index greater than 30%, or other typical oxygen acceptors.

[0098] The dopant includes electron acceptors which activate the ionic conduction mechanism. These electron acceptors can be pre-mixed along with the other ingredients, or supplied in the vapor phase as a post doping process. Typical electron acceptor dopants suitable for use include, but are not limited to: 2,3-dichloro-5,6-dicyano-1,4-benzoquinone (DDQ) ($C_8Cl_2N_2O_2$), Tetracyanoethylene (TCNE) (C_6N_4), and sulfur trioxide (SO_3).

[0099] The compounds including an ion source include, but are not limited to Li_2O and $LiOH$. Use of composite polymer-sulfur cathodes in Li/Sulfur test cells has shown that the composite polymer-stable cathodes are stable to lithium, sulfur, and organic electrolytes typically used in lithium/sulfur batteries.

[0100] The base polymer is a nonflammable polymer which has been shown to self-extinguish and pass the UL-VO Flammability test. The non-flammability of the base polymer is a safety benefit to batteries employing the composite polymer-sulfur cathode. The incorporation of the non-flammable composite polymer-sulfur cathode into a cell with non-flammable electrolyte will further improve the safety of the battery, an important attribute for high energy density batteries.

[0101] The sulfur component can include non-reduced and/or reduced forms of sulfur including elemental sulfur. In particular, the composite polymer-sulfur cathode includes a sulfur component including the fully lithiated form of sulfur (Li_2S), wherein the Li_2S is a solid. The composite polymer-sulfur cathode can also include a carbon component. The advantage to using the fully lithiated form of sulfur is that it provides a lithium source for a sulfur battery with a Li ion anode, which, unlike metal Li, must be lithiated during initial charge. Combination of a sulfur cathode with a Li-ion anode provides benefit in preventing the formation of lithium dendrites which can be formed after cycling lithium anodes. Dendrites are caused by a non-uniform plating of lithium onto the lithium metal anode during charging. These dendrites can grow through separator materials and cause internal short circuits between cathode and anode, often leading to high temperatures and compromised safety of the battery. Materials that reversibly incorporate lithium, either through intercalation or alloying, lessen the chance for dendrite formation and have been proposed for use in high safety lithium/sulfur cells. The composite polymer-sulfur cathode can be used with an anode material such as, for example, a carbon-based (petroleum coke, amorphous carbon, graphite, carbon nano tubes, graphene, etc.) material, Sn, SnO , SnO_2 and Sn-based composite oxides, including composites with transition metals, such as Co, Cu, Fe, Mn, Ni, etc. Furthermore, silicon has shown promise as a lithium ion anode material, in the elemental form, or as an oxide or composite material, as described for tin. Other lithium alloying materials (for example, Ge, Pb, B, etc.) could also be used for this purpose. Oxides of iron, such as Fe_2O_3 or Fe_3O_4 and various vanadium oxide materials have also been shown to reversibly incorporate lithium as a Li-ion anode material. Anode materials may be considered in different forms, including amorphous and crystalline, and nano-sized particles as well as nano-tubes.

[0102] The composite polymer-sulfur cathode can be combined with a standard liquid electrolyte, a standard nonwoven separator, and/or an electrolyte including a solid, ionically conducting polymer material with no liquid electrolyte. An example of a standard organic electrolyte solution includes a lithium salt, such as lithium bis(trifluoromethane sulfonyl)imide (LiTFSI), dissolved in a mixture of 1,3-dioxolane (DOL) and 1,2-dimethoxyethane (DME). Additives, such as $LiNO_3$, can be added to the electrolyte to improve cell performance. Other lithium salts can be utilized in organic liquid electrolyte, including: $LiPF_6$, $LiBF_4$, $LiAsF_6$, lithium triflate, among others. Additionally, other organic solvents can be used, such as propylene carbonate (PC), ethylene carbonate (EC), diethyl carbonate (DEC), dimethyl carbonate (DMC), ethyl methyl carbonate (EMC), fluoroethylene carbonate (FEC), as a few examples, either alone or as mixtures together or with DOL and DME. Examples of standard nonwoven separators include polypropylene (PP), polyethylene (PE), and combinations of PP/PE films. Other separator materials include polyimide, PTFE, ceramic coated films and glass-mat

separators. All of the above materials can be used with the composite polymer-sulfur cathode. Further, the composite polymer-sulfur cathode could also be utilized in a gel-polymer system, where for example, a PVDF-based polymer is swelled with an organic electrolyte.

[0103] It is believed that the ability of the composite polymer-sulfur cathode to provide lithium ionic conductivity improves the performance of the cell by limiting the polysulfide shuttle mechanism, while simultaneously providing a sulfur cathode with high voltage. Furthermore, this unique engineering composite polymer-sulfur cathode allows for the large scale, low cost manufacturing necessary for commercial viability of the cathode.

[0104] Thus, the unique composite polymer-sulfur cathode has numerous potential benefits to batteries, including:

- Improved safety, under normal and abuse conditions
- Enabling new battery form factors
- Large increase in energy density over existing Li-ion cells
- Prevention of the polysulfide shuttle mechanism, leading to greater charge/discharge reversibility
- Large decrease in manufacturing cost (raw materials, process and capital equipment) leading to improvement in the cost of energy storage

EXAMPLE 1

[0105] Solid polymer electrolyte was made by mixing PPS base polymer and ion source compound LiOH monohydrate in the proportion of 67% to 33% (by wt.), respectively, and mixed using jet milling. DDQ dopant was added to the resulting mixture in the amount of 1 mole of DDQ per 4.2 moles of PPS. The mixture was heat treated at 325/250 °C for 30 minutes under moderate pressure (500-1000 PSI). After cooling, the resulting material was grinded and placed into NMR fixture.

[0106] Self-diffusion coefficients were determined by using pulsed field gradient solid state NMR technique. The results shown in FIGs. 19 and 20 indicate, respectively, that Li^+ and OH^- diffusivity in the solid polymer electrolyte is the highest of any known solid, and over an order of magnitude higher at room temperature compared to recently developed $\text{Li}_{10}\text{GeP}_2\text{S}_{12}$ ceramic at much higher temperatures (140 °C) or the best PEO formulation at 90 °C.

EXAMPLE 2

[0107] PPS base polymer and ion source compound LiOH monohydrate were added together in the proportion of 67 wt. % to 33 wt. %, respectively, and mixed using jet milling. Cathode was prepared by additionally mixing 50% β -MnO₂ from Alfa Aesar, 5% of Bi₂O₃ and 15% of C45 carbon black. DDQ dopant was added to the resulting mixture in the amount of 1 mole of DDQ per 4.2 moles of PPS.

[0108] The mixture was compression molded onto stainless steel mesh (Dexmet) at 325/250 °C for 30 minutes under moderate pressure (500-1000 PSI), yielding cathode disc 25.4 mm (1 inch) in diameter and about 0.15 mm thick. The resulting disc was punched to 19 mm diameter and used as a cathode to assemble test cells, containing commercial non-woven separator (NKK) and Zn foils anode. 6M LiOH was added as electrolyte.

[0109] Cells were discharged under constant current conditions of 0.5 mA/cm² using Biologic VSP test system. The specific capacity of MnO₂ was 303 mAh/g or close to theoretical 1e⁻ discharge. FIG. 21 illustrates the voltage profile of the cell per Example 2 as a function of specific capacity of MnO₂ at 0.5 mA/cm² discharge rate.

EXAMPLE 3

[0110] PPS base polymer and ion source compound LiOH monohydrate were added together in the proportion of 67% to 33% (by wt.), respectively, and mixed using jet milling. Cathode was prepared by additionally mixing 50% β -MnO₂ from Alfa Aesar, 5% of Bi₂O₃ and 15% of C45 carbon black. DDQ dopant was added to the resulting mixture in the amount of 1 mole of DDQ per 4.2 moles of PPS.

[0111] The mixture was compression molded onto stainless steel mesh (Dexmet) at 325/250 C for 30 minutes under moderate pressure (500-1000 psi), yielding cathode disc 25.4 mm (1 inch) in diameter and 1.6-1.8 mm thick.

[0112] The resulting cathodes were used to assemble test cells, containing commercial non-woven separator (NKK) and Zn anode slurry extracted from commercial alkaline cells. 6M KOH solution in water was used as electrolyte.

[0113] Cells were discharged under constant current conditions using Biologic VSP test system. The specific capacity of MnO₂ was close to 600 mAh/g at C/9 discharge rate (35 mA/g), or close to theoretical 2 e⁻ discharge.

[0114] FIG. 22 shows the voltage profile of the cell per Example 3 as a function of specific capacity of MnO₂ at C/9 rate (35 mA/g).

EXAMPLE 4

[0115] PPS base polymer and ion source compound LiOH monohydrate were added together in the proportion of 67% to 33% (by wt.), respectively, and mixed using jet milling. Cathode was prepared by additionally mixing 50% β -MnO₂ form Alfa Aesar, 5% of Bi₂O₃ and 15% of C45 carbon black. DDQ dopant was added to the resulting mixture in the amount of 1 mole of DDQ per 4.2 moles of PPS.

[0116] The mixture was compression molded onto stainless steel mesh (Dexmet) at 325/250 °C for 30 minutes under moderate pressure (500-1000 PSI), yielding cathode disc 25.4 mm (1 inch) in diameter and about 0.15 mm thick.

[0117] The resulting disc was punched to 19 mm diameter and used as a cathode to assemble test cells, containing commercial non-woven separator (NKK) and Zn foil anode. 6M LiOH was added as electrolyte.

[0118] The cells were discharged and charged using a Biologic VSP test system. Discharge was conducted at 0.5 mA/cm² current to 0.8 V cut-off. Charge was performed at 0.25 mA/cm² to 1.65 V, then held at 1.65V for 3 hours or until current declined to 0.02 mA/cm². Every few cycles passivated Zn anode and separator were replaced with fresh. Specific capacity of MnO₂ as a function of cycle number in cells per Example 4 is plotted at FIG. 23. Each column represents separate cell. Only discharges with fresh Zn anode are shown. It is easy to see that MnO₂ cathode of present invention is rechargeable. Only discharges with fresh Zn anode are shown.

EXAMPLE 5

[0119] A 2035 coin cell was assembled using the solid polymer electrolyte of Example 1, the cathode of Example 2 and a Zn foil as anode. The cell was discharged and charged using a Biologic VSP test system. Discharge was conducted at 0.25 mA/cm² current to 0.8 V cut-off. Charge was performed at 0.25 mA/cm² to 1.65 V, then held at 1.65V for 3 hours or until current declined to 0.02 mA/cm². The cell demonstrated reversible behavior during such cycling. FIG. 24 shows the discharge curve of the coin cell per Example 5 as a function of test time.

EXAMPLE 6

[0120] PPS base polymer and ion source compound LiOH monohydrate were added together in the proportion of 67% to 33% (by wt.), respectively, and mixed using jet milling. Cathode was prepared by additionally mixing 55% β -MnO₂ form Alfa Aesar and 15% of C45 carbon black. DDQ dopant was added to the resulting mixture in the amount of 1 mole of DDQ per 4.2 moles of PPS.

[0121] The mixture was compression molded onto stainless steel mesh (Dexmet) at 325/250 C for 30 minutes under moderate pressure (500-1000 psi), yielding cathode disc 25.4 mm (1 inch) in diameter and about 0.15 mm thick.

[0122] The test cell was assembled using the resulting cathode, electrolyte per Example 1 and anode made of Zn powder. The cell was discharged using Biologic VSP test system at 0.5 mA/cm² current density to 0.8 V cut-off. Specific capacity of MnO₂ was 401 mAh/g or more than theoretical 1-electron discharge. FIG. 25 shows the voltage profile of the cell per Example 6 as a function of test time.

EXAMPLE 7

[0123] PPS base polymer and ion source compound LiOH monohydrate were added together in the proportion of 67% to 33% (by wt.), respectively, and mixed using jet milling. Anode was prepared by additionally mixing 60% of Zn powder and 10% of C45 carbon black. DDQ dopant was added to the resulting mixture in the amount of 1 mole of DDQ per 4.2 moles of PPS.

[0124] The mixture was compression molded onto stainless steel mesh (Dexmet) at 325/250 C for 30 minutes under moderate pressure (500-1000 psi), yielding cathode disc 25.4 mm (1 inch) in diameter and about 0.15 mm thick.

[0125] The 2035 coin cell was assembled using the resulting anode, cathode per example 2 and commercial NKK separator, containing saturated LiOH as electrolyte.

[0126] The control coin cell was made using Zn foil as anode, cathode per Example 2 and commercial NKK separator containing saturated LiOH as electrolyte.

[0127] The cells were discharged using a Biologic VSP test system at 0.5 mA/cm² current density. The discharge profile with anode of the present invention shows higher capacity at slightly higher voltage, which can be related to increased surface area of Zn anode and retention of soluble zincates inside the anode structure. FIG. 26 shows the discharge curve of coin cells per Example 7 as a function of discharge capacity. Discharge was conducted at 0.25 mA/cm² current to 0.7 V cut-off. Curve A - cell with anode of the present invention. Curve B - cell with Zn foil anode. FIG. 26 shows the discharge curve of coin cells per Example 7 as a function of discharge capacity. Discharge was conducted at 0.25 mA/cm² current to 0.7 V cut-off. Curve A - cell with anode of the present invention. Curve B - cell with Zn foil anode.

EXAMPLE 8

[0128] PPS base polymer and an ion source compound LiOH monohydrate were added together in the proportion of 67% to 33% (by wt.), respectively, and mixed using jet milling. Anode was prepared by additionally mixing 60% of Al powder and 10% of C45 carbon black. DDQ dopant was added to the resulting mixture in the amount of 1 mole of DDQ per 4.2 moles of PPS. The mixture was compression molded onto stainless steel mesh (Dexmet) at 325/250 C for 30 minutes under moderate pressure (500-1000 psi), yielding cathode disc 25.4 mm (1 inch) in diameter and about 0.15 mm thick.

[0129] The resulting anode was tested in test cell containing Zn counter electrode and commercial separator containing ZnSO₄ electrolyte. Anode made of Al foil was tested as a control.

[0130] The anode was polarized potentiodynamically at 1 mV/s sweep rate using Biologic VSP test system. FIG. 27 shows a potentiodynamic scan at 1 mV/s of anode of the present invention (curve A) and control Al foil (curve B) in ZnSO₄ electrolyte. Anode of the present invention demonstrated corrosion stability improved by 0.5 V compared to Al foil.

COMPARATIVE EXAMPLE 9

[0131] Discharge profile of Duracell Coppertop AA cell at 250 mA discharge was taken from the datasheet. Amount of MnO₂ in the cell was calculated by comparison of published specifications and MSDS, yielding between 8.4 and 9.6 g. Simple conversion results in current density between 26 and 30 mA/g. Product of service hours (per datasheet) and discharge current yields total capacity, which can be converted to specific capacity by dividing it by weight of MnO₂. Voltage profile of the Coppertop AA cell as a function of specific MnO₂ capacity, calculated in such manner, is shown at FIG. 28. Curve A corresponds to maximum amount MnO₂ (9.6 g) where specific capacity of Duracell Coppertop AA cell is under constant current discharge at 26 mA/g rate. Curve B corresponds to minimum amount of MnO₂ (8.4 g) where specific capacity of Duracell Coppertop AA cell under constant current discharge is at 30 mA/g rate. Curve C shows a specific capacity of Duracell Coppertop AA cell under a constant current discharge rate of 2.2 mA/g. It is easy to see that MnO₂ specific capacity, calculated to 0.9 V cut-off, is between 235 and 270 mAh/g. Extrapolation to 0.8 V cut-off will result in slightly better specific capacity between 245 and 275 mAh/g. Discharge curves have typical sloping shape, characteristic to Zn/MnO₂ cells. Difference between voltage at 5% depth of discharge and 95% depth of discharge is close to 0.5 V or 30% of initial (5% DOD) [2.1-2.4 V/Ah/g]. Discharging Coppertop cell at extremely low rate of 2.2 mA/g (assuming average amount of MnO₂ in the cell) results in appearance of additional plateau (curve C). Total specific capacity was 347 mA/g, corresponding to 1.13-electron discharge. The discharge curve still has typical sloping shape with close to 0.5 V voltage difference between 5 and 95% depth of discharge.

COMPARATIVE EXAMPLE 10

[0132] AA cells were purchased in retail store and subjected to 250 mA discharge, corresponding to mid-rate test, using a Maccor 4300 system. Table 10.1 shows performance of commercial AA cells under 250 mA continuous discharge. Total capacity delivered to 0.9 V cut-off is shown in Table 10.1. Assuming amount of MnO₂ in the cells is the same as Comparative example 9, the total capacity of the cell can be converted to specific capacity of MnO₂. As one can see, under these discharge conditions commercial AA cells deliver between 200 and 280 mAh/g. Even taking into account positive effect of intermittent discharge and extending voltage cut-off to 0.8V, it is a fair statement that commercial alkaline cells operate within 1-electron reduction of MnO₂, described by equation (1), and are limited to 308 mAh/g.

Table 10.1

Cell	Total Capacity Ah	Specific Capacity (mAh/g)	
		Min	Max
Rayovac	2.15	224	256
Rayovac	2.11	220	251
Energizer Max	1.84	191	219
Energizer Max	1.82	190	217
Duracell Coppertop	2.15	224	256
Duracell Coppertop	2.13	222	254

(continued)

	Total Capacity	Specific Capacity (mAh/g)	
Cell	Ah	Min	Max
Duracell Quantum	2.35	244	279
Duracell Quantum	2.33	243	277

COMPARATIVE EXAMPLE 11 per US 7,972,726

[0133] Figure 29 shows discharge curves for alkaline button cells with cathodes based on AgBiO₃ cathode (curve (a)), EMD (MnO₂) cathode (curve (b)) and 1:9 AgBiO₃:EMD mixture at 10 mA/g discharge rate (curve (c)), reproduced from US 7,972,726. Under these conditions, discharge profile for EMD (b) is similar to commercial alkaline cell described in comparative example 9 with 0.5 V difference between voltage at 5 and 95% DOD. MnO₂ capacity of about 290 mAh/g is consistent with 1-electron discharge. Cathodes made with AgBiO₃:EMD mixture displayed additional plateau at about 0.9 V, boosting MnO₂ capacity. Best performance was reported with 1:9 AgBiO₃:EMD mixture, which delivered 351 mAh/g before 0.8 V cut-off. This corresponds to 1.13-electron discharge of MnO₂.

EXAMPLE 12

[0134] PPS base polymer and ion source compound LiOH monohydrate were added together in the proportion of 67% to 33% (by wt.), respectively, and mixed using jet milling. Cathode was prepared by additionally mixing 50% β-MnO₂ from Alfa Aesar, 5% of Bi₂O₃ and 15% of C45 carbon black. DDQ dopant was added to the resulting mixture in the amount of 1 mole of DDQ per 4.2 moles of PPS.

[0135] The mixture was compression molded onto stainless steel mesh (Dexmet) at 325/250 C for 30 minutes under moderate pressure (500-1000 psi), yielding cathode disc 25.4 mm (1 inch) in diameter and 1.6-1.8 mm thick.

[0136] The resulting cathodes were used to assemble test cells, containing commercial non-woven separator (NKK) and Zn anode slurry extracted from commercial alkaline cells. 6M KOH solution in water was used as electrolyte.

[0137] Cell was discharged under constant current conditions using Biologic VSP test system. FIG. 30 shows the voltage profile of cell per Example 12 at 35 mA/g constant current discharge as a function of specific capacity of MnO₂. The discharge profile, shown at FIG. 30, looks significantly more flat, compared to conventional Zn/MnO₂ cells. Voltage difference between 5 and 95% DOD is about 0.1 V or less than 10% of initial. The specific capacity of MnO₂ was close to 600 mAh/g or 97% of theoretical 2-electron discharge (616 mAh/g).

EXAMPLE 13

[0138] PPS base polymer and ion source compound LiOH monohydrate were added together in the proportion of 67% to 33% (by wt.), respectively, and mixed using jet milling. Cathode was prepared by additionally mixing 50% EMD from Tronox (mixture of γ- and ε-MnO₂), 5% of Bi₂O₃ and 15% of C45 carbon black. DDQ dopant was added to the resulting mixture in the amount of 1 mole of DDQ per 4.2 moles of PPS.

[0139] The mixture was compression molded onto stainless steel mesh (Dexmet) at 325/250 C for 30 minutes under moderate pressure (500-1000 psi), yielding cathode disc 25.4 mm (1 inch) in diameter and 1.6-1.8 mm thick.

[0140] The resulting cathodes were used to assemble test cells, containing commercial non-woven separator (NKK) and Zn anode slurry extracted from commercial alkaline cells. 6M KOH solution in water was used as electrolyte.

[0141] Cells were discharged under constant current conditions using Biologic VSP test system. FIG. 31 shows the voltage profile of the cell per Example 13 as a function of specific capacity of MnO₂ at 29 mA/g (Curve A) and 59 mA/g (Curve B). The specific capacity of MnO₂ was close to 600 mAh/g at 29 mA/g rate and close to 560 mAh/g at 59 mA/g rate.

EXAMPLE 14

[0142] PPS base polymer and ion source compound LiOH monohydrate were added together in the proportion of 67% to 33% (by wt.), respectively, and mixed using jet milling. Cathode was prepared by additionally mixing 80% EMD from Tronox (mixture of γ- and ε-MnO₂), 5% of C45 carbon black. DDQ dopant was added to the resulting mixture in the amount of 1 mole of DDQ per 4.2 moles of PPS.

[0143] The mixture was compression molded onto stainless steel mesh (Dexmet) at 325/250 C for 30 minutes under moderate pressure (500-1000 psi), yielding cathode disc 25.4 mm (1 inch) in diameter and 1.6-1.8 mm thick.

[0144] The resulting cathodes were used to assemble test cells, containing commercial non-woven separator (NKK) and Zn anode slurry extracted from commercial alkaline cells. 7M KOH solution in water was used as electrolyte.

[0145] The cell was discharged under constant current conditions at a rate of 9 mA/g using Biologic VSP test system. The specific capacity of MnO₂ was 590 mAh/g. FIG. 32 shows the voltage profile of cell per Example 14 as a function of specific capacity of MnO₂ at 9 mA/g discharge rate (curve A) and Duracell Coppertop cells at 2.2 mA/g (curve B). The voltage difference between 5 and 95% DOD was 0.163V or 13.6% (Curve A). Discharge profile for Duracell Coppertop cell at 2.2 mA/g is shown for comparison (Curve B).

EXAMPLE 15

[0146] PPS base polymer and ion source compound LiOH monohydrate were added together in the proportion of 67% to 33% (by wt.), respectively, and mixed using jet milling. Cathode was prepared by additionally mixing 80% EMD from Erachem (mixture of γ - and ϵ -MnO₂), 5% of C45 carbon black. DDQ dopant was added to the resulting mixture in the amount of 1 mole of DDQ per 4.2 moles of PPS.

[0147] The mixture was compression molded onto stainless steel mesh (Dexmet) at 325/250 C for 30 minutes under moderate pressure (500-1000 psi), yielding cathode disc 25.4 mm (1 inch) in diameter and 1.6-1.8 mm thick.

[0148] The resulting cathodes were used to assemble test cells, containing commercial non-woven separator (NKK) and Zn anode slurry extracted from commercial alkaline cells. 7M KOH solution in water was used as electrolyte.

[0149] The cell was discharged under constant current conditions at a rate of 9.5 mA/g using Biologic VSP test system. The specific capacity of MnO₂ was 541 mAh/g. FIG. 33 shows the voltage difference between 5 and 95% DOD was 0.180V or 14.1% (Curve A). Discharge profile for Duracell Coppertop cell at 2.2 mA/g is shown for comparison (Curve B).

EXAMPLE 16

[0150] PPS base polymer and ion source compound LiOH monohydrate were added together in the proportion of 67% to 33% (wt/wt), respectively, and were mixed using jet milling. The mixture was compression molded at 325°C/250°C for 30 minutes under low pressure. The polymer-sulfur composite cathode was prepared by additionally mixing from 25% to 50% of sulfur powder, 5% to 15% of C45 carbon black, and 0% to 10% LiNO₃ with the solid, ionically conducting polymer material. The materials were compression molded onto stainless steel mesh (Dexmet) at 120°C for 30 minutes, yielding a cathode disc 15 mm in diameter and 0.3 to 0.4 mm thick.

[0151] The resulting cathodes were used to assemble test cells in 2035 coin cell hardware. Polypropylene separator (Celgard) 25 microns thick and 19 mm in diameter was used along with lithium foil anode material, 15 mm in diameter. A liquid electrolyte of 1M LiTFSI salt dissolved in a 50/50 (vol/vol) mixture of DOL/DME was used, with 0.5M LiNO₃ additive. The cells were assembled in an argon gas filled glovebox, with low oxygen and water levels. Cells were discharged under constant current conditions (1 mA) using a Maccor 4600 battery test system. Discharge was terminated at a voltage of 1.75 V.

[0152] FIG. 34 shows a first discharge voltage curve for a Li/composite polymer-sulfur cathode in a cell of the present invention. The discharge voltage profile for the first cycle is displayed in Figure 34. It can be seen that the composite polymer-sulfur cathode provides a high initial capacity of > 1300 mAh/g, based on the amount of sulfur in the cathode. The cell in FIG. 34 also displays a discharge voltage curve with two plateaus, at ~ 2.3V and ~2.1V. This shows that the composite polymer-sulfur system enables high capacity, while producing the expected voltage curve for a lithium/sulfur system, consistent with a stable electrochemical couple.

EXAMPLE 17

[0153] Composite polymer-sulfur cathodes were manufactured as described in Example 16. These cathodes were assembled into coin cells using lithium metal anodes, polypropylene separator, and 1M LiTFSI in DOL/DME electrolyte with 0.5M LiNO₃ additive.

Cells were discharged under constant current conditions (1 mA) using a Maccor 4600 battery test system. Discharge was terminated at a voltage of 1.75 V. Charge was accomplished in two steps, the first at a lower charge rate of 0.2 mA current to a maximum voltage of 2.3 V, and the second charge step at a higher rate of 1 mA current to a maximum voltage of 2.45 V. The overall charge capacity was limited for these test cells. These cells were allowed to cycle several times at room temperature.

[0154] FIG. 35 shows the discharge capacity curve plotted as a function of cycle number for Li/composite polymer-sulfur cell of the present invention. This graph shows that the composite polymer-sulfur cathode will support reversible charge/discharge, with high reversible capacity of at least 1000 mAh/g based on the amount of sulfur in the cathode.

COMPARATIVE EXAMPLE 18

[0155] A noteworthy example of a highly ordered interwoven composite electrode is presented in the literature [Ji, X.; Lee, K.T.; Nazar, L.F. *Nature Materials* 2009, 8, 500-506]. This composite cathode utilized CMK-3 mesoporous carbon with sulfur entrenched in the pores through heat treatment at 155°C. FIG. 36 compares the first discharge for literature example Li/Sulfur-CMK-3 with Li/composite polymer-sulfur of present invention.

The composite cathode in this example was slurry-cast from cyclopentanone onto a carbon coated aluminum current collector. The cathode utilized 84 wt% CMK-3/S composite, 8 wt% Super-S carbon and 8 wt% PVDF binder. The electrolyte was composed of 1.2 M LiPF₆ in ethyl methyl sulphone, and Li metal was used as the anode. In comparison, the results for the composite polymer-sulfur cathode of the invention, as described in Example 16, are plotted on the same graph. It is apparent that the composite polymer-sulfur cathode of the invention gives as good, or better, results than literature examples of composite sulfur cathodes.

COMPARATIVE EXAMPLE 19

[0156] The use of sulfur-conductive polymer composites as cathodes for lithium batteries has been demonstrated. In one case, polyacrylonitrile (PAN) is sulfurized to form a conductive and chemically active cathode material. The sulfurization of the polymer takes place at a relatively high temperature of ~ 300°C. An example of the discharge curve for this material is shown in FIG. 37, which was displayed in U.S. Patent Application 2014/0045059 [He, X.-M., et. al.]. FIG. 37 shows the typical voltage signature seen for Li/Sulfur-Polyacrylonitrile (S/PAN) cells. These cells are typified by a single sloping voltage plateau, with an average voltage below 2.0 V. In comparison to the voltage curve observed in FIG. 4 for the Li/composite polymer-sulfur cathode in a cell of the invention, it can be seen that the S/PAN cells display significantly lower voltage throughout discharge, which results in a lower energy density, based on Watt-hours. Thus, the voltage behavior displayed by the composite polymer polymer-sulfur cathode of the invention is superior to that of the sulfurized PAN-based cathodes.

EXAMPLE 20

[0157] Solid polymer electrolyte samples were made by mixing SRT802 (Liquid Crystal Polymer) polymer with lithium hydroxide monohydrate, as a compound comprising ion source, in a proportion 2:1, respectively (by weight). DDQ was used a dopant. Weight ratio of polymer to dopant was 2:1. Mixtures were heat treated at 325/250 °C for 30 minutes under moderate pressure (500-1000 PSI). The ionic surface conductivity of the samples were measured using standard AC-EIS. Samples were sandwiched between stainless steel blocking electrodes and placed in test fixture. AC-impedance was recorded in the range from 800 KHz to 100 Hz using Biologic VSP test system to determine the electrolyte conductivity. Six samples were prepared and tested. Average conductivity was 3.7×10^{-4} S/cm with about 19% standard deviation. The results are shown in the following Table 20.1.

Table 20.1

Sample	Conductivity (S/cm)
1	3.42E-04
2	4.78E-04
3	4.09E-04
4	2.69E-04
5	3.46E-04
6	4.04E-04
Average	3.75E-04
Standard Deviation	7.18E-05
Standard Deviation %	19.2%

EXAMPLE 21

[0158] Solid polymer electrolyte samples were made by mixing SRT900(Liquid Crystal Polymer) polymer with lithium hydroxide monohydrate, as a compound comprising ion source, in a proportion 2:1, respectively (by weight). DDQ was used a dopant. Weight ratio of polymer to dopant was 2:1. Mixtures were heat treated at 325/250 C for 30 minutes under moderate pressure (500-1000 psi). Samples were sandwiched between stainless steel electrodes and placed in test fixture. AC-impedance was recorded in the range from 800 KHz to 100 Hz using Biologic VSP test system to determine

EP 3 078 069 B9

the electrolyte conductivity. Six samples were prepared and tested. Average conductivity was 1.5×10^{-3} S/cm with about 25% standard deviation. The results are shown in the following Table 21.1

Table 21.1

Sample	Conductivity (S/cm)
1	1.14E-03
2	1.39E-03
3	1.59E-03
4	1.31E-03
5	1.20E-03
6	2.13E-03
Average	1.46E-03
Standard Deviation	3.63E-04
Standard Deviation %	24.9%

EXAMPLE 22

[0159] Polymer electrolyte samples were made by mixing polymer and compound comprising ion source in various proportions. DDQ was used a dopant. Molar ratio of polymer to dopant was 4.2. Mixtures were heat treated at 325/250 C for 30 minutes under moderate pressure (500-1000 psi). Samples were sandwiched between stainless steel electrodes and placed in test fixture. AC-impedance was recorded in the range from 800 KHz to 100 Hz using Biologic VSP test system to determine the electrolyte conductivity.

[0160] Results are shown in the table below. High observed conductivity suggests that the polymer electrolyte can conduct multiple ions, including to Li^+ , K^+ , Na^+ , Ca^{2+} , Mg^{2+} , Al^{3+} , OH^- and Cl^- .

Ion Source	Ion Source Wt. %	Conductivity (S/cm)
Li ₂ O	33%	1.9E-04
Na ₂ O	33%	4.2E-05
MgO	33%	6.3E-07
CaCl ₂	33%	6.2E-03
MgCl ₂	20%	8.0E-03
AlCl ₃	15%	2.4E-03
NaOH	50%	1.3E-04
KOH	50%	2.2E-04

[0161] Ability to conduct ions other than Li^+ opens new applications for the polymer electrolyte. Sodium- and potassium-based energy storage systems are viewed as alternative to Li-ion, driven primarily by low cost and relative abundance of the raw materials.

[0162] Calcium, magnesium and aluminum conductivity is important developing multivalent intercalation systems, potentially capable of increasing energy density beyond capabilities of Li-ion batteries. There is also a possibility to utilize such materials to create power sources with metal anodes, more stable and less costly than lithium.

[0163] Hydroxyl conductivity is crucial for numerous alkaline chemistries, including Zn/MnO₂, Ni/Zn, Ni-Cd, Ni-MH, Zn-air, Al-air. Polymer electrolytes conducting hydroxyl ions can be also used in alkaline fuel cells and super capacitors.

[0164] While the present invention has been described in conjunction with preferred embodiments, one of ordinary skill, after reading the foregoing specification, will be able to effect various changes.

Claims

1. A battery comprising
an anode;
a cathode; and

wherein at least one of the anode, and the cathode comprise a solid, ionically conducting, electrically non-conductive polymer material having an ionic conductivity greater than 1×10^{-4} S/cm at room temperature and having a crystallinity index of at least 30 %,

wherein the polymer material includes a base polymer, a dopant and at least one compound including an ion source, and

wherein ionic conductivity is measured according to the description.

2. The battery of claim 1, further comprising an electrolyte, wherein the electrolyte comprises the solid, ionically conducting polymer material.

3. The battery of claim 1, wherein the solid, ionically conducting polymer can conduct a plurality of OH⁻ ions and has an OH⁻ diffusivity of greater than 10^{-11} cm²/sec at a temperature in a range of 20 °C to 26 °C.

4. The battery of claim 1, wherein the solid, ionically conducting polymer material is formed from a reactant product comprising a base polymer, an electron acceptor, and a compound including a source of ions.

5. The battery of claim 1, wherein the cathode comprises an active material selected from the group comprising ferrate, iron oxide, cuprous oxide, iodate, cupric oxide, mercuric oxide, cobaltic oxide, manganese oxide, lead dioxide, silver oxide, oxygen, nickel oxyhydroxide, nickel dioxide, silver peroxide, permanganate, bromate, silver vanadium, carbon monofluoride, iron disulfide, iodine, vanadium oxide, copper sulfide, sulfur or carbon and combinations thereof.

6. The battery of claim 1, wherein the anode comprises an active material selected from the group comprising lithium, magnesium, aluminum, zinc, chromium, iron, nickel, tin, lead, hydrogen, copper, silver, palladium, mercury, platinum or gold, and combinations thereof.

7. The battery of claim 6, wherein said active material is alloyed.

8. The battery of claim 1, wherein the cathode comprises manganese dioxide, and wherein said anode comprises zinc.

9. The battery of claim 1, wherein at least one of the anode and cathode comprises particles of active material and wherein the solid, ionically conductive polymer material encapsulates at least one particle of the active material.

10. The battery of claim 1, wherein the cathode comprises an active material selected from the group of manganese dioxide and oxygen and combinations thereof, and wherein the cathode has a specific capacity greater than 400 mAh/g.

11. The battery of claim 4, wherein the base polymer is oxidatively doped in the presence of an ion source.

12. The battery of claim 4, wherein the ion source is a compound including at least one hydroxyl group or convertible to a compound containing at least one hydroxyl group.

13. The battery of claim 4 wherein the ion source is selected from the group consisting of a Li₂O, Na₂O, MgO, CaO, ZnO, LiOH, KOH, NaOH, CaCl₂, AlCl₃, MgCl₂, LiTFSI(lithium bis-trifluoromethanesulfonimide), LiBOB (Lithium bis(oxalate)borate) or a mixture of the preceding two components.

14. The battery of claim 4 wherein the base polymer is selected from the group comprising a liquid crystal polymer, a polyether ether ketone (PEEK), and a polyphenylene sulphide (PPS), or a semicrystalline polymer with a crystallinity index of greater than 30 %, and combinations thereof.

15. The battery of claim 4 wherein the electron acceptor is selected from the group comprising 2,3, dicloro-5,6-dicyano-1,4-benzoquinone, TCNE, sulfur trioxide or chloranil and combinations thereof.

Patentansprüche

1. Eine Batterie umfassend
eine Anode;
eine Kathode; und

wobei mindestens einer von der Anode und der Kathode ein festes, ionisch leitendes, elektrisch nicht leitendes Polymermaterial mit einer Ionenleitfähigkeit von mehr als 1×10^{-4} S/cm bei Raumtemperatur und mit einem Kristallinitätsindex von wenigstens 30 % umfasst,

wobei das Polymermaterial ein Basispolymer, ein Dotiermittel und zumindest eine Verbindung einschließt, die eine Ionenquelle enthält, und

wobei die Ionenleitfähigkeit gemäß der Beschreibung gemessen wird.

2. Batterie nach Anspruch 1, ferner umfassend einen Elektrolyten, wobei der Elektrolyt das feste, ionisch leitende Polymermaterial umfasst.

3. Batterie nach Anspruch 1, wobei das feste, ionisch leitende Polymer eine Vielzahl an OH⁻-Ionen leiten kann und eine OH⁻-Diffusionsfähigkeit von mehr als 10^{-11} cm²/s bei einer Temperatur in einem Bereich von 20 °C bis 26 °C aufweist.

4. Batterie nach Anspruch 1, wobei das feste, ionisch leitende Polymermaterial aus einem Reaktantenprodukt gebildet wird, das ein Basispolymer, einen Elektronenakzeptor und eine Verbindung umfasst, die eine Ionenquelle einschließt.

5. Batterie nach Anspruch 1, wobei die Kathode ein aktives Material umfasst, das aus der Gruppe ausgewählt ist, die Ferrat, Eisenoxid, kupferartiges Oxid, Iodat, Kupferoxid, Quecksilberoxid, Kobaltoxid, Manganoxid, Bleidioxid, Silberoxid, Sauerstoff, Nickeloxyhydroxid, Nickeldioxid, Silberperoxid, Permanganat, Bromat, Silbervanadium, Graphitfluorid, Eisendisulfid, Iod, Vanadiumoxid, Kupfersulfid, Schwefel oder Kohlenstoff und Kombinationen dieser umfasst.

6. Batterie nach Anspruch 1, wobei die Anode ein aktives Material umfasst, das aus der Gruppe ausgewählt ist, die Lithium, Magnesium, Aluminium, Zink, Chrom, Eisen, Nickel, Zinn, Blei, Wasserstoff, Kupfer, Silber, Palladium, Quecksilber, Platin oder Gold und Kombinationen dieser umfasst.

7. Batterie nach Anspruch 6, wobei das aktive Material legiert ist.

8. Batterie nach Anspruch 1, wobei die Kathode Mangandioxid umfasst, und wobei die Anode Zink umfasst.

9. Batterie nach Anspruch 1, wobei mindestens einer von der Anode und Kathode Partikel aus aktivem Material umfasst und wobei das feste, ionisch leitende Polymermaterial mindestens einen Partikel aus dem aktiven Material einkapselt.

10. Batterie nach Anspruch 1, wobei die Kathode ein aktives Material umfasst, das aus der Gruppe ausgewählt ist, die Mangandioxid und Sauerstoff und Kombinationen dieser umfasst, und wobei die Kathode eine spezifische Kapazität von mehr als 400 mAh/g aufweist.

11. Batterie nach Anspruch 4, wobei das Basispolymer in Gegenwart einer Ionenquelle oxidativ dotiert wird.

12. Batterie nach Anspruch 4, wobei die Ionenquelle eine Verbindung ist, die mindestens eine Hydroxylgruppe enthält oder in eine Verbindung umgewandelt werden kann, die mindestens eine Hydroxylgruppe enthält.

13. Batterie nach Anspruch 4, wobei die Ionenquelle aus der Gruppe ausgewählt ist, die aus einem Li₂O, Na₂O, MgO, CaO, ZnO, LiOH, KOH, NaOH, CaCl₂, AlCl₃, MgCl₂, LiTFSI (Lithiumbistrifluormethansulfonimid), LiBOB (Lithiumbis(oxalat)borat) oder einer Mischung der voranstehenden zwei Komponenten besteht.

14. Batterie nach Anspruch 4, wobei das Basispolymer aus der Gruppe ausgewählt ist, die ein Flüssigkristallpolymer, ein Polyetheretherketon (PEEK) und ein Polyphenylsulfid (PPS) oder ein teilkristallines Polymer mit einem Kristallinitätsindex von mehr als 30 %, und Kombinationen dieser umfasst.

15. Batterie nach Anspruch 4, wobei der Elektronenakzeptor aus der Gruppe ausgewählt ist, die 2,3-Dichlor-5,6-dicyano-1,4-benzochinon, TCNE, Schwefeltetroxid oder Chloranil und Kombinationen dieser umfasst.

Revendications

1. Batterie comprenant

une anode ;

une cathode ; et

dans laquelle au moins l'une parmi l'anode et la cathode comprend un matériau polymère solide électriquement non conducteur à conduction ionique présentant une conductivité ionique supérieure à 1×10^{-4} S/cm à température ambiante et présentant un indice de cristallinité d'au moins 30 %,

dans laquelle le matériau polymère comporte un polymère de base, un dopant et au moins un composé comportant une source d'ions, et

dans laquelle la conductivité ionique est mesurée selon la description.

2. Batterie selon la revendication 1, comprenant en outre un électrolyte, dans laquelle l'électrolyte comprend le matériau polymère solide à conduction ionique.

3. Batterie selon la revendication 1, dans laquelle le polymère solide à conduction ionique peut conduire une pluralité d'ions OH⁻ et présente une diffusivité de OH⁻ supérieure à 10^{-11} cm²/sec à une température située dans un intervalle allant de 20 °C à 26 °C.

4. Batterie selon la revendication 1, dans laquelle le matériau polymère solide à conduction ionique est formé à partir d'un produit réactif comprenant un polymère de base, un accepteur d'électrons, et un composé comportant une source d'ions.

5. Batterie selon la revendication 1, dans laquelle la cathode comprend un matériau actif sélectionné dans le groupe comprenant un ferrate, un oxyde de fer, un oxyde cuivreux, un iodate, un oxyde cuivrique, un oxyde mercurique, un oxyde cobaltique, un oxyde de manganèse, un dioxyde de plomb, un oxyde d'argent, l'oxygène, un oxyhydroxyde de nickel, un dioxyde de nickel, un peroxyde d'argent, un permanganate, un bromate, un vanadium d'argent, un monofluorure de carbone, un disulfure de fer, l'iode, un oxyde de vanadium, un sulfure de cuivre, le soufre ou le carbone et des combinaisons de ceux-ci.

6. Batterie selon la revendication 1, dans laquelle l'anode comprend un matériau actif sélectionné dans le groupe comprenant le lithium, le magnésium, l'aluminium, le zinc, le chrome, le fer, le nickel, l'étain, le plomb, l'hydrogène, le cuivre, l'argent, le palladium, le mercure, le platine ou l'or, et des combinaisons de ceux-ci.

7. Batterie selon la revendication 6, dans laquelle ledit matériau actif est allié.

8. Batterie selon la revendication 1, dans laquelle la cathode comprend du dioxyde de manganèse, et dans laquelle ladite anode comprend du zinc.

9. Batterie selon la revendication 1, dans laquelle au moins l'une parmi l'anode et la cathode comprend des particules de matériau actif et dans laquelle le matériau polymère solide à conduction ionique encapsule au moins une particule du matériau actif.

10. Batterie selon la revendication 1, dans laquelle la cathode comprend un matériau actif sélectionné dans le groupe du dioxyde de manganèse et de l'oxygène et des combinaisons de ceux-ci, et dans laquelle la cathode présente une capacité spécifique supérieure à 400 mAh/g.

11. Batterie selon la revendication 4, dans laquelle le polymère de base est dopé par oxydation en présence d'une source d'ions.

12. Batterie selon la revendication 4, dans laquelle la source d'ions est un composé comportant au moins un groupe hydroxyle ou convertible en un composé contenant au moins un groupe hydroxyle.

13. Batterie selon la revendication 4, dans laquelle la source d'ions est sélectionnée dans le groupe consistant en Li₂O, Na₂O, MgO, CaO, ZnO, LiOH, KOH, NaOH, CaCl₂, AlCl₃, MgCl₂, LiTFSI (bis-trifluorométhanesulfonimide de lithium), LiBOB (bis(oxalate)borate de lithium) ou un mélange des deux composants précédents.

14. Batterie selon la revendication 4, dans laquelle le polymère de base est sélectionné dans le groupe comprenant un polymère de cristaux liquides, une polyétheréthercétone (PEEK), et un polysulfure de phényle (PPS), ou un polymère semi-cristallin ayant un indice de cristallinité supérieur à 30 %, et des combinaisons de ceux-ci.

- 15.** Batterie selon la revendication 4, dans laquelle l'accepteur d'électrons est sélectionné dans le groupe comprenant la 2,3-dichloro-5,6-dicyano-1,4-benzoquinone, le TCNE, le trioxyde de soufre ou le chloranile et des combinaisons de ceux-ci.

5

10

15

20

25

30




35

40

45

50

55





Dynamic Scanning Calorimetry Curve of Semicrystalline Polymer

FIG. 2

Compounds	A	B	C	D
Base Resin				
Phillips-Chevron Ryton QC160N PPS	80 wt%	50 wt%	67 wt%	50 wt%
Ion Source Fillers				
Zinc Oxide, 20nm spheres	20 wt%	50 wt%		
Lithium Oxide, milled to <2 micron			33 wt%	50 wt%


FIG. 3

Table 1
Exemplary formulations investigated.






They can fold, and they can stack.
A stack of polymer chains folded
back on themselves like this is
called a lamella.

Amorphous and Crystalline Polymers


FIG. 4**FIG. 5**

2,3-dicyano-5,6-dichlorodicyanoquinone

**FIG. 6****FIG. 7**

**FIG. 8**

Ionic Film Passes UL-VO Flammability Test




Flame Applied to Ionic Film


Flame Self Extinguished in 2 sec.

UL94 Flammability test

FIG. 9




Cyclic Voltammetry of Ionically Conductive Polymer versus Lithium Metal

FIG. 10


Ionically conductive electrolyte and electrode components

FIG. 11





Solid State Battery-Electrode and electrolyte bonded together

FIG. 12




Flexible Form of Battery

FIG. 13




Battery Manufacture

FIG. 14



Film Thickness as low
as 0.0003" have been
achieved



Extrusion Process

FIG. 15




FIG. 16










FIG. 17



**FIG. 20****FIG. 21**

**FIG. 22****FIG. 23**




FIG. 24

02-26-split5-ZnZn sl-E465-C409-20C_C05.mpr

.... Bvevs. time














FIG. 25



**FIG. 26****FIG. 27**

**FIG. 28****FIG. 29**

**FIG. 30****FIG. 31**

**FIG. 32****FIG. 33**

**FIG. 34****FIG. 35**

**FIG. 36****FIG. 37**

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 7972726 B [0004] [0060] [0133]
- US 5156934 A [0004] [0062]
- US 5660953 A [0004] [0062]
- US 20130065128 A [0007]
- US 13861170 B [0010]
- US 20140045059 A [0156]

Non-patent literature cited in the description

- Y. F. YAO ; N. GUPTA ; H.S. WROBLOWA. *J. Electroanal. Chem.*, 1987, vol. 223, 107 [0004] [0062]
- H.S. WROBLOWA ; N. GUPTA. *J. Electroanal. Chem.*, 1987, vol. 238, 93 [0004] [0062]
- D.Y. QU ; L. BAI ; C.G. CASTLEDINE ; B.E. CONWAY. *J. Electroanal. Chem.*, 1994, vol. 365, 247 [0004] [0062]
- M. MINAKSHI ; P.SINGH. *J. Solid State Electrochem*, 2012, vol. 16, 1487 [0005] [0064]
- JEDDI, K. J. *Power Sources*, 2014, vol. 245, 656-662 [0007]
- LI, L. *J. Power Sources*, 2014, vol. 252, 107-112 [0007]
- ZHENG, G. *Nano Lett.*, 2013, vol. 13, 1265-1270 [0007]
- MA, G. *J. Power Sources*, 2014, vol. 254, 353-359 [0007]
- JI, X. ; LEE, K.T. ; NAZAR, L.F. *Nature Materials*, 2009, vol. 8, 500-506 [0155]