



(11) **EP 3 083 178 B9**

(12) **CORRECTED EUROPEAN PATENT SPECIFICATION**

(15) Correction information:  
**Corrected version no 1 (W1 B1)**  
**Corrections, see**  
**Description Paragraph(s) 19**  
**Claims EN 7**

(51) International Patent Classification (IPC):  
**B29C 35/02** <sup>(2006.01)</sup> **B29D 11/00** <sup>(2006.01)</sup>  
**B29C 33/42** <sup>(2006.01)</sup> **B29C 37/00** <sup>(2006.01)</sup>  
**B29C 33/38** <sup>(2006.01)</sup> **B29C 35/08** <sup>(2006.01)</sup>  
**B29K 101/10** <sup>(2006.01)</sup> **B29K 101/12** <sup>(2006.01)</sup>

(48) Corrigendum issued on:  
**26.10.2022 Bulletin 2022/43**

(52) Cooperative Patent Classification (CPC):  
**B29D 11/00557; B29C 33/38; B29C 33/42;**  
**B29C 35/02; B29C 35/0805; B29C 37/0053;**  
**B29D 11/00086; B29C 35/0222; B29C 35/0888;**  
**B29C 37/005; B29C 2035/0827; B29C 2035/0833;**  
**B29C 2791/004; B29K 2101/10; B29K 2101/12**

(45) Date of publication and mention  
of the grant of the patent:  
**03.08.2022 Bulletin 2022/31**

(21) Application number: **14824693.7**

(86) International application number:  
**PCT/US2014/070751**

(22) Date of filing: **17.12.2014**

(87) International publication number:  
**WO 2015/095278 (25.06.2015 Gazette 2015/25)**

(54) **METHODS FOR PREPARING CUSTOMIZED POLYMERIC ARTICLES**

VERFAHREN ZUR HERSTELLUNG VON PERSONALISIERTEN POLYMERARTIKELN

PROCÉDÉS POUR LA PRÉPARATION D'ARTICLES POLYMÈRES PERSONNALISÉS

(84) Designated Contracting States:  
**AL AT BE BG CH CY CZ DE DK EE ES FI FR GB**  
**GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO**  
**PL PT RO RS SE SI SK SM TR**

- **KRYGER, Matthew, J.**  
**Maplewood, MN 55119 (US)**
- **MENTA, Federico**  
**I-43121 Parma (IT)**
- **CROSS, Keith, M.**  
**Holden, Massachusetts 01520 (US)**
- **LUSHER, David, L.**  
**Cheswick, Pennsylvania 15024 (US)**

(30) Priority: **17.12.2013 US 201361917065 P**  
**16.12.2014 US 201414571691**

(43) Date of publication of application:  
**26.10.2016 Bulletin 2016/43**

(74) Representative: **f & e patent**  
**Braunsberger Feld 29**  
**51429 Bergisch Gladbach (DE)**

(73) Proprietor: **PPG Industries Ohio, Inc.**  
**Cleveland, OH 44111 (US)**

(72) Inventors:  
• **HICKENBOTH, Charles, R.**  
**Cranberry Township, Pennsylvania 16066 (US)**

(56) References cited:  
**US-A1- 2005 056 953 US-A1- 2012 225 252**  
**US-A1- 2013 122 129 US-B1- 6 467 904**

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

## Description

### FIELD OF THE INVENTION

**[0001]** The present invention is directed to a method of preparing a customized polymeric article through the use of magnetic fluids.

### BACKGROUND OF THE INVENTION

**[0002]** The molded polymeric article market is similar to several other markets in that it is trending towards customization and/or personalization. Moreover, there is a need to reduce production costs and provide molds that can be easily recycled or reused.

**[0003]** For example, the optical market is trending toward personalization of lenses. For example, digital surfacing technology allows for the potential to customize lenses to each individual's anatomical and optometric parameters, as well as other highly individualized measurements. It also allows lenses to take into account frame positioning; for example a lens shape can be created to allow for non-standard mounting (see <https://www.bb-gr.com/en-us/ensavoirplus/optique/Pages/LeSurfa%C3%A7ageDigital.aspx>). However, there are several disadvantages to creating lenses via digital surfacing. For example, since the process is based on the removal of lens material from a lens blank which is formed in the process, the process is wasteful and inefficient. It has been calculated that the digital surfacing of a typical lens from a blank to finished lens results in 50% or more of the lens material being cut away. The cut away material cannot be reused or recycled and, therefore, results in large amounts of landfill waste. It is, therefore, desirable to produce new methods of producing highly customized lenses which do not result in large amounts of waste.

**[0004]** One example of producing highly customized polymeric articles that meet the above requirements is to customize the mold surface such that a highly customized, finished article is obtained directly from the mold. However, since polished glass molds are expensive, it would be prohibitively expensive to make molds for every possible customized configuration in a traditional manner.

**[0005]** While it has been reported that polymeric articles, e.g., lenses, have been prepared using 3-dimensional printing processes, however, additive manufacturing processes are limited in the selection of polymeric resins that might be used.

**[0006]** US 2012/0225252 A1 discloses deformable ferrofluid layer devices for optical modulation and micro-molding.

**[0007]** The method of the present invention offers the ability to produce polymeric articles having specific customization features which are made using commonly known and industry acceptable polymeric materials. Further, it has now been found that the alternative approach of using a polymeric article casting process in which one

or both mold surfaces is highly customizable and reusable allows for the production of highly customized articles, e.g., lenses and other transparencies, with high optical surface quality, while the molds can be easily recycled or reused.

### SUMMARY OF THE INVENTION

**[0008]** The present invention is directed to a method for preparing a customized polymeric article comprising:

(a) providing two mold half-sections, each half-section having an outer surface and an inner surface;

(b) assembling the two mold half-sections to form a mold assembly such that the inner surfaces of the two mold half-sections oppose one another, thereby defining a cavity therebetween;

(c) prior to or subsequent to (b), applying one or more magnetic fluids to the inner surface of at least one mold half-section;

(d) inserting a fluid polymeric material into the cavity formed in (b);

(e) prior to or subsequent to (d), controllably applying a magnetic field to the one or more magnetic fluids to form a customized reversible surface in accordance with a predetermined specific surface topography;

(f) subjecting the mold assembly containing the fluid polymeric material to conditions sufficient to effect at least partial polymerization or hardening of the fluid polymeric material; and

(g) separating the two mold half-sections to provide a polymeric article having at least one surface corresponding to the predetermined specific surface topography of the magnetic fluid.

**[0009]** A polymeric article prepared by the above-described method also is provided.

### DETAILED DESCRIPTION OF THE INVENTION

**[0010]** As previously mentioned, the present invention is directed to a method for preparing a customized polymeric article comprising:

(a) providing two mold half-sections, each half-section having an outer surface and an inner surface;

(b) assembling the two mold half-sections to form a mold assembly such that the inner surfaces of the two mold half-sections oppose one another, thereby defining a cavity therebetween;

(c) prior to or subsequent to (b) applying one or more magnetic fluids to the inner surface of at least one mold half-section;

(d) inserting a fluid polymeric material into the cavity formed in (b);

(e) prior to or subsequent to (d), controllably applying a magnetic field to the one or more magnetic fluids to form a customized reversible surface in accordance with a predetermined specific surface topography (or geometry);

(f) subjecting the mold assembly containing the fluid polymeric material to conditions sufficient to effect at least partial polymerization or hardening of the fluid polymeric material; and

(g) separating the two mold half-sections to provide a polymeric article having at least one surface corresponding to the predetermined specific surface topography of the magnetic fluid.

**[0011]** The one or more magnetic fluids can be selected from any magnetically susceptible fluids known in the art. In a particular embodiment, the one or more magnetic fluids can be selected from the group consisting of ferrofluids and magnetorheological ("MR") fluids. Ferrofluids are stable colloidal suspensions of nanoscale ferromagnetic or ferrimagnetic particles suspended in a carrier fluid which typically contains a surfactant which prevents particle agglomeration even when a strong magnetic field is applied to the ferrofluid. The surfactant must be matched to the carrier type and must overcome the attractive van der Waals and magnetic forces between the particles. Generally, a typical ferrofluid can contain by volume 5% magnetic solid, 10% surfactant, and 85% carrier fluid. Non-limiting examples of surfactants can include fatty acids such as oleic acid, linoleic, stearic or isostearic acid, hydroxides, such as tetramethylammonium hydroxide, citric acid or salts thereof, amines, alcohols, and/or soy lecithin. Choice of surfactant is dependent on the end use of the ferrofluids employed and whether the carrier fluid is an aqueous or an organic solvent. Suitable polar carrier fluids can include, for example, water or ethylene glycol. Oil based carrier fluids can include, for example, hydrocarbons such as poly(alpha olefins), polyol esters, silicones, perhalogenated (e.g., perfluorinated) oils and solvents, as well as halosilanes. In one embodiment, the ferrofluid is a perhalogenated ferrofluid. There are generally two major steps in preparing a ferrofluid. The first is to make the magnetic nanoparticles (approximately 100 Angstroms diameter, about 10 nm) that will be dispersed in the colloidal suspension. The magnetic particles in ferrofluids useful in the method of the present invention are generally magnetite ( $\text{Fe}_3\text{O}_4$ ), although other magnetic particles such as maghemite and hematite may be employed as well as other magnetic

particles, such as cobalt and nickel-containing particles. Further contemplated are alloys and other magnetic elements. In the second step of preparing ferrofluids, the magnetic particles are dispersed in a carrier liquid by utilizing a suitable surfactant to create a colloidal suspension as discussed above.

**[0012]** The difference between ferrofluids and MR fluids is the size of the particles. As mentioned above, the particles in a ferrofluid primarily consist of nanoparticles which are suspended by Brownian motion and, generally, will not settle under normal conditions. By contrast, MR fluid particles primarily comprise micrometer-scale particles which may be too heavy for Brownian motion to maintain suspension and, thus, may settle over time. Also, MR fluids can gel or solidify in the presence of a magnetic field. MR fluids likewise comprise a carrier fluid and, optionally, a surfactant similar to those described above in reference to ferrofluids.

**[0013]** In the method of the present invention, the magnetic fluid typically is a ferrofluid in an aqueous form. Suitable aqueous ferrofluids can include, for example, EMG 703 and EMG 304 both commercially available from Ferrotec (USA) Corporation.

**[0014]** In the case of the customizable mold surface used in the present invention, both the carrier fluid and the surfactant should be selected so as not to adversely affect the polymerization or, in the case of thermoplastic polymeric materials, the hardening of the fluid polymeric materials employed or ultimate properties of the polymeric article formed by the method.

**[0015]** The magnetic fluid is immiscible with the fluid polymeric material. That is, the magnetic fluid and the fluid polymeric material are incapable of forming a homogeneous mixture at any ratio of the two materials. This ensures that there is no intermixing of the two materials at the interface between the magnetic fluid and the fluid polymeric material.

**[0016]** The magnetic field can be provided either by use of a fixed magnet or by application of an electromagnetic field. The magnetic field may be removed prior to or subsequent to separating the two mold half-sections in (e) as mentioned above. The magnetic field applied can be controlled in accordance to digitized specific topographical/geometrical and shape information such that the magnetic fluids form the customized inner mold surface. Once the polymeric article has been demolded, the magnetic fluid can be recycled or reused in a subsequent casting process.

**[0017]** The method of the present invention may be used to prepare any of a myriad of molded polymeric articles including, for example, polymeric sheets, polymeric transparencies, such as windows, display screens, face shields, lenses, and aerospace transparencies.

**[0018]** Of course, the mold half-sections can be configured in any shape or geometry dependent upon the shape or geometry of the polymeric article to be obtained. Further, the two mold half-sections can comprise the same or different materials. In one embodiment, partic-

ularly suitable for the preparation of polymeric lenses, at least one of the mold half-sections is glass. It is contemplated that one of the mold half-sections can be a preformed lens while the inner surface of the opposing mold half-section receives application of the magnetic fluid. Additionally, the mold half-section which receives application of the magnetic fluid can possess a "cuplike" conformation; and the magnetic fluid is applied within the "cup" and subjected to the magnetic field to form the predetermined specific surface topography.

**[0019]** In a particular embodiment of the invention, the customized polymeric article is a lens, such as a plano (non-prescription) lens and an ophthalmic (prescription lens). In this case, the predetermined specific surface topography can constitute a predetermined optical power or shape specific to an individual lens wearer. The lens can have an outer surface having a topography conforming to an unmodified front mold half-section, and a back surface having a topography conforming to the predetermined specific surface topography of the magnetic fluid. The lenses produced by the method of the present invention can comprise plano lenses, single vision lenses, multifocal lenses, or gradient power lenses.

**[0020]** The fluid polymeric material can include any of the polymeric material compositions known in the plastics molding art. For example, non-limiting examples of the polymeric material compositions can include photopolymerizable materials (e.g., (meth)acrylate-based materials), thermosetting materials (e.g., polyurethanes, allyl functional carbonates, and epoxides), or thermoplastic materials (e.g., polycarbonates and poly(cyclo)olefins). The fluid polymeric material can be selected from the group consisting of polycarbonate, bisallyl carbonate, polyurethane, polyureaurethane, polythiourea urethane, epoxides, thioepoxides, cycloolefin (co)polymers, and (meth)acrylate-based materials. For purposes of this invention, the term "(meth)acrylate" is intended to include both acrylate and methacrylate materials. The type of lens material utilized in the methods of the present invention is not critical to the invention.

**[0021]** Once the fluid polymeric material is inserted into the cavity between the two mold half-sections, the mold assembly containing the fluid polymeric material is subjected to conditions sufficient to effect at least partial polymerization (i.e., in the case of the photo-polymerizable or thermosetting polymeric materials) or hardening (i.e., in the case of thermoplastic polymeric materials) of the fluid polymeric material. The two mold half-sections are removed, thereby providing a polymeric article having at least one surface corresponding to the predetermined specific surface topography of the magnetic fluid.

**[0022]** It should be noted that, where the polymeric article is a lens, the predetermined surface topography can be adjusted to account for monomer deformation due to shrinkage and/or cure stress during curing/hardening in order to provide a predetermined optical power or shape specific to an individual wearer.

**[0023]** It is contemplated that the polymerization or

hardening step can be carried out to the extent that the article thus formed is only partially polymerized/hardened (but polymerized/hardened to the extent that the topography and shape is maintained), and the remainder of the polymerization/hardening can be carried out after the article is removed from the mold.

**[0024]** Conditions suitable to effect polymerization or hardening of the fluid polymeric material can be accomplished by a variety of methods depending, of course, on the polymeric material compositions employed. For example, polymerization can be effectuated by subjecting the filled mold assembly to one or more of thermal conditions and actinic radiation, for a time sufficient to complete polymerization; and hardening of a thermoplastic material can be accomplished by subjecting the filled mold assembly to thermal conditions for a time sufficient to at least partially harden the thermoplastic polymeric material.

**[0025]** By way of example, in the method of the present invention, the one mold half-section can be a preformed front mold section which is attached to a back mold half-section, where the inner surface of the back mold half-section has been "customized" using the magnetic fluid in accordance with the method of the present invention. The back mold half-section could include a port for insertion or injection of the fluid polymeric material used to form the customized polymeric article. The two mold half-sections can be joined using any sealing methods known in the art, including gaskets and sealants. As previously mentioned, the magnetic field can be controllably applied to the magnetic fluid prior to or subsequent to insertion of the fluid polymeric material into the cavity between the two mold half-sections.

**[0026]** Further, the size and shape of the mold could be set in such a way that no post-processing (edging) would be necessary prior to inserting the finished product into eyeglass frames for the end user.

## Claims

1. A method for preparing a customized polymeric article comprising:

- (a) providing two mold half-sections, each half-section having an outer surface and an inner surface;
- (b) assembling the two mold half-sections to form a mold assembly such that the inner surfaces of the two mold half-sections oppose one another, thereby defining a cavity therebetween;
- (c) prior to or subsequent to (b) applying one or more magnetic fluids to the inner surface of at least one mold half-section;
- (d) inserting a fluid polymeric material into the cavity formed in (b);
- (e) prior to or subsequent to (d), controllably applying a magnetic field to the one or more mag-

netic fluids to form a customized reversible surface in accordance with a predetermined specific surface topography;

(f) subjecting the mold assembly containing the fluid polymeric material to conditions sufficient to effect at least partial polymerization or hardening of the fluid polymeric material; and  
(g) separating the two mold half-sections to provide a polymeric article having at least one surface corresponding to the predetermined specific surface topography of the magnetic fluid.

2. The method of claim 1, wherein the magnetic field is removed prior to or subsequent to separating the two mold half-sections in (e).

3. The method of claim 1, wherein the magnetic fluid material is an aqueous ferrofluid or is a perhalogenated ferrofluid.

4. The method of claim 1, wherein the magnetic fluid comprises a magnetorheological fluid or comprises cobalt-containing particles, nickel-containing particles, and/or alloys.

5. The method of claim 1, wherein the magnetic fluid material is immiscible with the fluid polymeric material when a magnetic field is applied to the mold assembly.

6. The method of claim 1, wherein at least one of the two mold half-sections is comprised of glass.

7. The method of claim 1, wherein the customized polymeric article is a lens, wherein the lens comprises preferably a plano lens, a single vision lens, a multifocal lens, or a gradient power lens.

8. The method of claim 7, wherein the predetermined specific surface topography constitutes a predetermined optical power or shape specific to an individual lens wearer.

9. The method of claim 7, wherein the lens has an outer surface having a topography conforming to an unmodified front mold half-section, and a back surface having a topography conforming to the predetermined specific surface topography of the magnetic fluid.

10. The method of claim 1, wherein the fluid polymeric material is selected from the group consisting of photopolymerizable materials, thermosetting materials, and thermoplastic materials, wherein preferably:

(A) the fluid polymeric material comprises a thermosetting polymeric material which is partially polymerized in (f), and the method further comprises

(h) subjecting the partially polymerized polymeric article to conditions sufficient to complete polymerization of the partially polymerized polymeric article; or

(B) the fluid polymeric material comprises a thermoplastic polymeric material which is partially hardened in (f), and the method further comprises (h) subjecting the partially hardened polymeric article to conditions sufficient to complete hardening of the partially hardened polymeric article.

11. The method of claim 1, wherein the fluid polymeric material is selected from the group consisting of polycarbonate, bisallyl carbonate, polyurethane, polyurethane, polythioureaurethane, epoxides, thioepoxides, cycloolefin (co)polymers and (meth)acrylate-based materials.

12. The method of claim 1, wherein the one or more magnetic fluids is/are applied to the inner surface of at least one mold half-section prior to or subsequent to (b).

13. The method of claim 1, wherein the magnetic field is controllably applied to the one or more magnetic fluids to form a customized reversible surface in accordance with a predetermined specific surface topography prior to or subsequent to (d).

14. The method of claim 1, wherein the polymeric article is in the form of a polymeric sheet.

## Patentansprüche

1. Ein Verfahren zum Herstellen eines maßgefertigten Kunststoffgegenstands umfassend:

(a) Bereitstellen zweier Formhälften, jede Hälfte aufweisend eine äußere Oberfläche und eine innere Oberfläche,

(b) Montieren der beiden Formhälften, um eine Formbaugruppe zu bilden, so dass die inneren Oberflächen der beiden Formhälften einander gegenüberliegen, dadurch dazwischen einen Hohlraum definierend,

(c) vor oder nach (b) Anbringen eines oder mehrerer magnetischer Fluide auf die innere Oberfläche von wenigstens einer Formhälfte,

(d) Einbringen eines fluiden Polymermaterials in den Hohlraum, der in (b) gebildet wird,

(e) vor oder nach (d) kontrolliertes Anlegen eines magnetischen Feldes an das eine oder die mehreren magnetischen Fluid(e), um eine angepasste reversible Oberfläche in Übereinstimmung mit einer vorgegebenen spezifischen Oberflächentopographie zu bilden,

- (f) Aussetzen der Formbaugruppe enthaltend das fluide Polymermaterial gegenüber Bedingungen, die ausreichen, wenigstens eine teilweise Polymerisation oder Härtung des fluiden Polymermaterials zu bewirken, und  
5  
(g) Trennen der zwei Formhälften, um einen Kunststoffgegenstand, der wenigstens eine Oberfläche entsprechend der vorgegebenen spezifischen Oberflächentopographie des magnetischen Fluids aufweist, bereitzustellen.  
10
2. Das Verfahren des Anspruchs 1, wobei das magnetische Feld vor oder nach Trennen der zwei Formhälften in (e) entfernt wird.  
15
3. Das Verfahren des Anspruchs 1, wobei das magnetische Fluid ein wässriges Ferrofluid ist oder ein perhalogeniertes Ferrofluid ist.
4. Das Verfahren des Anspruchs 1, wobei das magnetische Fluid ein magnetorheologisches Fluid umfasst oder kobalthaltige Partikel, nickelhaltige Partikel und/oder Legierungen umfasst.  
20
5. Das Verfahren des Anspruchs 1, wobei das Material des magnetischen Fluids sich nicht mit dem fluiden Polymermaterial vermischt, wenn ein magnetisches Feld auf die Formbaugruppe angewendet wird.  
25
6. Das Verfahren des Anspruchs 1, wobei wenigstens eine der zwei Formhälften Glas umfasst.  
30
7. Das Verfahren des Anspruchs 1, wobei der maßgefertigte Kunststoffgegenstand eine Linse ist, wobei die Linse vorzugsweise eine plane Linse, eine Einstärkenlinse, eine multifokale Linse oder eine Linse mit Stärkegradienten umfasst.  
35
8. Das Verfahren des Anspruchs 7, wobei die vorgegebene spezifische Oberflächentopographie eine vorgegebene optische Stärke oder Form spezifisch für einen individuellen Linsenträger darstellt.  
40
9. Das Verfahren des Anspruchs 7, wobei die Linse eine äußere Oberfläche aufweisend eine Topographie, die sich an eine unmodifizierte vordere Formhälfte anpasst, und eine hintere Oberfläche aufweisend eine Topographie, die sich an die vorgegebene spezifische Oberflächentopographie des magnetischen Fluids anpasst, aufweist.  
45  
50
10. Das Verfahren des Anspruchs 1, wobei das fluide Polymermaterial aus der Gruppe bestehend aus photopolymerisierbaren Materialien, wärmehärtenden Materialien und thermoplastischen Materialien ausgewählt ist, wobei vorzugsweise:  
55
- (A) das fluide Polymermaterial ein wärmehärtendes Polymermaterial, welches in (f) teilweise polymerisiert wird, umfasst, und das Verfahren des Weiteren (h) ein Aussetzen des teilweise polymerisierten Kunststoffgegenstands gegenüber Bedingungen, die zur vollständigen Polymerisation des teilweise polymerisierten Kunststoffgegenstands ausreichen, umfasst, oder  
(B) das fluide Polymermaterial ein thermoplastisches Polymermaterial, welches teilweise in (f) gehärtet wird, umfasst, und das Verfahren des Weiteren (h) ein Aussetzen des teilweise gehärteten Kunststoffgegenstands gegenüber Bedingungen, die zum vollständigen Härten des teilweise gehärteten Kunststoffgegenstands ausreichen, umfasst.
11. Das Verfahren des Anspruchs 1, wobei das fluide Polymermaterial aus der Gruppe bestehend aus Polycarbonat, Bisallylcarbonat, Polyurethan, Polyharnstoffurethan, Polythioharnstoffurethan, Epoxiden, Thioepoxiden, Cycloolefin(co)polymeren und (meth)acrylatbasierten Materialien ausgewählt ist.
12. Das Verfahren des Anspruchs 1, wobei das eine oder die mehreren magnetischen Fluid(e) vor oder nach (b) auf die innere Oberfläche von wenigstens einer Formhälfte aufgebracht werden.
13. Das Verfahren des Anspruchs 1, wobei das magnetische Feld vor oder nach (d) kontrolliert an das ein oder die mehreren magnetischen Fluid(e) angelegt wird, um eine angepasste reversible Oberfläche mit einer vorgegebenen spezifischen Oberflächentopographie zu bilden.
14. Das Verfahren des Anspruchs 1, wobei der Kunststoffgegenstand in der Form einer Kunststoffscheibe vorliegt.

## Revendications

1. Procédé de préparation d'un article personnalisé en polymère, comportant les étapes suivantes :
- a) prendre deux moitiés de moule, étant entendu que chaque moitié présente une surface externe et une surface interne,  
b) assembler ces deux moitiés de moule pour qu'elles forment un moule assemblé, de telle manière que les surfaces internes des deux moitiés de moule soient opposées l'une à l'autre et définissent ainsi entre elles une cavité,  
c) avant ou après l'étape (b), appliquer un ou plusieurs liquides magnétiques sur la surface interne d'au moins l'une des moitiés de moule,  
d) introduire un matériau polymère liquide dans la cavité formée au cours de l'étape (b),

- e) avant ou après l'étape (d), appliquer un champ magnétique, de manière régulable, au ou aux liquide(s) magnétique(s), pour former une surface réversible personnalisée en concordance avec une topographie de surface spécifique prédéterminée, 5
- f) mettre le moule assemblé contenant le matériau polymère liquide dans des conditions suffisantes pour que s'effectue une polymérisation ou un durcissement, au moins partiel(le), du matériau polymère liquide, 10
- g) et séparer les deux moitiés de moule, pour obtenir un article en polymère dont au moins l'une des surfaces correspond à la topographie de surface spécifique prédéterminée du liquide magnétique. 15
2. Procédé conforme à la revendication 1, dans lequel on met fin à l'application du champ magnétique avant ou après la séparation des deux moitiés de moule au cours de l'étape (e). 20
3. Procédé conforme à la revendication 1, dans lequel le matériau liquide magnétique est un ferroluide aqueux ou un ferroluide perhalogéné. 25
4. Procédé conforme à la revendication 1, dans lequel le liquide magnétique comprend un liquide magnéto-rhéologique ou comprend des particules contenant du cobalt, des particules contenant du nickel, et/ou des alliages. 30
5. Procédé conforme à la revendication 1, dans lequel le matériau liquide magnétique n'est pas miscible avec le matériau polymère liquide quand un champ magnétique est appliqué au moule assemblé. 35
6. Procédé conforme à la revendication 1, dans lequel au moins l'une des deux moitiés de moule est en un verre. 40
7. Procédé conforme à la revendication 1, dans lequel l'article personnalisé en polymère est un verre de lunettes, lequel verre englobe, de préférence, un verre non-correcteur, un verre simple, un verre multifocal, ou un verre à gradient de puissance. 45
8. Procédé conforme à la revendication 7, dans lequel la topographie de surface spécifique prédéterminée constitue une forme ou une puissance optique prédéterminée, spécifique d'un individu porteur de lunettes. 50
9. Procédé conforme à la revendication 7, dans lequel le verre présente une surface externe dotée d'une topographie conforme à la moitié de moule avant non-modifiée, et une surface arrière dotée d'une topographie conforme à la topographie de surface spécifique prédéterminée du liquide magnétique. 55
10. Procédé conforme à la revendication 1, dans lequel le matériau polymère liquide est choisi dans l'ensemble formé par les matériaux photo-polymérisables, les matériaux thermodurcissables et les matériaux thermoplastiques, étant entendu que, de préférence,
- A) le matériau polymère liquide comprend un matériau polymère thermodurcissable qui est partiellement polymérisé au cours de l'étape (f), et le procédé comporte en outre une étape (h) où l'on met l'article en polymère partiellement polymérisé dans des conditions suffisantes pour que s'achève la polymérisation au sein de l'article en polymère partiellement polymérisé,
- B) ou le matériau polymère liquide comprend un matériau polymère thermoplastique qui est partiellement durci au cours de l'étape (f), et le procédé comporte en outre une étape (h) où l'on met l'article en polymère partiellement durci dans des conditions suffisantes pour que s'achève le durcissement au sein de l'article en polymère partiellement durci.
11. Procédé conforme à la revendication 1, dans lequel le matériau polymère liquide est choisi dans l'ensemble constitué par les suivants : polycarbonate, poly(carbonate de bis-allyle), polyuréthane, poly(urée uréthane), poly(thiourée uréthane), polyépoxydes, polythio-époxydes, polymères et copolymères de cyclooléfine, et matériaux à base d'acrylate ou de méthacrylate
12. Procédé conforme à la revendication 1, dans lequel le ou les liquide(s) magnétique(s) est ou sont appliqué(s) sur la surface interne d'au moins l'une des moitiés de moule, avant ou après l'étape (b).
13. Procédé conforme à la revendication 1, dans lequel le champ magnétique est appliqué, de manière régulable, au ou aux liquide(s) magnétique(s) pour que soit formée une surface réversible personnalisée en concordance avec une topographie de surface spécifique prédéterminée, avant ou après l'étape (d).
14. Procédé conforme à la revendication 1, dans lequel l'article en polymère se présente sous la forme d'une feuille de polymère.

**REFERENCES CITED IN THE DESCRIPTION**

*This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.*

**Patent documents cited in the description**

- US 20120225252 A1 [0006]