



(11) **EP 3 279 371 A1**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:  
**07.02.2018 Bulletin 2018/06**

(51) Int Cl.:  
**C25D 5/56 (2006.01) H01Q 1/24 (2006.01)**

(21) Application number: **17173475.9**

(22) Date of filing: **30.05.2017**

(84) Designated Contracting States:  
**AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR**  
Designated Extension States:  
**BA ME**  
Designated Validation States:  
**MA MD**

(71) Applicant: **Guangdong Oppo Mobile Telecommunications Corp., Ltd. Dongguan, Guangdong 523860 (CN)**

(72) Inventor: **JIANG, Zhengnan Dongguan,, Guangdong 523860 (CN)**

(74) Representative: **advotec. Patent- und Rechtsanwälte Widenmayerstrasse 4 80538 München (DE)**

(30) Priority: **03.08.2016 CN 201610635464**  
**03.08.2016 CN 201620842045 U**

(54) **METALLIC SHELL, METHOD FOR MANUFACTURING THE SAME AND MOBILE TERMINAL HAVING THE SAME**

(57) A metallic shell (100), a method for manufacturing the metallic shell (100) and a mobile terminal including the metallic shell (100) are provided. The metallic shell (100) includes a body (1) and an insulator (3). The body (1) has a slot (2). The insulator (3) is formed in the slot (2) and includes an insulating material. The insulating material includes a plastic material, a first coating and a second coating. The first coating is configured to colour the plastic material to make the insulator (3) exhibit a same colour as that of the body (1). The second coating is configured to improve luster of the plastic material to make the insulator (3) exhibit a same metallic luster as that of the body (1).




Fig. 2

**EP 3 279 371 A1**

## Description

### FIELD

[0001] The present disclosure relates to mobile terminal technology fields, and more particularly to a metallic shell, a method for manufacturing the metallic shell and a mobile terminal having the metallic shell.

### BACKGROUND

[0002] An antenna is part of a mobile terminal and is an important wireless device for transmitting and receiving communication signals when the mobile terminal communicates with a base station. When the mobile terminal transmits a communication signal, the antenna converts the electrical signal into an electromagnetic wave signal and sends it out, and at the same time, the received electromagnetic wave signal by the antenna can be converted into an electrical signal in time and output to the corresponding circuit inside the mobile terminal.

[0003] As the requirement on the appearance and touch of the mobile terminal by a user is improved, more and more mobile terminal shells are made of metal materials, that is, except for a front display screen, side and back surfaces of the entire body are made of a metal, thus making the mobile terminal have a better metal texture, greatly improving its appearance expressive ability, and also increasing the structural strength to a large extent. However, due to the electrostatic shielding effect, the metal shell design of the mobile terminal greatly affects the ability of the antenna to transmit and receive communication signals.

### SUMMARY

[0004] A metallic shell, a method for manufacturing the metallic shell and a mobile terminal including the metallic shell are provided, so as to achieve colour and luster consistency of the metallic shell and thus improve aesthetics of the metallic shell appearance without any negative effect on the antenna.

[0005] According to a first aspect of the present disclosure, a metallic shell is provided. The metallic shell includes a body having a slot; and an insulator formed in the slot, wherein the insulator comprises an insulating material, the insulating material comprises a plastic material, a first coating and a second coating, the first coating is configured to colour the plastic material to make the insulator exhibit a same colour as that of the body, the second coating is configured to improve luster of the plastic material to make the insulator exhibit a same metallic luster as that of the body.

[0006] According to a second aspect of the present disclosure, a method for manufacturing a metallic shell is provided. The method includes providing a slot at a predetermined location of a body; filling an insulating material in the slot to form an insulator in the slot, the insu-

lator comprising an insulating material, the insulating material comprising a plastic material, a first coating and a second coating, the first coating being configured to colour the plastic material to make the insulator exhibit a same colour as that of the body, the second coating being configured to improve luster of the plastic material to make the insulator exhibit a same metallic luster as that of the body.

[0007] According to a third aspect of the present disclosure, a mobile terminal is provided. The mobile terminal includes the metallic shell according to the first aspect.

[0008] In embodiments of the present disclosure, the first coating and the second coating are added into the plastic material to prepare the insulating material, so that the insulator filled in the slot by injection molding exhibits the same colour and luster as those of the body. The problem of inconsistency in appearances of the antenna partition bar and the body of the metallic shell is solved by filling the insulating material in the slot to form an insulator in the slot, thus ensuring the consistence in the appearances of the insulator and the body of the metallic shell without any negative effect on the antenna. In such a manner, a conventional step for spraying a color layer on the antenna partition bar may be omitted, so as to shorten the process, improve production efficiency, enhance metal texture of the whole device and achieve aesthetics effects.

[0009] Additional aspects and advantages of the embodiments of the present disclosure will be given in part in the following descriptions, become apparent in part from the following descriptions, or be learned from the practice of the embodiments of the present disclosure.

### BRIEF DESCRIPTION OF THE DRAWINGS

[0010] These and other aspects and advantages of the disclosure will become apparent and more readily appreciated from the following descriptions taken in conjunction with the drawings in which:

Fig. 1 is a schematic view of a metallic shell according to an embodiment of the present disclosure;

Fig. 2 is a sectional view of the metallic shell in Fig. 1 in a direction of A-A;

Fig. 3 is a block diagram of a method for manufacturing a metallic shell according to an embodiment of the present disclosure;

Fig. 4 is a schematic view of a metallic shell, which has been processed to define a slot, produced by a method for manufacturing a metallic shell according to an embodiment of the present disclosure; and Fig. 5 is a schematic view of a metallic shell, in which an insulating material has been filled in a slot, produced by a method for manufacturing a metallic shell according to an embodiment of the present disclosure.

## DETAILED DESCRIPTION

**[0011]** Embodiments of the present disclosure will be described in detail in the following descriptions, examples of which are shown in the accompanying drawings, in which the same or similar elements and elements having same or similar functions are denoted by like reference numerals throughout the descriptions. The embodiments described herein with reference to the accompanying drawings are explanatory and illustrative, which are used to generally understand the present disclosure. The embodiments shall not be construed to limit the present disclosure. In addition, for ease of description, the accompanying drawings only show components related to the present disclosure, not all the structure.

**[0012]** Fig. 1 is a schematic view of a metallic shell 100 according to an embodiment of the present disclosure. As shown in Fig. 1, the metallic shell 100 includes a body 1. The body 1 has a slot. An insulator 3 is formed in the slot and includes an insulating material. The insulating material includes a plastic material, a first coating and a second coating. Specifically, the first coating is configured to colour the plastic material to make the insulator 3 exhibit a same colour as that of the body 1. The second coating is configured to improve luster of the plastic material to make the insulator 3 exhibit a same metallic luster as that of the body 1.

**[0013]** The first coating is at a mass percentage comprised between 0.1% to 0.5% in the insulator, the second coating is at a mass percentage comprised between 0.1% to 1% in the insulator, and the balance is the plastic material. The plastic material includes polyphenylene sulfide (PPS), polybutylene terephthalate (PBT) or polyamide (PA). The first coating may be an organic coating, such as an azo coating (including monoazo, bisazo or azo lake), a phthalocyanine coating (including copper phthalocyanine, halogenated copper phthalocyanine or phthalocyanine lake) or a fused ring coating (isoindoline, isoindolinone or quinophthalone). Moreover, the first coating may also be an inorganic coating, such as a titanium oxide composite coating, a bismuth vanadate coating, an iron oxide coating, a lead chromate coating, a lead molybdate coating or an ultramarine coating. The second coating may include one or more compositions of a pearlescent coating, a silver slurry and an aluminum-silver slurry.

**[0014]** Fig. 2 is a sectional view of the metallic shell in Fig. 1 in a direction of A-A. As shown in Fig. 2, the slot in the body is at least one through-channel in a direction from a first surface (e.g., an outer surface) 11 to a second surface (e.g., an inner surface) 12 of the body, thus interrupting the closed circuit of the body and avoiding negatively affecting the ability of the antenna to transmit and receive communication signals due to the electrostatic shielding effect. The insulator 3 is filled in the through-channel. Thus, after the metallic shell is assembled to a mobile terminal, foreign matters are prevented from passing through the channel into the interior of the mobile

terminal.

**[0015]** According to the present embodiment, the first coating and the second coating are added into the plastic material to prepare the insulating material, so that the insulator filled in the slot by injection molding exhibits the same colour and luster as those of the body. The problem of inconsistency in appearances of the antenna partition bar and the body of the metallic shell is solved by filling the insulating material in the slot to form an insulator in the slot, thus ensuring the consistency in the appearances of the insulator and the body of the metallic shell without any negative effect on the antenna. In such a manner, a conventional step for spraying a color layer on the antenna partition bar may be omitted, so as to shorten the process, improve production efficiency, enhance metal texture of the whole device and achieve aesthetics effects.

**[0016]** In an embodiment of the present disclosure, the insulating material is filled in the slot by injection molding to form the insulator, so that the insulator is formed integrally with the body by an injection molding manner. In another embodiment of the present disclosure, the first coating and the second coating are uniformly dispersed in the plastic material, thus obtaining a uniform colour distribution on the surface of the insulation layer and showing a uniform and nature-like metallic luster. In a further embodiment of the present disclosure, the insulator is formed integrally with the body without any seam. Moreover, in an embodiment of the present disclosure, a height of the insulator 3 in the slot is the same as a depth of the slot, i.e. a surface (e.g., an outer surface) of the insulator 3 is aligned with the first surface 11 of the body 1. Thus, the metallic shell has a flat outer surface and a consistent appearance.

**[0017]** In an embodiment of the present disclosure, the metallic shell 100 may include a colour layer 4 provided on an outer surface of the metallic shell. As shown in Fig. 1, the insulator 3 may have the same colour and luster as those of the body 1, thus showing a visually seamless appearance and solving the problem of inconsistency in appearances of the antenna partition bar and the body of the metallic shell 100.

**[0018]** In an embodiment of the present disclosure, the metallic shell 100 may further include a metal oxide layer provided on the colour layer 4, thus improving abrasive resistance and corrosion resistance of the metallic shell 100.

**[0019]** In an embodiment of the present disclosure, the body comprises one or more compositions of aluminum, aluminum alloy, magnesium, magnesium alloy, stainless steel, copper, copper alloy, titanium and titanium alloy, thus providing a substrate colour and facilitating to colour the surface of the metallic shell by a surface treatment process (e.g., a physical vapor deposition process).

**[0020]** Fig. 3 is a block diagram of a method for manufacturing a metallic shell according to an embodiment of the present disclosure. The method is applied to prepare the metallic shell described above. As shown in Fig.

3, the method includes following steps.

**[0021]** At block 110: a slot is provided at a predetermined location of a body.

**[0022]** Fig. 4 is a schematic view of a metallic shell, which has been processed to define a slot, produced by the method for manufacturing the metallic shell. As an example of a back metallic shell of a smartphone shown in Fig. 4, two through-channels are provided in a direction from a first surface to a second surface of a body 1 of the back metallic shell at a top and a bottom of the body 1 respectively to be used as slots 2, thus destroying the closeness of the body 1.

**[0023]** In an embodiment of the present disclosure, a slot may also be provided at a headset jack of the mobile terminal, thus increasing the number of the slots and further reducing the negative effect on the ability of the antenna to transmit and receive communication signals without destroying aesthetics of the metallic shell.

**[0024]** At block 120: an insulating material is filled in the slot to form an insulator in the slot.

**[0025]** Fig. 5 is a schematic view of a metallic shell, in which an insulating material has been filled in the slot, produced by the method for manufacturing the metallic shell. The plastic material, the first coating and the second coating are filled in the slot by injection molding to provide the insulator 3, so that the insulating layer 3 is formed integrally with the body 1 without any seam. Moreover, in another embodiment of the present disclosure, a height of the insulator 3 in the slot is the same as a depth of the slot, i.e. a surface (e.g., an outer surface) of the insulator 3 is aligned with the first surface 11 of the body 1, so that the metallic shell 100 has a flat outer surface and a consistent appearance, thus obtaining the metallic shell shown in Fig. 5.

**[0026]** Specifically, the insulating material includes a plastic material, a first coating and a second coating. In addition, the first coating is configured to colour the plastic material to make the insulator exhibit a same colour as that of the body. The second coating is configured to improve luster of the plastic material to make the insulator exhibit a same metallic luster as that of the body.

**[0027]** In an embodiment, the second coating may include one or more compositions of a pearlescent coating, a silver slurry and an aluminum-silver slurry. Specifically, colour of pearlescent powder may be silver, shining gold, metallic color, rainbow interference color and a series of gradient colours, thus satisfying users' requirements for different colours of the metallic shell. Pearlescent powders with different particle sizes may be chosen according to actual practice. For example, in order to achieve a better coverage, pearlescent powders with a smaller size may be used, and the smaller the particle size is, the larger the coverage of the pearlescent powder is. For example, in order to achieve a better luster, pearlescent powders with a larger size may be used, and the larger the particle size is, the higher the luster of the pearlescent powder is.

**[0028]** The silver slurry is a coating with a metal glittering effect, having advantages of a uniform particle size distribution, a smooth surface, a great glittering effect.

ting effect, having advantages of a uniform particle size distribution, a smooth surface, a great glittering effect.

**[0029]** The aluminum-silver slurry is a coating with a metal glittering effect. That is, through a special processing technology and surface treatment, a flat aluminum surface is obtained with a regular shape and a concentrated particle size distribution, thus achieving an excellent light reflection and metallic luster.

**[0030]** The inventors of the present disclosure have found that a mass percentage between 0.1% to 0.5% of the first coating (which may be a single coating or may be a mixture of several coatings according to actual needs) and a mass percentage between 0.1% to 1% of the pearlescent powder are added in the plastic material, and then the insulator is obtained in the slot by injection molding method. Thus, the insulator shows the colour needed actually and a better high-brightness effect, and exhibits the same colour and luster as those of the body.

**[0031]** In an embodiment of the present disclosure, the pearlescent powder added in the plastic material is at a mass percentage comprised between 0.5% to 1% in the insulator.

**[0032]** In an embodiment of the present disclosure, the silver slurry added in the plastic material is at a mass percentage comprised between 0.1% to 1% in the insulator.

**[0033]** In an embodiment of the present disclosure, the silver slurry added in the plastic material is at a mass percentage comprised between 0.5% to 1% in the insulator.

**[0034]** In an embodiment of the present disclosure, the aluminum-silver slurry added in the plastic material is at a mass percentage comprised between 0.1% to 1% in the insulator.

**[0035]** In an embodiment of the present disclosure, the aluminum-silver slurry added in the plastic material is at a mass percentage comprised between 0.5% to 1% in the insulator.

**[0036]** In an embodiment of the present disclosure, a mixture of any two of the pearlescent powder, the silver slurry and the aluminum-silver slurry added in the plastic material is at a mass percentage comprised between 0.1% to 1% in the insulator.

**[0037]** In an embodiment of the present disclosure, a mixture of any two of the pearlescent powder, the silver slurry and the aluminum-silver slurry added in the plastic material is at a mass percentage comprised between 0.5% to 1% in the insulator.

**[0038]** In an embodiment of the present disclosure, a mixture of the pearlescent powder, the silver slurry and the aluminum-silver slurry added in the plastic material is at a mass percentage comprised between 0.1% to 1% in the insulator.

**[0039]** In an embodiment of the present disclosure, a mixture of the pearlescent powder, the silver slurry and the aluminum-silver slurry added in the plastic material is at a mass percentage comprised between 0.5% to 1% in the insulator.

**[0040]** According to the present embodiment, the first coating and the second coating are added into the plastic material to prepare the insulating material, so that the insulator filled in the slot by injection molding exhibits the same colour and luster as those of the body. The problem of inconsistency in appearances of the antenna partition bar and the body of the metallic shell is solved by filling the insulating material in the slot to form an insulator in the slot, thus ensuring the consistency in the appearances of the insulator and the body of the metallic shell without any negative effect on the antenna. In such a manner, a conventional step for spraying a color layer on the antenna partition bar may be omitted, so as to shorten the process, improve production efficiency, enhance metal texture of the whole device and achieve aesthetics effects.

**[0041]** In an embodiment of the present disclosure, the method may also include following steps.

**[0042]** At block 130: after the slot is filled with the insulating material, the body is further coloured by providing a colour layer on an outer surface of the metallic shell.

**[0043]** Specifically, the colour layer is prepared by methods including physical vapor deposition (PVD). After filling the insulating material, the body with the insulator is treated by PVD to provide the colour layer 4, as shown in Fig. 1. The PVD process may be performed on metals, such as stainless steel, copper, titanium, or zinc-aluminum alloy to provide chromium nitride (CrN), titanium nitride (TiN), titanium carbonitride (TiCN) and titanium aluminum nitride (TiAlN), thus providing a colour layer of gold, brass, rose gold, silver, black, smoke gray, copper, brown, purple, blue, wine red or bronze on the metal surface. Therefore, the insulator exhibits the same colour and luster as those of the body of the metallic shell, thus exhibiting a visually seamless appearance effect, and solving the problem of inconsistency in appearances of the antenna partition bar and the body of the metallic shell.

**[0044]** At block 140: the body is further subjected to a layer protecting treatment, that is, a metal oxide layer is provided on the colour layer.

**[0045]** Specifically, the protecting treatment includes an anodization method. The body with the insulating layer is placed in an electrolytic bath with an electrolytic solution of dilute sulfuric acid and used as an anode. After the electrolytic bath is powered on, the metal oxide layer (usually a porous white translucent film) is provided on the colour layer, thus improving the abrasive resistance and the corrosion resistance of metallic shell.

**[0046]** According to an embodiment of the present embodiment, a mobile terminal is provided, including the metallic shell as described in the above embodiment and a component for providing normal function of the mobile terminal. For example, the mobile terminal in the present embodiment may specifically be a terminal such as a mobile phone (e.g., a smartphone), a tablet computer, or a digital reader, preferably a smartphone. The metallic shell may be a back housing or a middle frame of a mobile

terminal. The metallic shell is prepared by the method of manufacturing the metallic shell described above to make the insulator exhibit the same colour and luster as those of the body of the metallic shell, thus exhibiting a visually seamless appearance effect, and solving the problem of inconsistency in appearances of the antenna partition bar and the body of the metallic shell. Furthermore, in such a manner, a conventional step for spraying a color layer on the antenna partition bar may be omitted, so as to shorten the process, improve the production efficiency, enhance the metal texture of whole mobile terminal and achieve aesthetics effects.

**[0047]** Although explanatory embodiments have been shown and described, it would be appreciated by those skilled in the art that changes, alternatives, and modifications may be made in the embodiments without departing from spirit and principles of the disclosure. Such changes, alternatives, and modifications all fall into the scope of the claims and their equivalents.

## Claims

1. A metallic shell (100), comprising:
  - a body (1) having a slot (2); and
  - an insulator (3) formed in the slot (2), wherein the insulator (3) comprises an insulating material, the insulating material comprises a plastic material, a first coating and a second coating, the first coating is configured to colour the plastic material to make the insulator (3) exhibit a same colour as that of the body (1), the second coating is configured to improve luster of the plastic material to make the insulator (3) exhibit a same metallic luster as that of the body (1).
2. The metallic shell (100) according to claim 1, wherein the second coating comprises one or more compositions of a pearlescent coating, a silver slurry and an aluminum-silver slurry.
3. The metallic shell (100) according to claim 1 or 2, wherein the second coating is at a mass percentage comprised between 0.1% to 1% in the insulator.
4. The metallic shell (100) according to any one of claims 1 to 3, wherein the first coating and the second coating are uniformly dispersed in the plastic material.
5. The metallic shell (100) according to any one of claims 1 to 4, wherein the plastic material comprises polyphenylene sulfide (PPS), polybutylene terephthalate (PBT) or polyamide (PA).
6. The metallic shell (100) according to any one of claims 1 to 5, wherein the insulator (3) is formed in-

- tegrally with the body (1) by an injection molding manner.
7. The metallic shell (100) according to any one of claims 1 to 6, wherein a height of the insulator (3) in the slot (2) is the same as a depth of the slot (2). 5
8. The metallic (100) shell according to any one of claims 1 to 7, further comprising a colour layer (4) provided on an outer surface (11) of the metallic shell (100). 10
9. The metallic shell (100) according to claim 8, further comprising a metal oxide layer provided on the colour layer (4). 15
10. The metallic shell (100) according to any one of claims 1 to 9, wherein the body (1) comprises one or more compositions of aluminum, aluminum alloy, magnesium, magnesium alloy, stainless steel, copper, copper alloy, titanium and titanium alloy. 20
11. A method for manufacturing a metallic shell, comprising: 25
- providing a slot at a predetermined location of a body;
- filling an insulating material in the slot to form an insulator in the slot, the insulator comprising an insulating material, the insulating material comprising a plastic material, a first coating and a second coating, the first coating being configured to colour the plastic material to make the insulator exhibit a same colour as that of the body, the second coating being configured to improve luster of the plastic material to make the insulator exhibit a same metallic luster as that of the body. 30 35
12. The method according to claim 11, wherein the second coating comprises one or more compositions of a pearlescent coating, a silver slurry and an aluminum-silver slurry, specially, the second coating is at a mass percentage comprised between 0.1% to 1% in the insulator; 40 45
- and/or
- a height of the insulator in the slot is the same as a depth of the slot.
13. The method according to claim 11 or 12, wherein filling the insulating material in the slot comprises: 50
- filling the insulating material in the slot by injection molding so that the insulator is formed integrally with the body. 55
14. The method according to any one of claims 11 to 13, further comprising:
- providing a colour layer on an outer surface of the metallic shell; and
- providing a metal oxide layer on the colour layer.
15. A mobile terminal comprising a metallic shell according to any one of claims 1 to 10.




Fig. 1




Fig. 2




Fig. 3




Fig. 4




Fig. 5



EUROPEAN SEARCH REPORT

Application Number  
EP 17 17 3475

5

10

15

20

25

30

35

40

45

50

55

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (IPC)
A	CN 105 283 013 A (GUANGDONG OPPO MOBILE TELECOMM) 27 January 2016 (2016-01-27) * paragraph [0027] - paragraph [0057]; figure 1 *	1-15	INV. C25D5/56 H01Q1/24
A	----- CN 201 189 798 Y (WEICHUAN CHEN [CN]) 4 February 2009 (2009-02-04) * page 6 - page 9; figures 1-4 *	1-15	
A	----- US 2015/057054 A1 (SU WEI-CHENG [TW] ET AL) 26 February 2015 (2015-02-26) * abstract; figure 1 *	1-15	
			TECHNICAL FIELDS SEARCHED (IPC)
			C25D H01Q
The present search report has been drawn up for all claims			
Place of search The Hague		Date of completion of the search 20 December 2017	Examiner La Casta Muñoa, S
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons ..... & : member of the same patent family, corresponding document	

EPO FORM 1503 03/82 (P04/C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT  
ON EUROPEAN PATENT APPLICATION NO.**

EP 17 17 3475

5 This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.  
The members are as contained in the European Patent Office EDP file on  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

20-12-2017

10

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
CN 105283013 A	27-01-2016	NONE	
-----			
CN 201189798 Y	04-02-2009	NONE	
-----			
US 2015057054 A1	26-02-2015	CN 203466294 U	05-03-2014
		TW M502974 U	11-06-2015
		US 2015057054 A1	26-02-2015
-----			

15

20

25

30

35

40

45

50

55

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82