



(19)

Europäisches
Patentamt
European
Patent Office
Office européen
des brevets



(11)

EP 3 323 573 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
16.09.2020 Bulletin 2020/38

(51) Int Cl.:

B27M 1/02 (2006.01)**B27K 5/00** (2006.01)**B27K 5/06** (2006.01)(21) Application number: **17202100.8**(22) Date of filing: **16.11.2017**

(54) A METHOD FOR THE THERMOMECHANICAL DENSIFICATION OF POPLAR PLYWOOD
VERFAHREN ZUR THERMOMECHANISCHEN VERDICHTUNG VON PAPPELSPERRHOLZ
PROCÉDÉ DE DENSIFICATION THERMOMÉCANIQUE DE CONTREPLAQUÉ DE PEUPLIER

(84) Designated Contracting States:

**AL AT BE BG CH CY CZ DE DK EE ES FI FR GB
GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO
PL PT RO RS SE SI SK SM TR**

- **Chawlowski, Grzegorz**
07-200 Wyszków (PL)
- **Perzyna, Kamil**
07-202 Wyszków (PL)

(30) Priority: **17.11.2016 PL 41949916**

(74) Representative: **Kondrat, Mariusz**
Kondrat & Partners
Al. Niepodleglosci 223/1
02-087 Warszawa (PL)

(43) Date of publication of application:

23.05.2018 Bulletin 2018/21

(73) Proprietor: **Versal Sp. z o.o.**
03-231 Warsaw (PL)

(56) References cited:
CN-A- 101 603 623 US-A- 4 606 388
US-B1- 6 689 301

(72) Inventors:

- **Nadolski, Tadeusz**
01-493 Warszawa (PL)

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

[0001] The subject of the invention is a thermomechanical method of compression of poplar plywood, used in the production of thin, flexible poplar plywood, the density of which increases during the compression process. The document CN 101603623 B discloses a method of thermomechanical densification of poplar wood.

[0002] Plywood is a composite material, made by gluing together thin layers of wood veneers, rotated so that the grains of the adjacent layers are at different angles, up to 90°. The physical and mechanical properties depend on the type of wood used, the quality of the face veneers (external layers), the thickness and arrangement of the veneers, the type of resin used and the method of gluing. Varieties of plywood include moisture-resistant plywood (glued with urea resin), semi-waterproof (glued using melamine resin) and waterproof (using Bakelite and synthetic resins).

[0003] Plywood, not according to the invention is made from various types of wood, most commonly pine, birch, alder and beech or exotic trees. The core veneers are often from a different, cheaper type of wood than the face veneers.

[0004] Due to the roughness of the surface, we differentiate: unpolished (0) and polished (1) plywood. Plywood can relatively easily be shaped (bent) when hot, which allows for the production of shapes useful in furniture making: drawers, door panels, back panels, structural components of office and workshop furniture. Consequently, plywood is commonly used in the production of domestic and office furniture. Currently, flexible plywood is produced from exotic soft woods such as Fume or Ocoumé, that have a spongy wood structure.

[0005] SUPERFORM bendy plywood has been well-known for several years, with a wide range of applications in the furniture making, boatbuilding industries etc. It is a material that, due to its properties, can be substituted for other currently-used flexible materials such as slotted MDF. SUPERFORM plywood maintains high rigidity after final fixing. It can be shaped into any designed shape. Use of SUPERFORM plywood eliminates the need to use skeleton structures when forming radii.

[0006] SUPERFORM three-layer plywood is made from the exotic deciduous tree fuma/ceiba, using a melamine based resin; its sheets are polished.

[0007] Patent description PL215663 describes the process of modifying wood by heating the wood and then pulsar compression at a temperature between 70 and 170°, for relative deformations between 5 and 40%, perpendicular to the grain between press plates with a high frequency field generator, or in a heated press. Once the compression process is completed, the compressed wood cools between the press plates, and then acclimatizes until it achieves a moisture content equal to that which it will have in service.

[0008] Patent description US7404422 provides the method of continuous viscoelastic thermal compression

of wood or wood components. Wood processed in this way may have a moisture content of between 15% and 30%. The process employs a press to ensure continuous compression. The process takes place at the glass transition temperature of the wood and under pressure between 650 and 2000 kPa.

[0009] Unexpectedly, it was discovered that it is possible to obtain flexible plywood by its compression in an interval process at temperatures up to 100°C. This process differs from those previously known, in that the relative deformation of the plywood amounts to 50%-75%, and there is no need for cooling between the press plates, which drastically cuts the production process. High pressure, between 500kPa and 20000kPa is used. It is important that the moisture of the plywood not exceed 15%.

[0010] The essence of the invention is a thermomechanical method of compression of poplar plywood consisting of heating poplar plywood wherein plywood with a 5-15% moisture level is subjected to interval compression between the press plates, where the poplar plywood is heated to a temperature between 70° - 105° and then pressed in 2-3 cycles at a pressure of 5-20MPa, reducing the plywood to 25-50% of its initial thickness.

[0011] The plywood obtained according to the method of the invention is characterized by relative deformation from 50% to 75%.

[0012] The subject of the invention is a method for the production of thin, flexible poplar plywood, which is densified during compression.

[0013] The method of densifying poplar plywood according to the invention consists of the thermomechanical densification of plywood characterized by the fact that poplar plywood is heated to a temperature between 70°-105°C and then compressed in 2-3 cycles in a high-pressure press, reducing the thickness of the plywood to 25-50% of its original thickness. The lignin in plywood heated above 70°C is subject to plasticization, and rapid spring-back after the first compression of the wood causes the elastication of the cell walls of the wood thanks to which the wood cell walls are not destroyed during compression, but only moved by removing empty spaces, which used to transport water. Plywood densified in this way obtains unexpected mechanical properties, i.e., great elasticity, thanks to which it can be bent to a radius of 100mm. Additionally, the surface of the plywood is smoothed and divested of the initial pores, which reduces by 30-50% the amount of chemicals necessary to bond it and to finish the surface.

[0014] The method of densification of the plywood is presented in more detail in the examples given below.

Example 1

[0015] Three-ply poplar plywood, with a temperature of 18° and 2.8mm thickness, of 9.5% moisture is placed between press plates heated to 95°C, whereupon the press is closed, compressing the plywood to a thickness of 2.6mm. After 180 seconds, the plywood is heated to

90-95°C, when the press plates are lifted, and lowered once more, compressing the plywood to a thickness of 1.5mm for 30 seconds. The press is opened for a second tie and closed again, compressing the plywood to a thickness of 0.7mm for 60 seconds. When the press is opened, the plywood has a thickness of about 0.9mm. The compression was performed using an Italpresse GL260PS high pressure press, allowing the achievement of a force of 22000kN.

Example 2

[0016] Thermally modified poplar plywood (conditioning in a temperature 170-215°C for 6-10 hours), 3mm thickness and 8% moisture is placed between press plates heated to a temperature of 95°C, whereupon the press is closed, compressing the plywood to a thickness of 2.8mm. After 180 seconds, the plywood is heated to 90-95°C, when the press plates are lifted, and lowered once more, compressing the plywood to a thickness of 1.5mm for 30 seconds. The press is opened for a second tie and closed again, compressing the plywood to a thickness of 0.6mm for 60 seconds. During the final cycle, the press plates are pressed with a force of 10000kN - 20000kN which, depending on the area of the plywood, provides pressure of about 5-20MPa. After the opening of the press, the plywood has a thickness of about 0.9mm. It is then cooled and climatized to a moisture content equal to that which it will have in service. The densified poplar plywood, that had previously been subjected to thermal modification has additional properties: it is resistant to mould and woodworm as well as greater dimensional stability.

Example 3

[0017] Three-ply poplar plywood, with a temperature of 18° and 2.8mm thickness, of 15% moisture is placed between press plates heated to 95°C, whereupon the press is closed, compressing the plywood to a thickness of 2.6mm. After 60 seconds, the plywood is heated to 90-95°C, when the press plates are lifted, and lowered once more, compressing the plywood to a thickness of 1.0mm for 30 seconds. The press is opened for a second tie and closed again, compressing the plywood to a thickness of 0.7mm for 60 seconds. When the press is opened, the plywood has a thickness of about 1.67mm. The compression was performed using an Italpresse GL260PS high pressure press, allowing the achievement of a force of 22000kN. The resulting plywood has a hardness on the Brinell scale in the order of 35MPa (compared to raw plywood - 10MPa).

Claims

1. The method of the thermomechanical densification of poplar plywood consisting of heating poplar ply-

wood is such that plywood of a moisture of 5-15% is subjected to interval compression between the press plates, where the poplar plywood is heated to a temperature between 70° - 105°C, and then compressed in 2-3 cycles under pressure of 5-20MPa, reducing the thickness of the plywood to 25-50% of its original thickness and that the relative deformation of the obtained plywood amounts to 50%-75%.

Patentansprüche

1. Verfahren zur thermomechanischen Verdichtung von Pappelsperrholz, bei dem das Pappelsperrholz erhitzt wird, **dadurch gekennzeichnet, dass** das Sperrholz mit einem Feuchtigkeitsgehalt von 5 - 15% zwischen Pressplatten gepresst wird, wobei das Pappelsperrholz auf eine Temperatur zwischen 70° und 105° Grad erhitzt und anschließend einem Pressvorgang von 2-3 Zyklen mit einem Pressdruck von 5 - 20 MPa unterzogen wird, wodurch die Sperrholzdicke auf 25-50% ihrer Ausgangsdicke reduziert wird und die relative Verformung des so behandelten Sperrholzes 50% bis 75% beträgt.

Revendications

1. Méthode de compactage thermomécanique du contre-plaqué de peuplier consistant à réchauffer le contre-plaqué de peuplier et **caractérisée par le fait que** le contre-plaqué ayant un taux d'humidité compris en 5 et 15% est soumis à la pression entre deux plaques d'appui et le contre-plaqué de peuplier est réchauffé à une température de 70° - 105°C, puis compressé durant 2 ou 3 cycles de compression, avec une pression d'appui de 5 à 20 MPa, ce qui permet de réduire l'épaisseur jusqu'à une valeur allant de 25 à 50% de son épaisseur initiale et la déformation relative du contre-plaqué obtenu est de 50 à 75%.

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- CN 101603623 B [0001]
- PL 215663 [0007]
- US 7404422 B [0008]