



(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
13.06.2018 Bulletin 2018/24

(51) Int Cl.:
C23C 14/06 (2006.01) **C23C 14/54 (2006.01)**
C23C 14/56 (2006.01)

(21) Application number: **17210307.9**

(22) Date of filing: **12.09.2007**

(84) Designated Contracting States:
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IS IT LI LT LU LV MC MT NL PL PT RO SE SI SK TR

- **Kaelin, Marc**
8155 Niederhasli (CH)
- **Rudmann, Dominik**
4054 Basel (CH)
- **Studer, Thomas**
4562 Biberist (CH)

(62) Document number(s) of the earlier application(s) in accordance with Art. 76 EPC:
07803444.4 / 2 188 406

(71) Applicant: **Flisom AG**
8155 Niederhasli (CH)

(74) Representative: **Parrini, Lorenzo**
Flisom AG
Gewerbestrasse 16
8155 Niederhasli (CH)

(72) Inventors:
• **Budde, Felix**
8053 Zurich (CH)

Remarks:
This application was filed on 22-12-2017 as a divisional application to the application mentioned under INID code 62.

(54) **METHOD FOR MANUFACTURING A COMPOUND FILM WITH COMPOSITIONAL GRADING**

(57) A method for manufacturing a compound film comprising a substrate (1) and at least one additional layer (2, 3, 4, 5, 6, 7), the compound film satisfying pre-defined compound film properties, in particular being pre-defined values for compound-film thickness, compound-film overall composition and compositional profile, the latter being defined as a compound-film composition as a function of a position on or in the compound film, the method comprising the steps of:

- depositing at least three chemical elements (A, B, C) on the substrate (1) and/or on the at least one additional layer (2, 3, 4, 5, 6, 7) using depositions sources (12),
- maintaining depositing of the at least three chemical elements (A, B, C) while the substrate (1) and the deposition sources (12) are being moved relative to each other,

characterized in that

at least the chemical element A is deposited by at least two different deposition sources (12A, 12A') positioned at two different locations, so that a gradient of the compositional profile of said chemical element A is achieved through the compound film thickness.




Fig. 11

Description

[0001] The present invention is related to a method for manufacturing a compound film according to the preamble of claim 1. More particular, the present invention is related to a method for measuring physical parameters of thin films, where the measurement takes place during or after film growth and where the measurement results are used for controlling film deposition processes. The invention also relates to a method for deposition of one or several thin films using vacuum deposition processes for the manufacturing of thin-film solar cells and modules, which are based on absorber layers typically containing the elements copper, indium, gallium, and selenium.

[0002] The generation of environmental-friendly energy by means of photovoltaic cells (solar cells) has received growing interest in recent years. Solar cells generate energy by converting light, typically sunlight, into electricity, and fulfill the demands on a sustainable, renewable energy technology. Standard solar cell technology today is based on crystalline or multi-crystalline silicon absorbers, for the production of which a comparatively high amount of material and energy is required, which in turn limits the production cost potential. Thin-film solar cell technologies have proven to have a high potential for low-cost production while also achieving high light-to-electricity conversion efficiencies, a particularly promising candidate being based on the material copper-indium-gallium-diselenide. Especially promising is the deposition of solar cells using a roll-to-roll deposition technology, which allows quasi-continuous processing. In order to achieve low production costs, a high production yield is mandatory. Hence, mass production of solar cells must be very reliable and a good production process control is crucial, in particular control of the absorber deposition process. With a given manufacturing process, it is crucial to achieve cells and modules with highest conversion efficiencies (also called cell or module efficiencies or simply efficiencies). The efficiency is the most important parameter to characterize the performance or energy conversion quality of a solar cell or module.

[0003] A typical CIGS solar cell is based on the semiconductor layer CIGS, which can be $\text{Cu}(\text{In,Ga})\text{Se}_2$. A CIGS layer needs to be deposited onto a back contact layer, or onto a stack of back contact layers, which in turn is deposited onto a substrate with or without additional intermediate coatings.

[0004] Fig. 1 shows a CIGS solar cell structure: A supporting structure, the substrate 1, for example, a polymer or metal foil or sheet or a glass sheet, is coated with a back contact film 2, for example made of Mo or another electrically conducting material or compound. The alkalimetal-containing CIGS absorber layer 3 is deposited thereafter onto the structure, where the alkali atoms are added to the CIGS by diffusion from underlying layers (not shown in Fig. 1) or from the substrate during CIGS growth, by co-deposition during CIGS growth, or by dif-

fusion after CIGS growth. The CIGS layer is coated by a buffer layer 4 made of CdS or related compounds such as $\text{Cd}(\text{O,OH,S})$ or of ZnS , ZnO , In_2S_3 , or of other compounds. As a next layer, a front contact or window layer 5 is deposited, typically consisting of a bi-layer of intrinsic ZnO (i- ZnO) and a transparent conducting oxide (TCO), such as doped ZnO (e.g. ZnO:Al) or indium tin oxide (ITO), or consisting of a single layer such as a TCO alone. In-between the deposition steps, one or several patterning steps may be applied, where layers are structured such that individual solar cells are connected in parallel and/or series, resulting in arrays of solar cells, which are called "modules". Grid structures 6 that can assist carrier collection and can make contact to adjacent cells may be deposited after deposition of the window layer. An anti-reflection coating 7 may be deposited on top in addition. Not all layers described here need to be deposited in a production process in order to get a working solar cell. Especially for economic or practical reasons or to enhance the cell performance, some layers can be omitted or others can be added, where the efficiency of the solar cells and modules may be affected or not.

[0005] The deposition of CIGS solar cells and monolithic integration into modules is described, for example, in US-5 078 804 and by Mitchell, Proceedings of the 20th IEEE PV Conference 1988, pp. 1384-1389, respectively.

[0006] An economic way of producing thin-film solar cells and modules is to use in-line processing, where batches of individual substrates 1 move one after the other through one or several deposition zones in a deposition chamber 8 (Fig. 2), such that the deposition processes are kept running continuously while the substrates get progressively coated as they move further through the deposition zones, as it is depicted in Fig. 2 (a). Several deposition chambers 8 may be lined up in sequence, and one or several adjacent chambers 9, typically containing substrate manipulation mechanisms or measurement devices, may be added on either side of each deposition chamber.

[0007] A potentially even more economic way of producing thin-film solar cells and modules is to use flexible substrates such as metallic, polymeric, glassy, or ceramic foils, and to coat said flexible substrates with the solar cells or modules using roll-to-roll deposition technology, as it is depicted in Fig. 2 (b). With roll-to-roll deposition, large substrate areas can be coated without the need of interrupting or changing the deposition process over long periods of time. The substrate (also called "web") moves through one or several deposition zones and gets progressively coated as it moves further through the deposition zones.

[0008] The use of x-ray fluorescence (XRF) for thickness and/or composition measurement in thin-film technology is well known. The use of XRF for simultaneous multilayer thickness measurement for individual samples is described in US-4 162 528, for example. The use of XRF in thin-film production systems is described in US-6 611 576, where metal films deposited onto semicon-

ductor wafers are characterized using XRF during growth, allowing to determine an end point and to stop the deposition once the determined film thickness reaches a preset value. The latter invention is useful for batch-to-batch deposition systems, where one batch of samples is processed until an end point is reached, before processing on the next batch starts. However, in a continuous-processing deposition system, like a roll-to-roll or in-line deposition system, an end point in the above sense is never reached and a deposition process is not stopped once a coating is completed.

[0009] CIGS deposition control has been addressed in WO 2005/086 238, where a transition of a Cu-rich CIGS layer into a Cu-deficient CIGS layer is detected in an in-line evaporation process. In this known teaching, an option to use XRF to measure overall film composition and thickness after the deposition zone in order to control the deposition process using a feedback signal is also described. In this connection, reference is made to the paper entitled "Manufacture of Thin-Film Solar Cells: Modeling and Control of Cu(InGa)Se₂ Physical Vapor Deposition onto a Moving Substrate" by Junker et al. (Ind. Eng. Chem. Res. 2004, 43, pp. 566-576), in which a method is disclosed that allows controlling one evaporation source for each metal, e.g. evaporation sources arranged in the sequence Cu-Ga-In or Ga-Cu-In. The known teaching does not allow measuring material gradients in the CIGS layer, or controlling all evaporation sources when arranged in sequences such as Ga-Cu-In-Ga, for example. Instead, XRF is described for the case of several evaporation sources distributed across the width of the substrate (perpendicular to the traveling direction of the substrate), and it is described how to use the XRF for controlling the individual sources.

[0010] WO 03/038 871 A1 (or US-2003/082 834 A1) discloses method for optical process control based on reflectometry for CIGS deposition.

[0011] EP-0 394 128 B1 discloses a movable x-ray source and the measurement of x-ray transmission through a substrate using a feedback loop.

[0012] A method for composition depth profiling of CIGS films using XRF is described by V. Alberts et al. (Solar Energy Materials & Solar Cells Vol. 64 (2000), p. 371-383), where XRF is applied in several steps on progressively etched CIGS films after growth. This treatment destroys the sample and is therefore not suited for non-destructive deposition-process control.

[0013] I.L. Eisgruber et al. (Conference Record of the 28th IEEE Photovoltaic Specialists Conference, 2000, p. 505-508) describe the use of XRF for standard in-line thickness and overall-composition measurement in a CIGS production process.

[0014] In the case of a deposition process where two or more atomic species form a compound, such as a CIGS deposition process, a film thickness measurement in combination with a film overall-composition measurement allows to determine the absolute amount of atoms of each species present in the layer. Hence, if all atoms

of one species in the film stem from only one deposition source, e.g. as it is depicted in Fig. 3 (a), and if overall-composition and/or thickness deviate from a desired, pre-defined value then corrective action on one or several of the sources can be taken. This is the case for example, when CIGS is deposited from three metal sources, i.e., from one Cu, one In, and one Ga source (the precise control of Se deposition rate is normally not required for typical CIGS layers, therefore it is not considered here and just assumed to happen satisfactorily independent of metal source control).

[0015] However, if the atoms of one species in the film stem from more than one deposition source, typically from a second, similar deposition source, e.g. as it is depicted in Fig. 3 (b), in which a second A-source 12, depositing a material A, is present, then the film overall-composition and thickness measurement performed by a measurement device 10 does not allow separating the contributions from the two similar A-sources anymore. Therefore, it is not clear, which of the A-sources needs corrective action, and source control is no more possible for all deposition sources.

[0016] In the example of CIGS deposition using one Cu, one In, and one Ga source, said control problem occurs as soon as a second Cu, In, or Ga source is added to the three metal deposition sources.

[0017] For example, if a second Ga source is added to the Cu, the In, and the Ga source, the overall-composition and thickness measurement signal can only tell how much Ga there is in the film, but not how much of the measured Ga was supplied by the first Ga source and how much by the second Ga source.

[0018] As a second example, sources arranged in the sequence In-Ga-Cu-In do not permit separate control of the In sources with merely a thickness and overall-composition measurement after film deposition.

[0019] It is well known to those skilled in the art that compositional gradients in CIGS films can exist and that they can have a significant influence on the solar cell conversion efficiency. In particular, the deposition of CIGS films in a way such that Ga/In compositional gradings occur can be advantageous. For example, when the Ga/In concentration ratio increases towards the back contact, which is called "back grading" or "normal grading" (see Fig. 4(b)), electron collection in the CIGS during solar cell operation is supported, which benefits the cell efficiency. When the Ga/In concentration ratio increases towards the buffer layer ("front grading"), the voltage of the device is enhanced, which again benefits the cell efficiency.

[0020] Particularly beneficial is the combination of a back and a front grading to a "double grading", as it is depicted in Fig. 4(c).

[0021] If CIGS is deposited from only one deposition source for each metal, e.g. from sources in the sequence Ga-Cu-In or In-Cu-Ga, either no front grading or no back grading is achieved. Fig. 5 (a) shows such a configuration. In order to achieve both gradings, i.e. a double grad-

ing, an additional metal deposition source is required, for examples a second Ga source enabling the sequence Ga-Cu-In-Ga (or Ga-In-Cu-Ga). Such a configuration is depicted in Fig. 5 (b). However, as described above, when a second Ga source (or any other second similar source) is used, individual control of two similar deposition sources is no more possible with merely a thickness and overall-composition measurement. Similarly, if other deposition source sequences are desired, such as Ga-In-Ga-Cu, Ga-In-Cu-In, Ga-In-Cu-In-Ga, or any other combination, the control problem remains the same.

[0022] In addition, for example to increase the throughput of the deposition machine or to shape the compositional profiles of the as-deposited films more accurately, it may be desirable to have a sequence of several "blocks" 13 of deposition sources 12, where every deposition-source block contains an array of deposition sources in a certain sequence, for example Ga-In-Cu followed by Cu-In-Ga, or Ga-In followed by Cu-In-Ga, or as depicted in Fig. 6. Any combination of sources and blocks can be used in a deposition process. An array of deposition-source blocks may be placed within one deposition chamber 8, within consecutive deposition chambers, or within one or several deposition chambers having an internal separation feature 14 such as a shield or wall. As described above, as soon as one material is deposited by more than one deposition source before an overall-thickness and composition measurement is performed, the control problem occurs.

[0023] When there are several deposition-source blocks, a known measurement device usually needs to be placed after every block. Since known measurement devices are heat-sensitive and since metal evaporation sources have to be operated at temperatures in the vicinity of 1000 °C or above, evaporation-source blocks cannot be placed close to each other because room is required for protection of the measurement devices from material deposition and heat radiation. Hence, deposition machines can become very large and complicated, and the film stack may cool down while moving through the measurement zone before reaching the following evaporation-source block.

[0024] It is therefore one object of the present invention to control deposition of compound films comprising at least two chemical elements.

[0025] This and other objects are obtained by the features given in the characterizing part of claim 1. Further embodiments as well as an apparatus are given in further claims.

[0026] Throughout the following description, the term CIGS must be understood as a typical CIGS solar cell that is based on the semiconductor layer CIGS, which can be $\text{Cu}(\text{In,Ga})\text{Se}_2$ or a related compound formed from any combination of the elements Cu, Ag, In, Ga, Al, Se, S, Te yielding a semiconductor in the form $(\text{Cu,Ag})_x(\text{In,Ga,Al})_y(\text{Se,S,Te})_z$, for example, the compound $\text{Cu}(\text{In,Ga})(\text{Se,S})_2$. It is understood that this class of compounds also comprises non-stoichiometric compounds such as

$\text{Cu}_{0.9}(\text{In,Ga})_{1.1}\text{Se}_2$, or $\text{Cu}(\text{In,Ga})_3\text{Se}_5$, etc., over wide ranges of compositions. Such compounds typically, but not always, contain a small amount of an alkali metal - added on purpose actively or passively - for example Na, K, or Li.

[0027] The present invention is directed to a method for manufacturing a compound film comprising a substrate and at least one additional layer, the compound film satisfying predefined compound film properties, in particular being predefined values for compound-film thickness, compound-film overall composition and compositional profile, the latter being defined as a compound-film composition as a function of a position on or in the compound film. The method comprising the steps of:

- depositing at least two chemical elements on the substrate and/or on the at least one additional layer using depositions sources,
- maintaining depositing of the at least two chemical elements while the substrate and the deposition sources are being moved relative to each other,
- optionally measuring the compound film properties, particularly being compound film thickness, compound-film overall composition, and compound-film composition in one or several positions of the compound film,
- optionally comparing the predefined values for the compound film properties to the measured compound film properties, and
- optionally adjusting the deposition of the at least two chemical elements in case the measure compound film properties do not match the predefined compound film properties.

[0028] In an embodiment of the present invention, the method is characterized in that the substrate is a flexible foil, made at least in part of metal, polymer, or ceramic, and that said foil can be rolled up.

[0029] In a further embodiment of the present invention, the method is characterized in that the substrate is at least partially coated by one or several additional layers.

[0030] In a still further embodiment of the present invention, the method is characterized in that the substrate is a plate of a material that is at least partially made of glass, metal, or polymer, and wherein the plates are continuously fed, one after the other, in order to be coated.

[0031] In yet another embodiment of the present invention, the method is characterized in that the substrate is coated by one or several additional layers, wherein the same or different coatings can be applied on either side of the substrate.

[0032] In yet another embodiment of the present invention, the method is characterized in that the step of measuring the compound film properties is performed by a measurement device that is moved in directions perpendicular and/or parallel to a traveling direction of the substrate, enabling measurements at different locations

of the substrate, in particular across an entire width of the substrate.

[0033] In yet another embodiment of the present invention, the method is characterized by further comprising the step of individually adjusting a deposition rate of the deposition sources.

[0034] In yet another embodiment of the present invention, the method is characterized in that the deposition sources are arranged in a plurality of deposition-source blocks.

[0035] In yet another embodiment of the present invention, the method is characterized in that at least a part of the measurement device is arranged opposite to the deposition sources with regard to the substrate. Therewith, the measurement device is protected from being coated and can be brought very close to the substrate or even touching the substrate without the risk of scratching the film.

[0036] In yet another embodiment of the present invention, the method is characterized by positioning the measurement device in-between deposition-source blocks.

[0037] In yet another embodiment of the present invention, the method is characterized in that the step of adjusting the deposition source is performed by modifying temperature, power supply or gas supply.

[0038] In yet another embodiment of the present invention, the method is characterized in that the measurement device comprises an x-ray detector for detecting characteristic fluorescence radiation from appropriately excited atoms in the substrate and/or any of the additional layers, where said x-ray detector is capable of distinguishing the energies or wavelengths of the radiation and of the respective radiation intensities.

[0039] In yet another embodiment of the present invention, the method is characterized in that the measurement device comprises an excitation source, which excites atoms in fractions or all of the compound film and possibly also in a part or all of the substrate.

[0040] In yet another embodiment of the present invention, the method is characterized in that the excitation source is an electron source, where the penetration depth of the electrons can be adjusted by changing the electron acceleration voltage.

[0041] In yet another embodiment of the present invention, the method is characterized in that the excitation source is an x-ray source, where at least a part of the exciting x-rays are high enough in energy to induce K and L lines in the fluorescence spectrum of at least a part of the excited atom species.

[0042] In yet another embodiment of the present invention, the method is characterized in that the excitation source comprises an x-ray source in combination with an electron source, where the x-ray source is capable of exciting atoms in all additional layers and in the substrate, while the electron source is capable of exciting only parts of the additional layers and/or the substrate.

[0043] In yet another embodiment of the present in-

vention, the method is characterized in that the compound film is a polycrystalline semiconductor compound of the form $(\text{Cu}, \text{Ag}) (\text{In}, \text{Ga}, \text{Al}) (\text{Se}, \text{S})_2$, particularly the compounds $\text{Cu}(\text{In}, \text{Ga})\text{Se}_2$ or $\text{Cu}(\text{In}, \text{Ga}) (\text{Se}, \text{S})_2$.

[0044] In yet another embodiment of the present invention, the method is characterized in that the substrate is a polyimide foil, which is particularly transparent for x-ray radiation, coated by an electrically conductive layer consisting of a single material.

[0045] In yet another embodiment of the present invention, the method is characterized in that the electrically conductive layer on the foil is made of Mo.

[0046] In yet another embodiment of the present invention, the method is characterized in that the electrically conductive layer on the foil is made of a metal nitride.

[0047] The present invention improves deposition control for deposition of compound films comprising at least two chemical elements, such as CIGS. The invention increases the degree of freedom, to which elemental deposition profile shapes can be created, and enables to ensure consistent and reliable film properties. The deposition control improvement is also achieved by employing one or several measurement sensors, together forming one measurement device, which allow determining film thickness, average film composition of the complete film (overall composition), as well as film composition in one or several fractions of the layer.

[0048] The measurement device can be a fluorescence spectrometer, where the fluorescence radiation to be detected is x-ray radiation. Such a measurement is non-destructive and hence does not cause material quality loss in the probed portions of the films. The essential components of such a spectrometer typically are an excitation source (or alternatively at least two excitation sources) and a detector, all aligned in a way suitable for efficient measurement-signal detection and properly cooled and shielded. Source and detector do not necessarily have to be in the same housing, they can also be spatially separated, for example, they can be placed one on the back and one on the front side of the film to be probed. The excitation source typically emits x-rays or electrons. The detector detects the wavelengths of the fluorescence radiation and the intensities of the radiation of such wavelengths. Alternatively, instead of wavelengths, the detector may be sensitive to the energies or frequencies of the fluorescence radiation, which in the end is equivalent to sensitivity to wavelengths due to the interrelation of radiation wavelength, energy, and frequency. The detector works usually either sequentially, e.g. by measuring one wavelength after the other, or simultaneously, e.g. by measuring all energies in the spectrum simultaneously with the help of a multi-channel analyzer. The wavelengths of the detected radiation are characteristic for the atom species present in the film. The intensity of radiation of a certain wavelength depends on the number of atoms of the corresponding atom species present in the probed part of the film. Hence, wavelength and intensity measurements allow quantify-

ing the composition and, once the system has been calibrated, also the thickness of a film. Depending on the wavelengths of the excitation radiation and the film thickness, all or only a part of the film to be measured can be probed. Also depending on the wavelength of the fluorescent radiation, a negligible or significant part or the complete fluorescence signal of a certain wavelength is re-absorbed within the film (or in adjacent layers or in the substrate) and hence cannot reach the detector. With a suitable combination of excitation and fluorescence wavelengths, different fractions of the film (or the entire film) to be measured are probed. Ideally, several combinations are used at the same time, such that several fractions of the film are probed at the same time. Such a fluorescence spectrometer is capable of determining film thickness, film overall composition, and film composition in one or several fractions of the layer, either in one or else in consecutive measurement steps.

[0049] With reference to Fig. 3, the signals of the measurement device 10 can be used by a control device such as a computer 11 to determine whether or not the output of a deposition source, or of a part of a deposition source 12, needs to be adjusted or not. Adjustment of source output can be achieved, for example, by modification of the source temperature, the power fed to the source, or the gas environment of the source. The closer to the deposition zone a measurement device can be positioned, i.e., the shorter the way a certain portion of a film needs to travel to come past the measurement device, the sooner the decision about the need for adjustment can be taken, which prevents more effectively the occurrence of faulty deposition and eventually of low production yield.

[0050] The present invention is further described in the following by referring to drawings showing exemplified embodiments.

Fig. 1 schematically shows a known CIGS solar cell in a cross-sectional view.

Fig. 2a schematically illustrates a deposition process step in a chamber using in-line processing.

Fig. 2b schematically illustrates a deposition process step in a chamber using roll-to-roll processing.

Fig. 3 schematically shows a deposition process control using a feedback signal, where film properties are measured after the deposition process is finished in the same or a separate chamber. Several deposition sources for different materials A, B and C are sketched in example (a), while in example (b) a further deposition source depositing the same material A as one of the other deposition sources is add-

Fig. 4

5

10

Fig. 5

15

20

25

Fig. 6a and 6b

30

35

Fig. 7

40

45

Fig. 8

50

Fig. 9

55

ed.

is a schematic illustration of band-gap grading concepts in CIGS or similar compounds. VBM = valence band maximum, CBM = conduction band minimum. Eg = band gap; the dot represents an electron being guided by the gradient in the CBM. (a) no grading, (b) normal grading (= back grading), (c) double grading (= back grading + front grading).

is a schematic illustration of possible deposition source arrangements for a CIGS deposition process: (a) three metals sources, (b) four metals sources. For both cases, an example for deposition-rate profiles for each element, an example for the corresponding Ga/(In+Ga) concentration-ratio profile through the film, and an example for the effect on the band-gap (Eg) profile through the film is shown: (a) back grading, (b) double grading. VBM = valence band maximum, CBM = conduction band minimum.

are schematic illustrations of possible deposition source arrangements within a deposition-source block, and of possible deposition-source block arrangements within a deposition chamber. The deposition-source blocks could also be located in individual chambers.

is a schematic illustration of a section of a deposition chamber, as seen by looking onto the plane of the substrate, where a measurement device is moved perpendicular to the traveling direction of wide substrates to an arbitrary location, allowing the control of film properties across the full width of the substrate.

is a schematic illustration similar to Fig. 7, but where the deposition sources consist of several deposition-source units.

is a schematic illustration of a section of a deposition chamber, as seen by looking parallel to the plane of the substrate: (a) after every deposition-source block a measurement device is placed, which can also move per-

pendicular to the traveling direction of the substrate (into the plane of the paper); (b) one measurement device, which can also be moved parallel to the traveling direction of the substrate, is used to measure after every deposition block.

Fig. 10a is a schematic illustration of a measurement device comprising an x-ray source and an x-ray detector.

Fig. 10b is a schematic illustration of a measurement device comprising an electron source and an x-ray detector.

Fig. 10c is a schematic illustration of a measurement device comprising an electron source, an x-ray source, and x-ray detector.

Fig. 11 is a schematic illustration of possible ways of placing a measurement device such that the substrate is located in between the deposition sources and the measurement device or parts of the latter, wherein the measurement device is partially placed behind substrate according to Fig. 11a, wherein the measurement device is completely behind the substrate according to Fig. 11b, and wherein the measurement device is behind the substrate, moving between deposition source blocks, or into deposition zone, according to Fig. 11c.

[0051] A method is disclosed that improves deposition control such that the number of installed, controllable deposition sources requiring precise control can be increased without having to increase the number of measurement devices, and such that the flexibility for placement of such deposition sources and for source arrangements is enhanced.

[0052] For example, instead of three deposition sources 12 in Fig. 5a, a fourth deposition source can be controlled (Fig. 5b). This enhanced flexibility allows to reliably deposit films (or layers) with well-defined and particularly beneficial compositional gradients (see Fig. 5). As possible consequences, higher solar cell and module conversion efficiencies can be achieved and/or the thickness of the film can be reduced without or with reduced loss in conversion efficiency. This is realizable by using a measurement device capable of determining compound-film thickness, compound-film overall composition, and compositional profile, the latter being defined as a compound-film composition as a function of a position on or in the compound film.

[0053] A further embodiment of the present invention uses a measurement device 10 comprising, for example, an x-ray source 16 and an x-ray detector 18, placed in the same housing as the detector depicted in Fig. 10a, or in different housings, for example one part identified by 22 comprising the detector above the substrate 1 and one part identified by 23 comprising the source below the substrate 1, as schematically illustrated in Fig. 11a. The x-ray source 16 may emit monochromatic or broadband x-ray radiation 17. The radiation 17 of the x-ray source 16 is used to excite atoms in all layers and in the substrate 1. The excited atoms relax by emitting fluorescent radiation 19 of discrete wavelengths. A part of this fluorescent radiation 19 is in the x-ray regime and is therein classified according to the transitions in the radiating atoms as K, L, M, etc. lines. The K lines of the fluorescent radiation 19 are those with the smallest wavelengths and usually the highest penetration depths (the lowest absorption coefficients) in a material. Typically, the absorption of K lines within a layer of about 1 μm can be neglected; hence K lines can be taken to measure the total number of atoms of a certain element in the complete film. The L lines, however, occur at higher wavelengths, where absorption within a layer is significant. The intensity of L-line radiation in a material falls exponentially due to the absorption. In a layer of about 1 μm thickness, the L-line radiation can be completely absorbed within the film such that it cannot be detected anymore. Even if the penetration depth of L-line radiation is larger than the film thickness, there will still be significantly more L-line radiation from atoms closer to the surface, due to the exponential intensity decrease with thickness. The typical penetration depth of L-line radiation from a particular element in a material varies from element to element and from material to material. However, in most cases, K-line fluorescence radiation detected outside the film by a detector will stem from atoms distributed throughout the film, while L-line fluorescence radiation will stem from atoms located closer to the surface. In this way, composition in different depths of one or several films can be measured. In particular, the measurement is sensitive to changes in the compositional profile, which is what is primarily needed for process control: Any change of the deposition process should be detectable and allow corrective action to be taken.

[0054] As an example, a CIGS film with a Ga/In compositional double grading through the film can be characterized by using the In K lines for measurement of total In content in the film (corresponding to the average In concentration) and using the In L lines for measurement of the In content in the top part of the film.

[0055] Alternatively, the same measurement could be done correspondingly with Ga lines instead of In lines, or with Ga lines in addition to the In lines.

[0056] Another embodiment uses a measurement device 10 comprising an electron source 20 and an x-ray detector, placed in the same housing as the one in Fig. 10b, or in different housings, for example one part above

the substrate 1 and one part below the substrate 1. The electrons 21 of the electron source 20 are used to excite atoms in certain parts of the film or films. The penetration depth and the excitation region and volume in a film are determined by the energy of the impinging electrons and by the material properties of the probed film. Hence, by changing the energies of the electrons 21 from the electron source 20, for example by changing the electron acceleration voltage, atoms in different depths of a film are excited. By employing an x-ray detector 18 measuring K lines only, or K and L lines, fluorescence radiation 19 from the excited atoms can be detected and hence composition in different depths of one or several films can be measured. In particular, the measurement is sensitive to changes in the compositional profile.

[0057] For example, in the case of a double-graded CIGS film, by using different electron acceleration voltages, a rough depth profile of the In/Ga concentration ratio can be established. Any changes in that profile are detectable and allow adjusting the deposition-process parameters.

[0058] Yet another embodiment uses a measurement device 10 comprising an x-ray source 16, an electron source 20, and an x-ray detector 18, placed in the same housing as in Fig. 10c or in different housings, for example one part above the substrate 1 and one part below the substrate 1. With this arrangement, the x-ray source 16 and the x-ray detector 18 can be used to measure overall composition and thickness, for example by analyzing K-line fluorescence radiation. The exciting electrons can penetrate into different depths of a film, where they excite further atoms, hence giving rise to additional contributions to the fluorescence radiation, for example, the K-line fluorescence radiation. When either the x-ray source 16 and/or the electron source 20 is switched off periodically or from time to time, then separation of the signals is possible and overall composition and thickness as well as depth profiles can be extracted from the measurements. In particular, the measurement is sensitive to changes in the compositional profile.

[0059] If during a deposition process, a control device such as a computer 11 receives signals from the measurement device 10 that are interpreted by the control device as a deviation of film thickness, film overall composition, and/or film compositional profile from pre-defined values, then the control device can take corrective action on the deposition process by feeding back a signal to the concerned deposition sources 12 (Fig. 3). The feedback signal can initiate a change or changes in material deposition rate of one or several deposition sources, or of a part or parts of one or several deposition sources. A change in material deposition rate of a source or a part thereof can be achieved, for example, by modification of the supplied heating or sputter power or by modifying the local gas environment (pressure). A fast feedback signal is advantageous in order to take corrective action on the deposition process quickly, which allows preventing effectively the occurrence of faulty deposition and eventu-

ally of low production yield. Once the corrective action has been taken, the control device can check if these actions lead to the desired results and take further corrective actions if required.

[0060] A further embodiment of the present invention is disclosed which allows the control of film properties across the full width of wide substrates, perpendicular to the traveling direction of coated or uncoated substrates (Fig. 7). Such control enables fine-tuning the material output rates of a wide deposition source over the full width of the source, not only in one or few points. This is particularly important if the relative deposition rates in different locations of a wide deposition source change with time, for example, because the source's reservoir of material to be deposited changes or because local heating/cooling or pressure characteristics change. The method furthermore allows controlling and fine-tuning deposition sources 12 consisting of at least two narrower deposition-source units 15 of similar or differing design and arranged side by side with or without gaps in between (Fig. 8), for example, two or more narrower deposition-source units, or, as another example, an array of several point sources distributed along a line, where each point source corresponds to a deposition-source unit.

[0061] A still further embodiment of the present invention is disclosed, which allows the control of the deposition sources arranged in two or more deposition-source blocks, each block consisting of the same or a different arrangement of one or several deposition sources, by using only one or only few measurement devices. This is achieved by moving each measurement device 10 not only across substrates (perpendicular to the traveling direction of the substrates), but also parallel to the traveling direction of the substrates to measure also in-between deposition source blocks 13, such as illustrated in Fig. 9b for the case of two deposition-source blocks.

[0062] Another approach would be to use measurement devices 10 after every deposition-source block 13. But because good deposition sources do not change their deposition rate characteristics quickly, it is possible to sequentially employ only one measurement device in a large number of different locations. After completion of every measurement cycle, the measurement results can be compared to the results from previous measurement cycles and corrective actions on the deposition sources can be taken, if necessary. In this way, one or only few moving measurement devices suffice for controlling all deposition sources and hence can replace a larger number of non-moveable measurement devices.

[0063] A further embodiment of the present invention is disclosed, which allows to employ a measurement device close to or even in the deposition zone, enabling a feedback signal for deposition source control with minimum delay, or even enabling real-time deposition source control by measurement of film properties in the deposition zone, while the film is still being grown.

[0064] Good protection of the measurement device from thermal radiation, e.g. stemming from hot deposition

sources, and appropriate shielding preventing material deposition on sensitive parts of the measurement device are necessary. A particularly suitable way to achieve this is to place the measurement device 10 (or parts 22, 23 thereof) behind the substrate, such that the substrate is located in-between the measurement device (or parts 22, 23 thereof) and the deposition sources, for example as illustrated in Figs. 11a and 11b. In this way, the substrate protects the measurement device from material deposition and also to some extent from thermal radiation. When the entire measurement device is placed behind the substrate, it cannot interfere with the atomic flux from the deposition sources, hence it is possible to move consecutive deposition-source blocks closer together while still measuring with the measurement device in-between (Fig. 11c), with no shadowing effects as they would occur with a measurement device placed on the front side of the substrate.

[0065] Furthermore, placing a measurement device behind the substrate has the advantage that the measurement device can be positioned very close to or even touching the substrate. Because the measurement device is on the back side of the substrate, there is no risk of scratching sensitive, as deposited films. Having the measurement device placed close to the substrate means that the detection count rate of, for example, fluorescence radiation is high, since the count rate falls off rapidly with the square of the distance between film and detector. In turn, high count rates enable to use a short measurement time and hence to employ only one measurement device in many different locations.

[0066] Still a further method is disclosed that allows correcting fluctuations in the measurement device results stemming from excitation source and/or detector drift with time, and/or from variations in source-film and/or film-detector distances. Distance variations can occur especially due to the moving substrates, especially if the substrates are flexible, and due to a certain amount of irreproducibility in measurement device placement in different locations. In order to be able to correct the count rate fluctuations, the measurement signal from underlying layers, or from the substrate, needs to be analyzed as a reference signal. However, this signal often is received together with the main measurement signal and hence does not need any additional measurement sensors. If the layer or substrate giving rise to the reference signal, the "reference layer", should happen to be inhomogeneous in thickness, it is required that, prior to the measurement of the compound film properties using the measurement device, the thickness profile of the reference layer is determined and used to correct the signal from the measurement device. The thickness profile of the reference layer can already be determined during deposition of the reference layer, for example by using a well-known quartz crystal microbalance or of optical emission spectrometry. For example, when the compound film is CIGS for solar cell applications, the reference layer can be the back contact, typically Mo, or additional layers

deposited prior to CIGS deposition or the substrate, or even a layer deposited on the back side of the substrate. If there are further layers in addition to the reference layer deposited prior to the compound film deposition, or if there are further layers and the reference signal stems from the substrate, the deposition processes of these further layers can be controlled using the same measurement device by feeding back the measurement information to the respective deposition sources. If the reference signal stems from a layer or substrate sufficiently thick, i.e. thicker than the penetration or exit length of the excitation or fluorescence radiation, then the thickness of this reference layer or substrate does not need to be known exactly, as long as it always is thick enough.

[0067] If, as the case may be, distance variations between the parts of the measurement device and the film can be neglected, the signal of the reference layer can be used to control the reference-layer-deposition process at the same time as the compound film deposition process. For example, when the compound film is CIGS for solar cell applications, the back contact can be taken as reference layer and the back contact deposition process (often Mo deposition by dc sputtering) can be controlled at the same time as the CIGS deposition process. Obviously, the time lag between deposition and measurement of the reference layer can become large, depending on the machine configuration. But if the reference layer does not need very tight control, such as Mo for solar cell applications, it can be acceptable if the reference layer characteristics deviate from the specifications for a limited period of time. Furthermore, if there is more than one layer deposited prior to the compound film deposition process, the deposition processes for all these layers can be controlled simultaneously using the same measurement device by feeding back the measurement data to the respective deposition source controllers. Long-term drift of detector and/or source can be corrected in this case of negligible distance variations by occasionally measuring the composition and thickness of a suitable, stable, inert piece of material or coating located at an accessible place where it neither can move nor be coated with, for example, the coating materials, such as Se.

Claims

1. A method for manufacturing a compound film comprising a substrate (1) and at least one additional layer (2, 3, 4, 5, 6, 7), the compound film satisfying predefined compound film properties, in particular being predefined values for compound-film thickness, compound-film overall composition and compositional profile, the latter being defined as a compound-film composition as a function of a position on or in the compound film, the method comprising the steps of:

- depositing at least three chemical elements (A, B, C) on the substrate (1) and/or on the at least one additional layer (2, 3, 4, 5, 6, 7) using deposition sources (12),

- maintaining depositing of the at least three chemical elements (A, B, C) while the substrate (1) and the deposition sources (12) are being moved relative to each other,

characterized in that

at least the chemical element A is deposited by at least two different deposition sources (12A, 12A') positioned at two different locations, so that a gradient of the compositional profile of said chemical element A is achieved through the compound film thickness.

2. The method according to claim 1, whereby the chemical element A, and the chemical element B, and the chemical element C are deposited by physical vapour deposition (PVD), in particular by thermal evaporation.
3. The method according to any of the preceding claims, used for the manufacturing of thin-film solar cells and/or modules.
4. The method according to any of the preceding claims, whereby the chemical elements A, B and C are deposited according to the deposition source sequence A-B-C-A or A-C-B-A or A-C-A-B or A-C-B-C, or A-C-B-C-A.
5. The method according to any of the preceding claims, whereby the chemical element A is Gallium (Ga), and/or the chemical element B is Copper (Cu), and/or the chemical element C is Indium (In).
6. The method according to any of the preceding claims, **characterized in that** the substrate (1) is a flexible foil, made at least in part of metal, polymer, or ceramic, and that said foil can be rolled up.
7. The method according to any of the preceding claims, **characterized in that** the deposition sources (12) are arranged in a plurality of deposition-source blocks (13).
8. The method according to claim 7, **characterized in that** the chemical elements A, B and C are deposited by at least two deposition-source blocks (13, 13'), whereby the chemical elements A, B and C are deposited by the first source block (13) according to the deposition source sequence A-B-C-A, and by the second source block (13') according to the deposition source sequence A-C-B-A or C-B-A.
9. The method according to claim 8, **characterized in**

that the chemical elements A, B and C are deposited by at least two deposition-source blocks (13, 13'), whereby the chemical elements A, B and C are deposited by the first source block (13) according to the deposition source sequence C-A-B or A-C, and by the second source block (13') according to the deposition source sequence B-C-A.

10. The method according to any of the preceding claims, **characterized in that** the compound film is a polycrystalline semiconductor compound of the form (Cu,Ag)(In,Ga,Al)(Se,S)₂, particularly the compounds Cu(In,Ga)Se₂ or Cu(In,Ga)(Se,S)₂.
11. The method according to any of the preceding claims, **characterized in that** the substrate (1) is a polyimide foil, coated by an electrically conductive layer consisting of a single material.
12. The method according to claim 11, **characterized in that** the electrically conductive layer on the foil is made of Mo.
13. The method according to any of the preceding claims, further comprising the steps of:
 - measuring the compound film properties, particularly being compound film thickness, compound-film overall composition, and compound-film composition in one or several positions of the compound film,
 - comparing the predefined values for the compound film properties to the measured compound film properties, and
 - adjusting the deposition of the at least three chemical elements (A, B, C) in case the measure compound film properties do not match the predefined compound film properties.
14. A compound film produced according to the method of any of the preceding claims.
15. A solar cell or a solar module comprising a compound film according to claim 14.




Fig. 1




Fig. 2




Fig. 3




Fig. 4




Fig. 5




Fig. 6




Fig. 7




Fig. 8




Fig. 9




Fig. 10




Fig. 11



EUROPEAN SEARCH REPORT

Application Number
EP 17 21 0307

5

10

15

20

25

30

35

40

45

50

55

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (IPC)
X	US 6 310 281 B1 (WENDT ROBERT G [US] ET AL) 30 October 2001 (2001-10-30)	1-12,14,15	INV. C23C14/06
Y	* column 25, line 23 - column 26, line 35; claims 1,4,11,13; figures 12-14 *	13	C23C14/54 C23C14/56

X	EP 1 619 728 A1 (MATSUSHITA ELECTRIC IND CO LTD [JP]) 25 January 2006 (2006-01-25)	14,15	
A	* paragraph [0042]; examples *	1-13	

Y,D	WO 2005/086238 A (SOLIBRO AB [SE]; STOLT LARS [SE]; KESSLER JOHN [FR]) 15 September 2005 (2005-09-15)	13	
	* page 6, line 12 - page 17, line 5; figures *		

			TECHNICAL FIELDS SEARCHED (IPC)
			C23C
The present search report has been drawn up for all claims			
Place of search The Hague		Date of completion of the search 13 April 2018	Examiner Patterson, Anthony
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

 1
EPO FORM 1503 03/02 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 17 21 0307

5

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

13-04-2018

10

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 6310281	B1	30-10-2001	NONE

EP 1619728	A1	25-01-2006	CN 1771610 A 10-05-2006
			EP 1619728 A1 25-01-2006
			JP WO2004090995 A1 06-07-2006
			US 2006220059 A1 05-10-2006
			WO 2004090995 A1 21-10-2004

WO 2005086238	A	15-09-2005	-----

15

20

25

30

35

40

45

50

55

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 5078804 A [0005]
- US 4162528 A [0008]
- US 6611576 B [0008]
- WO 2005086238 A [0009]
- WO 03038871 A1 [0010]
- US 2003082834 A1 [0010]
- EP 0394128 B1 [0011]

Non-patent literature cited in the description

- **MITCHELL.** *Proceedings of the 20th IEEE PV Conference*, 1988, 1384-1389 [0005]
- **JUNKER et al.** Manufacture of Thin-Film Solar Cells: Modeling and Control of Cu(InGa)Se₂ Physical Vapor Deposition onto a Moving Substrate. *Ind. Eng. Chem. Res.*, 2004, vol. 43, 566-576 [0009]
- **V. ALBERTS et al.** *Solar Energy Materials & Solar Cells*, 2000, vol. 64, 371-383 [0012]
- **I.L. EISGRUBER et al.** *Conference Record of the 28th IEEE Photovoltaic Specialists Conference*, 2000, 505-508 [0013]