

(11) **EP 3 731 320 A8**

(12) CORRECTED EUROPEAN PATENT APPLICATION

published in accordance with Art. 153(4) EPC

(15) Correction information:

Corrected version no 1 (W1 A1) Corrections, see Bibliography INID code(s) 72

(48) Corrigendum issued on: **09.06.2021 Bulletin 2021/23**

(43) Date of publication: **28.10.2020 Bulletin 2020/44**

(21) Application number: 19858626.5

(22) Date of filing: 06.06.2019

(51) Int CI.:

H01M 8/0282 (2016.01) H01M 8/0236 (2016.01) C25B 1/10 (2006.01) C25B 9/18 (2006.01) H01M 8/2428 (2016.01) H01M 8/0217 (2016.01) H01M 8/1253 (2016.01) C25B 9/10 (2006.01) H01M 8/124 (2016.01)

(86) International application number:

PCT/JP2019/022593

(87) International publication number: WO 2020/174707 (03.09.2020 Gazette 2020/36)

(84) Designated Contracting States:

AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

Designated Extension States:

BA ME KH MA MD TN

(30) Priority: **26.02.2019 JP 2019032909**

(71) Applicant: Mitsubishi Power, Ltd. Yokohama-shi, Kanagawa 220-8401 (JP) (72) Inventors:

 SUEMORI, Shigenori Chiyoda-ku, Tokyo 1008332 (JP)

 HIWATASHI, Kenichi Yokohama-shi, Kanagawa 2208401 (JP)

 YOSHIDA, Shin Yokohama-shi, Kanagawa 2208401 (JP)

(74) Representative: Hoffmann Eitle
Patent- und Rechtsanwälte PartmbB
Arabellastraße 30
81925 München (DE)

(54) FUEL CELL, FUEL CELL MODULE, POWER GENERATION SYSTEM, HIGH TEMPERATURE STEAM ELECTROLYSIS CELL, AND PRODUCTION METHODS OF THOSE

(57) It is an object to provide a single fuel cell and a high-temperature steam electrolysis cell that can prevent gas leakage. A single fuel cell (101) according to the present disclosure includes a power generation section (105), a power non-generation section (110) which does not include the power generation section (105), and an oxygen-ion-insulating gas seal film (117) arranged so as to cover the surface of the power non-generation section, and the gas seal film is configured by a structure formed by firing a material containing MTiO₃ (M: alkaline earth metal element) and metal oxide. The structure may in-

clude a first structure and a second structure which are different in composition, the first structure may include components derived from ${\rm MTiO_3}$ in larger amounts than the second structure, the second structure may include a metal element contained in the metal oxide in a larger amount than the first structure, and the area ratio of the second structure in the structure may be not less than 1% and not more than 50%.

FIG. 1

