



(12) **CORRECTED EUROPEAN PATENT SPECIFICATION**

(15) Correction information:
Corrected version no 2 (W2 B1)
Corrections, see
Description Paragraph(s) 94, 95

(48) Corrigendum issued on:
19.07.2023 Bulletin 2023/29

(45) Date of publication and mention
of the grant of the patent:
22.02.2023 Bulletin 2023/08

(21) Application number: **19713578.3**

(22) Date of filing: **27.02.2019**

(51) International Patent Classification (IPC):
C09B 62/008 ^(2006.01) **A61L 27/00** ^(2006.01)
G02C 7/04 ^(2006.01) **C09B 62/465** ^(2006.01)
C08F 220/30 ^(2006.01) **G02B 1/04** ^(2006.01)
C07D 311/78 ^(2006.01) **C08F 271/02** ^(2006.01)
C07D 335/12 ^(2006.01) **C08F 230/08** ^(2006.01)
C08F 283/12 ^(2006.01) **G02C 7/10** ^(2006.01)
C07D 311/82 ^(2006.01) **C07D 219/06** ^(2006.01)
A61L 31/14 ^(2006.01) **A61L 31/04** ^(2006.01)
A61L 27/16 ^(2006.01)

(52) Cooperative Patent Classification (CPC):
(C-Sets available)
C09B 62/465; A61L 27/00; A61L 27/16;
A61L 27/26; A61L 27/52; A61L 31/041;
A61L 31/048; A61L 31/145; C07D 219/02;
C07D 219/06; C07D 311/78; C07D 311/82;
C07D 311/90; C07D 335/12; C07D 335/20; (Cont.)

(86) International application number:
PCT/IB2019/051582

(87) International publication number:
WO 2019/166971 (06.09.2019 Gazette 2019/36)

(54) **AN OPHTHALMIC DEVICE COMPRISING POLYMERIZABLE ABSORBERS OF UV AND HIGH ENERGY VISIBLE LIGHT**

OPHTHALMISCHES GERÄT, DAS POLYMERISIERBARE ABSORBER VON UV- UND HOCHENERGIE-SICHTBAREM LICHT UMFASST

DISPOSITIF OPHTALMIQUE COMPRENANT DES ABSORBEURS POLYMERISABLES D'UV ET DE LUMIERE VISIBLE A HAUTE ENERGIE

(84) Designated Contracting States:
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB
GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO
PL PT RO RS SE SI SK SM TR

(30) Priority: **02.03.2018 US 201862637505 P**
28.06.2018 US 201862691112 P
06.02.2019 US 201916268897

(43) Date of publication of application:
06.01.2021 Bulletin 2021/01

(60) Divisional application:
23156522.7

(73) Proprietor: **Johnson & Johnson Vision Care, Inc.**
Jacksonville, FL 32256 (US)

(72) Inventors:
• **MAHADEVAN, Shivkumar**
Jacksonville, Florida 32256 (US)
• **WRIGHT, Dawn D.**
Jacksonville, Florida 32256 (US)

(74) Representative: **Carpmaels & Ransford LLP**
One Southampton Row
London WC1B 5HA (GB)

(56) References cited:
WO-A1-99/63366 WO-A1-2014/025370

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

WO-A2-2007/050395 US-A1- 2015 175 732

(52) Cooperative Patent Classification (CPC): (Cont.)
C08F 230/08; C08F 271/02; C08F 283/12;
G02B 1/04; G02B 1/043; G02C 7/04; G02C 7/10;
A61L 2430/16

C-Sets

A61L 27/16, C08L 33/00;
A61L 27/26, C08L 33/00;
A61L 27/26, C08L 83/04;
A61L 31/041, C08L 33/00;
A61L 31/041, C08L 83/04;
A61L 31/048, C08L 33/00;
C08F 230/08, C08F 230/08, C08F 220/54,
C08F 220/20, C08F 222/102, C08F 220/365;
C08F 230/08, C08F 230/08, C08F 220/54,
C08F 220/20, C08F 222/102, C08F 220/387;
C08F 230/08, C08F 230/08, C08F 220/54,
C08F 220/20, C08F 222/102, C08F 220/387,
C08F 220/365;
C08F 271/02, C08F 230/08, C08F 220/56,
C08F 220/20, C08F 222/102;
C08F 283/12, C08F 230/08, C08F 220/56,
C08F 220/20, C08F 222/102;
C08F 283/12, C08F 230/08, C08F 220/56,
C08F 220/20, C08F 222/102, C08F 212/22;
G02B 1/043, C08K 5/0041

DescriptionField of the Invention

5 **[0001]** The invention relates to UV and high energy visible light absorbers. More particularly, the invention relates to compounds with polymerizable functionality that absorb various wavelengths of UV and/or high energy visible light, and yet are visibly transparent when incorporated in an article. Thus, the compounds may be used in polymeric articles, including biomedical devices, such as ophthalmic devices.

10 Background of the Invention

[0002] High energy light from the sun, such as UV light and high-energy visible light, is known to be responsible for cellular damage. While most of the radiation below 280 nm in wavelength is absorbed by the earth's atmosphere, photons possessing wavelengths ranging between 280 and 400 nm have been associated with several ocular disorders including
15 corneal degenerative changes, and age-related cataract and macular degeneration. (See Statement on Ocular Ultraviolet Radiation Hazards in Sunlight, American Optometric Association, November 10, 1993). The human cornea absorbs some radiation up to 320 nm in wavelength (30% transmission) (Doutch, J.J., Quantock, A.J., Joyce, N.C., Meek, K.M., Biophys. J, 2012, 102, 1258-1264), but is inefficient in protecting the back of the eye from radiation ranging from 320 to 400 nm in wavelength.

20 **[0003]** Contact lens standards define the upper UV radiation wavelength at 380 nm. The current Class I UV absorbing criteria defined by the American Optometric Association require > 99% of the radiation between 280 and 315 nm (UV B) and > 90% of the 316 to 380 nm (UV A) radiation to be absorbed by the contact lens. While the criteria effectively address protection of the cornea (< 1% UV B transmittance), there is little attention paid to the lower energy UV radiation (> 380 < 400 nm) associated with retinal damage (Ham, W.T, Mueller, H. A., Sliney, D. H. Nature 1976; 260(5547):153-5)
25 or to high energy visible radiation.

[0004] High energy-visible (HEV) radiation may cause visual discomfort or circadian rhythm disruption. For example, computer and electronic device screens, flat screen televisions, energy efficient lights, and LED lights are known to generate HEV light. Prolonged exposure to such sources of HEV light may cause eye strain. Viewing HEV light emitting devices at night is also postulated to disrupt the natural circadian rhythm leading, for example, to inadequate sleep.

30 **[0005]** Absorption of high energy light radiation before it reaches the eye continues to be a desirable goal in the ophthalmics field. However, the extent to which a particular wavelength range is absorbed is also important. For instance, in the UV A and UV B ranges, it may be desirable to absorb as much radiation as possible. On the other hand, since HEV light forms a part of the visible spectrum, complete absorption of HEV light may negatively affect vision. With HEV light, therefore, partial absorption may be more desirable.

35 **[0006]** There is a need for materials that provide targeted absorption of undesirable wavelengths of high energy radiation, and that are processable into functional products. Compounds that absorb or attenuate high energy radiation, when used in ophthalmic devices, can help protect the cornea, as well as the interior cells in the ocular environment, from degradation, strain, and/or circadian rhythm disruption.

[0007] US 2015/175732 A1 describes an optical polymeric material that is alleged to substantially block the transmission of ultraviolet light as well as selected portion of violet light.
40

[0008] WO 2007/050395 A2 describes a radiation-absorbing polymeric material comprising units of a polymerizable UV-absorbing compound, a violet light-absorbing compound, and a monomer, which is alleged to be capable of absorbing UV radiation, at least about 90 percent of light having wavelength of 425 nm, less than about 50 percent of light having wavelength of 450 nm, and less than about 30 percent of light having wavelength of 475 nm. Ophthalmic devices, such
45 as contact lenses, corneal rings, corneal inlays, keratoprotheses, and intraocular lenses, are made from such polymeric material.

[0009] WO 99/63366 A1 describes a method for preparing a lens having UV-absorbing properties involving charging to a mold a monomer mixture comprising lens-forming monomers and an essentially non-UV-absorbing compound; exposing the monomer mixture in the mold to a light source including ultraviolet light to cure the monomer mixture and
50 form the lens, whereby the non-UV-absorbing compound converts to a UV-absorbing agent.


Summary of the Invention

55 **[0010]** The invention relates to high energy light absorbing compounds that absorb UV and/or high energy visible (HEV) light while substantially transmitting (e.g., greater than 80% transmission) at wavelengths longer than about 450 nm. The compounds are therefore effective at providing targeted absorption of high energy light, such as UV (UVA and UVB), low energy UV light (385 nm to 400 nm), or HEV light (e.g., 400 to 450 nm). The invention is defined by the claims.

[0011] The compounds are also polymerizable and are generally compatible with other raw materials, as well as the

polymerization and processing conditions that are typically used for making ophthalmic devices such as soft contact lenses. The compounds can therefore be readily covalently incorporated into the final product without the need for significant modification of existing manufacturing processes and equipment.

[0012] Compounds of formula I are described herein:



Formula I

wherein:

m and n are independently 0, 1, 2, 3, or 4;

T is a bond, O, or NR;

X is O, S, NR, SO, or SO₂;

Y is a linking group;

P_g is a polymerizable group;

R at each occurrence is independently H, C₁-C₆ alkyl, cycloalkyl, heterocycloalkyl, aryl, heteroaryl, or Y-P_g;

R¹ and R², when present, are independently at each occurrence C₁-C₆ alkyl, C₁-C₆ alkoxy, C₁-C₆ thioalkyl, C₃-C₇ cycloalkyl, aryl, halo, hydroxy, amino, NR³R⁴, or benzyl, wherein R³ and R⁴ are independently H or C₁-C₆ alkyl, or two adjacent R¹ or R² groups, together with the carbon atoms to which they are attached, combine to form a cycloalkyl or aryl ring; and


EWG is an electron withdrawing group, such as cyano, amide, ester, keto, or aldehyde (preferably cyano).

[0013] In an aspect, the invention provides an ophthalmic device that is a free radical reaction product of a reactive mixture comprising: one or more monomers suitable for making the ophthalmic device; and a polymerizable high energy light absorbing compound comprising a compound of formula I as described herein.

[0014] In a further aspect, the invention provides a method for making an ophthalmic device. The method comprises: (a) providing a reactive mixture containing a compound of formula I as described herein, one or more device forming monomers, and a radical initiator; and (b) polymerizing the reactive mixture to form the ophthalmic device.

[0015] The ophthalmic device of the invention preferably provides an ophthalmic device that is a reaction product of a reactive mixture comprising: a polymerizable high energy light absorbing compound; and one or more monomers suitable for making an ophthalmic device, wherein the ophthalmic device transmits: 45 percent or less of light having a wavelength of 280 to 399 nm; from 1 percent to 70 percent of light having a wavelength of 400 to 409 nm; and at least 80 percent of light having a wavelength of 450 to 800 nm.

[0016] In a yet further aspect, the disclosure provides an ophthalmic device that is a polymerized reaction product of a reactive mixture comprising one or more reactive components (such as a hydrophilic component and a silicone containing compound), wherein the polymerized reaction product contains, as covalently bound substituents, one or more chromophores of formula IV:



Formula IV

wherein m, n, X, R¹, R², R⁵, and EWG are as defined herein.

Brief Description of Drawings

[0017]

FIG. 1 shows UV-VIS Transmission Spectra of 0.2 mM solutions of exemplary Compounds (B), (C), and (E) in methanol.

FIG. 2 shows UV-VIS Transmission Spectra of 0.2 mM solutions of Compounds (G), (H), and (J) in methanol and of Compound (L) in dichloromethane

FIG. 3 shows UV-VIS Transmission Spectrum of exemplary Silicone Hydrogel Contact Lenses 9A and 9B.

FIG. 4 shows UV-VIS Transmission Spectrum of exemplary Silicone Hydrogel Contact Lenses 9A and 9C.

FIG. 5 shows UV-VIS Transmission Spectrum of exemplary Silicone Hydrogel Contact Lenses 9A and 9D.

FIG. 6 shows UV-VIS Transmission Spectrum of exemplary Silicone Hydrogel Contact Lenses 10A and 10B.

FIG. 7 shows UV-VIS Transmission Spectrum of exemplary Silicone Hydrogel Contact Lenses 10A and 10C.

FIG. 8 shows UV-VIS Transmission Spectrum of exemplary Silicone Hydrogel Contact Lenses 10A and 10B.

FIG. 9 shows UV-VIS Transmission Spectra of Silicone Hydrogel Contact Lenses (11A) comprising Compound (B) after exposure to direct sunlight

FIG. 10 shows UV-VIS Transmission Spectra of Silicone Hydrogel Contact Lenses (11B) comprising Compound (B) after exposure to indoor lighting

Detailed Description of the Invention

[0018] It is to be understood that the invention is not limited to the details of construction or process steps set forth in the following description. The invention is capable of other embodiments and of being practiced or being carried out in various ways using the teaching herein.

[0019] As noted above, in one aspect, the invention provides UV/HEV absorbing compounds. The compounds contain polymerizable functionality. It has been discovered that ophthalmic devices that absorb substantial amounts of UV light as well as some amounts of HEV light can be readily prepared as described herein.

[0020] It has also been discovered that light absorbing compounds can be selected to provide targeted absorption of UV and/or high energy visible light (e.g., increased UV absorption and less HEV absorption, or increased HEV absorption, etc.). Such targeting may be achieved, for example, with compounds of formula I, which contain a hetero tricyclic core chromophore. For instance, as described in more detail below, compounds of formula I where the heteroatom (X in formula I) is sulfur, may absorb HEV light. On the other hand, compounds of formula I where the heteroatom is oxygen (X is O) may absorb less HEV light, but more UV light. Thus, the compounds may be used to absorb select regions of UV and/or HEV light or they may be mixed together or with other absorbing compounds to provide broad spectrum protection (e.g., UV and HEV light). Advantageously, the compounds exhibit a transmission cut-off (e.g., they absorb 20 percent or less) at visible wavelengths of 450 nm or longer.

[0021] It has further been discovered that compounds of formula I are substantially photostable, meaning that the compounds, when incorporated in an ophthalmic device, do not undergo significant degradation over time when exposed to lighting, such as indoor or outdoor lighting. Such photostability can be determined by measuring the UV/Vis transmission spectrum of the ophthalmic device over a test period, such as 21 weeks. Significant changes in the spectrum over the test period are indicative of a lack of photostability. By way of example, ophthalmic devices (such as contact lenses) containing compounds of the invention, when exposed to indoor office lighting over a 21 week period at room temperature, exhibit 5 % or less, preferable 2 % or less, more preferably 0.5 % or less, even more preferably 0.4 % or less of change in their average transmission over a wavelength range of 380 to 700 nm. By way of further example, ophthalmic devices (such as contact lenses) containing compounds of the invention, when exposed to indoor office lighting over a 21 week period at room temperature, exhibit 5 % or less, preferable 2 % or less, more preferably 1 % or less, even more preferably 0.7 % or less of change in their average transmission over a wavelength range of 400 to 500 nm. Such changes may be calculated as the absolute value of the difference between the average transmission (over the indicated wavelength range) at time 21 weeks and at time zero.

[0022] Thus, compounds of the invention may successfully absorb UV (UVA, UVB), and/or HEV, while transmitting in the visible spectrum. The compounds are suitable for incorporation in a variety of products, including biomedical devices and ophthalmic devices.

[0023] With respect to the terms used in this disclosure, the following definitions are provided.

[0024] Unless defined otherwise, all technical and scientific terms used herein have the same meaning as commonly understood by one of ordinary skill in the art to which the invention belongs. The polymer definitions are consistent with those disclosed in the Compendium of Polymer Terminology and Nomenclature, IUPAC Recommendations 2008, edited

by: Richard G. Jones, Jaroslav Kahovec, Robert Stepto, Edward S. Wilks, Michael Hess, Tatsuki Kitayama, and W. Val Metanowski.

[0025] As used herein, the term "(meth)" designates optional methyl substitution. Thus, a term such as "(meth)acrylates" denotes both methacrylates and acrylates.

[0026] Wherever chemical structures are given, it should be appreciated that alternatives disclosed for the substituents on the structure may be combined in any combination. Thus, if a structure contained substituents R* and R**, each of which contained three lists of potential groups, 9 combinations are disclosed. The same applies for combinations of properties.

[0027] When a subscript, such as "n" in the generic formula $[***]_n$, is used to depict the number of repeating units in a polymer's chemical formula, the formula should be interpreted to represent the number average molecular weight of the macromolecule.

[0028] The term "individual" includes humans and vertebrates.

[0029] The term "biomedical device" refers to any article that is designed to be used while either in or on mammalian tissues or fluids, and preferably in or on human tissue or fluids. Examples of these devices include but are not limited to wound dressings, sealants, tissue fillers, drug delivery systems, coatings, adhesion prevention barriers, catheters, implants, stents, and ophthalmic devices such as intraocular lenses and contact lenses. The biomedical devices may be ophthalmic devices, particularly contact lenses, most particularly contact lenses made from silicone hydrogels or conventional hydrogels.

[0030] The term "ocular surface" includes the surface and glandular epithelia of the cornea, conjunctiva, lacrimal gland, accessory lacrimal glands, nasolacrimal duct and meibomian gland, and their apical and basal matrices, puncta and adjacent or related structures, including eyelids linked as a functional system by both continuity of epithelia, by innervation, and the endocrine and immune systems.

[0031] The term "ophthalmic device" refers to any device which resides in or on the eye or any part of the eye, including the ocular surface. These devices can provide optical correction, cosmetic enhancement, vision enhancement, therapeutic benefit (for example as bandages) or delivery of active components such as pharmaceutical and nutraceutical components, or a combination of any of the foregoing. Examples of ophthalmic devices include but are not limited to lenses, optical and ocular inserts, including but not limited to punctal plugs, and the like. "Lenses" include soft contact lenses, hard contact lenses, hybrid contact lenses, intraocular lenses, and overlay lenses. The ophthalmic device may comprise a contact lens.

[0032] The term "contact lens" refers to an ophthalmic device that can be placed on the cornea of an individual's eye. The contact lens may provide corrective, cosmetic, or therapeutic benefit, including wound healing, the delivery of drugs or nutraceuticals, diagnostic evaluation or monitoring, ultraviolet light absorbing, visible light or glare reduction, or any combination thereof. A contact lens can be of any appropriate material known in the art and can be a soft lens, a hard lens, or a hybrid lens containing at least two distinct portions with different physical, mechanical, or optical properties, such as modulus, water content, light transmission, or combinations thereof.

[0033] The biomedical devices, ophthalmic devices, and lenses of the present invention may be comprised of silicone hydrogels or conventional hydrogels. Silicone hydrogels typically contain at least one hydrophilic monomer and at least one silicone-containing component that are covalently bound to one another in the cured device.

[0034] "Target macromolecule" means the macromolecule being synthesized from the reactive monomer mixture comprising monomers, macromers, prepolymers, cross-linkers, initiators, additives, diluents, and the like.

[0035] The term "polymerizable compound" means a compound containing one or more polymerizable groups. The term encompasses, for instance, monomers, macromers, oligomers, prepolymers, cross-linkers, and the like.

[0036] "Polymerizable groups" are groups that can undergo chain growth polymerization, such as free radical and/or cationic polymerization, for example a carbon-carbon double bond which can polymerize when subjected to radical polymerization initiation conditions. Non-limiting examples of free radical polymerizable groups include (meth)acrylates, styrenes, vinyl ethers, (meth)acrylamides, *N*-vinyl lactams, *N*-vinylamides, *O*-vinylcarbamates, *O*-vinylcarbonates, and other vinyl groups. Preferably, the free radical polymerizable groups comprise (meth)acrylate, (meth)acrylamide, *N*-vinyl lactam, *N*-vinylamide, and styryl functional groups, and mixtures of any of the foregoing. More preferably, the free radical polymerizable groups comprise (meth)acrylates, (meth)acrylamides, and mixtures thereof. The polymerizable group may be unsubstituted or substituted. For instance, the nitrogen atom in (meth)acrylamide may be bonded to a hydrogen, or the hydrogen may be replaced with alkyl or cycloalkyl (which themselves may be further substituted).

[0037] Any type of free radical polymerization may be used including but not limited to bulk, solution, suspension, and emulsion as well as any of the controlled radical polymerization methods such as stable free radical polymerization, nitroxide-mediated living polymerization, atom transfer radical polymerization, reversible addition fragmentation chain transfer polymerization, organotellurium mediated living radical polymerization, and the like.

[0038] A "monomer" is a mono-functional molecule which can undergo chain growth polymerization, and in particular, free radical polymerization, thereby creating a repeating unit in the chemical structure of the target macromolecule. Some monomers have di-functional impurities that can act as cross-linking agents. A "hydrophilic monomer" is also a

monomer which yields a clear single phase solution when mixed with deionized water at 25°C at a concentration of 5 weight percent. A "hydrophilic component" is a monomer, macromer, prepolymer, initiator, cross-linker, additive, or polymer which yields a clear single phase solution when mixed with deionized water at 25°C at a concentration of 5 weight percent. A "hydrophobic component" is a monomer, macromer, prepolymer, initiator, cross-linker, additive, or polymer which is slightly soluble or insoluble in deionized water at 25°C.

[0039] A "macromolecule" is an organic compound having a number average molecular weight of greater than 1500, and may be reactive or non-reactive.

[0040] A "macromonomer" or "macromer" is a macromolecule that has one group that can undergo chain growth polymerization, and in particular, free radical polymerization, thereby creating a repeating unit in the chemical structure of the target macromolecule. Typically, the chemical structure of the macromer is different than the chemical structure of the target macromolecule, that is, the repeating unit of the macromer's pendent group is different than the repeating unit of the target macromolecule or its mainchain. The difference between a monomer and a macromer is merely one of chemical structure, molecular weight, and molecular weight distribution of the pendent group. As a result, and as used herein, the patent literature occasionally defines monomers as polymerizable compounds having relatively low molecular weights of about 1,500 Daltons or less, which inherently includes some macromers. In particular, monomethacryloxypropyl terminated mono-n-butyl terminated polydimethylsiloxane (molecular weight = 500-1500 g/mol) (mPDMS) and mono-(2-hydroxy-3-methacryloxypropyl)-propyl ether terminated mono-n-butyl terminated polydimethylsiloxane (molecular weight = 500-1500 g/mol) (OH-mPDMS) may be referred to as monomers or macromers. Furthermore, the patent literature occasionally defines macromers as having one or more polymerizable groups, essentially broadening the common definition of macromer to include prepolymers. As a result and as used herein, di-functional and multi-functional macromers, prepolymers, and crosslinkers may be used interchangeably.

[0041] A "silicone-containing component" is a monomer, macromer, prepolymer, cross-linker, initiator, additive, or polymer in the reactive mixture with at least one silicon-oxygen bond, typically in the form of siloxy groups, siloxane groups, carbosiloxane groups, and mixtures thereof.

[0042] Examples of silicone-containing components which are useful in this invention may be found in U.S. Patent Nos. 3,808,178, 4,120,570, 4,136,250, 4,153,641, 4,740,533, 5,034,461, 5,070,215, 5,244,981, 5,314,960, 5,331,067, 5,371,147, 5,760,100, 5,849,811, 5,962,548, 5,965,631, 5,998,498, 6,367,929, 6,822,016, 6,943,203, 6,951,894, 7,052,131, 7,247,692, 7,396,890, 7,461,937, 7,468,398, 7,538,146, 7,553,880, 7,572,841, 7,666,921, 7,691,916, 7,786,185, 7,825,170, 7,915,323, 7,994,356, 8,022,158, 8,163,206, 8,273,802, 8,399,538, 8,415,404, 8,420,711, 8,450,387, 8,487,058, 8,568,626, 8,937,110, 8,937,111, 8,940,812, 8,980,972, 9,056,878, 9,125,808, 9,140,825, 9,156,934, 9,170,349, 9,217,813, 9,244,196, 9,244,197, 9,260,544, 9,297,928, 9,297,929, and European Patent No. 080539.

[0043] A "polymer" is a target macromolecule composed of the repeating units of the monomers used during polymerization.

[0044] A "homopolymer" is a polymer made from one monomer; a "copolymer" is a polymer made from two or more monomers; a "terpolymer" is a polymer made from three monomers. A "block copolymer" is composed of compositionally different blocks or segments. Diblock copolymers have two blocks. Triblock copolymers have three blocks. "Comb or graft copolymers" are made from at least one macromer.

[0045] A "repeating unit" is the smallest group of atoms in a polymer that corresponds to the polymerization of a specific monomer or macromer.

[0046] An "initiator" is a molecule that can decompose into radicals which can subsequently react with a monomer to initiate a free radical polymerization reaction. A thermal initiator decomposes at a certain rate depending on the temperature; typical examples are azo compounds such as 1,1'-azobisisobutyronitrile and 4,4'-azobis(4-cyanovaleric acid), peroxides such as benzoyl peroxide, tert-butyl peroxide, tert-butyl hydroperoxide, tert-butyl peroxybenzoate, dicumyl peroxide, and lauroyl peroxide, peracids such as peracetic acid and potassium persulfate as well as various redox systems. A photo-initiator decomposes by a photochemical process; typical examples are derivatives of benzil, benzoin, acetophenone, benzophenone, camphorquinone, and mixtures thereof as well as various monoacyl and bisacyl phosphine oxides and combinations thereof.

[0047] A "cross-linking agent" is a di-functional or multi-functional monomer or macromer which can undergo free radical polymerization at two or more locations on the molecule, thereby creating branch points and a polymeric network. Common examples are ethylene glycol dimethacrylate, tetraethylene glycol dimethacrylate, trimethylolpropane trimethacrylate, methylene bisacrylamide, triallyl cyanurate, and the like.

[0048] A "prepolymer" is a reaction product of monomers which contains remaining polymerizable groups capable of undergoing further reaction to form a polymer.

[0049] A "polymeric network" is a cross-linked macromolecule that can swell but cannot dissolve in solvents. "Hydrogels" are polymeric networks that swell in water or aqueous solutions, typically absorbing at least 10 weight percent water. "Silicone hydrogels" are hydrogels that are made from at least one silicone-containing component with at least one hydrophilic component. Hydrophilic components may also include non-reactive polymers.

[0050] "Conventional hydrogels" refer to polymeric networks made from components without any siloxy, siloxane or carbosiloxane groups. Conventional hydrogels are prepared from reactive mixtures comprising hydrophilic monomers. Examples include 2-hydroxyethyl methacrylate ("HEMA"), N-vinyl pyrrolidone ("NVP"), N, N-dimethylacrylamide ("DMA") or vinyl acetate. U.S. Patent Nos. 4,436,887, 4,495,313, 4,889,664, 5,006,622, 5,039,459, 5,236,969, 5,270,418, 5,298,533, 5,824,719, 6,420,453, 6,423,761, 6,767,979, 7,934,830, 8,138,290, and 8,389,597 disclose the formation of conventional hydrogels. Commercially available conventional hydrogels include, but are not limited to, etafilcon, genfilcon, hilaafilcon, lenefilcon, nesofilcon, omafilcon, polymacon, and vifilcon, including all of their variants.

[0051] "Silicone hydrogels" refer to polymeric networks made from at least one hydrophilic component and at least one silicone-containing component. Examples of silicone hydrogels include aquafilcon, asmoafilcon, balafilcon, comfilcon, delefilcon, enfilcon, fanfilcon, formofilcon, galyfilcon, lotrafilcon, naraafilcon, riofilcon, samfilcon, senofilcon, somofilcon, and stenfilcon, including all of their variants, as well as silicone hydrogels as prepared in US Patent Nos. 4,659,782, 4,659,783, 5,244,981, 5,314,960, 5,331,067, 5,371,147, 5,998,498, 6,087,415, 5,760,100, 5,776,999, 5,789,461, 5,849,811, 5,965,631, 6,367,929, 6,822,016, 6,867,245, 6,943,203, 7,247,692, 7,249,848, 7,553,880, 7,666,921, 7,786,185, 7,956,131, 8,022,158, 8,273,802, 8,399,538, 8,470,906, 8,450,387, 8,487,058, 8,507,577, 8,637,621, 8,703,891, 8,937,110, 8,937,111, 8,940,812, 9,056,878, 9,057,821, 9,125,808, 9,140,825, 9,156,934, 9,170,349, 9,244,196, 9,244,197, 9,260,544, 9,297,928, 9,297,929 as well as WO 03/22321, WO 2008/061992, and US 2010/0048847.

[0052] An "interpenetrating polymeric network" comprises two or more networks which are at least partially interlaced on the molecular scale but not covalently bonded to each other and which cannot be separated without breaking chemical bonds. A "semi-interpenetrating polymeric network" comprises one or more networks and one or more polymers characterized by some mixing on the molecular level between at least one network and at least one polymer. A mixture of different polymers is a "polymer blend." A semi-interpenetrating network is technically a polymer blend, but in some cases, the polymers are so entangled that they cannot be readily removed.

[0053] The terms "reactive mixture" and "reactive monomer mixture" refer to the mixture of components (both reactive and non-reactive) which are mixed together and, when subjected to polymerization conditions, form the conventional or silicone hydrogels of the present invention as well as biomedical devices, ophthalmic devices, and contact lenses made therefrom. The reactive monomer mixture may comprise reactive components such as the monomers, macromers, prepolymers, cross-linkers, and initiators, additives such as wetting agents, polymers, dyes, light absorbing compounds such as UV absorbers, pigments, dyes and photochromic compounds, any of which may be reactive or non-reactive but are capable of being retained within the resulting biomedical device, as well as pharmaceutical and nutraceutical compounds, and any diluents. It will be appreciated that a wide range of additives may be added based upon the biomedical device which is made and its intended use. Concentrations of components of the reactive mixture are expressed as weight percentages of all components in the reactive mixture, excluding diluent. When diluents are used, their concentrations are expressed as weight percentages based upon the amount of all components in the reactive mixture and the diluent.

[0054] "Reactive components" are the components in the reactive mixture which become part of the chemical structure of the polymeric network of the resulting hydrogel by covalent bonding, hydrogen bonding, electrostatic interactions, the formation of interpenetrating polymeric networks, or any other means.

[0055] The term "silicone hydrogel contact lens" refers to a hydrogel contact lens that is made from at least one silicone-containing compound. Silicone hydrogel contact lenses generally have increased oxygen permeability compared to conventional hydrogels. Silicone hydrogel contact lenses use both their water and polymer content to transmit oxygen to the eye.

[0056] The term "multi-functional" refers to a component having two or more polymerizable groups. The term "mono-functional" refers to a component having one polymerizable group.

[0057] The terms "halogen" or "halo" indicate fluorine, chlorine, bromine, and iodine.

[0058] "Alkyl" refers to an optionally substituted linear or branched alkyl group containing the indicated number of carbon atoms. If no number is indicated, then alkyl (including any optional substituents on alkyl) may contain 1 to 16 carbon atoms. Preferably, the alkyl group contains 1 to 10 carbon atoms, alternatively 1 to 8 carbon atoms, alternatively 1 to 6 carbon atoms, or alternatively 1 to 4 carbon atoms. Examples of alkyl include methyl, ethyl, propyl, isopropyl, butyl, iso-, sec- and tert-butyl, pentyl, hexyl, heptyl, 3-ethylbutyl, and the like. Examples of substituents on alkyl include 1, 2, or 3 groups independently selected from hydroxy, amino, amido, oxa, carboxy, alkyl carboxy, carbonyl, alkoxy, thioalkyl, carbamate, carbonate, halogen, phenyl, benzyl, and combinations thereof. "Alkylene" means a divalent alkyl group, such as $-CH_2-$, $-CH_2CH_2-$, $-CH_2CH_2CH_2-$, $-CH_2CH(CH_3)CH_2-$, and $-CH_2CH_2CH_2CH_2-$.

[0059] "Haloalkyl" refers to an alkyl group as defined above substituted with one or more halogen atoms, where each halogen is independently F, Cl, Br or I. A preferred halogen is F. Preferred haloalkyl groups contain 1-6 carbons, more preferably 1-4 carbons, and still more preferably 1-2 carbons. "Haloalkyl" includes perhaloalkyl groups, such as $-CF_3-$ or $-CF_2CF_3-$. "Haloalkylene" means a divalent haloalkyl group, such as $-CH_2CF_2-$.

[0060] "Cycloalkyl" refers to an optionally substituted cyclic hydrocarbon containing the indicated number of ring carbon

atoms. If no number is indicated, then cycloalkyl may contain 3 to 12 ring carbon atoms. Preferred are C₃-C₈ cycloalkyl groups, C₃-C₇ cycloalkyl, more preferably C₄-C₇ cycloalkyl, and still more preferably C₅-C₆ cycloalkyl. Examples of cycloalkyl include cyclopropyl, cyclobutyl, cyclopentyl, cyclohexyl, cycloheptyl and cyclooctyl. Examples of substituents on cycloalkyl include 1, 2, or 3 groups independently selected from alkyl, hydroxy, amino, amido, oxa, carbonyl, alkoxy, thioalkyl, amido, carbamate, carbonate, halo, phenyl, benzyl, and combinations thereof. "Cycloalkylene" means a divalent cycloalkyl group, such as 1,2-cyclohexylene, 1,3- cyclohexylene, or 1,4- cyclohexylene.

[0061] "Heterocycloalkyl" refers to a cycloalkyl ring or ring system as defined above in which at least one ring carbon has been replaced with a heteroatom selected from nitrogen, oxygen, and sulfur. The heterocycloalkyl ring is optionally fused to or otherwise attached to other heterocycloalkyl rings and/or non-aromatic hydrocarbon rings and/or phenyl rings. Preferred heterocycloalkyl groups have from 5 to 7 members. More preferred heterocycloalkyl groups have 5 or 6 members. Heterocycloalkylene means a divalent heterocycloalkyl group.

[0062] "Aryl" refers to an optionally substituted aromatic hydrocarbon ring system containing at least one aromatic ring. The aryl group contains the indicated number of ring carbon atoms. If no number is indicated, then aryl may contain 6 to 14 ring carbon atoms. The aromatic ring may optionally be fused or otherwise attached to other aromatic hydrocarbon rings or non-aromatic hydrocarbon rings. Examples of aryl groups include phenyl, naphthyl, and biphenyl. Preferred examples of aryl groups include phenyl. Examples of substituents on aryl include 1, 2, or 3 groups independently selected from alkyl, hydroxy, amino, amido, oxa, carboxy, alkyl carboxy, carbonyl, alkoxy, thioalkyl, carbamate, carbonate, halo, phenyl, benzyl, and combinations thereof. "Arylene" means a divalent aryl group, for example 1,2-phenylene, 1,3-phenylene, or 1,4-phenylene.

[0063] "Heteroaryl" refers to an aryl ring or ring system, as defined above, in which at least one ring carbon atom has been replaced with a heteroatom selected from nitrogen, oxygen, and sulfur. The heteroaryl ring may be fused or otherwise attached to one or more heteroaryl rings, aromatic or nonaromatic hydrocarbon rings or heterocycloalkyl rings. Examples of heteroaryl groups include pyridyl, furyl, and thienyl. "Heteroarylene" means a divalent heteroaryl group.

[0064] "Alkoxy" refers to an alkyl group attached to the parent molecular moiety through an oxygen bridge. Examples of alkoxy groups include, for instance, methoxy, ethoxy, propoxy and isopropoxy. "Thioalkyl" means an alkyl group attached to the parent molecule through a sulfur bridge. Examples of thioalkyl groups include, for instance, methylthio, ethylthio, n-propylthio and iso-propylthio. "Aryloxy" refers to an aryl group attached to a parent molecular moiety through an oxygen bridge. Examples include phenoxy. "Cyclic alkoxy" means a cycloalkyl group attached to the parent moiety through an oxygen bridge.

[0065] "Alkylamine" refers to an alkyl group attached to the parent molecular moiety through an -NH bridge. Alkylamine means a divalent alkylamine group, such as -CH₂CH₂NH-.

[0066] "Siloxanyl" refers to a structure having at least one Si-O-Si bond. Thus, for example, siloxanyl group means a group having at least one Si-O-Si group (i.e. a siloxane group), and siloxanyl compound means a compound having at least one Si-O-Si group. "Siloxanyl" encompasses monomeric (e.g., Si-O-Si) as well as oligomeric/polymeric structures (e.g., -[Si-O]_n-, where n is 2 or more). Each silicon atom in the siloxanyl group is substituted with independently selected R^A groups (where R^A is as defined in formula A options (b)-(i)) to complete their valence.

[0067] "Silyl" refers to a structure of formula R₃Si- and "siloxyl" refers to a structure of formula R₃Si-O-, where each R in silyl or siloxyl is independently selected from trimethylsiloxy, C₁-C₈ alkyl (preferably C₁-C₃ alkyl, more preferably ethyl or methyl), and C₃-C₈ cycloalkyl.

[0068] "Alkyleneoxy" refers to groups of the general formula -(alkylene-O)_p- or -(O-alkylene)_p-, wherein alkylene is as defined above, and p is from 1 to 200, or from 1 to 100, or from 1 to 50, or from 1 to 25, or from 1 to 20, or from 1 to 10, wherein each alkylene is independently optionally substituted with one or more groups independently selected from hydroxyl, halo (e.g., fluoro), amino, amido, ether, carbonyl, carboxyl, and combinations thereof. If p is greater than 1, then each alkylene may be the same or different and the alkyleneoxy may be in block or random configuration. When alkyleneoxy forms a terminal group in a molecule, the terminal end of the alkyleneoxy may, for instance, be a hydroxy or alkoxy (e.g., HO-[CH₂CH₂O]_p- or CH₃O-[CH₂CH₂O]_p-). Examples of alkyleneoxy include polyethyleneoxy, polypropyleneoxy, polybutyleneoxy, and poly(ethyleneoxy-co-propyleneoxy).

[0069] "Oxaalkylene" refers to an alkylene group as defined above where one or more non-adjacent CH₂ groups have been substituted with an oxygen atom, such as -CH₂CH₂OCH(CH₃)CH₂-. "Thiaalkylene" refers to an alkylene group as defined above where one or more non-adjacent CH₂ groups have been substituted with a sulfur atom, such as -CH₂CH₂SCH(CH₃)CH₂-.

[0070] The term "linking group" refers to a moiety that links a polymerizable group to the parent molecule. The linking group may be any moiety that is compatible with the compound of which it is a part, and that does not undesirably interfere with the polymerization of the compound, is stable under the polymerization conditions as well as the conditions for the processing and storage of the final product. For instance, the linking group may be a bond, or it may comprise one or more alkylene, haloalkylene, amide, amine, alkylamine, carbamate, ester (-CO₂-), arylene, heteroarylene, cycloalkylene, heterocycloalkylene, alkyleneoxy, oxaalkylene, thiaalkylene, haloalkyleneoxy (alkyleneoxy substituted with one or more halo groups, e.g., -OCF₂-, -OCF₂CF₂-, -OCF₂CH₂-), siloxanyl, alkylensiloxanyl, or combinations

thereof. The linking group may optionally be substituted with 1 or more substituent groups. Suitable substituent groups may include those independently selected from alkyl, halo (e.g., fluoro), hydroxyl, HO-alkyleneoxy, MeO-alkyleneoxy, siloxanyl, siloxy, siloxy-alkyleneoxy-, siloxy-alkylene-alkyleneoxy- (where more than one alkyleneoxy groups may be present and wherein each methylene in alkylene and alkyleneoxy is independently optionally substituted with hydroxyl), ether, amine, carbonyl, carbamate, and combinations thereof. The linking group may also be substituted with a polymerizable group, such as (meth)acrylate (in addition to the polymerizable group to which the linking group is linked).

[0071] Preferred linking groups include C₁-C₈ alkylene (preferably C₂-C₆ alkylene) and C₁-C₈ oxaalkylene (preferably C₂-C₆ oxaalkylene), each of which is optionally substituted with 1 or 2 groups independently selected from hydroxyl and siloxy. Preferred linking groups also include carboxylate, amide, C₁-C₈ alkylene-carboxylate-C₁-C₈ alkylene, or C₁-C₈ alkylene-amide-C₁-C₈ alkylene.

[0072] When the linking group is comprised of combinations of moieties as described above (e.g., alkylene and cycloalkylene), the moieties may be present in any order. For instance, if in Formula E below, L is indicated as being -alkylene-cycloalkylene-, then Rg-L may be either Rg-alkylene-cycloalkylene-, or Rg-cycloalkylene-alkylene-. Notwithstanding this, the listing order represents the preferred order in which the moieties appear in the compound starting from the terminal polymerizable group (Rg or Pg) to which the linking group is attached. For example, if in Formula E, L and L² are indicated as both being alkylene-cycloalkylene-, then Rg-L is preferably Rg-alkylene-cycloalkylene- and -L²-Rg is preferably -cycloalkylene-alkylene-Rg.

[0073] The term "electron withdrawing group" (EWG) refers to a chemical group which withdraws electron density from the atom or group of atoms to which the electron withdrawing group is attached. Examples of EWGs include, but are not limited to, cyano, amide, ester, keto, or aldehyde. A preferred EWG is cyano (CN).

[0074] The terms "high energy radiation absorber," "UV/HEV absorber," or "high energy light absorbing compound" refer to chemical materials that absorb various wavelengths of ultraviolet light, high energy visible light, or both. A material's ability to absorb certain wavelengths of light can be determined by measuring its UV Nis transmission spectrum. Compounds that exhibit no absorption at a particular wavelength will exhibit substantially 100 percent transmission at that wavelength. Conversely, compounds that completely absorb at a particular wavelength will exhibit substantially 0 % transmission at that wavelength. If the amount of a material's transmission is indicated as a percentage for a particular wavelength range, it is to be understood that the material exhibits the percent transmission at all wavelengths within that range.

[0075] Unless otherwise indicated, ratios, percentages, parts, and the like are by weight.

[0076] Unless otherwise indicated, numeric ranges, for instance as in "from 2 to 10," are inclusive of the numbers defining the range (e.g., 2 and 10).

[0077] As noted above, one aspect the invention provides an ophthalmic device that is a reaction product of a reactive mixture comprising: one or more polymerizable high energy light absorbing compounds and one or more monomers suitable for making an ophthalmic device, wherein the ophthalmic device transmits: 45 percent or less of light having a wavelength of 280 to 399 nm; at least 1 percent and up to 70 percent of light having a wavelength of 400 to 409 nm; and at least 80 percent of light having a wavelength of 450 to 800 nm. Preferably the ophthalmic device also transmits at least 10 percent and up to 95 percent of light having a wavelength of 410 to 424 nm. Also preferably, the ophthalmic device transmits at least 50 percent of light having a wavelength of 425 to 449 nm. Further preferably, the ophthalmic device transmits 10 percent or less of light having a wavelength of 200 to 279 nm.

[0078] Preferably, the transmission of the ophthalmic device at 200 to 279 nm is 5 percent or less or 1 percent or less. Or preferably it is less than 1 percent.

[0079] Preferably, the transmission of the ophthalmic device at 280 to 399 nm is 35 percent or less, or 25 percent or less, or 20 percent or less, or 10 percent or less, or 5 percent or less, or 1 percent or less.

[0080] Preferably, the transmission of the ophthalmic device at 400 to 409 nm is at least 2 percent, at least 3 percent, or at least 4 percent. Also preferably, the transmission of the ophthalmic device at 400 to 409 nm is up to 60 percent, or up to 50 percent, or up to 40 percent, or up to 30 percent, or up to 20 percent.


[0081] Preferably, the transmission of the ophthalmic device at 410 to 424 nm is at least 15 percent. Also preferably, the transmission of the ophthalmic device at 410 to 424 nm is up to 85 percent, up to 75 percent, or up to 65 percent.

[0082] Preferably, the transmission of the ophthalmic device at 425 to 449 nm is at least 60 percent.

[0083] Preferably, the transmission of the ophthalmic device at 450 to 800 nm is at least 85 percent.

[0084] Preferred ophthalmic devices are contact lenses, more preferably soft hydrogel contact lenses. The foregoing transmission wavelengths and percentages may be measured on various thicknesses of lenses. For example, the center thickness may be from 80 to 100 microns, or from 90 to 100 microns or from 90 to 95 microns. Various concentrations of the one or more polymerizable high energy light absorbing compounds may be used to achieve the foregoing results. For instance, the concentration may be in the range of at least 0.1 percent or at least 2 percent; and up to 10 percent or up to 5 percent, based on the weight percentages of all components in the reactive mixture, excluding diluent. A typical concentration may be in the range of 1 to 5 percent.

[0085] The invention also provides UV/HEV absorbing compounds of formula I:



Formula I

wherein:

m and n are independently 0, 1, 2, 3, or 4;

T is a bond, O, or NR;

X is O, S, NR, SO, or SO₂;

Y is a linking group;

P_g is a polymerizable group;

R at each occurrence is independently H, C₁-C₆ alkyl, cycloalkyl, heterocycloalkyl, aryl, heteroaryl, or Y-P_g;

R¹ and R², when present, are independently at each occurrence C₁-C₆ alkyl, C₁-C₆ alkoxy, C₁-C₆ thioalkyl, C₃-C₇ cycloalkyl, aryl (preferably unsubstituted phenyl or phenyl substituted with alkyl or halo), halo, hydroxy, amino, NR³R⁴, or benzyl, wherein R³ and R⁴ are independently H or C₁-C₆ alkyl, or two adjacent R¹ or R² groups, together with the carbon atoms to which they are attached, combine to form a cycloalkyl or aryl ring; and
EWG is an electron withdrawing group.

[0086] Compounds of formula I preferably contain one or two Y-P_g groups. More preferably, the compounds contain one Y-P_g group.

[0087] Formula I-1. Compounds of formula I may include compounds of formula I-1, which are compounds of formula I wherein X is S.

[0088] I-2. Compounds of formula I may include compounds of formula I-2, which are compounds of formula I wherein X is O.

[0089] I-3. Compounds of formula I may include compounds of formula I-3, which are compounds of formula I wherein X is NR, preferably NH or N-alkyl.

[0090] I-4. Compounds of formula I may include compounds of formula I-4, which are compounds of formula I wherein X is SO.

[0091] I-5. Compounds of formula I may include compounds of formula I-5, which are compounds of formula I wherein X is SO₂.

[0092] I-6. Compounds of formulae I, I-1, I-2, I-3, I-4, and I-5 may include compounds of formula I-6, which are compounds of formula I, I-1, I-2, I-3, I-4, or I-5 wherein m and n are independently 0 or 1, or alternatively both are 0.

[0093] I-7. Compounds of formulae I, I-1, I-2, I-3, I-4, and I-5 may include compounds of formula I-7, which are compounds of formula I, I-1, I-2, I-3, I-4, or I-5 wherein m is 1 and R¹ is C₁-C₆ alkyl, preferably ethyl or methyl.

[0094] I-8. Compounds of formulae I, I-1, I-2, I-3, I-4, I-5, and I-7 may include compounds of formula I-8, which are compounds of formula I, I-1, I-2, I-3, I-4, I-5, or I-7 wherein n is 1 and R² is C₁-C₆ alkyl, preferably ethyl or methyl.

[0095] I-9. Compounds of formulae I, I-1, I-2, I-3, I-4, I-5, I-6, I-7 and I-8 may include compounds of formula I-9, which are compounds of formula I, I-1, I-2, I-3, I-4, I-5, I-6, I-7 or I-8 wherein R is H, or C₁-C₆ alkyl. Preferably, R in the group T is H.

[0096] I-10. Compounds of formulae I, I-1, I-2, I-3, I-4, I-5, I-6, I-7, I-8, and I-9 may include compounds of formula I-10, which are compounds of formula I, I-1, I-2, I-3, I-4, I-5, I-6, I-7, I-8, or I-9 wherein P_g (a polymerizable group) at each occurrence independently comprises styryl, vinyl carbonate, vinyl ether, vinyl carbamate, N-vinyl lactam, N-vinylamide, (meth)acrylate, or (meth)acrylamide. The polymerizable group allows the compounds of the invention to form covalent bonds when reacted with monomers, crosslinking agents, and other components generally used in making polymeric devices. The compatibility of the compounds with the reactive mixture can be controlled via the selection of the polymerizable group (and the linking group). Preferred polymerizable groups include (meth)acrylate or (meth)acrylamide. A more preferred polymerizable group is methacrylate.


[0097] I-11. Compounds of formulae I, I-1, I-2, I-3, I-4, I-5, I-6, I-7, I-8, I-9, and I-10 may include compounds of formula I-11, which are compounds of formula I, I-1, I-2, I-3, I-4, I-5, I-6, I-7, I-8, I-9, or I-10 wherein Y (a linking group) is alkylene, cycloalkylene, heterocycloalkylene, arylene (e.g., phenylene), heteroarylene, oxaalkylene, alkylene-amide-alkylene, alkylene-amine-alkylene, or combinations of any of the foregoing groups. Preferred linking groups include C₁-C₈ alkylene (e.g., ethylene or propylene), C₁-C₈ oxaalkylene, C₁-C₈ alkylene-amide-C₁-C₈ alkylene, and C₁-C₈ alkylene-amine-

C₁-C₈ alkylene. Particularly preferred is C₁-C₈ alkylene, especially ethylene (-CH₂CH₂-). When T in the compound of formula I is O, it is preferred that the carbon atom of the linking group to which the O is attached be hindered. For instance, if T is O and Y is alkylene, a preferred alkylene is -C(R^H)₂(CH₂)_x-, where R^H is independently C₁-C₆ alkyl (preferably independently methyl or ethyl) and x is from 1 to 5.

[0098] I-12. Compounds of formulae I, I-1, I-2, I-3, I-4, I-5, I-6, I-7, I-8, I-9, I-10, and I-11 may include compounds of formula I-12, which are compounds of formula I, I-1, I-2, I-3, I-4, I-5, I-6, I-7, I-8, I-9, I-10, or I-11 wherein T is a bond or is NR (preferably NH).

[0099] I-13. Compounds of formulae I, I-1, I-2, I-3, I-4, I-5, I-6, I-7, I-8, I-9, I-10, I-11, and I-12 may include compounds of formula I-13, which are compounds of formula I, I-1, I-2, I-3, I-4, I-5, I-6, I-7, I-8, I-9, I-10, I-11, or I-12 wherein EWG is cyano, amide, ester, keto, or aldehyde. Preferably, EWG is cyano.

[0100] Preferred compounds of formula I include compounds of formula II:



Formula II

wherein:

m and n are independently 0, 1, 2, 3, or 4;

T is a bond, O, or NR;

X is O, S, NR, SO, or SO₂;

Y is a linking group;

P_g is a polymerizable group;

R at each occurrence is independently H, C₁-C₆ alkyl, cycloalkyl, heterocycloalkyl, aryl, heteroaryl, or Y-P_g; and R¹ and R², when present, are independently at each occurrence C₁-C₆ alkyl, C₁-C₆ alkoxy, C₁-C₆ thioalkyl, C₃-C₇ cycloalkyl, aryl (preferably unsubstituted phenyl or phenyl substituted with alkyl or halo), halo, hydroxy, amino, NR³R⁴, or benzyl, wherein R³ and R⁴ are independently H or C₁-C₆ alkyl, or two adjacent R¹ or R² groups, together with the carbon atoms to which they are attached, combine to form a cycloalkyl or aryl ring. Compounds of formula I preferably contain one or two Y-P_g groups. More preferably, the compounds contain one Y-P_g group.

[0101] Formula II-1. Compounds of formula II may include compounds of formula II-1, which are compounds of formula II wherein X is S.

[0102] II-2. Compounds of formula II may include compounds of formula II-2, which are compounds of formula II wherein X is O.

[0103] II-3. Compounds of formula II may include compounds of formula II-3, which are compounds of formula II wherein X is NR, preferably NH or N-alkyl.

[0104] II-4. Compounds of formula II may include compounds of formula II-4, which are compounds of formula II wherein X is SO.

[0105] II-5. Compounds of formula II may include compounds of formula II-5, which are compounds of formula II wherein X is SO₂.

[0106] II-6. Compounds of formulae II, II-1, II-2, II-3, II-4, and II-5 may include compounds of formula II-6, which are compounds of formula II, II-1, II-2, II-3, II-4, or II-5 wherein m and n are independently 0 or 1, or alternatively both are 0.

[0107] II-7. Compounds of formulae II, II-1, II-2, II-3, II-4, and II-5 may include compounds of formula II-7, which are compounds of formula II, II-1, II-2, II-3, II-4, or II-5 wherein m is 1 and R¹ is C₁-C₆ alkyl, preferably ethyl or methyl.

[0108] II-8. Compounds of formulae II, II-1, II-2, II-3, II-4, II-5, and II-7 may include compounds of formula II-8, which are compounds of formula II, II-1, II-2, II-3, II-4, II-5, or II-7 wherein n is 1 and R² is C₁-C₆ alkyl, preferably ethyl or methyl.

[0109] II-9. Compounds of formulae II, II-1, II-2, II-3, II-4, II-5, II-6, II-7 and II-8 may include compounds of formula II-9, which are compounds of formula II, II-1, II-2, II-3, II-4, II-5, II-6, II-7 or II-8 wherein R is H, or C₁-C₆ alkyl. Preferably, R in the group T is H.


[0110] II-10. Compounds of formulae II, II-1, II-2, II-3, II-4, II-5, II-6, II-7, II-8, and II-9 may include compounds of formula II-10, which are compounds of formula II, II-1, II-2, II-3, II-4, II-5, II-6, II-7, II-8, or II-9 wherein P_g (a polymerizable group)

at each occurrence independently comprises styryl, vinyl carbonate, vinyl ether, vinyl carbamate, N-vinyl lactam, N-vinylamide, (meth)acrylate, or (meth)acrylamide. The polymerizable group allows the compounds of the invention to form covalent bonds when reacted with monomers, crosslinking agents, and other components generally used in making polymeric devices. The compatibility of the compounds with the reactive mixture can be controlled via the selection of the polymerizable group (and the linking group). Preferred polymerizable groups include (meth)acrylate or (meth)acrylamide. A more preferred polymerizable group is methacrylate.

[0111] II-11. Compounds of formulae II, II-1, II-2, II-3, II-4, II-5, II-6, II-7, II-8, II-9, and II-10 may include compounds of formula II-11, which are compounds of formula II, II-1, II-2, II-3, II-4, II-5, II-6, II-7, II-8, II-9, or II-10 wherein Y (a linking group) is alkylene, cycloalkylene, heterocycloalkylene, arylene (e.g., phenylene), heteroarylene, oxaalkylene, alkylene-amide-alkylene, alkylene-amine-alkylene, or combinations of any of the foregoing groups. Preferred linking groups include C₁-C₈ alkylene (e.g., ethylene or propylene), C₁-C₈ oxaalkylene, C₁-C₈ alkylene-amide-C₁-C₈ alkylene, and C₁-C₈ alkylene-amine-C₁-C₈ alkylene. Particularly preferred is C₁-C₈ alkylene, especially ethylene (-CH₂CH₂-). When T in the compound of formula II is O, it is preferred that the carbon atom of the linking group to which the O is attached be hindered. For instance, if T is O and Y is alkylene, a preferred alkylene is -C(R^H)₂(CH₂)_x-, where R^H is independently C₁-C₆ alkyl (preferably independently methyl or ethyl) and x is from 1 to 5.

[0112] II-12. Compounds of formulae II, II-1, II-2, II-3, II-4, II-5, II-6, II-7, II-8, II-9, II-10, and II-11 may include compounds of formula II-12, which are compounds of formula II, II-1, II-2, II-3, II-4, II-5, II-6, II-7, II-8, II-9, II-10, or II-11 wherein T is a bond or is NR (preferably NH).

[0113] Preferred compounds of formula I and formula II include compounds of formula III:



Formula III

wherein:

m and n are independently 0, 1, 2, 3, or 4;

X is O, S, NR, SO, or SO₂;

Y is a linking group;

P_g is a polymerizable group;

R at each occurrence is independently H, C₁-C₆ alkyl, cycloalkyl, heterocycloalkyl, aryl, heteroaryl, or Y-P_g; and

R¹ and R², when present, are independently at each occurrence C₁-C₆ alkyl, C₁-C₆ alkoxy, C₁-C₆ thioalkyl, C₃-C₇ cycloalkyl, aryl (preferably unsubstituted phenyl or phenyl substituted with alkyl or halo), halo, hydroxy, amino, NR³R⁴, or benzyl, wherein R³ and R⁴ are independently H or C₁-C₆ alkyl, or two adjacent R¹ or R² groups, together with the carbon atoms to which they are attached, combine to form a cycloalkyl or aryl ring. Compounds of formula II preferably contain one or two Y-P_g groups. More preferably, the compounds contain one Y-P_g group.

[0114] Formula III-1. Compounds of formula III may include compounds of formula III-1, which are compounds of formula III wherein X is S.

[0115] III-2. Compounds of formula III may include compounds of formula III-2, which are compounds of formula III wherein X is O.

[0116] III-3. Compounds of formula III may include compounds of formula III-3, which are compounds of formula III wherein X is NR, preferably NH or N-alkyl.

[0117] III-4. Compounds of formula III may include compounds of formula III-4, which are compounds of formula III wherein X is SO.

[0118] III-5. Compounds of formula III may include compounds of formula III-5, which are compounds of formula III wherein X is SO₂.

[0119] III-6. Compounds of formulae III, III-1, III-2, III-3, III-4, and III-5 may include compounds of formula III-6, which are compounds of formula III, III-1, III-2, III-3, III-4, or III-5 wherein m and n are independently 0 or 1, or alternatively both are 0.

[0120] III-7. Compounds of formulae III, III-1, III-2, III-3, III-4, and III-5 may include compounds of formula III-7, which

are compounds of formula III, III-1, III-2, III-3, III-4, or III-5 wherein m is 1 and R¹ is C₁-C₆ alkyl, preferably ethyl or methyl.

[0121] III-8. Compounds of formulae III, III-1, III-2, III-3, III-4, III-5, and III-7 may include compounds of formula III-8, which are compounds of formula III, III-1, III-2, III-3, III-4, III-5, or III-7 wherein n is 1 and R² is C₁-C₆ alkyl, preferably ethyl or methyl.




[0122] III-9. Compounds of formulae III, III-1, III-2, III-3, III-4, III-5, III-6, III-7 and III-8 may include compounds of formula III-9, which are compounds of formula III, III-1, III-2, III-3, III-4, III-5, III-6, III-7 or III-8 wherein R at each occurrence is independently H, or C₁-C₆ alkyl. Preferably, R at each occurrence is H. Preferably R in the group T is H

[0123] III-10. Compounds of formulae III, III-1, III-2, III-3, III-4, III-5, III-6, III-7, III-8, and III-9 may include compounds of formula III-10, which are compounds of formula III, III-1, III-2, III-3, III-4, III-5, III-6, III-7, III-8, or III-9 wherein P_g (a polymerizable group) at each occurrence independently comprises styryl, vinyl carbonate, vinyl ether, vinyl carbamate, N-vinyl lactam, N-vinylamide, (meth)acrylate, or (meth)acrylamide. The polymerizable group allows the compounds of the invention to form covalent bonds when reacted with monomers, crosslinking agents, and other components generally used in making polymeric devices. The compatibility of the compounds with the reactive mixture can be controlled via the selection of the polymerizable group (and the linking group). Preferred polymerizable groups include (meth)acrylate or (meth)acrylamide. A more preferred polymerizable group is methacrylate.

[0124] III-11. Compounds of formulae III, III-1, III-2, III-3, III-4, III-5, III-6, III-7, III-8, III-9, and III-10 may include compounds of formula III-11, which are compounds of formula III, III-1, III-2, III-3, III-4, III-5, III-6, III-7, III-8, III-9, or III-10 wherein Y (a linking group) is alkylene, cycloalkylene, heterocycloalkylene, arylene (e.g., phenylene), heteroarylene, oxaalkylene, alkylene-amide-alkylene, alkylene-amine-alkylene, or combinations of any of the foregoing groups. Preferred linking groups include C₁-C₈ alkylene (e.g., ethylene or propylene), C₁-C₈ oxaalkylene, C₁-C₈ alkylene-amide-C₁-C₈ alkylene, and C₁-C₈ alkylene-amine-C₁-C₈ alkylene. Particularly preferred is C₁-C₈ alkylene, especially ethylene (-CH₂CH₂-).


[0125] Specific examples of compounds of formula I include, but are not limited to, the compounds shown in Table 1.

Table 1

 2-(2-cyano-2-(9H-thioxanthen-9-ylidene)acetamido)ethyl methacrylate
 2-(2-cyano-2-(9H-thioxanthen-9-ylidene)acetamido)ethyl acrylate
 N-(2-(2-cyano-2-(9H-thioxanthen-9-ylidene)acetamido)ethyl)methacrylamide

(continued)


5



10

N-(2-(2-cyano-2-(9H-thioxanthen-9-ylidene)acetamido)ethyl)acrylamide


15



20

2-(2-cyano-N-methyl-2-(9H-thioxanthen-9-ylidene)acetamido)ethyl methacrylate


25



30

2-cyano-2-(9H-thioxanthen-9-ylidene)-N-(2-(N-vinylacetamido)ethyl)acetamide


35



40

2-(2-cyano-2-(9H-xanthen-9-ylidene)acetamido)ethyl methacrylate


45



50

2-(2-cyano-2-(9H-xanthen-9-ylidene)acetamido)ethyl acrylate


55



N-(2-(2-cyano-2-(9H-xanthen-9-ylidene)acetamido)ethyl)methacrylamide

(continued)


5



10

N-(2-(2-cyano-2-(9H-xanthen-9-ylidene)acetamido)ethyl)acrylamide


15



20

2-(2-cyano-N-methyl-2-(9H-xanthen-9-ylidene)acetamido)ethyl methacrylate


25



30

2-cyano-N-(2-(N-vinylacetamido)ethyl)-2-(9H-xanthen-9-ylidene)acetamide


35



40

2-(2-(acridin-9(10H)-ylidene)-2-cyanoacetamido)ethyl acrylate


45



50


N-(2-(2-(acridin-9(10H)-ylidene)-2-cyanoacetamido)ethyl)methacrylamide

55




N-(2-(2-(acridin-9(10H)-ylidene)-2-cyanoacetamido)ethyl)acrylamide


(continued)




2-(2-(acridin-9(10H)-ylidene)-2-cyano-N-methylacetamido)ethyl methacrylate




2-(acridin-9(10H)-ylidene)-2-cyano-N-(2-(N-vinylacetamido)ethyl)acetamide



2-(2-cyano-2-(9H-thioxanthen-9-ylidene)acetamido)-2-methylpropyl methacrylate




2-(2-cyano-2-(9H-xanthen-9-ylidene)acetoxy)-2-methylpropyl acrylate



(Z)-2-(2-cyano-2-(3-hydroxyacridin-9(10H)-ylidene)acetamido)ethyl methacrylate

(continued)


5



10

2-(2-cyano-2-(10-methylacrididin-9(10H)-ylidene)acetamido)ethyl methacrylate


15



20

2-(2-cyano-2-(3,6-dihydroxyacrididin-9(10H)-ylidene)acetamido)ethyl methacrylate


25



30

(E)-2-(2-(7H-benzo[c]xanthen-7-ylidene)-2-cyanoacetamido)ethyl methacrylate


35



40

(Z)-2-(2-cyano-2-(3-methoxy-9H-xanthen-9-ylidene)acetamido)ethyl methacrylate

45




50


2-(2-cyano-2-(3,6-dihydroxy-9H-xanthen-9-ylidene)acetamido)ethyl methacrylate

55


(continued)




(E)-2-(2-cyano-2-(2-methyl-9H-xanthen-9-ylidene)acetamido)ethyl methacrylate




(E)-2-(2-cyano-2-(1-hydroxy-9H-xanthen-9-ylidene)acetamido)ethyl methacrylate



(E)-2-(2-cyano-2-(2,4-dichloro-9H-thioxanthen-9-ylidene)acetamido)ethyl methacrylate



(E)-2-(2-(2-chloro-9H-thioxanthen-9-ylidene)-2-cyanoacetamido)ethyl methacrylate




(E)-2-(2-cyano-2-(2-isopropyl-9H-thioxanthen-9-ylidene)acetamido)ethyl methacrylate

(continued)

5


10



(E)-2-(2-cyano-2-(4-isopropyl-9H-thioxanthen-9-ylidene)acetamido)ethyl methacrylate

15


20



2-(3-oxo-2-(9H-thioxanthen-9-ylidene)propanamido)ethyl methacrylate

25


30



2-(3-oxo-2-(9H-thioxanthen-9-ylidene)butanamido)ethyl methacrylate

35


40



2-(3-methoxy-3-oxo-2-(9H-thioxanthen-9-ylidene)propanamido)ethyl methacrylate

45

50



2-(3-amino-3-oxo-2-(9H-thioxanthen-9-ylidene)propanamido)ethyl methacrylate

2-(2-cyano-2-(10,10-dioxido-9H-thioxanthen-9-ylidene)acetamido)ethyl methacrylate

N-(2-(2-cyano-2-(10-methylacridin-9(10H)ylidene)acetamido)ethyl) methacrylamide

2-(2-cyano-2-(9H-thioxanthen-9-ylidene)acetoxo)ethyl methacrylate

55

[0126] Compounds of the invention can be selected to provide targeted absorption of UV and/or high energy visible light. Such targeting may be achieved, for example, through selection of the hetero atom of the core tricyclic structure

(X in formula I). For instance, compounds of formula I-1 (the heteroatom is sulfur) may absorb HEV light. On the other hands, compounds of formula I-2 (the heteroatom is oxygen) may absorb UV light and some HEV light although to a lesser extent than formula I-1 compounds.


[0127] Additional tuning of the absorption characteristics for a given X in the compounds of formula I may be provided by adding or varying the substituents R¹ and R² to, for instance, obtain bathochromic or hypsochromic shifts. Electron donating substituents may, for example, may cause red shifts to the UV-VIS absorption spectrum, while electron withdrawing groups may cause blue shifts; the magnitude of these shifts may depend on the electron donating or withdrawing ability, and the position, of the substituent. For example, an alkoxy substituent may result in a smaller red shift than, for instance, an amino or thioalkyl group at the same carbon center.

[0128] Preferred X groups in the compounds of the invention are S, O, and NR, more preferably S and O. However, additional oxidation states of sulfur such as sulfoxide and sulfone may also provide a means to modify UV-VIS spectra of the compounds. Sulfoxide and sulfone have reduced electron density on the sulfur atom and may be used to create hypsochromic (blue) shifted spectra.

[0129] Compounds of formula I may be used in combination with other absorbing compounds to provide desirable absorption characteristics. For example, preferred compositions may comprise a compound of formula I-1 (X is S) and a second compound that absorbs UV. The second compound may, for example, also be a compound of formula I that absorbs in the UV region (such as compounds of formula I-2 (X is O)), or it may be another UV absorbing compound. Suitable UV absorbing compounds are known in the art, and fall into several classes which include, but are not limited to, benzophenones, benzotriazoles, triazines, substituted acrylonitriles, salicylic acid derivatives, benzoic acid derivatives, cinnamic acid derivatives, chalcone derivatives, dypnone derivatives, crotonic acid derivatives, or any mixtures thereof. A preferred class of UV absorbing compound is benzotriazoles, such as Norbloc (2-(2'-hydroxy-5-methacryloxyethylphenyl)-2H-benzotriazole).

[0130] A particularly preferred composition comprises 2-(2-cyano-2-(9H-thioxanthen-9-ylidene)acetamido)ethyl methacrylate and 2-(2-cyano-2-(9H-xanthen-9-ylidene)acetamido)ethyl methacrylate. Another preferred composition comprises 2-(2-cyano-2-(9H-thioxanthen-9-ylidene)acetamido)ethyl methacrylate and 2-(2'-hydroxy-5-methacryloxyethylphenyl)-2H-benzotriazole. A further preferred composition comprises N-(2-(2-cyano-2-(10-methylacridin-9(10H)ylidene)acetamido)ethyl) methacrylamide.

[0131] Compounds of formula I may be prepared by those skilled in the art using literature methods. By way of example, various compounds of formula I where the EWG is cyano may be prepared as shown in Scheme 1 and the associated description. Exemplary reagents and procedures for these reactions appear in the working examples.



Scheme 1

[0132] Scheme 1 shows a method for preparing exemplary compounds of the invention. Thus, the carbonyl moiety of the starting material is converted to a reactive dihalide intermediate, which is further reacted with the active methylene compound without further purification or isolation. The reaction mixture is protected from air and moisture until completion of the reaction with the cyanomethyl amide derivative. Other compounds of the invention may be prepared by those skilled in the art using analogous procedures to those shown in Scheme 1 with appropriate substitution of reagents.

[0133] High energy light absorbing compounds, such as the compounds of formula I, may be included in reactive mixtures to form various products, including biomedical devices and ophthalmic devices. Generally, the high energy light absorbing compounds can be present in any amount up to the limit of their solubility. For instance, the compounds may be present in an amount in the range of about 0.1 % to about 10 % by weight, or from about 0.5 to about 5% by weight, or from about 0.75% to about 4% by weight. The upper limit is typically determined by the solubility of the compound with other co-monomers and or diluents in the reactive monomer mix.

[0134] Preferably, the high energy light absorbing compounds of the invention are included in ophthalmic devices. A variety of ophthalmic devices may be prepared, including hard contact lenses, soft contact lenses, corneal onlays, corneal inlays, intraocular lenses, or overlay lenses. Preferably, the ophthalmic device is a soft contact lens, which may be made from conventional or silicone hydrogel formulations.

[0135] Ophthalmic devices of the invention comprise a free radical reaction product of a reactive mixture containing one or more polymerizable high energy light absorbing compounds, such as compounds of formula I, one or more monomers suitable for making the desired ophthalmic device (also referred to herein as device forming monomers or

hydrogel forming monomers), and optional components. Thus, the reactive mixture may, for example, include, in addition to a polymerizable high energy light absorbing compound as described above, one or more of: hydrophilic components, hydrophobic components, silicone-containing components, wetting agents such as polyamides, crosslinking agents, and further components such as diluents and initiators.

Hydrophilic Components

[0136] Examples of suitable families of hydrophilic monomers include (meth)acrylates, styrenes, vinyl ethers, (meth)acrylamides, N-vinyl lactams, N-vinyl amides, N-vinyl imides, N-vinyl ureas, O-vinyl carbamates, O-vinyl carbonates, other hydrophilic vinyl compounds, and mixtures thereof.

[0137] Non-limiting examples of hydrophilic (meth)acrylate and (meth)acrylamide monomers include: acrylamide, N-isopropyl acrylamide, N,N-dimethylaminopropyl (meth)acrylamide, N,N-dimethyl acrylamide (DMA), 2-hydroxyethyl methacrylate (HEMA), 2-hydroxypropyl (meth)acrylate, 3-hydroxypropyl (meth)acrylate, 2,3-dihydroxypropyl (meth)acrylate, 2-hydroxybutyl (meth)acrylate, 3-hydroxybutyl (meth)acrylate, 4-hydroxybutyl (meth)acrylate, N-(2-hydroxyethyl) (meth)acrylamide, N,N-bis(2-hydroxyethyl) (meth)acrylamide, N-(2-hydroxypropyl) (meth)acrylamide, N,N-bis(2-hydroxypropyl) (meth)acrylamide, N-(3-hydroxypropyl) (meth)acrylamide, N-(2-hydroxybutyl) (meth)acrylamide, N-(3-hydroxybutyl) (meth)acrylamide, N-(4-hydroxybutyl) (meth)acrylamide, 2-aminoethyl (meth)acrylate, 3-aminopropyl (meth)acrylate, 2-aminopropyl (meth)acrylate, N-2-aminoethyl (meth)acrylamides, N-3-aminopropyl (meth)acrylamide, N-2-aminopropyl (meth)acrylamide, N,N-bis-2-aminoethyl (meth)acrylamides, N,N-bis-3-aminopropyl (meth)acrylamide, N,N-bis-2-aminopropyl (meth)acrylamide, glycerol methacrylate, polyethyleneglycol monomethacrylate, (meth)acrylic acid, vinyl acetate, acrylonitrile, and mixtures thereof.

[0138] Hydrophilic monomers may also be ionic, including anionic, cationic, zwitterions, betaines, and mixtures thereof. Non-limiting examples of such charged monomers include (meth)acrylic acid, N-[(ethenyl)oxy]carbonyl-β-alanine (VINYL), 3-acrylamidopropanoic acid (ACA1), 5-acrylamidopentanoic acid (ACA2), 3-acrylamido-3-methylbutanoic acid (AMBA), 2-(methacryloyloxy)ethyl trimethylammonium chloride (Q Salt or METAC), 2-acrylamido-2-methylpropane sulfonic acid (AMPS), 1-propanaminium, N-(2-carboxyethyl)-N,N-dimethyl-3-[(1-oxo-2-propen-1-yl)amino]-, inner salt (CBT), 1-propanaminium, N,N-dimethyl-N-[3-[(1-oxo-2-propen-1-yl)amino]propyl]-3-sulfo-, inner salt (SBT), 3,5-Dioxo-8-aza-4-phosphadec-10-en-1-aminium, 4-hydroxy-N,N,N-trimethyl-9-oxo-, inner salt, 4-oxide (9CI) (PBT), 2-methacryloyloxyethyl phosphorylcholine, 3-(dimethyl(4-vinylbenzyl)ammonio)propane-1-sulfonate (DMVBAPS), 3-((3-acrylamidopropyl)dimethylammonio)propane-1-sulfonate (AMPDAPS), 3-((3-methacrylamidopropyl)dimethylammonio)propane-1-sulfonate (MAMPDAPS), 3-((3-(acryloyloxy)propyl)dimethylammonio)propane-1-sulfonate (APDAPS), and methacryloyloxypropyl)dimethylammonio)propane-1-sulfonate (MAPDAPS).

[0139] Non-limiting examples of hydrophilic N-vinyl lactam and N-vinyl amide monomers include: N-vinyl pyrrolidone (NVP), N-vinyl-2-piperidone, N-vinyl-2-caprolactam, N-vinyl-3-methyl-2-caprolactam, N-vinyl-3-methyl-2-piperidone, N-vinyl-4-methyl-2-piperidone, N-vinyl-4-methyl-2-caprolactam, N-vinyl-3-ethyl-2-pyrrolidone, N-vinyl-4,5-dimethyl-2-pyrrolidone, N-vinyl acetamide (NVA), N-vinyl-N-methylacetamide (VMA), N-vinyl-N-ethyl acetamide, N-vinyl-N-ethyl formamide, N-vinyl formamide, N-vinyl-N-methylpropionamide, N-vinyl-N-methyl-2-methylpropionamide, N-vinyl-2-methylpropionamide, N-vinyl-N,N'-dimethylurea, 1-methyl-3-methylene-2-pyrrolidone, 1-methyl-5-methylene-2-pyrrolidone, 5-methyl-3-methylene-2-pyrrolidone; 1-ethyl-5-methylene-2-pyrrolidone, N-methyl-3-methylene-2-pyrrolidone, 5-ethyl-3-methylene-2-pyrrolidone, 1-N-propyl-3-methylene-2-pyrrolidone, 1-N-propyl-5-methylene-2-pyrrolidone, 1-isopropyl-3-methylene-2-pyrrolidone, 1-isopropyl-5-methylene-2-pyrrolidone, N-vinyl-N-ethyl acetamide, N-vinyl-N-ethyl formamide, N-vinyl formamide, N-vinyl isopropylamide, N-vinyl caprolactam, N-vinylimidazole, and mixtures thereof.

[0140] Non-limiting examples of hydrophilic O-vinyl carbamates and O-vinyl carbonates monomers include N-2-hydroxyethyl vinyl carbamate and N-carboxy-β-alanine N-vinyl ester. Further examples of hydrophilic vinyl carbonate or vinyl carbamate monomers are disclosed in U.S. Patent No. 5,070,215. Hydrophilic oxazolone monomers are disclosed in U.S. Patent No. 4,910,277.

[0141] Other hydrophilic vinyl compounds include ethylene glycol vinyl ether (EGVE), di(ethylene glycol) vinyl ether (DEGVE), allyl alcohol, and 2-ethyl oxazoline.

[0142] The hydrophilic monomers may also be macromers or prepolymers of linear or branched poly(ethylene glycol), polypropylene glycol, or statistically random or block copolymers of ethylene oxide and propylene oxide, having polymerizable moieties such as (meth)acrylates, styrenes, vinyl ethers, (meth)acrylamides, N-vinylamides, and the like. The macromers of these polyethers have one polymerizable group; the prepolymers may have two or more polymerizable groups.

[0143] The preferred hydrophilic monomers of the present invention are DMA, NVP, HEMA, VMA, NVA, and mixtures thereof. Preferred hydrophilic monomers include mixtures of DMA and HEMA. Other suitable hydrophilic monomers will be apparent to one skilled in the art.

[0144] Generally, there are no particular restrictions with respect to the amount of the hydrophilic monomer present in the reactive monomer mixture. The amount of the hydrophilic monomers may be selected based upon the desired

characteristics of the resulting hydrogel, including water content, clarity, wettability, protein uptake, and the like. Wettability may be measured by contact angle, and desirable contact angles are less than about 100°, less than about 80°, and less than about 60°. The hydrophilic monomer may be present in an amount in the range of, for instance, about 0.1 to about 100 weight percent, alternatively in the range of about 1 to about 80 weight percent, alternatively about 5 to about 65 weight percent, alternatively in the range of about 40 to about 60 weight percent, or alternatively about 55 to about 60 weight percent, based on the total weight of the reactive components in the reactive monomer mixture.

Silicone-Containing Components


[0145] Silicone-containing components suitable for use in the invention comprise one or more polymerizable compounds, where each compound independently comprises at least one polymerizable group, at least one siloxane group, and one or more linking groups connecting the polymerizable group(s) to the siloxane group(s). The silicone-containing components may, for instance, contain from 1 to 220 siloxane repeat units, such as the groups defined below. The silicone-containing component may also contain at least one fluorine atom.

[0146] The silicone-containing component may comprise: one or more polymerizable groups as defined above; one or more optionally repeating siloxane units; and one or more linking groups connecting the polymerizable groups to the siloxane units. The silicone-containing component may comprise: one or more polymerizable groups that are independently a (meth)acrylate, a styryl, a vinyl ether, a (meth)acrylamide, an N-vinyl lactam, an N-vinylamide, an O-vinylcarbamate, an O-vinylcarbonate, a vinyl group, or mixtures of the foregoing; one or more optionally repeating siloxane units; and one or more linking groups connecting the polymerizable groups to the siloxane units.

[0147] The silicone-containing component may comprise: one or more polymerizable groups that are independently a (meth)acrylate, a (meth)acrylamide, an N-vinyl lactam, an N-vinylamide, a styryl, or mixtures of the foregoing; one or more optionally repeating siloxane units; and one or more linking groups connecting the polymerizable groups to the siloxane units.

[0148] The silicone-containing component may comprise: one or more polymerizable groups that are independently a (meth)acrylate, a (meth)acrylamide, or mixtures of the foregoing; one or more optionally repeating siloxane units; and one or more linking groups connecting the polymerizable groups to the siloxane units.

[0149] Formula A. The silicone-containing component may comprise one or more polymerizable compounds of Formula A:



Formula A

wherein:

at least one R^{A} is a group of formula $\text{R}_g\text{-L}$ wherein R_g is a polymerizable group and L is a linking group, and the remaining R^{A} are each independently:


- (a) $\text{R}_g\text{-L}$,
- (b) $\text{C}_1\text{-C}_{16}$ alkyl optionally substituted with one or more hydroxy, amino, amido, oxa, carboxy, alkyl carboxy, carbonyl, alkoxy, amido, carbamate, carbonate, halo, phenyl, benzyl, or combinations thereof,
- (c) $\text{C}_3\text{-C}_{12}$ cycloalkyl optionally substituted with one or more alkyl, hydroxy, amino, amido, oxa, carbonyl, alkoxy, amido, carbamate, carbonate, halo, phenyl, benzyl, or combinations thereof,
- (d) a $\text{C}_6\text{-C}_{14}$ aryl group optionally substituted with one or more alkyl, hydroxy, amino, amido, oxa, carboxy, alkyl carboxy, carbonyl, alkoxy, amido, carbamate, carbonate, halo, phenyl, benzyl, or combinations thereof,
- (e) halo,
- (f) alkoxy, cyclic alkoxy, or aryloxy,
- (g) siloxy,
- (h) alkyleneoxy-alkyl or alkoxy-alkyleneoxy-alkyl, such as polyethyleneoxyalkyl, polypropyleneoxyalkyl, or poly(ethyleneoxy-co-propyleneoxyalkyl), or
- (i) a monovalent siloxane chain comprising from 1 to 100 siloxane repeat units optionally substituted with alkyl,

alkoxy, hydroxy, amino, oxa, carboxy, alkyl carboxy, alkoxy, amido, carbamate, halo or combinations thereof; and

n is from 0 to 500 or from 0 to 200, or from 0 to 100, or from 0 to 20, where it is understood that when n is other than 0, n is a distribution having a mode equal to a stated value. When n is 2 or more, the SiO units may carry the same or different R^A substituents and if different R^A substituents are present, the n groups may be in random or block configuration.

[0150] In Formula A, three R^A may each comprise a polymerizable group, alternatively two R^A may each comprise a polymerizable group, or alternatively one R^A may comprise a polymerizable group.

[0151] Formula B. The silicone-containing component of formula A may be a mono-functional polymerizable compound of formula B:



Formula B

wherein:

R_g is a polymerizable group;

L is a linking group;

j₁ and j₂ are each independently whole numbers from 0 to 220, provided that the sum of j₁ and j₂ is from 1 to 220; R^{A1}, R^{A2}, R^{A3}, R^{A4}, R^{A5}, and R^{A7} are independently at each occurrence C₁-C₆ alkyl, C₃-C₁₂ cycloalkyl, C₁-C₆ alkoxy, C₄-C₁₂ cyclic alkoxy, alkoxy-alkyleneoxy-alkyl, aryl (e.g., phenyl), aryl-alkyl (e.g., benzyl), haloalkyl (e.g., partially or fully fluorinated alkyl), siloxy, fluoro, or combinations thereof, wherein each alkyl in the foregoing groups is optionally substituted with one or more hydroxy, amino, amido, oxa, carboxy, alkyl carboxy, carbonyl, alkoxy, carbamate, carbonate, halo, phenyl, or benzyl, each cycloalkyl is optionally substituted with one or more alkyl, hydroxy, amino, amido, oxa, carbonyl, alkoxy, carbamate, carbonate, halo, phenyl, or benzyl and each aryl is optionally substituted with one or more alkyl, hydroxy, amino, amido, oxa, carboxy, alkyl carboxy, carbonyl, alkoxy, carbamate, carbonate, halo, phenyl, or benzyl; and

R^{A6} is siloxy, C₁-C₈ alkyl (e.g., C₁-C₄ alkyl, or butyl, or methyl), or aryl (e.g., phenyl), wherein alkyl and aryl may optionally be substituted with one or more fluorine atoms.

[0152] Formula B-1. Compounds of formula B may include compounds of formula B-1, which are compounds of formula B wherein j₁ is zero and j₂ is from 1 to 220, or j₂ is from 1 to 100, or j₂ is from 1 to 50, or j₂ is from 1 to 20, or j₂ is from 1 to 5, or j₂ is 1.

[0153] B-2. Compounds of formula B may include compounds of formula B-2, which are compounds of formula B wherein j₁ and j₂ are independently from 4 to 100, or from 4 to 20, or from 4 to 10, or from 24 to 100, or from 10 to 100.

[0154] B-3. Compounds of formulae B, B-1, and B-2 may include compounds of formula B-3, which are compounds of formula B, B-1, or B-2 wherein R^{A1}, R^{A2}, R^{A3}, and R^{A4} are independently at each occurrence C₁-C₆ alkyl or siloxy. Preferred alkyl are C₁-C₃ alkyl, or more preferably, methyl. Preferred siloxy is trimethylsiloxy.

[0155] B-4. Compounds of formulae B, B-1, B-2, and B-3 may include compounds of formula B-4, which are compounds of formula B, B-1, B-2, or B-3 wherein R^{A5} and R^{A7} are independently alkoxy-alkyleneoxy-alkyl, preferably they are independently a methoxy capped polyethyleneoxyalkyl of formula CH₃O-[CH₂CH₂O]_p-CH₂CH₂CH₂, wherein p is a whole number from 1 to 50.

[0156] B-5. Compounds of formulae B, B-1, B-2, and B-3 may include compounds of formula B-5, which are compounds of formula B, B-1, B-2, or B-3 wherein R^{A5} and R^{A7} are independently siloxy, such as trimethylsiloxy.

[0157] B-6. Compounds of formulae B, B-1, B-2, and B-3 may include compounds of formula B-6, which are compounds of formula B, B-1, B-2, or B-3 wherein R^{A5} and R^{A7} are independently C₁-C₆ alkyl, alternatively C₁-C₄ alkyl, or alternatively, butyl or methyl.

[0158] B-7. Compounds of formulae B, B-1, B-2, B-3, B-4, B-5, and B-6 may include compounds of formula B-7, which are compounds of formula B, B-1, B-2, B-3, B-4, B-5, or B-6 wherein R^{A6} is C₁-C₈ alkyl, preferably C₁-C₆ alkyl, more preferably C₁-C₄ alkyl (for example methyl, ethyl, n-propyl, or n-butyl). More preferably R^{A6} is n-butyl.

[0159] B-8. Compounds of formulae B, B-1, B-2, B-3, B-4, B-5, B-6, and B-7, may include compounds of formula B-8, which are compounds of formula B, B-1, B-2, B-3, B-4, B-5, B-6, or B-7 wherein Rg comprises styryl, vinyl carbonate, vinyl ether, vinyl carbamate, N-vinyl lactam, N-vinylamide, (meth)acrylate, or (meth)acrylamide. Preferably, Rg comprises (meth)acrylate, (meth)acrylamide, or styryl. More preferably, Rg comprises (meth)acrylate or (meth)acrylamide. When Rg is (meth)acrylamide, the nitrogen group may be substituted with R^{A9}, wherein R^{A9} is H, C₁-C₈ alkyl (preferably C₁-C₄ alkyl, such as n-butyl, n-propyl, methyl or ethyl), or C₃-C₈ cycloalkyl (preferably C₅-C₆ cycloalkyl), wherein alkyl and cycloalkyl are optionally substituted with one or more groups independently selected from hydroxyl, amide, ether, silyl (e.g., trimethylsilyl), siloxy (e.g., trimethylsiloxyl), alkyl-siloxanyl (where alkyl is itself optionally substituted with fluoro), aryl-siloxanyl (where aryl is itself optionally substituted with fluoro), and silyl-oxaalkylene- (where the oxaalkylene is itself optionally substituted with hydroxyl).

[0160] B-9. Compounds of formulae B, B-1, B-2, B-3, B-4, B-5, B-6, B-7, and B-8 may include compounds of formula B-9, which are compounds of formula B, B-1, B-2, B-3, B-4, B-5, B-6, B-7, or B-8 wherein the linking group comprises alkylene (preferably C₁-C₄ alkylene), cycloalkylene (preferably C₅-C₆ cycloalkylene), alkyleneoxy (preferably ethyleneoxy), haloalkyleneoxy (preferably haloethyleneoxy), amide, oxaalkylene (preferably containing 3 to 6 carbon atoms), siloxanyl, alkylenesiloxanyl, carbamate, alkyleneamine (preferably C₁-C₆ alkyleneamine), or combinations of two or more thereof, wherein the linking group is optionally substituted with one or more substituents independently selected from alkyl, hydroxyl, ether, amine, carbonyl, siloxy, and carbamate.

[0161] B-10. Compounds of formulae B, B-1, B-2, B-3, B-4, B-5, B-6, B-7, B-8, and B-9 may include compounds of formula B-10, which are compounds of formula B, B-1, B-2, B-3, B-4, B-5, B-6, B-7, B-8, or B-9 wherein the linking group is alkylene-siloxanyl-alkylene-alkyleneoxy-, or alkylene-siloxanyl-alkylene-[alkyleneoxy-alkylene-siloxanyl]_q-alkyleneoxy-, where q is from 1 to 50.

[0162] B-11. Compounds of formulae B, B-1, B-2, B-3, B-4, B-5, B-6, B-7, B-8, and B-9 may include compounds of formula B-11, which are compounds of formula B, B-1, B-2, B-3, B-4, B-5, B-6, B-7, B-8, or B-9 wherein the linking group is C₁-C₆ alkylene, preferably C₁-C₃ alkylene, more preferably n-propylene.

[0163] B-12. Compounds of formulae B, B-1, B-2, B-3, B-4, B-5, B-6, B-7, B-8, and B-9 may include compounds of formula B-12, which are compounds of formula B, B-1, B-2, B-3, B-4, B-5, B-6, B-7, B-8, or B-9 wherein the linking group is alkylene-carbamate-oxaalkylene. Preferably, the linking group is CH₂CH₂N(H)-C(=O)-O-CH₂CH₂-O-CH₂CH₂CH₂.

[0164] B-13. Compounds of formulae B, B-1, B-2, B-3, B-4, B-5, B-6, B-7, B-8, and B-9 may include compounds of formula B-13, which are compounds of formula B, B-1, B-2, B-3, B-4, B-5, B-6, B-7, B-8, or B-9 wherein the linking group is oxaalkylene. Preferably, the linking group is CH₂CH₂-O-CH₂CH₂CH₂.

[0165] B-14. Compounds of formulae B, B-1, B-2, B-3, B-4, B-5, B-6, B-7, B-8, and B-9 may include compounds of formula B-14, which are compounds of formula B, B-1, B-2, B-3, B-4, B-5, B-6, B-7, B-8, or B-9 wherein the linking group is alkylene-[siloxanyl-alkylene]_q-, where q is from 1 to 50. An example of such a linking group is: -(CH₂)₃-[Si(CH₃)₂-O-Si(CH₃)₂-(CH₂)₂]_q-.

[0166] B-15. Compounds of formulae B, B-1, B-2, B-3, B-4, B-5, B-6, B-7, B-8, and B-9 may include compounds of formula B-15, which are compounds of formula B, B-1, B-2, B-3, B-4, B-5, B-6, B-7, B-8, or B-9 wherein the linking group is alkyleneoxy-carbamate-alkylene-cycloalkylene-carbamate-oxaalkylene, wherein cycloalkylene is optionally substituted with or 1, 2, or 3 independently selected alkyl groups (preferably C₁-C₃ alkyl, more preferably methyl). An example of such a linking group is -[OCH₂CH₂]_q-OC(=O)-NH-CH₂-[1,3-cyclohexylene]-NHC(=O)-O-CH₂CH₂-O-CH₂CH₂-, wherein the cyclohexylene is substituted at the 1 and 5 positions with 3 methyl groups.

[0167] B-16. Compounds of formulae B, B-1, B-2, B-3, B-4, B-5, B-6, B-7, B-8, and B-9 may include compounds of formula B-16, which are compounds of formula B, B-1, B-2, B-3, B-4, B-5, B-6, B-7, B-8, or B-9 wherein Rg comprises styryl and the linking group is a bond or is alkyleneoxy, wherein each alkylene in alkyleneoxy is independently optionally substituted with hydroxyl. An example of such a linking group is -O-(CH₂)₃-. Another example of such a linking group is -O-CH₂CH(OH)CH₂-O-(CH₂)₃-.

[0168] B-17. Compounds of formulae B, B-1, B-2, B-3, B-4, B-5, B-6, B-7, B-8, and B-9 may include compounds of formula B-17, which are compounds of formula B, B-1, B-2, B-3, B-4, B-5, B-6, B-7, B-8, or B-9 wherein Rg comprises styryl and the linking group is alkyleneamine. An example of such a linking group is -NH-(CH₂)₃-.

[0169] B-18. Compounds of formulae B, B-1, B-2, B-3, B-4, B-5, B-6, B-7, B-8, and B-9 may include compounds of formula B-18, which are compounds of formula B, B-1, B-2, B-3, B-4, B-5, B-6, B-7, B-8, or B-9 wherein the linking group is oxaalkylene optionally substituted with hydroxyl, siloxy, or silyl-alkyleneoxy (where the alkyleneoxy is itself optionally substituted with hydroxyl). An example of such a linking group is -CH₂CH(G)CH₂-O-(CH₂)₃-, wherein G is hydroxyl. In another example, G is R₃SiO- wherein two R groups are trimethylsiloxy and the third is C₁-C₈ alkyl (preferably C₁-C₃ alkyl, more preferably methyl) or the third is C₃-C₈ cycloalkyl. In a further example, G is R₃Si-(CH₂)₃-O-CH₂CH(OH)CH₂-O-, wherein two R groups are trimethylsiloxy and the third is C₁-C₈alkyl (preferably C₁-C₃ alkyl, more preferably methyl) or C₃-C₈ cycloalkyl. In a still further example, G is a polymerizable group, such as (meth)acrylate. Such compounds may function as crosslinkers.


[0170] B-19. Compounds of formulae B, B-1, B-2, B-3, B-4, B-5, B-6, B-7, B-8, and B-9 may include compounds of

formula B-19, which are compounds of formula B, B-1, B-2, B-3, B-4, B-5, B-6, B-7, B-8, or B-9 wherein Rg comprises styryl and the linking group is amine-oxaalkylene optionally substituted with hydroxyl. An example of such a linking group is -NH-CH₂CH(OH)CH₂-O-(CH₂)₃-.

[0171] B-20. Compounds of formulae B, B-1, B-2, B-3, B-4, B-5, B-6, B-7, B-8, and B-9 may include compounds of formula B-20, which are compounds of formula B, B-1, B-2, B-3, B-4, B-5, B-6, B-7, B-8, or B-9 wherein Rg comprises styryl and the linking group is alkyleneoxy-carbamate-oxaalkylene. An example of such a linking group is -O-(CH₂)₂-N(H)C(=O)O-(CH₂)₂-O-(CH₂)₃-.

[0172] B-21. Compounds of formulae B, B-1, B-2, B-3, B-4, B-5, B-6, B-7, B-8, and B-9 may include compounds of formula B-21, which are compounds of formula B, B-1, B-2, B-3, B-4, B-5, B-6, B-7, B-8, or B-9 wherein the linking group is alkylene-carbamate-oxaalkylene. An example of such a linking group is -(CH₂)₂-N(H)C(=O)O-(CH₂)₂-O-(CH₂)₃-.

[0173] Formula C. Silicone-containing components of formulae A, B, B-1, B-2, B-3, B-4, B-5, B-6, B-7, B-8, B-9, B-10, B-11, B-12, B-13, B-14, B-15, B-18, and B-21 may include compounds of formula C, which are compounds of formula A, B, B-1, B-2, B-3, B-4, B-5, B-6, B-7, B-8, B-9, B-10, B-11, B-12, B-13, B-14, B-15, B-18, or B-21 having the structure:



Formula C

wherein

R^{A8} is hydrogen or methyl;

Z is O, S, or N(R^{A9}); and


L, j₁, j₂, R^{A1}, R^{A2}, R^{A3}, R^{A4}, R^{A5}, R^{A6}, R^{A7}, and R^{A9} are as defined in formula B or its various sub-formulae (e.g., B-1, B-2, etc.).

[0174] C-1. Compounds of formula C may include (meth)acrylates of formula C-1, which are compounds of formula C wherein Z is O.

[0175] C-2. Compounds of formula C may include (meth)acrylamides of formula C-2, which are compounds of formula C wherein Z is N(R^{A9}), and R^{A9} is H.

[0176] C-3. Compounds of formulae C may include (meth)acrylamides of formula C-3, which are compounds of formula C wherein Z is N(R^{A9}), and R^{A9} is C₁-C₈ alkyl that is unsubstituted or is optionally substituted as indicated above. Examples of R^{A9} include CH₃, -CH₂CH(OH)CH₂(OH), -(CH₂)₃-siloxanyl, -(CH₂)₃-SiR₃, and -CH₂CH(OH)CH₂-O-(CH₂)₃-SiR₃ where each R in the foregoing groups is independently selected from trimethylsiloxy, C₁-C₈ alkyl (preferably C₁-C₃ alkyl, more preferably methyl), and C₃-C₈ cycloalkyl. Further examples of R^{A9} include: -(CH₂)₃-Si(Me)(SiMe₃)₂, and -(CH₂)₃-Si(Me)₂-[O-SiMe₂]₁₋₁₀-CH₃.

[0177] Formula D. Compounds of formula C may include compounds of formula D:



Formula D

wherein

R^{A8} is hydrogen or methyl;

Z¹ is O or N(R^{A9});

L¹ is alkylene containing 1 to 8 carbon atoms, or oxaalkylene containing 3 to 10 carbon atoms, wherein L¹ is optionally substituted with hydroxyl; and
j₂, R^{A3}, R^{A4}, R^{A5}, R^{A6}, R^{A7}, and R^{A9} are as defined above in formula B or its various sub-formulae (e.g., B-1, B-2, etc.).

[0178] D-1. Compounds of formula D may include compounds of formula D-1, which are compounds of formula D wherein L¹ is C₂-C₅ alkylene optionally substituted with hydroxyl. Preferably L¹ is n-propylene optionally substituted with hydroxyl.

[0179] D-2. Compounds of formula D may include compounds of formula D-2, which are compounds of formula D wherein L¹ is oxaalkylene containing 4 to 8 carbon atoms optionally substituted with hydroxyl. Preferably L¹ is oxaalkylene containing five or six carbon atoms optionally substituted with hydroxyl. Examples include -(CH₂)₂-O-(CH₂)₃-, and -CH₂CH(OH)CH₂-O-(CH₂)₃-.

[0180] D-3. Compounds of formulae D, D-1, and D-2 may include compounds of formula D-3, which are compounds of formula D, D-1, or D-2 wherein Z¹ is O.

[0181] D-4. Compounds of formulae D, D-1, and D-2 may include compounds of formula D-4, which are compounds of formula D, D-1, or D-2 wherein Z¹ is N(R^{A9}), and R^{A9} is H.

[0182] D-5. Compounds of formulae D, D-1, and D-2 may include compounds of formula D-5, which are compounds of formula D, D-1, or D-2 wherein Z¹ is N(R^{A9}), and R^{A9} is C₁-C₄ alkyl optionally substituted with 1 or 2 substituents selected from hydroxyl, siloxy, and C₁-C₆ alkyl-siloxanyl-.


[0183] D-6. Compounds of formulae D, D-1, D-2, D-3, D-4, and D-5 may include compounds of formula D-6, which are compounds of formula D, D-1, D-2, D-3, D-4, or D-5 wherein j₂ is 1.

[0184] D-7. Compounds of formulae D, D-1, D-2, D-3, D-4, and D-5 may include compounds of formula D-7, which are compounds of formula D, D-1, D-2, D-3, D-4, or D-5 wherein j₂ is from 2 to 220, or from 2 to 100, or from 10 to 100, or from 24 to 100, or from 4 to 20, or from 4 to 10.

[0185] D-8. Compounds of formulae D, D-1, D-2, D-3, D-4, D-5, D-6, and D-7 may include compounds of formula D-8, which are compounds of formula D, D-1, D-2, D-3, D-4, D-5, D-6, or D-7 wherein R^{A3}, R^{A4}, R^{A5}, R^{A6}, and R^{A7} are independently C₁-C₆ alkyl or siloxy. Preferably R^{A3}, R^{A4}, R^{A5}, R^{A6}, and R^{A7} are independently selected from methyl, ethyl, n-propyl, n-butyl, and trimethylsiloxy. More preferably, R^{A3}, R^{A4}, R^{A5}, R^{A6}, and R^{A7} are independently selected from methyl, n-butyl, and trimethylsiloxy.

[0186] D-9. Compounds of formulae D, D-1, D-2, D-3, D-4, D-5, D-6, and D-7 may include compounds of formula D-9, which are compounds of formula D, D-1, D-2, D-3, D-4, D-5, D-6, or D-7 wherein R^{A3} and R^{A4} are independently C₁-C₆ alkyl (e.g., methyl or ethyl) or siloxy (e.g., trimethylsiloxy), and R^{A5}, R^{A6}, and R^{A7} are independently C₁-C₆ alkyl (e.g., methyl, ethyl, n-propyl, or n-butyl).

[0187] Formula E. The silicone-containing component for use in the invention may comprise a multi-functional silicone-containing component. Thus, for example, the silicone-containing component of formula A may comprise a bifunctional material of formula E:



Formula E

wherein

R_g, L, j₁, j₂, R^{A1}, R^{A2}, R^{A3}, R^{A4}, R^{A5}, and R^{A7} are as defined above for formula B or its various sub-formulae (e.g., B-1, B-2, etc.);

L² is a linking group; and

R_g¹ is a polymerizable group.

[0188] E-1. Compounds of formula E may include compounds of formula E-1, which are compounds of formula E wherein R_g and R_g¹ are each a vinyl carbonate of structure CH₂=CH-O-C(=O)-O- or structure CH₂=C(CH₃)-O-C(=O)-O-.

[0189] E-2. Compounds of formula E may include compounds of formula E-2, which are compounds of formula E wherein R_g and R_g¹ are each (meth)acrylate.

[0190] E-3. Compounds of formula E may include compounds of formula E-3, which are compounds of formula E

wherein Rg and Rg¹ are each (meth)acrylamide, wherein the nitrogen group may be substituted with R^{A9} (wherein R^{A9} is as defined above).

[0191] E-4. Suitable compounds of formulae E, E-1, E-2, and E-3 include compounds of formula E-4, which are compounds of formula E, E-1, E-2, or E-3 wherein j₁ is zero and j₂ is from 1 to 220, or j₂ is from 1 to 100, or j₂ is from 1 to 50, or j₂ is from 1 to 20.

[0192] E-5. Suitable compounds of formulae E, E-1, E-2, and E-3 include compounds of formula E-5, which are compounds of formula E, E-1, E-2, or E-3, wherein j₁ and j₂ are independently from 4 to 100.

[0193] E-6. Suitable compounds of formulae E, E-1, E-2, E-3, E-4, and E-5 include compounds of formula E-6, which are compounds of formula E, E-1, E-2, E-3, E-4, or E-5 wherein R^{A1}, R^{A2}, R^{A3}, R^{A4}, and R^{A5} are independently at each occurrence C₁-C₆ alkyl, preferably they are independently C₁-C₃ alkyl, or preferably, each is methyl.

[0194] E-7. Suitable compounds of formulae E, E-1, E-2, E-3, E-4, E-5, and E-6 include compounds of formula E-7, which are compounds of formula E, E-1, E-2, E-3, E-4, E-5, or E-6 wherein R^{A7} is alkoxy-alkyleneoxy-alkyl, preferably it is a methoxy capped polyethyleneoxyalkyl of formula CH₃O-[CH₂CH₂O]_p-CH₂CH₂CH₂, wherein p is a whole number from 1 to 50, or from 1 to 30, or from 1 to 10, or from 6 to 10.

[0195] E-8. Suitable compounds of formulae E, E-1, E-2, E-3, E-4, E-5, E-6, and E-7 include compounds of formula E-8, which are compounds of formula E, E-1, E-2, E-3, E-4, E-5, E-6, or E-7 wherein L comprises alkylene, carbamate, siloxanyl, cycloalkylene, amide, haloalkyleneoxy, oxaalkylene, or combinations of two or more thereof, wherein the linking group is optionally substituted with one or more substituents independently selected from alkyl, hydroxyl, ether, amine, carbonyl, and carbamate.








[0196] E-9. Suitable compounds of formulae E, E-1, E-2, E-3, E-4, E-5, E-6, E-7, and E-8 include compounds of formula E-9, which are compounds of formula E, E-1, E-2, E-3, E-4, E-5, E-6, E-7, or E-8 wherein L² comprises alkylene, carbamate, siloxanyl, cycloalkylene, amide, haloalkyleneoxy, oxaalkylene, or combinations of two or more thereof, wherein the linking group is optionally substituted with one or more substituents independently selected from alkyl, hydroxyl, ether, amine, carbonyl, and carbamate.

[0197] Examples of silicone-containing components suitable for use in the invention include, but are not limited to, compounds listed in Table 2. Where the compounds in Table 2 contain polysiloxane groups, the number of SiO repeat units in such compounds, unless otherwise indicated, is preferably from 3 to 100, more preferably from 3 to 40, or still more preferably from 3 to 20.


Table 2

1	mono-methacryloxypropyl terminated mono-n-butyl terminated polydimethylsiloxanes (mPDMS) (preferably containing from 3 to 15 SiO repeating units)
2	mono-acryloxypropyl terminated mono-n-butyl terminated polydimethylsiloxane
3	mono(meth)acryloxypropyl terminated mono-n-methyl terminated polydimethylsiloxane
4	mono(meth)acryloxypropyl terminated mono-n-butyl terminated polydiethylsiloxane
5	mono(meth)acryloxypropyl terminated mono-n-methyl terminated polydiethylsiloxane
6	mono(meth)acrylamidoalkylpolydialkylsiloxanes
7	mono(meth)acryloxyalkyl terminated mono-alkyl polydiarylsiloxanes
8	3-methacryloxypropyltris(trimethylsiloxy)silane (TRIS)
9	3-methacryloxypropylbis(trimethylsiloxy)methylsilane
10	3-methacryloxypropylpentamethyl disiloxane
11	mono(meth)acrylamidoalkylpolydialkylsiloxanes
12	mono(meth)acrylamidoalkyl polydimethylsiloxanes
13	N-(2,3-dihydroxypropane)-N'-(propyl tetra(dimethylsiloxy) dimethylbutylsilane)acrylamide
14	N-[3-tris(trimethylsiloxy)silyl]-propyl acrylamide (TRIS-Am)
15	2-hydroxy-3-[3-methyl-3,3-di(trimethylsiloxy)silylpropoxy]-propyl methacrylate (SiMAA)
16	2-hydroxy-3-methacryloxypropyloxypropyl-tris(trimethylsiloxy)silane

(continued)

5	17	
10		mono-(2-hydroxy-3-methacryloxypropyloxy)-propyl terminated mono-n-butyl terminated polydimethylsiloxanes (OH-mPDMS) (containing from 4 to 30, or from 4 to 20, or from 4 to 15 SiO repeat units)
15	18	
20	19	
25	20	
35	21	
40	22	
45	23	
50		

(continued)










[0198] Additional non-limiting examples of suitable silicone-containing components are listed in Table 3. Unless otherwise indicated, j2 where applicable is preferably from 1 to 100, more preferably from 3 to 40, or still more preferably from 3 to 15. In compounds containing j1 and j2, the sum of j1 and j2 is preferably from 2 to 100, more preferably from 3 to 40, or still more preferably from 3 to 15.


Table 3

25 25	
26 26 p is 1 to 10	
27 27 p is 5-10	
28 28	

(continued)

29	
30	1,3-bis[4-(vinylphenoxy)but-1-yl]tetramethyl-disiloxane
31	3-(vinylphenoxy)propyl-[tris(trimethylsiloxy)silane]
32	3-[tris(trimethylsiloxy)silyl] propyl allyl carbamate
33	3-[tris(trimethylsiloxy)silyl] propyl vinyl carbamate
34	tris(trimethylsiloxy)silylstyrene (Styryl-TRIS)
35	 $R^A = \text{CH}_3$ (a) or $\text{CH}_2\text{CH}_2\text{CF}_3$ (b) or $\text{CH}_2-(\text{CH}_2)_2-$ $[\text{OCH}_2\text{CH}_2]_{1-10}-\text{OCH}_3$ (c); $a + b + c = n$
36	
37	
38	
39	
40	

(continued)



[0199] Mixtures of silicone-containing components may be used. By way of example, suitable mixtures may include, but are not limited to: a mixture of mono-(2-hydroxy-3-methacryloxypropyloxy)-propyl terminated mono-n-butyl terminated polydimethylsiloxane (OH-mPDMS) having different molecular weights, such as a mixture of OH-mPDMS containing 4 and 15 SiO repeat units; a mixture of OH-mPDMS with different molecular weights (e.g., containing 4 and 15 repeat SiO repeat units) together with a silicone based crosslinker, such as bis-3-acryloxy-2-hydroxypropyloxypropyl polydimethylsiloxane (ac-PDMS); a mixture of 2-hydroxy-3-[3-methyl-3,3-di(trimethylsiloxy)silylpropoxy]-propyl methacrylate (SiMAA) and mono-methacryloxypropyl terminated mono-n-butyl terminated polydimethylsiloxane (mPDMS), such as mPDMS 1000.


[0200] Silicone-containing components for use in the invention may have an average molecular weight of from about 400 to about 4000 daltons.

[0201] The silicone containing component(s) may be present in amounts up to about 95 weight %, or from about 10 to about 80 weight %, or from about 20 to about 70 weight %, based upon all reactive components of the reactive mixture (excluding diluents).


Polyamides

[0202] The reactive mixture may include at least one polyamide. As used herein, the term "polyamide" refers to polymers and copolymers comprising repeating units containing amide groups. The polyamide may comprise cyclic amide groups, acyclic amide groups and combinations thereof and may be any polyamide known to those of skill in the art. Acyclic polyamides comprise pendant acyclic amide groups and are capable of association with hydroxyl groups. Cyclic polyamides comprise cyclic amide groups and are capable of association with hydroxyl groups.

[0203] Examples of suitable acyclic polyamides include polymers and copolymers comprising repeating units of Formulae G1 and G2:



Formula G1




Formula G2


wherein X is a direct bond, $-(CO)-$, or $-(CONHR_{44})-$, wherein R_{44} is a C_1 to C_3 alkyl group; R_{40} is selected from H, straight or branched, substituted or unsubstituted C_1 to C_4 alkyl groups; R_{41} is selected from H, straight or branched, substituted or unsubstituted C_1 to C_4 alkyl groups, amino groups having up to two carbon atoms, amide groups having up to four carbon atoms, and alkoxy groups having up to two carbon groups; R_{42} is selected from H, straight or branched, substituted or unsubstituted C_1 to C_4 alkyl groups; or methyl, ethoxy, hydroxyethyl, and hydroxymethyl; R_{43} is selected from H, straight or branched, substituted or unsubstituted C_1 to C_4 alkyl groups; or methyl, ethoxy, hydroxyethyl, and hydroxymethyl; wherein the number of carbon atoms in R_{40} and R_{41} taken together is 8 or less, including 7, 6, 5, 4, 3, or less; and wherein the number of carbon atoms in R_{42} and R_{43} taken together is 8 or less, including 7, 6, 5, 4, 3, or less. The number of carbon atoms in R_{40} and R_{41} taken together may be 6 or less or 4 or less. The number of carbon atoms in R_{42} and R_{43} taken together may be 6 or less. As used herein substituted alkyl groups include alkyl groups substituted with an amine, amide, ether, hydroxyl, carbonyl or carboxy groups or combinations thereof.

[0204] R_{40} and R_{41} may be independently selected from H, substituted or unsubstituted C_1 to C_2 alkyl groups. X may be a direct bond, and R_{40} and R_{41} may be independently selected from H, substituted or unsubstituted C_1 to C_2 alkyl groups. R_{42} and R_{43} can be independently selected from H, substituted or unsubstituted C_1 to C_2 alkyl groups, methyl, ethoxy, hydroxyethyl, and hydroxymethyl.

[0205] The acyclic polyamides of the present invention may comprise a majority of the repeating units of Formula LV or Formula LVI, or the acyclic polyamides can comprise at least 50 mole percent of the repeating unit of Formula G or Formula G1, including at least 70 mole percent, and at least 80 mole percent. Specific examples of repeating units of Formula G and Formula G1 include repeating units derived from N-vinyl-N-methylacetamide, N-vinylacetamide, N-vinyl-N-methylpropionamide, N-vinyl-N-methyl-2-methylpropionamide, N-vinyl-2-methyl-propionamide, N-vinyl-N,N'-dimethylurea, N, N-dimethylacrylamide, methacrylamide, and acyclic amides of Formulae G2 and G3:




Formula G2



Formula G3

[0206] Examples of suitable cyclic amides that can be used to form the cyclic polyamides of include α -lactam, β -lactam, γ -lactam, δ -lactam, and ϵ -lactam. Examples of suitable cyclic polyamides include polymers and copolymers comprising

repeating units of Formula G4:



Formula G4

wherein Ras is a hydrogen atom or methyl group; wherein f is a number from 1 to 10; wherein X is a direct bond, $-(CO)-$, or $-(CONHR_{46})-$, wherein R_{46} is a C_1 to C_3 alkyl group. In Formula LIX, f may be 8 or less, including 7, 6, 5, 4, 3, 2, or 1. In Formula G4, f may be 6 or less, including 5, 4, 3, 2, or 1. In Formula G4, f may be from 2 to 8, including 2, 3, 4, 5, 6, 7, or 8. In Formula LIX, f may be 2 or 3. When X is a direct bond, f may be 2. In such instances, the cyclic polyamide may be polyvinylpyrrolidone (PVP).

[0207] The cyclic polyamides of the present invention may comprise 50 mole percent or more of the repeating unit of Formula G4, or the cyclic polyamides can comprise at least 50 mole percent of the repeating unit of Formula G4, including at least 70 mole percent, and at least 80 mole percent.

[0208] The polyamides may also be copolymers comprising repeating units of both cyclic and acyclic amides. Additional repeating units may be formed from monomers selected from hydroxyalkyl(meth)acrylates, alkyl(meth)acrylates, other hydrophilic monomers and siloxane substituted (meth)acrylates. Any of the monomers listed as suitable hydrophilic monomers may be used as co-monomers to form the additional repeating units. Specific examples of additional monomers which may be used to form polyamides include 2-hydroxyethyl (meth)acrylate, vinyl acetate, acrylonitrile, hydroxypropyl (meth)acrylate, methyl (meth)acrylate and hydroxybutyl (meth)acrylate, dihydroxypropyl (meth)acrylate, polyethylene glycol mono(meth)acrylate, and the like and mixtures thereof. Ionic monomers may also be included. Examples of ionic monomers include (meth)acrylic acid, N-[(ethenoxy)carbonyl]- β -alanine (VINAL, CAS #148969-96-4), 3-acrylamidopropanoic acid (ACA1), 5-acrylamidopentanoic acid (ACA2), 3-acrylamido-3-methylbutanoic acid (AMBA), 2-(methacryloyloxy)ethyl trimethylammonium chloride (Q Salt or METAC), 2-acrylamido-2-methylpropane sulfonic acid (AMPS), 1-propanaminium, N-(2-carboxyethyl)-N,N-dimethyl-3-[(1-oxo-2-propen-1-yl)amino]-, inner salt (CBT, carboxybetaine; CAS 79704-35-1), 1-propanaminium, N,N-dimethyl-N-[3-[(1-oxo-2-propen-1-yl)amino]propyl]-3-sulfo-, inner salt (SBT, sulfobetaine, CAS 80293-60-3), 3,5-Dioxa-8-aza-4-phosphaundec-10-en-1-aminium, 4-hydroxy-N,N,N-trimethyl-9-oxo-, inner salt, 4-oxide (9CI) (PBT, phosphobetaine, CAS 163674-35-9, 2-methacryloyloxyethyl phosphorylcholine, 3-(dimethyl(4-vinylbenzyl)ammonio)propane-1-sulfonate (DMVBAPS), 3-((3-acrylamidopropyl)dimethylammonio)propane-1-sulfonate (AMPDAPS), 3-((3-methacrylamidopropyl)dimethylammonio)propane-1-sulfonate (MAMPDAPS), 3-((3-(acryloyloxy)propyl)dimethylammonio)propane-1-sulfonate (APDAPS), methacryloyloxy)propyl)dimethylammonio)propane-1-sulfonate (MAPDAPS).

[0209] The reactive monomer mixture may comprise both an acyclic polyamide and a cyclic polyamide or copolymers thereof. The acyclic polyamide can be any of those acyclic polyamides described herein or copolymers thereof, and the cyclic polyamide can be any of those cyclic polyamides described herein or copolymers thereof. The polyamide may be selected from the group polyvinylpyrrolidone (PVP), polyvinylmethacrylamide (PVMA), polydimethylacrylamide (PDMA), polyvinylacetamide (PNVA), poly(hydroxyethyl(meth)acrylamide), polyacrylamide, and copolymers and mixtures thereof. The polyamide may be a mixture of PVP (e.g., PVP K90) and PVMA (e.g., having a M_w of about 570 KDa).

[0210] The total amount of all polyamides in the reactive mixture may be in the range of between 1 weight percent and about 35 weight percent, including in the range of about 1 weight percent to about 15 weight percent, and in the range of about 5 weight percent to about 15 weight percent, in all cases, based on the total weight of the reactive components of the reactive monomer mixture.

[0211] Without intending to be bound by theory, when used with a silicone hydrogel, the polyamide functions as an internal wetting agent. The polyamides of the present invention may be non-polymerizable, and in this case, are incorporated into the silicone hydrogels as semi-interpenetrating networks. The polyamides are entrapped or physically retained within the silicone hydrogels. Alternatively, the polyamides of the present invention may be polymerizable, for example as polyamide macromers or prepolymers, and in this case, are covalently incorporated into the silicone hydrogels. Mixtures of polymerizable and non-polymerizable polyamides may also be used.

[0212] When the polyamides are incorporated into the reactive monomer mixture they may have a weight average molecular weight of at least 100,000 daltons; greater than about 150,000; between about 150,000 to about 2,000,000 daltons; between about 300,000 to about 1,800,000 daltons. Higher molecular weight polyamides may be used if they are compatible with the reactive monomer mixture.

Cross-linking Agents

[0213] It is generally desirable to add one or more cross-linking agents, also referred to as cross-linking monomers, multi-functional macromers, and prepolymers, to the reactive mixture. The cross-linking agents may be selected from bifunctional crosslinkers, trifunctional crosslinkers, tetrafunctional crosslinkers, and mixtures thereof, including silicone-containing and non-silicone containing cross-linking agents. Non-silicone-containing cross-linking agents include ethylene glycol dimethacrylate (EGDMA), tetraethylene glycol dimethacrylate (TEGDMA), trimethylolpropane trimethacrylate (TMPTMA), triallyl cyanurate (TAC), glycerol trimethacrylate, methacryloxyethyl vinylcarbonate (HEMAVc), allylmethacrylate, methylene bisacrylamide (MBA), and polyethylene glycol dimethacrylate wherein the polyethylene glycol has a molecular weight up to about 5000 Daltons. The cross-linking agents are used in the usual amounts, e.g., from about 0.000415 to about 0.0156 mole per 100 grams of reactive Formulas in the reactive mixture. Alternatively, if the hydrophilic monomers and/or the silicone-containing components are multifunctional by molecular design or because of impurities, the addition of a cross-linking agent to the reactive mixture is optional. Examples of hydrophilic monomers and macromers which can act as the cross-linking agents and when present do not require the addition of an additional cross-linking agent to the reactive mixture include (meth)acrylate and (meth)acrylamide endcapped polyethers. Other cross-linking agents will be known to one skilled in the art and may be used to make the silicone hydrogel of the present invention.

[0214] It may be desirable to select crosslinking agents with similar reactivity to one or more of the other reactive components in the formulation. In some cases, it may be desirable to select a mixture of crosslinking agents with different reactivity in order to control some physical, mechanical or biological property of the resulting silicone hydrogel. The structure and morphology of the silicone hydrogel may also be influenced by the diluent(s) and cure conditions used.

[0215] Multifunctional silicone-containing components, including macromers, cross-linking agents, and prepolymers, may also be included to further increase the modulus and retain tensile strength. The silicone containing cross-linking agents may be used alone or in combination with other cross-linking agents. An example of a silicone containing component which can act as a cross-linking agent and, when present, does not require the addition of a crosslinking monomer to the reactive mixture includes α , ω -bismethacryloxypropyl polydimethylsiloxane. Another example is bis-3-acryloxy-2-hydroxypropyloxypropyl polydimethylsiloxane (ac-PDMS).

[0216] Cross-linking agents that have rigid chemical structures and polymerizable groups that undergo free radical polymerization may also be used. Non-limiting examples of suitable rigid structures include cross-linking agents comprising phenyl and benzyl ring, such as 1,4-phenylene diacrylate, 1,4-phenylene dimethacrylate, 2,2-bis(4-methacryloxyphenyl)-propane, 2,2-bis[4-(2-acryloxyethoxy)phenyl]propane, 2,2-bis[4-(2-hydroxy-3-methacryloxypropoxy)-phenyl]propane, and 4-vinylbenzyl methacrylate, and combinations thereof. Rigid crosslinking agents may be included in amounts between about 0.5 and about 15, or 2-10, 3-7 based upon the total weight of all of the reactive components. The physical and mechanical properties of the silicone hydrogels of the present invention may be optimized for a particular use by adjusting the components in the reactive mixture.

[0217] Non-limiting examples of silicone cross-linking agents also include the multi-functional silicone-containing components described above, such as compounds of Formula E (and its sub-formulae) and the multi-functional compounds shown in Table 3.

Further Constituents

[0218] The reactive mixture may contain additional components such as, but not limited to, diluents, initiators, UV absorbers, visible light absorbers, photochromic compounds, pharmaceuticals, nutraceuticals, antimicrobial substances, tints, pigments, copolymerizable dyes, nonpolymerizable dyes, release agents, and combinations thereof.

[0219] Classes of suitable diluents for silicone hydrogel reactive mixtures include alcohols having 2 to 20 carbon atoms, amides having 10 to 20 carbon atoms derived from primary amines and carboxylic acids having 8 to 20 carbon atoms. The diluents may be primary, secondary, and tertiary alcohols.

[0220] Generally, the reactive components are mixed in a diluent to form a reactive mixture. Suitable diluents are known in the art. For silicone hydrogels, suitable diluents are disclosed in WO 03/022321 and US 6020445.

Classes of suitable diluents for silicone hydrogel reactive mixtures include alcohols having 2 to 20 carbons, amides having 10 to 20 carbon atoms derived from primary amines, and carboxylic acids having 8 to 20 carbon atoms. Primary and tertiary alcohols may be used. Preferred classes include alcohols having 5 to 20 carbons and carboxylic acids having 10 to 20 carbon atoms. Specific diluents which may be used include 1-ethoxy-2-propanol, diisopropylaminoethanol, isopropanol, 3,7-dimethyl-3-octanol, 1-decanol, 1-dodecanol, 1-octanol, 1-pentanol, 2-pentanol, 1-hexanol, 2-hexanol,

2-octanol, 3-methyl-3-pentanol, tert-amyl alcohol, tert-butanol, 2-butanol, 1-butanol, 2-methyl-2-pentanol, 2-propanol, 1-propanol, ethanol, 2-ethyl-1-butanol, (3-acetoxy-2-hydroxypropyloxy)-propylbis(trimethylsiloxy) methylsilane, 1-tert-butoxy-2-propanol, 3,3-dimethyl-2-butanol, tert-butoxyethanol, 2-octyl-1-dodecanol, decanoic acid, octanoic acid, dodecanoic acid, 2-(diisopropylamino)ethanol mixtures thereof and the like. Examples of amide diluents include N,N-dimethyl propionamide and dimethyl acetamide.

[0221] Preferred diluents include 3,7-dimethyl-3-octanol, 1-dodecanol, 1-decanol, 1-octanol, 1-pentanol, 1-hexanol, 2-hexanol, 2-octanol, 3-methyl-3-pentanol, 2-pentanol, t-amyl alcohol, tert-butanol, 2-butanol, 1-butanol, 2-methyl-2-pentanol, 2-ethyl-1-butanol, ethanol, 3,3-dimethyl-2-butanol, 2-octyl-1-dodecanol, decanoic acid, octanoic acid, dodecanoic acid, mixtures thereof and the like.

[0222] More preferred diluents include 3,7-dimethyl-3-octanol, 1-dodecanol, 1-decanol, 1-octanol, 1-pentanol, 1-hexanol, 2-hexanol, 2-octanol, 1-dodecanol, 3-methyl-3-pentanol, 1-pentanol, 2-pentanol, t-amyl alcohol, tert-butanol, 2-butanol, 1-butanol, 2-methyl-2-pentanol, 2-ethyl-1-butanol, 3,3-dimethyl-2-butanol, 2-octyl-1-dodecanol, mixtures thereof and the like. If a diluent is present, generally there are no particular restrictions with respect to the amount of diluent present. When diluent is used, the diluent may be present in an amount in the range of about 2 to about 70 weight percent, including in the range of about 5 to about 50 weight percent, and in the range of about 15 to about 40 weight percent, based on the total weight of the reactive mixtures (including reactive and nonreactive Formulas). Mixtures of diluents may be used.

[0223] A polymerization initiator may be used in the reactive mixture. The polymerization initiator may include, for instance, at least one of lauroyl peroxide, benzoyl peroxide, iso-propyl percarbonate, azobisisobutyronitrile, and the like, that generate free radicals at moderately elevated temperatures, and photoinitiator systems such as aromatic alpha-hydroxy ketones, alkoxyoxybenzoin, acetophenones, acylphosphine oxides, bisacylphosphine oxides, and a tertiary amine plus a diketone, mixtures thereof and the like. Illustrative examples of photoinitiators are 1-hydroxycyclohexyl phenyl ketone, 2-hydroxy-2-methyl-1-phenyl-propan-1-one, bis(2,6-dimethoxybenzoyl)-2,4,4-trimethylpentyl phosphine oxide (DMBAPO), bis(2,4,6-trimethylbenzoyl)-phenyl phosphine oxide (Irgacure 819), 2,4,6-trimethylbenzoyldiphenyl phosphine oxide and 2,4,6-trimethylbenzoyl diphenylphosphine oxide, benzoin methyl ester and a combination of camphorquinone and ethyl 4-(N,N-dimethylamino)benzoate.

[0224] Commercially available (from IGM Resins B.V., The Netherlands) visible light initiator systems include Irgacure® 819, Irgacure® 1700, Irgacure® 1800, Irgacure® 819, Irgacure® 1850 and Lucrin® TPO initiator. Commercially available (from IGM Resins B.V.) UV photoinitiators include Darocur® 1173 and Darocur® 2959. These and other photoinitiators which may be used are disclosed in Volume III, Photoinitiators for Free Radical Cationic & Anionic Photopolymerization, 2nd Edition by J. V. Crivello & K. Dietliker; edited by G. Bradley; John Wiley and Sons; New York; 1998. The initiator is used in the reactive mixture in effective amounts to initiate photopolymerization of the reactive mixture, e.g., from about 0.1 to about 2 parts by weight per 100 parts of reactive monomer mixture. Polymerization of the reactive mixture can be initiated using the appropriate choice of heat or visible or ultraviolet light or other means depending on the polymerization initiator used. Alternatively, initiation can be conducted using e-beam without a photoinitiator. However, when a photoinitiator is used, the preferred initiators are bisacylphosphine oxides, such as bis(2,4,6-trimethylbenzoyl)-phenyl phosphine oxide (Irgacure® 819) or a combination of 1-hydroxycyclohexyl phenyl ketone and bis(2,6-dimethoxybenzoyl)-2,4,4-trimethylpentyl phosphine oxide (DMBAPO).

[0225] The reactive mixture for making the ophthalmic devices of the invention may comprise, in addition to a high energy light absorbing compound, any of the polymerizable compounds and optional components described above.

[0226] Preferred reactive mixtures may comprise: a high energy light absorbing compound, such as a formula I compound, and a hydrophilic component.

[0227] Preferred reactive mixtures may comprise: a high energy light absorbing compound, such as a formula I compound, and a hydrophilic component selected from DMA, NVP, HEMA, VMA, NVA, methacrylic acid, and mixtures thereof. Preferred are mixtures of HEMA and methacrylic acid.

[0228] Preferred reactive mixtures may comprise: a high energy light absorbing compound, such as a formula I compound, a hydrophilic component, and a silicone-containing component.

[0229] Preferred reactive mixtures may comprise: a high energy light absorbing compound, such as a formula I compound, a hydrophilic component, and a silicone-containing component comprising a compound of formula D (or its sub-formulae, such as D-1, D-2, etc.).

[0230] Preferred reactive mixtures may comprise: a high energy light absorbing compound, such as a formula I compound, a hydrophilic component selected from DMA, NVP, HEMA, VMA, NVA, and mixtures thereof; a silicone-containing component comprising a compound of formula D (or its sub-formulae, such as D-1, D-2, etc.); and an internal wetting agent.

[0231] Preferred reactive mixtures may comprise: a high energy light absorbing compound, such as a formula I compound, a hydrophilic component selected from DMA, HEMA and mixtures thereof; a silicone-containing component selected from 2-hydroxy-3-[3-methyl-3,3-di(trimethylsiloxy)silylpropoxy]-propyl methacrylate (SiMAA), mono-methacryloxypropyl terminated mono-n-butyl terminated polydimethylsiloxane (mPDMS), mono-(2-hydroxy-3-methacryloxypro-


pyl)-propyl ether terminated mono-n-butyl terminated polydimethylsiloxane (OH-mPDMS), and mixtures thereof; and a wetting agent (preferably PVP or PVMA). For the hydrophilic component, mixtures of DMA and HEMA are preferred. For the silicone containing component, mixtures of SiMAA and mPDMS are preferred.

[0232] Preferred reactive mixtures may comprise: a high energy light absorbing compound, such as a formula I compound, a hydrophilic component comprising a mixture of DMA and HEMA; a silicone-containing component comprising a mixture of OH-mPDMS having from 2 to 20 repeat units (preferably a mixture of 4 and 15 repeat units). Preferably, the reactive mixture further comprises a silicone-containing crosslinker, such as ac-PDMS. Also preferably, the reactive mixture contains a wetting agent (preferably DMA, PVP, PVMA or mixtures thereof).

[0233] Preferred reactive mixtures may comprise: a high energy light absorbing compound, such as a formula I compound; between about 1 and about 15 wt% at least one polyamide (e.g., an acyclic polyamide, a cyclic polyamide, or mixtures thereof); at least one first mono-functional, hydroxyl substituted poly(disubstituted siloxane) having 4 to 8 siloxane repeating units (e.g., OH-mPDMS where n is 4 to 8, preferably n is 4); at least one second hydroxyl substituted poly(disubstituted siloxane) that is a mono-functional hydroxyl substituted poly(disubstituted siloxane)s having 10 to 200 or 10-100 or 10-50 or 10-20 siloxane repeating units (e.g., OH-mPDMS where n is 10 to 200 or 10-100 or 10-50 or 10-20, preferably n is 15); about 5 to about 35 wt% of at least one hydrophilic monomer; and optionally a multifunctional hydroxyl substituted poly(disubstituted siloxane)s having 10 to 200, or 10 to 100 siloxane repeating units (e.g., ac-PDMS). Preferably, the first mono-functional, hydroxyl substituted poly(disubstituted siloxane) and the second hydroxyl substituted poly(disubstituted siloxane) are present in concentrations to provide a ratio of weight percent of the first mono-functional, hydroxyl substituted poly(disubstituted siloxane) to weight percent of the second hydroxyl substituted poly(disubstituted siloxane) of 0.4-1.3, or 0.4-1.0.

[0234] The foregoing reactive mixtures may contain optional ingredients such as, but not limited to, one or more initiators, internal wetting agents, crosslinkers, other UV or HEV absorbers, and diluents.

[0235] Compounds of formula I, when copolymerized with other reactive components, provide polymerized products that contain chromophoric substituents. Such chromophoric substituents can provide the product with desirable light absorbing properties as described above. For instance, ophthalmic devices, such as a contact lenses, that contain the chromophoric substituent, may block undesirable high energy light, as described in detail above. Thus, the invention encompasses ophthalmic devices that are polymerized reaction products of a reactive mixture (comprising, for instance, a hydrophilic component, and a silicone containing compound), wherein the polymerized reaction product contains, as covalently bound substituents, one or more chromophores of formula IV:



Formula IV

wherein m and n are independently 0, 1, 2, 3, or 4; X is O, S, NR, SO, or SO₂; R at each occurrence is independently H, C₁-C₆ alkyl, cycloalkyl, heterocycloalkyl, aryl, heteroaryl, or a link to the polymerized reaction product; R¹ and R², when present, are independently at each occurrence C₁-C₆ alkyl, C₁-C₆ alkoxy, C₁-C₆ thioalkyl, C₃-C₇ cycloalkyl, aryl, halo, hydroxy, amino, NR³R⁴, or benzyl, wherein R³ and R⁴ are independently H or C₁-C₆ alkyl, or two adjacent R¹ or R² groups, together with the carbon atoms to which they are attached, combine to form a cycloalkyl or aryl ring; R⁵ is a link to the polymerized reaction product; and EWG is an electron withdrawing group (preferably cyano).

[0236] In formula IV, X is preferably O or S. In formula IV, the link to the polymerized reaction product preferably comprises the residue of a polymerizable group and one or more of an alkylene group, a cycloalkylene group, a heterocycloalkylene group, an arylene group, a heteroarylene group, an oxaalkylene group, an alkylene-amide-alkylene group, or an alkylene-amine-alkylene group. Preferred polymerizable groups include styryl, vinyl carbonate, vinyl ether, vinyl carbamate, N-vinyl lactam, N-vinylamide, (meth)acrylate, or (meth)acrylamide.

[0237] Preferred polymerized reaction products may further comprise one or more covalently attached UV absorbing chromophores, in addition to the chromophore of formula IV. Preferred UV absorbing chromophores include the residue of a benzophenone, a benzotriazole, a triazine, a substituted acrylonitrile, a salicylic acid derivative, a benzoic acid derivative, a cinnamic acid derivative, a chalcone derivative, a dypnone derivative, a crotonic acid derivative, or mixtures thereof.

Curing of Hydrogels and Manufacture of Lens

[0238] The reactive mixtures may be formed by any of the methods known in the art, such as shaking or stirring, and used to form polymeric articles or devices by known methods. The reactive components are mixed together either with or without a diluent to form the reactive mixture.

[0239] For example, ophthalmic devices may be prepared by mixing reactive components, and, optionally, diluent(s), with a polymerization initiator and curing by appropriate conditions to form a product that can be subsequently formed into the appropriate shape by lathing, cutting, and the like. Alternatively, the reactive mixture may be placed in a mold and subsequently cured into the appropriate article.

[0240] A method of making a molded ophthalmic device, such as a silicone hydrogel contact lens, may comprise: preparing a reactive monomer mixture; transferring the reactive monomer mixture onto a first mold; placing a second mold on top the first mold filled with the reactive monomer mixture; and curing the reactive monomer mixture by free radical copolymerization to form the silicone hydrogel in the shape of a contact lens.

[0241] The reactive mixture may be cured via any known process for molding the reactive mixture in the production of contact lenses, including spincasting and static casting. Spincasting methods are disclosed in U.S. Patents Nos. 3,408,429 and 3,660,545, and static casting methods are disclosed in U.S. Patents Nos. 4,113,224 and 4,197,266. The contact lenses of this invention may be formed by the direct molding of the silicone hydrogels, which is economical, and enables precise control over the final shape of the hydrated lens. For this method, the reactive mixture is placed in a mold having the shape of the final desired silicone hydrogel and the reactive mixture is subjected to conditions whereby the monomers polymerize, thereby producing a polymer in the approximate shape of the final desired product.

[0242] After curing, the lens may be subjected to extraction to remove unreacted components and release the lens from the lens mold. The extraction may be done using conventional extraction fluids, such organic solvents, such as alcohols or may be extracted using aqueous solutions.

[0243] Aqueous solutions are solutions which comprise water. The aqueous solutions of the present invention may comprise at least about 20 weight percent water, or at least about 50 weight percent water, or at least about 70 weight percent water, or at least about 95 weight percent water. Aqueous solutions may also include additional water soluble Formulas such as inorganic salts or release agents, wetting agents, slip agents, pharmaceutical and nutraceutical Formulas, combinations thereof and the like. Release agents are compounds or mixtures of compounds which, when combined with water, decrease the time required to release a contact lens from a mold, as compared to the time required to release such a lens using an aqueous solution that does not comprise the release agent. The aqueous solutions may not require special handling, such as purification, recycling or special disposal procedures.

[0244] Extraction may be accomplished, for example, via immersion of the lens in an aqueous solution or exposing the lens to a flow of an aqueous solution. Extraction may also include, for example, one or more of: heating the aqueous solution; stirring the aqueous solution; increasing the level of release aid in the aqueous solution to a level sufficient to cause release of the lens; mechanical or ultrasonic agitation of the lens; and incorporating at least one leaching or extraction aid in the aqueous solution to a level sufficient to facilitate adequate removal of unreacted components from the lens. The foregoing may be conducted in batch or continuous processes, with or without the addition of heat, agitation or both.

[0245] Application of physical agitation may be desired to facilitate leach and release. For example, the lens mold part to which a lens is adhered can be vibrated or caused to move back and forth within an aqueous solution. Other methods may include ultrasonic waves through the aqueous solution.

[0246] The lenses may be sterilized by known means such as, but not limited to, autoclaving.

[0247] As indicated above, preferred ophthalmic devices are contact lenses, more preferably soft hydrogel contact lenses. The transmission wavelengths and percentages described herein may be measured on various thicknesses of lenses using, for instance, the methodologies described in the Examples. By way of example, a preferred center thickness for measuring transmission spectra in a soft contact lens may be from 80 to 100 microns, or from 90 to 100 microns or from 90 to 95 microns. Typically, the measurement may be made at the center of the lens using, for instance, a 4 nm instrument slit width. Various concentrations of the one or more polymerizable high energy light absorbing compounds may be used to achieve the transmission characteristics described above. For instance, the concentration may be in the range of at least 1 percent, or at least 2 percent; and up to 10 percent, or up to 5 percent, based on the weight percentages of all components in the reactive mixture, excluding diluent. A typical concentration may be in the range of 3 to 5 percent.

[0248] Silicone hydrogel ophthalmic devices (e.g., contact lenses) according to the invention preferably exhibit the following properties. All values are prefaced by "about," and the devices may have any combination of the listed properties. The properties may be determined by methods known to those skilled in the art, for instance as described in United States pre-grant publication US20180037690, which is incorporated herein by reference.

Water concentration %: at least 20 %, or at least 25 % and up to 80 % or up to 70 %

Haze: 30 % or less, or 10 % or less

Kruss dynamic contact angle (°): 100° or less, or 50° or less

Tensile Modulus (psi): (1 psi = 6894.76 Pa): 120 or less, or 80 to 120

Oxygen permeability (Dk, barrers): (1 barrer = 3.35×10^{-16} mol m (m² s Pa)⁻¹): at least 80, or at least 100, or at least 150, or at least 200

Elongation to Break: at least 100

For ionic silicon hydrogels, the following properties may also be preferred (in addition to those recited above):

Lysozyme uptake (μg/lens): at least 100, or at least 150, or at least 500, or at least 700

Polyquaternium 1 (PQ1) uptake (%): 15 or less, or 10 or less, or 5 or less

[0249] Some embodiments of the invention will now be described in detail in the following Examples.

EXAMPLES

Test Methods

[0250] Ultraviolet-visible spectra of compounds in solution were measured on a Perkin Elmer Lambda 45 or an Agilent Cary 6000i UV/VIS scanning spectrometer. The instrument was thermally equilibrated for at least thirty minutes prior to use. For the Perkin Elmer instrument, the scan range was 200-800 nm; the scan speed was 960 nm per minute; the slit width was 4 nm; the mode was set on transmission or absorbance; and baseline correction was selected. For the Cary instrument, the scan range was 200-800 nm; the scan speed was 600 nm/min; the slit width was 2 nm; the mode was transmission or absorbance; and baseline correction was selected. A baseline correction was performed before samples were analyzed using the autozero function.

[0251] Ultraviolet-visible spectra of contact lenses formed in part from the claimed compositions were measured on a Perkin Elmer Lambda 45 UV/VIS or an Agilent Cary 6000i UV/VIS scanning spectrometer using packing solution. The instrument was thermally equilibrated for at least thirty minutes prior to use. For the Perkin Elmer instrument, the scan range was 200-800 nm; the scan speed was 960 nm per minute; the slit width was 4 nm; the mode was set on transmission; and baseline correction was selected. Baseline correction was performed using cuvettes containing plastic two-piece lens holders and the same solvents. These two-piece contact lens holders were designed to hold the sample in the quartz cuvette in the location through which the incident light beam traverses. The reference cuvette also contained a two-piece holder. To ensure that the thickness of the samples is constant, all lenses were made using identical molds. The center thickness of the contact lens was measured using an electronic thickness gauge. Reported center thickness and percent transmission spectra are obtained by averaging three individual lens data.

[0252] It is important to ensure that the outside surfaces of the cuvette are completely clean and dry and that no air bubbles are present in the cuvette. Repeatability of the measurement is improved when the reference cuvette and its lens holder remain constant and when all samples use the same sample cuvette and its lens holder, making sure that both cuvettes are properly inserted into the instrument.

[0253] The following abbreviations will be used throughout the Examples and Figures and have the following meanings:

BC: back or base curve plastic mold

FC: front curve plastic mold

DMA: N, N-dimethylacrylamide (Jarchem)

HEMA: 2-hydroxyethyl methacrylate (Bimax)

PVP: poly(N-vinylpyrrolidone) (ISP Ashland)

PDMA: polydimethylacrylamide

PVMA: polyvinylmethacrylamide

EGDMA: ethylene glycol dimethacrylate (Esstech)

TEGDMA: tetraethylene glycol dimethacrylate (Esstech)

Irgacure 819: bis(2,4,6-trimethylbenzoyl)-phenylphosphineoxide (BASF or Ciba Specialty Chemicals)

Irgacure 1870: blend of bis(2,6-dimethoxybenzoyl)-2,4,4-trimethyl-pentylphosphineoxide and 1-hydroxy-cyclohexyl-phenyl-ketone (BASF or Ciba Specialty Chemicals)

mPDMS: mono-n-butyl terminated monomethacryloxypropyl terminated polydimethylsiloxane (M_n = 800-1000 daltons) (Gelest)

HO-mPDMS: mono-n-butyl terminated mono-(2-hydroxy-3-methacryloxypropyloxy)-propyl terminated polydimethylsiloxane (M_n = 400-1500 daltons) (Ortec or DSM-Polymer Technology Group)

ac-PDMS: bis-3-acryloxy-2-hydroxypropyloxypropyl polydimethylsiloxane (Tegomer V-Si 2250 from Evonik)

Blue HEMA: 1-amino-4-[3-(4-(2-methacryloyloxy-ethoxy)-6-chlorotriazin-2-ylamino)-4-sulfophenylamino]anthraquinone-2-sulfonic acid, as described in US Patent No. 5,944,853

Da: dalton or g/mole

kDa: kilodalton or an atomic mass unit equal to 1,000 daltons

SiMAA: 2-propenoic acid, 2-methyl-2-hydroxy-3-[3-[1,3,3,3-tetramethyl-1-[(trimethylsilyl)oxy]disiloxanyl]propoxy]propyl ester (Toray) or 3-(3-(1,1,1,3,5,5,5-heptamethyltrisiloxan-3-yl)propoxy)-2-hydroxypropyl methacrylate

RB247: 1,4-Bis[2-methacryloxyethylamino]-9,10-anthraquinone

BHT:- butylated hydroxytoluene

D3O: 3,7-dimethyl-3-octanol (Vigon)

DIW: deionized water

MeOH: methanol

IPA: isopropyl alcohol

HCl: hydrochloric acid

CH₂Cl₂ or DCM: methylene chloride or dichloromethane

SOCl₂: thionyl chloride

mCPBA: m-chloroperbenzoic acid

EtOAc: ethyl acetate

NH₂CH₂CH₂OH: ethanolamine or 2-aminoethanol

Norbloc: 2-(2'-hydroxy-5-methacryloyloxyethylphenyl)-2H-benzotriazole (Janssen)

PP: polypropylene which is the homopolymer of propylene

TT: Tuftec which is a hydrogenated styrene butadiene block copolymer (Asahi Kasei Chemicals)

Z: Zeonor which is a polycycloolefin thermoplastic polymer (Nippon Zeon Co Ltd)

TL03 lights: Phillips TLK 40W/03 bulbs

LED: light emitting diode

¹N NMR: proton nuclear magnetic resonance spectroscopy

UV-VIS: ultraviolet-visible spectroscopy

L: liter

mL: milliliter

Equiv. or eq.: equivalent

kg: kilogram

g: gram

mol: mole

mmol: millimole

min: minute(s)


nm: nanometer(s)

TLC: thin layer chromatography

Borate Buffered Packing Solution: 18.52 grams (300 mmol) of boric acid, 3.7 grams (9.7 mmol) of sodium borate decahydrate, and 28 grams (197 mmol) of sodium sulfate were dissolved in enough deionized water to fill a 2-liter volumetric flask.

Example 1 - Synthesis of 2-(2-cyanoacetamido)ethyl methacrylate (A) and 2-(2-cyano-2-(9H-thioxanthen-9-ylidene)acetamido)ethyl methacrylate (B) as shown in Scheme 2

[0254]



Scheme 2

20 **[0255]** Methyl cyanoacetate (40 grams, 0.4037 mole) and 25 mL of dichloromethane were stirred in a 3 neck, 500 mL round bottom flask under equipped with a reflux condenser under a nitrogen environment. 2-aminoethanol (23.8 grams, 0.3897 mole, -0.97 eq.) was added to the solution via an addition funnel, after which the temperature rose and the methylene chloride began to reflux. After the exotherm ceased, external heat was applied to continue a gentle reflux for a total of two hours, after which no ethanolamine was observed by thin layer chromatography.

25 **[0256]** The reaction may also be conducted at room temperature and is complete within a few hours.


[0257] The mixture was cooled to room temperature and all the methylene chloride was evaporated at reduced pressure. The residual oil was washed three times with 50 mL of ethyl acetate to remove unreacted starting material and non-polar impurities. The residual ethyl acetate was then removed under reduced pressure, and the resulting oil was used for acylation without any further purification.

30 **[0258]** The crude N-2-hydroxyethylacetamide derivative was dissolved in 150 mL of dichloromethane containing 40 grams of pyridine (~ 0.5 mole) in a three-neck round bottom flask equipped with a reflux condenser, an addition funnel, and a magnetic stirring bar. The flask was immersed in an ice bath and allowed to cool down to around 0°C. Methacryloyl chloride (45.76 grams, -0.44 mole) was added dropwise from the addition funnel, and the resulting reaction mixture was allowed to warm up to room temperature while constantly stirring the system. Methanol (20 mL) was added to the flask to quench any unreacted methacryloyl chloride. The volatile components were removed by rotary evaporation under reduced pressure, and the crude product dissolved in 800 mL of dilute aqueous HCl. The resulting aqueous solution was extracted three times with 100 mL of hexanes in a separatory funnel to remove any non-polar impurities. The organic layers were discarded. Sodium chloride was added to the aqueous layer which was then extracted three times with 300 mL of ethyl acetate. About 50 milligrams of BHT were added to the combined organic fractions as an inhibitor, and the ethyl acetate removed by rotary evaporation under reduced pressure. The crude product crystallized out of solution during solvent removal. When about 100 mL of ethyl acetate was left in the flask, 250 mL of hexanes was added, and the crude product was isolated by vacuum filtration using a fritted glass funnel. Thin layer chromatography indicated the presence of a single compound. The filter cake was washed two times with 150 mL of hexanes and then vacuum dried at 40°C, yielding 53 grams (about 70% yield) of 2-(2-cyanoacetamido)ethyl methacrylate (A). ¹H NMR (500 MHz, CDCl₃) δ 1.93 (3H, s, CH₃), 3.36 (2H, s, CNCH₂), 3.60 (2H, dd, CH₂NH), 4.26 (2H, t, CH₂OC=O), 5.59 (1H, m, vinylic), 6.11 (1H, bs, vinylic), 6.52 (1H, bs, NH).

45 **[0259]** A mixture of 9H-thioxanthene-9-one (2.12 grams, 0.01 mole) and thionyl chloride (5 mL, 8.2 grams, -0.07 mole) was refluxed in a 50 mL round bottom flask under a nitrogen atmosphere with constant stirring. After two hours, the red solution was evaporated to dryness ensuring that all unreacted thionyl chloride was removed from the system. 2-(2-Cyanoacetamido)ethyl methacrylate (A) (2.3 grams, 0.0117 mole, -1.17 eq.) and 15 mL of dichloromethane were added, and the resulting reaction mixture was heated to reflux under a nitrogen blanket. The reaction was monitored by thin layer chromatography. After two hours, no changes were observed in the chromatogram, so the reactive mixture was allowed to cool down to room temperature. 2-(2-cyano-2-(9H-thioxanthene-9-ylidene)acetamido)ethyl methacrylate (B) was isolated as yellow crystals (3.2 grams, 82% yield) after passing through a short silica gel column (CH₂Cl₂, followed by 8 weight % EtOAc in CH₂Cl₂). The UV-VIS transmission spectrum of a 0.2 mM methanol solution Compound B is shown in FIG. 1. ¹H NMR (500 MHz, CDCl₃) δ 1.84 (3H, s, CH₃), 3.47 (2H, m, CH₂NH), 4.01 (2H, t, CH₂OC=O), 5.55 (1H, m, vinylic), 5.91 (1H, bs, NH), 5.98 (1H, bs, vinylic), 7.24 (1H, t, Ar-H), 7.31 (1H, t, Ar-H), 7.39 (2H, m, Ar-H), 7.49 (1H, d, Ar-H), 7.55 (1H, m, Ar-H), 7.61 (1H, d, Ar-H), 8.04 (1H, m, Ar-H).

Example 2 - Synthesis of 2-(2-cyano-2-(9H-xanthen-9-ylidene)acetamido)ethyl methacrylate (C) as shown in Scheme 3

[0260]



Scheme 3

15

[0261] A mixture of 9H-xanthen-9-one (5.0 grams, 0.0255 mole) and thionyl chloride (10 mL, 16.4 grams, 0.138 mole) was refluxed in a 50 mL round bottom flask under a nitrogen atmosphere with constant stirring. After three hours, the red solution was evaporated to dryness ensuring that all unreacted thionyl chloride was removed from the system. 2-(2-cyanoacetamido)ethyl methacrylate (A) (6.0 grams, 0.0306 mole, ~1.2 eq.) and 20 mL of dichloromethane were added and the resulting reaction mixture was heated to reflux under a nitrogen blanket. The reaction was monitored by thin layer chromatography. The mixture was cooled to room temperature after 2.5 hours and 2-(2-cyano-2-(9H-xanthen-9-ylidene)acetamido)ethyl methacrylate (C) purified after passing through a short silica gel column (CH_2Cl_2 , and ethyl acetate in CH_2Cl_2). The off-white precipitate formed during rotary evaporation is washed with hexane and dried in a vacuum oven at 40°C overnight. The UV-VIS transmission spectrum of Compound (C) is shown in FIG. 1 in a 0.2 mM methanol solution. ^1H NMR(500 MHz, CDCl_3) δ 1.85 (3H, s, CH_3), 3.60 (2H, dd, CH_2NH), 4.2 (2H, t, $\text{CH}_2\text{OC}=\text{O}$), 5.53 (1H, t, vinylic), 5.99 (1H, bs, vinylic), 6.17 (1H, t, NH), 7.12 (1H, t, Ar-H), 7.29-7.34 (3H, m, Ar-H), 7.45 (1H, ddd, Ar-H), 7.52 (1H, ddd, Ar-H), 7.67 (1H, dd, Ar-H), 8.41 (1H, dd, Ar-H).


20

25

Example 3 - Synthesis of 2-(2-cyano-2-(10-methylacridin-9(10H)-ylidene)acetamido)ethyl methacrylate (D) as shown in Scheme 4 (Prophetic)

30

[0262]



Scheme 4

45


[0263] A mixture of 10-methylacridin-9(10H)-one (2.09 grams, 0.01 mole) and thionyl chloride (5 mL, 8.2 grams, -0.07 mole) is refluxed in a 50 mL round bottom flask under a nitrogen atmosphere with constant stirring. After two hours, the solution is evaporated to dryness ensuring that all unreacted thionyl chloride is removed from the system. 2-(2-cyanoacetamido)ethyl methacrylate (A) (2.3 grams, 0.0117 mole, ~1.17 eq.) and 15 mL of dichloromethane are added and the resulting reaction mixture is heated to reflux under a nitrogen blanket. The reaction is monitored by thin layer chromatography. When no changes are observed in the chromatogram, the reactive mixture is allowed to cool down to room temperature. 2-(2-cyano-2-(10-methylacridin-9(10H)-ylidene)acetamido)ethyl methacrylate (D) may be isolated by known methods, for instance after passing through a short silica gel column.

50

Example 4 - Synthesis of 2-(2-cyano-2-(10,10-dioxido-9H-thioxanthen-9-ylidene)acetamido)ethyl methacrylate (E) as shown in Scheme 5

55

[0264]



Scheme 5


15 **[0265]** To a chilled solution of 2-(2-cyano-2-(9H-thioxanthen-9-ylidene)acetamido)ethyl methacrylate (B) (2.0 grams, 5.2 mmol) in dichloromethane, 2.32 grams of m-chloroperbenzoic acid (75% purity, ~ 2 eq., mCPBA) were added. The mixture was stirred cold for one hour and then allowed to warm up to room temperature. The solution lost its yellow color as the reaction proceeded, and a white solid crystallized or precipitated out of solution. The volatiles were evaporated under reduced pressure. The residue was re-dissolved in ethyl acetate and extracted with dilute aqueous base, followed by dilute aqueous saline solutions. The organic layer was separated, and the solvent removed by rotary evaporation under reduced pressure. The residue was washed with hexanes over a fritted glass funnel and vacuum dried. The UV-VIS transmission spectrum of a 0.2 mM methanolic solution of Compound E is shown in FIG. 1. ¹H NMR(500 MHz, CDCl₃) δ 1.85 (3H, s, CH₃), 3.35 (1H, m, CH₂NH), 3.61 (1H, m, CH₂NH), 3.81 (1H, m, CH₂OC=O), 4.05 (1H, m, CH₂OC=O), 5.55 (1H, m, vinylic), 5.95 (1H, m, vinylic), 6.35 (1H, bs, NH), 7.5-7.75 (5H, m, Ar-H), 8.03 (2H, t, Ar-H), 8.12 (1H, d, Ar-H).

20

25

Example 5 - Synthesis of 2-(2-cyanoacetamido)ethyl methacrylate (F) and N-(2-(2-cyano-2-(9H-thioxanthen-9-ylidene)acetamido)ethyl)methacrylamide (G) as shown in Scheme 6

30 **[0266]**



Scheme 6

50 **[0267]** Methyl cyanoacetate (22 grams, 0.22 mole) and 250 mL of dichloromethane were stirred in a 3 neck, 500 mL round bottom flask under equipped with a reflux condenser under a nitrogen environment. The solution is cooled in a water bath and 1,2-diaminoethane (12 grams, 0.2 mole, ~0.9 eq.) added to the mixture. As the reaction progresses, the mixture appears more and more heterogenous, with the product crashing out of solution. After four hours of stirring at room temperature, the volatiles are evaporated under reduced pressure and the residue is washed with ethyl acetate over a fritted glass funnel and dried at 50°C prior to further use. ¹H NMR (500 MHz, D₂O) δ 2.74 (2H, t, CH₂NH₂), 3.29 (2H, t, CH₂NH), 3.38 (2H, s, CH₂CN).

55


[0268] 2-aminoethyl cyanoacetamide (12.7 g, 0.1 mole) and 12.0 grams of sodium carbonate are stirred in 150 mL of methanol while being chilled in an ice bath. Methacryloyl chloride (11.5 g, 1.1 eq.) is added to the suspension in a

dropwise manner, while maintaining the reaction temperature below 30°C at all times. Once the reaction is complete, evaporate all volatiles under reduced pressure, redissolve the product in acetonitrile and filter the solution to remove all the salts present. Evaporate the acetonitrile under reduced pressure and wash the resulting solids with ethyl acetate over a fritted glass funnel to obtain the desired 2-(2-cyanoacetamido)ethyl methacrylamide (F). ¹H NMR (500 MHz, CD₃OD) δ 1.86 (3H, s, CH₃), 3.22-3.26 (4H, m, NH, CH₂CN), 3.29 (4H, m, CH₂NH), 5.31 (1H, m, vinylic), 5.63 (1H, m, vinylic).

[0269] A mixture of thioxanthone (4.24 grams, 0.02 mole) and 8 mL of thionyl chloride (13.12 grams, -0.11 mole) was gently refluxed under a nitrogen atmosphere with constant stirring. After two hours of heating, the solution was evaporated to dryness under reduced pressure, ensuring that all unreacted thionyl chloride was removed. 2-(2-cyanoacetamido)ethyl methacrylamide (F) (4.2 grams, ~1.1 eq.) and 20 mL of degassed methylene chloride were added to the flask, and the mixture was gently refluxed for 3 hours under a nitrogen environment, while monitoring the progress by TLC. The volatiles were evaporated under reduced pressure, and the organics are washed with ethyl acetate. Large quantities of a precipitate enriched with the major product were observed. The suspension was filtered, and the residual solids washed with ethyl acetate prior to drying in a vacuum oven. The UV-VIS transmission spectrum of a 0.2 mM methanolic solution of Compound G is shown in FIG. 2. ¹H NMR (500 MHz, CDCl₃) δ 1.89 (3H, s, CH₃), 3.26 (2H, m, CH₂NH), 3.32 (2H, m, CH₂NH), 5.33 (1H, m, vinylic), 5.68 (1H, m, vinylic), 6.63 (1H, m, NH), 6.49 (1H, m, NH), 7.25 (1H, m, Ar-H), 7.33 (1H, dt, Ar-H), 7.39 (2H, m, Ar-H), 7.51-7.59 (3H, m, Ar-H), 8.05 (1H, m, Ar-H).

Example 6 - N-(2-(2-cyano-2-(10-methylacridin-9(10H)ylidene)acetamido)ethyl) methacrylamide (H) as shown in Scheme 7

[0270]



Scheme 7

[0271] N-(2-Aminoethyl)-2-cyanoacetamide (2): Compound 1 (30 g, 303 mmol, 1.0 equiv) was added to a solution of ethylene diamine (54.5 g, 909 mmol, 3 equiv) in dichloromethane (600 mL) at -20 °C over 30 minutes. The reaction was warmed to room temperature over 2 hours and stirred for 3 hours, at which point LC-MS indicated the reaction was complete. The resulting precipitate was filtered and washed with dichloromethane (2 × 100 mL) to give compound 2 (25 g, 66% yield, >95% purity) as a white solid.

[0272] N-(2-(2-Cyanoacetamido)ethyl) methacrylamide (3): A solution of methylacrylic anhydride (41 g, 264 mmol, 1.3 equiv) and triethylamine (40 mL, 287 mmol, 1.3 equiv) in dichloromethane (300 mL) was stirred at room temperature for 1 hour. The reaction was cooled to 0 °C and compound 2 (28 g, 220 mmol, 1.0 equiv) was added portionwise to the reaction mixture at 0 °C. The reaction was warmed to room temperature and stirred for 5 hours, at which point LC-MS indicated the reaction was complete. The resulting precipitate was filtered and washed with dichloromethane (2 × 100 mL) to give compound 3 (25.1 g, 60% yield, >95% purity) as a white solid.

[0273] 9,9-Dichloro-10-methyl-9,10-dihydroacridine (5): Compound 4 (10 g, 4.85 mmol, 1.0 equiv) in thionyl chloride (200 mL, 2.75 mol, 55 equiv) was stirred at 60 °C for 2 hours, at which point ¹H-NMR indicated the reaction was complete. The thionyl chloride was removed under reduced pressure. The residue was azeotroped with toluene (2 × 20 mL) to give crude compound 5 as a yellow solid (12.5 g), which was used subsequently.


[0274] N-(2-(2-Cyano-2-(10-methylacridin-9(10H)ylidene)acetamido)ethyl) methacrylamide (H): Triethylamine (20 mL, 143 mmol, 3.0 equiv) was added dropwise to a solution of the crude compound 5 (12.5 g, 48.5 mmol, 1.0 equiv) and compound 3 (9.33 g, 48.5 mmol, 1.0 equiv) in 1 to 1 mixture of dichloromethane and acetonitrile (200 mL) at 0 °C over 30 minutes. The reaction was warmed to room temperature and stirred for 2 hours, at which point LC-MS indicated the reaction was complete. The mixture was passed through a plug of silica gel (150 g), eluting with dichloromethane (500 mL). The organics were concentrated under reduced pressure. The residue was purified over silica gel (800 g),

eluting with ethyl acetate, to give compound (H) as a yellow solid. The solid was triturated with methyl tert-butyl ether (2×200 mL) for 2 hours. The solid was collected by filtration and triturated with chloroform (50 mL) for 30 minutes to give the pure compound (H) (11.9 g, 60% yield from two steps, 97.5% purity) as a yellow solid.

[0275] The UV-VIS transmission spectrum of a 0.2 mM methanolic solution of Compound H is shown in FIG. 2. ^1H NMR (500 MHz, DMSO- d_6) δ 1.87 (3H, m, CH_3), 3.15-3.20 (4H, m, CH_2NH), 3.72 (3H, s, CH_3N), 5.36 (1H, s, vinylic), 5.68 (1H, m, vinylic), 7.14 (1H, bt, NH), 7.29 (1H, bt, NH), 7.49-7.65 (4H, m, Ar-H), 8.02 - 8.81 (4H, Ar-H).

Example 7 - Synthesis of 2-(2-cyanoacetamido)ethyl acrylamide (I) and N-(2-(2-cyano-2-(9H-xanthen-9-ylidene)acetoamido)ethyl)acrylamide (J) as shown in Scheme 8

[0276]




Scheme 8

[0277] 2-(2-Cyanoacetamido)ethyl acrylamide (I) was prepared by the same methodology as used for 2-(2-cyanoacetamido)ethyl methacrylate (F). 2-aminoethyl cyanoacetamide (12.7 g, 0.1 mole) and 12.0 grams of sodium carbonate are stirred in 150 mL of methanol while being chilled in an ice bath. Acryloyl chloride (9.9 g, 1.1 eq.) is added to the suspension in a dropwise manner, while maintaining the reaction temperature below 30°C at all times. Once the reaction is complete, evaporate all volatiles under reduced pressure, redissolve the product in acetonitrile and filter the solution to remove all the salts present. Evaporate the acetonitrile under reduced pressure and wash the resulting solids with ethyl acetate over a fritted glass funnel to obtain the desired 2-(2-cyanoacetamido)ethyl acrylamide(I). ^1H NMR (500 MHz, CD_3OD) δ 3.22-3.31 (8H, m, NH, CH_2), 5.59 (1H, dd, vinylic), 6.14 (2H, dd, vinylic).

[0278] A mixture of xanthone (3.92 grams, 0.02 mole) and 5 mL of thionyl chloride (8.2 grams, -0.07 mole) in 10 mL of toluene was gently refluxed under a nitrogen atmosphere with constant stirring. After six hours of heating, the solution cooled and volatiles were evaporated under reduced pressure, ensuring that all unreacted thionyl chloride was removed from the system. 2-(2-cyanoacetamido)ethyl acrylamide (I) (3.8 grams, -1.05 eq.) and 20 mL of methylene chloride were added to the flask, and the mixture was gently refluxed for 3 hours under a nitrogen environment, while monitoring the progress by TLC. Volatile components were evaporated under reduced pressure. The residue was washed with warm ethyl acetate and filtered over a fritted glass funnel. The filter cake was washed with additional ethyl acetate, followed by water. The light-yellow solid was dried in a vacuum oven. The UV-VIS transmission spectrum of a 0.2 mM methanolic solution of Compound J is shown in FIG. 2. ^1H NMR (500 MHz, DMSO- d_6) δ 3.15-3.25 (4H, m, CH_2), 5.62 (1H, dd, vinylic), 6.08-6.23 (2H, m, vinylic), 7.32-7.75 (1H, dt, Ar-H), 7.46-7.72 (6H, Ar-H), 8.17 (1H, bt, NH), 8.34 (1H, dd, Ar-H), 8.88 (1H, bt, NH).

Example 8 - Synthesis of 2-(2-cyanoacetoxy)ethyl methacrylate (K) and 2-(2-cyano-2-(9H-thioxanthen-9-ylidene)acetoxy)ethyl methacrylate (L) as shown in Scheme 9

[0279]



Scheme 9

[0280] 2-(2-Cyanoacetoxy)ethyl methacrylate (K) was prepared by coupling cyanoacetic acid with 2-hydroxyethyl methacrylate as follows. Cyanoacetic acid (9 g, 0.106 mole) and 13g of 2-hydroxyethyl methacrylate (HEMA, are stirred in 250 mL of dichloromethane, and ethyl dimethylaminopropyl carbodiimide hydrochloride (EDC) is added to the suspension in 4 batches of 5 grams each (20 g, 0.104 mole). The mixture gradually becomes more homogenous as the less polar derivative is formed and volatiles are evaporated under reduced pressure after completion of the reaction. The product is redissolved in a 25:75 mixture of ethyl acetate and hexanes by weight and extracted several times with deionized water to remove any residual salts and unreacted HEMA. A small amount of 4-methoxyhydroquinone (<20 mg) is added to the organic layer and the product is obtained pure after evaporation of the solvents under reduced pressure. ¹H NMR (500 MHz, CDCl₃) δ 1.92 (3H, m, CH₃), 3.47 (2H, s, NCCH₂), 4.36 (2H, m, OCH₂), 4.44 (2H, m, OCH₂), 4.59 (1H, m, vinylic), 6.10 (1H, m, vinylic).

[0281] A mixture of thioxanthone (4.24 grams, 0.02 mole) and 8 mL of thionyl chloride (13.12 grams, ~0.11 mole) was gently refluxed under a nitrogen atmosphere with constant stirring. After two hours of heating, the solution was evaporated to dryness under reduced pressure, ensuring that all unreacted thionyl chloride was removed. A solution of 2-(2-cyanoacetoxy)ethyl methacrylate (K) (4.33 grams, ~1.1 eq.) in 20 mL of degassed methylene chloride was added to the flask, and the mixture was gently refluxed for 3 hours under a nitrogen environment, while monitoring the progress by TLC. The residue was washed with methanol to remove most of the unreacted starting thioxanthone, re-concentrated, and the crude product was purified by chromatography over a silica gel plug and vacuum dried overnight. The UV-VIS transmission spectrum of a 0.2 mM solution of Compound L in dichloromethane is shown in Fig. 2. ¹H NMR (500 MHz, CDCl₃) δ 1.92 (3H, s, CH₃), 4.36 (2H, m, CH₂), 4.44 (2H, m, CH₂), 5.59 (1H, m, vinylic), 6.10 (1H, m, vinylic), 7.24-7.62 (7H, m, Ar-H), 8.1 (1H, m, Ar-H).

Example 9 - Silicone Hydrogel Formulations Comprising Compound (B)

[0282] Reactive monomer mixtures were prepared composed of 77 weight percent of the formulations listed in Table 4 and 23 weight percent of the diluent D3O. The reactive monomer mixtures were individually filtered through a 3 μm filter using a stainless-steel syringe under pressure.

TABLE 4

Component	Ex 9A (weight %)	Ex 9B (weight %)	Ex 9C (weight %)	Ex 9D (weight %)
mPDMS 1000	30.85	30.7	30.55	30.39
SiMAA	27.61	27.48	27.35	27.2
DMA	23.76	23.6	23.53	23.4
HEMA	5.94	5.91	5.88	5.85
TEGDMA	1.52	1.52	1.51	1.5
PVP K90	6.9	6.9	6.8	6.8
Irgacure 1870	0.35	0.34	0.34	0.34

(continued)

Component	Ex 9A (weight %)	Ex 9B (weight %)	Ex 9C (weight %)	Ex 9D (weight %)
RB247	0.02	0.02	0.02	0.02
Compound (B)	3.05	3.03	3.02	3
Norbloc®	0	0.5	1	1.5
Σ Components	100	100	100	100

[0283] Formulations 9A-9D were degassed at ambient temperature by applying vacuum (40 torr, 5333 Pa) for 45 minutes. Then, in a glove box with a nitrogen gas atmosphere and less than about 0.1-0.2 percent oxygen gas, about 75 μ L of the reactive mixture were dosed using an Eppendorf pipet at room temperature into the FC made of 90:10 (w/w) Zeonor/TT blend. The BC made of 90:10 (w/w) Z:TT blend was then placed onto the FC. The molds were equilibrated for a minimum of twelve hours in the glove box prior to dosing. Pallets containing eight mold assemblies each were transferred into an adjacent glove box maintained at 65°C, and the lenses were cured from the top and the bottom for 15 minutes using 435 nm LED lights having an intensity of about 2 mW/cm² at the tray's location.

[0284] The lenses were manually de-molded with most lenses adhering to the FC and released by suspending the lenses in about one liter of 70 percent IPA for about one hour, followed by soaking two more times with fresh 70 percent IPA for 30 minutes; then two times with fresh DIW for 15 minutes; then two times with packing solution for 30 minutes. The lenses were equilibrated and stored in borate buffered packaging solution. A person of ordinary skill recognizes that the exact lens release process can be varied depending on the lens formulation and mold materials, regarding the concentrations of the aqueous isopropanol solutions, the number of washings with each solvent, and the duration of each step. The purpose of the lens release process is to release all of the lenses without defects and transition from diluent swollen networks to the packaging solution swollen hydrogels. The average center thickness of each lens set was measured; 9A = 87.7 microns, 9B = 85.3 microns, 9C = 87.3 microns, and 9D = 85.7 microns.

[0285] Figures 3-5 show the UV-VIS spectra of the lenses made from Formulations 9A-9D demonstrating that compound (B) or combinations of compound (B) and Norbloc® may provide complete or nearly complete absorption between 300 nm and 400 nm with some absorption in the high energy visible region between 400 nm and 450 nm.

Example 10 - Silicone Hydrogel Formulations Comprising Compounds (B) and (C)

[0286] Reactive monomer mixtures were prepared composed of 77 weight percent of the formulations listed in Table 5 and 23 weight percent of the diluent D3O. The reactive monomer mixtures were individually filtered through a 3 μ m filter using a stainless-steel syringe under pressure.

TABLE 5

Component	Ex 10A (weight %)	Ex 10B (weight %)	Ex 10C (weight %)	Ex 10D (weight %)
mPDMS 1000	30.87	30.69	30.51	30.33
SiMAA	27.66	27.5	27.34	27.18
DMA	23.83	23.7	23.57	23.44
HEMA	5.98	5.95	5.92	5.89
TEGDMA	1.5	1.5	1.5	1.5
PVP K90	6.8	6.8	6.8	6.8
Irgacure 1870	0.34	0.34	0.34	0.34
RB247	0.02	0.02	0.02	0.02
Compound (B)	0	3	3	3
Compound (C)	3	0.5	1	1.5
Σ Components	100	100	100	100

[0287] Formulations 10A-10D were degassed at ambient temperature by applying vacuum (40 torr, 5333 Pa) for 45 minutes. Then, in a glove box with a nitrogen gas atmosphere and less than about 0.1-0.2 percent oxygen gas, about

75 μ L of the reactive mixture were dosed using an Eppendorf pipet at room temperature into the FC made of 90:10 (w/w) Zeonor/TT blend. The BC made of 90:10 (w/w) Z:TT blend was then placed onto the FC. The molds were equilibrated for a minimum of twelve hours in the glove box prior to dosing. Pallets containing eight mold assemblies each were transferred into an adjacent glove box maintained at 65°C, and the lenses were cured from the top and the bottom for 15 minutes using 435 nm LED lights having an intensity of about 2 mW/cm² at the tray's location.

[0288] The lenses were manually de-molded with most lenses adhering to the FC and released by suspending the lenses in about one liter of 70 percent IPA for about one hour, followed by soaking two more times with fresh 70 percent IPA for 30 minutes; then two times with fresh DIW for 15 minutes; then two time with packing solution for 30 minutes. The lenses were equilibrated and stored in borate buffered packaging solution. A person of ordinary skill recognizes that the exact lens release process can be varied depending on the lens formulation and mold materials, regarding the concentrations of the aqueous isopropanol solutions, the number of washings with each solvent, and the duration of each step. The purpose of the lens release process is to release all of the lenses without defects and transition from diluent swollen networks to the packaging solution swollen hydrogels. The average center thickness of each lens set was measured; 10A = 93.7 microns, 10B = 93.7 microns, 10C = 95.3 microns, and 10D = 92.3 microns.

[0289] Figures 6-8 show the UV-VIS spectra of the lenses made from Formulations 10A-10D demonstrating that combinations of compounds (B) and (C) may provide complete or nearly complete absorption between 300 nm and 400 nm with some absorption in the high energy visible region between 400 nm and 450 nm. The figures also demonstrate that compound (C) alone provides absorption at various wavelength ranges.

Example 11

[0290] Lenses were made using the reactive monomer mixture comprising the components listed as 9D in Table 4 and same curing and hydration steps except that the oxygen gas concentration in the glove box was less than 0.5%. Lenses were packaged in glass vials containing PS and then placed either on a window sill with direct sunlight (11A) or on top of a cabinet without exposure to direct sunlight, only indoor lighting (11B). Controls were stored in the dark. After 3, 5, 9, 15, and 21 weeks of exposure, UV-Visible transmission spectra of the lenses were measured as shown in FIG. 9 and FIG. 10.

[0291] For lenses exposed to direct sunlight, the absorption of high energy visible light between 400 nm and 450 nm did not change over time. There were minor (about 1%) changes in the UV-VIS transmission spectra between 450 nm and 700 nm over the duration of the study.

[0292] For lenses exposed to indoor lighting, the absorption of high energy visible light between 400 nm and 450 nm did not change over time. The UV-VIS transmission spectra did not change more than about 2% or 3% between 450 nm and 700 nm over the duration of the study.

Examples 12-25 are prophetic

Example 12: (Z)-2-(2-cyano-2-(3-hydroxyacridin-9(10H)-ylidene)acetamido)ethyl methacrylate

[0293] The title compound can be synthesized by analogous procedures to those described above, starting from 3-hydroxyacridone (CAS reg. no. 20168-55-2).

Example 13: 2-(2-cyano-2-(10-methylacridin-9(10H)-ylidene)acetamido)ethyl methacrylate

[0294] The title compound can be synthesized by analogous procedures to those described above, starting from N-methylacridone (719-54-0).

Example 14: 2-(2-cyano-2-(3,6-dihydroxyacridin-9(10H)-ylidene)acetamido)ethyl methacrylate

[0295] The title compound can be synthesized by analogous procedures to those described above, starting from 3,6-dihydroxyacridone (122105-95-7).

Example 15: (E)-2-(2-(7H-benzo[c]xanthen-7-ylidene)-2-cyanoacetamido)ethyl methacrylate

[0296] The title compound can be synthesized by analogous procedures to those described above, starting from benzo[C]xanthone (63154-69-8).

Example 16: (Z)-2-(2-cyano-2-(3-methoxy-9H-xanthen-9-ylidene)acetamido)ethyl methacrylate

[0297] The title compound can be synthesized by analogous procedures to those described above, starting from 3-methoxyxanthone (3722-52-9).

Example 17: 2-(2-cyano-2-(3,6-dihydroxy-9H-xanthen-9-ylidene)acetamido)ethyl methacrylate

[0298] The title compound can be synthesized by analogous procedures to those described above, starting from 3,6-dihydroxyxanthone (1214-24-0).

Example 18: (E)-2-(2-cyano-2-(2-methyl-9H-xanthen-9-ylidene)acetamido)ethyl methacrylate

[0299] The title compound can be synthesized by analogous procedures to those described above, starting from 2-methylxanthone (2680-45-1).

Example 19: (E)-2-(2-cyano-2-(1-hydroxy-9H-xanthen-9-ylidene)acetamido)ethyl methacrylate

[0300] The title compound can be synthesized by analogous procedures to those described above, starting from 1-hydroxyxanthone (19-41-5).

Example 20: (E)-2-(2-cyano-2-(2,4-dichloro-9H-thioxanthen-9-ylidene)acetamido)ethyl methacrylate

[0301] The title compound can be synthesized by analogous procedures to those described above, starting from 2,4-dichlorothioxanthone.

Example 21: (E)-2-(2-(2-chloro-9H-thioxanthen-9-ylidene)-2-cyanoacetamido)ethyl methacrylate

[0302] The title compound can be synthesized by analogous procedures to those described above, starting from 2-chlorothioxanthone.

Example 22: (E)-2-(2-cyano-2-(2-isopropyl-9H-thioxanthen-9-ylidene)acetamido)ethyl methacrylate and (E)-2-(2-cyano-2-(4-isopropyl-9H-thioxanthen-9-ylidene)acetamido)ethyl methacrylate

[0303] The title compounds can be synthesized as a mixture by analogous procedures to those described above, starting from a mixture of 2 and 4-isopropyl thioxanthone.

Examples 23-25

[0304] Contact lenses from the silicone hydrogel formulations shown in Table 6 can be prepared using analogous procedures to those described in Example 6. In these examples, 77 weight percent of the formulations listed in Table 6 are diluted with 23 weight percent of diluent (e.g., D3O).

TABLE 6


Component	Ex 23 (weight %)	Ex. 24 (weight %)	Ex. 25 (weight %)
OH-mPDMS (n=15)	28.00	28.50	28.00
OH-mPDMS (n=4)	25.00	25.50	25.00
ac-PDMS	5.00	4.00	5.00
DMA	24.00	20.00	20.00
HEMA	7.98	7.98	7.98
Blue HEMA	0.02	0.02	0.02
PDMA (M _w =740kDa)	5.00	0	0
PVP K90	0	7.00	9.00
PVMA (M _w =570kDa)	0	2.00	0

(continued)

Component	Ex. 23 (weight %)	Ex. 24 (weight %)	Ex. 25 (weight %)
EGDMA	0.25	0.25	0.25
Compound (B)	3.00	3.00	3.00
Norbloc® or compound (C)	1.50	1.50	1.50
Irgacure 1870	0.25	0.25	0.25
Σ Components	100	100	100

Claims

1. An ophthalmic device that is a free radical reaction product of a reactive mixture comprising: one or more monomers suitable for making the ophthalmic device; and a polymerizable high energy light absorbing compound of formula I:



Formula I

wherein:

m and n are independently 0, 1, 2, 3, or 4;

T is a bond, O, or NR;

X is O, S, NR, SO, or SO₂;

Y is a linking group;

P_g is a polymerizable group;

R at each occurrence is independently H, C₁-C₆ alkyl, cycloalkyl, heterocycloalkyl, aryl, heteroaryl, or Y-P_g;


R¹ and R², when present, are independently at each occurrence C₁-C₆ alkyl, C₁-C₆ alkoxy, C₁-C₆ thioalkyl, C₃-C₇ cycloalkyl, aryl, halo, hydroxy, amino, NR³R⁴, or benzyl, wherein R³ and R⁴ are independently H or C₁-C₆ alkyl, or two adjacent R¹ or R² groups, together with the carbon atoms to which they are attached, combine to form a cycloalkyl or aryl ring; and

EWG is an electron withdrawing group.

2. The ophthalmic device of claim 1 wherein the reactive mixture further comprises a second polymerizable high energy light absorbing compound; optionally wherein the second polymerizable high energy light absorbing compound is a UV absorbing compound; for example wherein the UV absorbing compound is a compound of formula I, a benzophenone, a benzotriazole, a triazine, a substituted acrylonitrile, a salicyclic acid derivative, a benzoic acid derivative, a cinnamic acid derivative, a chalcone derivative, a dyponone derivative, a crotonic acid derivative, or mixtures thereof.
3. The ophthalmic device of claims 1 or 2 wherein the reactive mixture comprises a mixture of:
- (a) a compound of formula I wherein X is S and a compound of formula I wherein X is O; or
- (b) a compound of formula I wherein X is S and a benzotriazole UV absorbing compound.
4. The ophthalmic device of any one of claims 1 to 3 wherein the monomer suitable for making the ophthalmic device comprises a hydrophilic component, a silicone-containing component, or mixtures thereof.

5. The ophthalmic device of any one of claims 1 to 4 that is a contact lens, a corneal onlay, a corneal inlay, an intraocular lens, or an overlay lens; optionally wherein the ophthalmic device is a hydrogel contact lens.
6. A method for making an ophthalmic device, the method comprising:

(a) providing a reactive mixture containing one or more device forming monomers, a radical initiator, and a compound of formula I:



Formula I

wherein:

m and n are independently 0, 1, 2, 3, or 4;

T is a bond, O, or NR;

X is O, S, NR, SO, or SO₂;

Y is a linking group;

P_g is a polymerizable group;

R at each occurrence is independently H, C₁-C₆ alkyl, cycloalkyl, heterocycloalkyl, aryl, heteroaryl, or Y-P_g;

R¹ and R², when present, are independently at each occurrence C₁-C₆ alkyl, C₁-C₆ alkoxy, C₁-C₆ thioalkyl, C₃-C₇ cycloalkyl, aryl, halo, hydroxy, amino, NR³R⁴, or benzyl, wherein R³ and R⁴ are independently H or C₁-C₆ alkyl, or two adjacent R¹ or R² groups, together with the carbon atoms to which they are attached, combine to form a cycloalkyl or aryl ring; and

EWG is an electron withdrawing group; and

(b) polymerizing the reactive mixture to form the ophthalmic device.

7. The ophthalmic device of any preceding claim, or the method of any preceding claim, wherein m and n are each independently 0 or 1.
8. The ophthalmic device of any preceding claim, or the method of any preceding claim, wherein Y at each occurrence is independently alkylene, cycloalkylene, heterocycloalkylene, arylene, heteroarylene, oxaalkylene, alkylene-amide-alkylene, alkylene-amine-alkylene, or combinations thereof.
9. The ophthalmic device of any preceding claim, or the method of any preceding claim, wherein P_g comprises styryl, vinyl carbonate, vinyl ether, vinyl carbamate, N-vinyl lactam, N-vinylamide, (meth)acrylate, or (meth)acrylamide.
10. The ophthalmic device of any preceding claim, or the method of any preceding claim, wherein X is:
- (a) O; or
- (b) S.
11. The ophthalmic device of any preceding claim, or the method of any preceding claim, wherein EWG is cyano, amide, ester, keto, or aldehyde; optionally wherein EWG is cyano.
12. The ophthalmic device of any one of claims 1 to 5, or the method of claim 6, wherein the compound of formula I is:

2-(2-cyano-2-(9H-thioxanthen-9-ylidene)acetamido)ethyl methacrylate;

2-(2-cyano-2-(9H-thioxanthen-9-ylidene)acetamido)ethyl acrylate;

N-(2-(2-cyano-2-(9H-thioxanthen-9-ylidene)acetamido)ethyl)methacrylamide;
 N-(2-(2-cyano-2-(9H-thioxanthen-9-ylidene)acetamido)ethyl)acrylamide;
 2-(2-cyano-N-methyl-2-(9H-thioxanthen-9-ylidene)acetamido)ethyl methacrylate;
 2-cyano-2-(9H-thioxanthen-9-ylidene)-N-(2-(N-vinylacetamido)ethyl)acetamide;
 2-(2-cyano-2-(9H-xanthen-9-ylidene)acetamido)ethyl methacrylate;
 2-(2-cyano-2-(9H-xanthen-9-ylidene)acetamido)ethyl acrylate;
 N-(2-(2-cyano-2-(9H-xanthen-9-ylidene)acetamido)ethyl)methacrylamide;
 N-(2-(2-cyano-2-(9H-xanthen-9-ylidene)acetamido)ethyl)acrylamide;
 2-(2-cyano-N-methyl-2-(9H-xanthen-9-ylidene)acetamido)ethyl methacrylate;
 2-cyano-N-(2-(N-vinylacetamido)ethyl)-2-(9H-xanthen-9-ylidene)acetamide;
 2-(2-(acridin-9(10H)-ylidene)-2-cyanoacetamido)ethyl acrylate;
 N-(2-(2-(acridin-9(10H)-ylidene)-2-cyanoacetamido)ethyl)methacrylamide;
 N-(2-(2-(acridin-9(10H)-ylidene)-2-cyanoacetamido)ethyl)acrylamide;
 2-(2-(acridin-9(10H)-ylidene)-2-cyano-N-methylacetamido)ethyl methacrylate;
 2-(acridin-9(10H)-ylidene)-2-cyano-N-(2-(N-vinylacetamido)ethyl)acetamide;
 2-(2-cyano-2-(9H-thioxanthen-9-ylidene)acetamido)-2-methylpropyl methacrylate;
 2-(2-cyano-2-(9H-xanthen-9-ylidene)acetoxo)-2-methylpropyl acrylate;
 (Z)-2-(2-cyano-2-(3-hydroxyacridin-9(10H)-ylidene)acetamido)ethyl methacrylate;
 2-(2-cyano-2-(10-methylacridin-9(10H)-ylidene)acetamido)ethyl methacrylate;
 2-(2-cyano-2-(3,6-dihydroxyacridin-9(10H)-ylidene)acetamido)ethyl methacrylate;
 (E)-2-(2-(7H-benzo[c]xanthen-7-ylidene)-2-cyanoacetamido)ethyl methacrylate;
 (Z)-2-(2-cyano-2-(3-methoxy-9H-xanthen-9-ylidene)acetamido)ethyl methacrylate;
 2-(2-cyano-2-(3,6-dihydroxy-9H-xanthen-9-ylidene)acetamido)ethyl methacrylate;
 (E)-2-(2-cyano-2-(2-methyl-9H-xanthen-9-ylidene)acetamido)ethyl methacrylate;
 (E)-2-(2-cyano-2-(1-hydroxy-9H-xanthen-9-ylidene)acetamido)ethyl methacrylate;
 (E)-2-(2-cyano-2-(2,4-dichloro-9H-thioxanthen-9-ylidene)acetamido)ethyl methacrylate;
 (E)-2-(2-(2-chloro-9H-thioxanthen-9-ylidene)-2-cyanoacetamido)ethyl methacrylate;
 (E)-2-(2-cyano-2-(2-isopropyl-9H-thioxanthen-9-ylidene)acetamido)ethyl methacrylate;
 (E)-2-(2-cyano-2-(4-isopropyl-9H-thioxanthen-9-ylidene)acetamido)ethyl methacrylate;
 2-(3-oxo-2-(9H-thioxanthen-9-ylidene)propanamido)ethyl methacrylate;
 2-(3-oxo-2-(9H-thioxanthen-9-ylidene)butanamido)ethyl methacrylate;
 2-(3-methoxy-3-oxo-2-(9H-thioxanthen-9-ylidene)propanamido)ethyl methacrylate;
 2-(3-amino-3-oxo-2-(9H-thioxanthen-9-ylidene)propanamido)ethyl methacrylate;
 2-(2-cyano-2-(10,10-dioxido-9H-thioxanthen-9-ylidene)acetamido)ethyl methacrylate;
 N-(2-(2-cyano-2-(10-methylacridin-9(10H)ylidene)acetamido)ethyl) methacrylamide; or
 2-(2-cyano-2-(9H-thioxanthen-9-ylidene)acetoxo)ethyl methacrylate.

13. The ophthalmic device of any preceding claim, wherein the ophthalmic device transmits:

45 percent or less of light having a wavelength of 280 to 399 nm;
 from 1 percent to 70 percent of light having a wavelength of 400 to 409 nm; and
 at least 80 percent of light having a wavelength of 450 to 800 nm;
 optionally wherein the ophthalmic device further transmits:

from 10 percent to 95 percent of light having a wavelength of 410 to 424 nm; and
 at least 50 percent of light having a wavelength of 425 to 449 nm;

optionally wherein the ophthalmic device transmits:


20 percent or less of light having a wavelength of 280 to 399 nm;
 from 3 percent to 70 percent of light having a wavelength of 400 to 409 nm; and
 at least 85 percent of light having a wavelength of 450 to 800 nm.

14. The ophthalmic device of claim 13 wherein m and n in the compound of formula I at each occurrence are each 0.

15. The ophthalmic device of claim 13, wherein the ophthalmic device is a silicone hydrogel contact lens, and wherein
 the silicone hydrogel contact lens has a contact angle of about 70° or less, a water content of at least 25 percent,
 and an oxygen permeability of at least $268 \times 10^{-16} \text{ mol m (m}^2 \text{ s Pa)}^{-1}$ (80 barrers).

Patentansprüche


1. Ophthalmische Vorrichtung, bei der es sich um ein Radikalreaktionsprodukt einer reaktiven Mischung handelt, die Folgendes umfasst: ein oder mehrere Monomere, die zur Herstellung der ophthalmischen Vorrichtung geeignet sind, und eine polymerisierbare energiereiches Licht absorbierende Verbindung der Formel I:



Formel I

wobei:

- m und n unabhängig für 0, 1, 2, 3 oder 4 stehen;
 T für eine Bindung, O oder NH steht;
 X für O, S, NR, SO oder SO₂ steht;
 Y für eine Verknüpfungsgruppe steht;
 P_g für eine polymerisierbare Gruppe steht;
 R bei jedem Auftreten unabhängig für H, C₁-C₆-Alkyl, Cycloalkyl, Heterocycloalkyl, Aryl, Heteroaryl oder Y-P_g steht;
 R¹ und R², wenn vorhanden, unabhängig bei jedem Auftreten für C₁-C₆-Alkyl, C₁-C₆-Alkoxy, C₁-C₆-Thioalkyl, C₃-C₇-Cycloalkyl, Aryl, Halogen, Hydroxy, Amino, NR³R⁴ oder Benzyl stehen, wobei R³ und R⁴ unabhängig für H oder C₁-C₆-Alkyl stehen, oder zwei benachbarte R¹- oder R²-Gruppen zusammen mit den Kohlenstoffatomen, an die sie gebunden sind, einen Cycloalkyl- oder Arylring bilden und
 EWG für eine elektronenziehende Gruppe steht.
2. Ophthalmische Vorrichtung nach Anspruch 1, wobei die reaktive Mischung ferner eine zweite polymerisierbare energiereiches Licht absorbierende Verbindung umfasst;
 gegebenenfalls wobei es sich bei der zweiten polymerisierbaren energiereiches Licht absorbierenden Verbindung um eine UV-absorbierende Verbindung handelt; beispielsweise wobei es sich bei der UV-absorbierenden Verbindung um eine Verbindung der Formel I, ein Benzophenon, ein Benzotriazol, ein Triazin, ein substituiertes Acrylnitril, ein Salicylsäurederivat, ein Benzoessäurederivat, ein Zimtsäurederivat, ein Chalkonderivat, ein Dyponderivat, ein Crotonsäurederivat oder Mischungen davon handelt.
3. Ophthalmische Vorrichtung nach Anspruch 1 oder 2, wobei die reaktive Mischung eine Mischung von
 (a) einer Verbindung der Formel I, wobei X für S steht, und einer Verbindung der Formel I, wobei X für O steht; oder
 (b) einer Verbindung der Formel I, wobei X für S steht, und einer UV-absorbierenden Benzotriazolverbindung umfasst.
4. Ophthalmische Vorrichtung nach einem der Ansprüche 1 bis 3, wobei das zur Herstellung der ophthalmischen Vorrichtung geeignete Monomer eine hydrophile Komponente, eine silikonhaltige Komponente oder Mischungen davon umfasst.
5. Ophthalmische Vorrichtung nach einem der Ansprüche 1 bis 4, bei der es sich um eine Kontaktlinse, ein Hornhaut-Onlay, ein Hornhaut-Inlay, eine Intraokularlinse oder eine Overlay-Linse handelt; gegebenenfalls wobei es sich bei der ophthalmischen Vorrichtung um eine Hydrogel-Kontaktlinse handelt.
6. Verfahren zur Herstellung einer ophthalmischen Vorrichtung, das Folgendes umfasst:
 (a) Bereitstellen einer reaktiven Mischung, enthaltend ein oder mehrere vorrichtungsbildende Monomere, einen Radikalinitiator und eine Verbindung der Formel I:



Formel I

wobei:

m und n unabhängig für 0, 1, 2, 3 oder 4 stehen;

T für eine Bindung, O oder NH steht;

X für O, S, NR, SO oder SO₂ steht;

Y für eine Verknüpfungsgruppe steht;

P_g für eine polymerisierbare Gruppe steht;

R bei jedem Auftreten unabhängig für H, C₁-C₆-Alkyl, Cycloalkyl, Heterocycloalkyl, Aryl, Heteroaryl oder Y-P_g steht;

R¹ und R², wenn vorhanden, unabhängig bei jedem Auftreten für C₁-C₆-Alkyl, C₁-C₆-Alkoxy, C₁-C₆-Thioalkyl, C₃-C₇-Cycloalkyl, Aryl, Halogen, Hydroxy, Amino, NR³R⁴ oder Benzyl stehen, wobei R³ und R⁴ unabhängig für H oder C₁-C₆-Alkyl stehen, oder zwei benachbarte R¹- oder R²-Gruppen zusammen mit den Kohlenstoffatomen, an die sie gebunden sind, einen Cycloalkyl- oder Arylring bilden und EWG für eine elektronenziehende Gruppe steht; und

(b) Polymerisieren der reaktiven Mischung zur Bildung der ophthalmischen Vorrichtung.

7. Ophthalmische Vorrichtung nach einem der vorhergehenden Ansprüche oder Verfahren nach einem der vorhergehenden Ansprüche, wobei m und n jeweils unabhängig für 0 oder 1 stehen.

8. Ophthalmische Vorrichtung nach einem der vorhergehenden Ansprüche oder Verfahren nach einem der vorhergehenden Ansprüche, wobei Y bei jedem Auftreten unabhängig für Alkylen, Cycloalkylen, Heterocycloalkylen, Arylen, Heteroarylen, Oxaalkylen, Alkylen-amid-alkylen, Alkylen-aminalkylen oder Kombinationen davon steht.

9. Ophthalmische Vorrichtung nach einem der vorhergehenden Ansprüche oder Verfahren nach einem der vorhergehenden Ansprüche, wobei P_g Styryl, Vinylcarbonat, Vinylether, Vinylcarbamat, N-Vinylactam, N-Vinylamid, (Meth)acrylat oder (Meth)-acrylamid umfasst.

10. Ophthalmische Vorrichtung nach einem der vorhergehenden Ansprüche oder Verfahren nach einem der vorhergehenden Ansprüche, wobei X für

(a) O oder

(b) S

steht.

11. Ophthalmische Vorrichtung nach einem der vorhergehenden Ansprüche oder Verfahren nach einem der vorhergehenden Ansprüche, wobei EWG für Cyano, Amid, Ester, Keto oder Aldehyd steht; gegebenenfalls wobei EWG für Cyano steht.

12. Ophthalmische Vorrichtung nach einem der Ansprüche 1 bis 5 oder Verfahren nach Anspruch 6, wobei es sich bei der Verbindung der Formel I um

2-(2-Cyano-2-(9H-thioxanthen-9-yliden)acetamido)ethylmethacrylat;

2-(2-Cyano-2-(9H-thioxanthen-9-yliden)acetamido)ethylacrylat;

N-(2-(2-Cyano-2-(9H-thioxanthen-9-yliden)acetamido)ethyl)methacrylamid;

N-(2-(2-Cyano-2-(9H-thioxanthen-9-yliden)acetamido)ethyl)acrylamid;

2-(2-Cyano-N-methyl-2-(9H-thioxanthen-9-yliden)acetamido)ethylmethacrylat;

2-Cyano-2-(9H-thioxanthen-9-yliden)-N-(2-(N-vinylacetamido)ethyl)acetamid;
 2-(2-Cyano-2-(9H-xanthen-9-yliden)acetamido)ethylmethacrylat;
 2-(2-Cyano-2-(9H-xanthen-9-yliden)acetamido)ethylacrylat;
 N-(2-(2-Cyano-2-(9H-xanthen-9-yliden)acetamido)ethyl)methacrylamid;
 N-(2-(2-Cyano-2-(9H-xanthen-9-yliden)acetamido)ethyl)acrylamid;
 2-(2-Cyano-N-methyl-2-(9H-xanthen-9-yliden)acetamido)ethylmethacrylat;
 2-Cyano-N-(2-(N-vinylacetamido)ethyl)-2-(9H-xanthen-9-yliden)acetamid;
 2-(2-(Acridin-9(10H)-yliden)-2-cyanoacetamido)ethylacrylat;
 N-(2-(2-(Acridin-9(10H)-yliden)-2-cyanoacetamido)ethyl)methacrylamid;
 N-(2-(2-(Acridin-9(10H)-yliden)-2-cyanoacetamido)ethyl)acrylamid;
 2-(2-(Acridin-9(10H)-yliden)-2-cyano-N-methylacetamido)ethylmethacrylat;
 2-(Acridin-9(10H)-yliden)-2-cyano-N-(2-(N-vinylacetamido)ethyl)acetamid;
 2-(2-Cyano-2-(9H-thioxanthen-9-yliden)acetamido)-2-methylpropylmethacrylat;
 2-(2-Cyano-2-(9H-xanthen-9-yliden)acetoxyl)-2-methylpropylacrylat;
 (Z)-2-(2-Cyano-2-(3-hydroxyacridin-9(10H)-yliden)acetamido)ethylmethacrylat;
 2-(2-Cyano-2-(10-methylacridin-9(10H)-yliden)acetamido)ethylmethacrylat;
 2-(2-Cyano-2-(3,6-dihydroxyacridin-9(10H)-yliden)acetamido)ethylmethacrylat;
 (E)-2-(2-(7H-Benzo[c]xanthen-7-yliden)-2-cyanoacetamido)ethylmethacrylat;
 (Z)-2-(2-Cyano-2-(3-methoxy-9H-xanthen-9-yliden)acetamido)ethylmethacrylat;
 2-(2-Cyano-2-(3,6-dihydroxy-9H-xanthen-9-yliden)acetamido)ethylmethacrylat;
 (E)-2-(2-Cyano-2-(2-methyl-9H-xanthen-9-yliden)acetamido)ethylmethacrylat;
 (E)-2-(2-Cyano-2-(1-hydroxy-9H-xanthen-9-yliden)acetamido)ethylmethacrylat;
 (E)-2-(2-Cyano-2-(2,4-dichlor-9H-thioxanthen-9-yliden)acetamido)ethylmethacrylat;
 (E)-2-(2-(2-Chlor-9H-thioxanthen-9-yliden)-2-cyanoacetamido)ethylmethacrylat;
 (E)-2-(2-Cyano-2-(2-isopropyl-9H-thioxanthen-9-yliden)acetamido)ethylmethacrylat;
 (E)-2-(2-Cyano-2-(4-isopropyl-9H-thioxanthen-9-yliden)acetamido)ethylmethacrylat;
 2-(3-Oxo-2-(9H-thioxanthen-9-yliden)propanamido)ethylmethacrylat;
 2-(3-Oxo-2-(9H-thioxanthen-9-yliden)butanamido)ethylmethacrylat;
 2-(3-Methoxy-3-oxo-2-(9H-thioxanthen-9-yliden)propanamido)ethylmethacrylat;
 2-(3-Amino-3-oxo-2-(9H-thioxanthen-9-yliden)propanamido)ethylmethacrylat;
 2-(2-Cyano-2-(10,10-dioxido-9H-thioxanthen-9-yliden)acetamido)ethylmethacrylat;
 N-(2-(2-Cyano-2-(10-methylacridin-9(10H)yliden)acetamido)ethyl)methacrylamid oder
 2-(2-Cyano-2-(9H-thioxanthen-9-yliden)acetoxyl)ethylmethacrylat handelt.

- 13.** Ophthalmische Vorrichtung nach einem der vorhergehenden Ansprüche, wobei die ophthalmische Vorrichtung Folgendes durchlässt:


45 Prozent oder weniger Licht mit einer Wellenlänge von 280 bis 399 nm;
 1 Prozent bis 70 Prozent Licht mit einer Wellenlänge von 400 bis 409 nm und
 mindestens 80 Prozent Licht mit einer Wellenlänge von 450 bis 800 nm;
 gegebenenfalls wobei die ophthalmische Vorrichtung ferner Folgendes durchlässt:
 10 Prozent bis 95 Prozent Licht mit einer Wellenlänge von 410 bis 424 nm und
 mindestens 50 Prozent Licht mit einer Wellenlänge von 425 bis 449 nm;
 gegebenenfalls wobei die ophthalmische Vorrichtung Folgendes durchlässt:
 20 Prozent oder weniger Licht mit einer Wellenlänge von 280 bis 399 nm;
 3 Prozent bis 70 Prozent Licht mit einer Wellenlänge von 400 bis 409 nm und
 mindestens 85 Prozent Licht mit einer Wellenlänge von 450 bis 800 nm.

- 14.** Ophthalmische Vorrichtung nach Anspruch 13, wobei m und n in der Verbindung der Formel I bei jedem Auftreten jeweils für 0 stehen.

- 15.** Ophthalmische Vorrichtung nach Anspruch 13, wobei es sich bei der ophthalmischen Vorrichtung um eine Silikonhydrogel-Kontaktlinse handelt, und wobei die Silikonhydrogel-Kontaktlinse einen Kontaktwinkel von etwa 70° oder weniger, einen Wassergehalt von mindestens 25 Prozent und eine Sauerstoffdurchlässigkeit von mindestens $268 \times 10^{-16} \text{ mol m (m}^2 \text{ s Pa)}^{-1}$ (80 Barrer) aufweist.


Revendications

1. Dispositif ophtalmique qui est un produit de réaction par voie radicalaire libre d'un mélange réactif comprenant : un ou plusieurs monomères appropriés pour préparer le dispositif ophtalmique ; et un composé absorbant la lumière à haute énergie polymérisable de formule I :



formule I

- m et n étant indépendamment 0, 1, 2, 3, ou 4 ;
 T étant une liaison, O, ou NR ;
 X étant O, S, NR, SO, ou SO₂ ;
 Y étant un groupe de liaisons ;
 P_g étant un groupe polymérisable ;
 R étant en chaque occurrence indépendamment H, C₁-C₆ alkyle, cycloalkyle, hétérocycloalkyle, aryle, hétéroaryle, ou Y-P_g ;
 R¹ et R², s'ils sont présents, étant indépendamment en chaque occurrence C₁-C₆ alkyle, C₁-C₆ alcoxy, C₁-C₆ thioalkyle, C₃-C₇ cycloalkyle, aryle, halogéno, hydroxy, amino, NR³R⁴, ou benzyle, R³ et R⁴ étant indépendamment H ou C₁-C₆ alkyle, ou deux groupes R¹ ou R² adjacents, conjointement avec les atomes de carbone auxquels ils sont fixés, se combinant pour former un cycle cycloalkyle ou aryle ; et
 EWG étant un groupe électroattracteur.
2. Dispositif ophtalmique selon la revendication 1, le mélange réactif comprenant en outre un deuxième composé absorbant la lumière à haute énergie polymérisable ; éventuellement, le deuxième composé absorbant la lumière à haute énergie polymérisable étant un composé absorbant des UV ; par exemple, le composé absorbant des UV étant un composé de formule I, une benzophénone, un benzotriazole, une triazine, un acrylonitrile substitué, un dérivé d'acide salicylique, un dérivé d'acide benzoïque, un dérivé d'acide cinnamique, un dérivé de chalcone, un dérivé de dypnone, un dérivé d'acide crotonique, ou des mélanges correspondants.
3. Dispositif ophtalmique selon la revendication 1 ou 2, le mélange réactif comprenant un mélange de :
 (a) un composé de formule I dans laquelle X est S et un composé de formule I dans laquelle X est O ; ou
 (b) un composé de formule I dans laquelle X est S et un composé absorbant des UV de type benzotriazole.
4. Dispositif ophtalmique selon l'une quelconque des revendications 1 à 3, le monomère approprié pour la préparation du dispositif ophtalmique comprenant un composant hydrophile, un composant contenant une silicone ou des mélanges correspondants.
5. Dispositif ophtalmique selon l'une quelconque des revendications 1 à 4 qui est une lentille de contact, un onlay cornéen, un inlay cornéen, une lentille intraoculaire ou une lentille de superposition ; éventuellement le dispositif ophtalmique étant une lentille de contact d'hydrogel.
6. Procédé pour la préparation d'un dispositif ophtalmique, le procédé comprenant :
 (a) la mise à disposition d'un mélange de réactifs contenant un ou plusieurs monomères de formation de dispositif, un initiateur de radicaux, et un composé de formule I :



formule I

m et n étant indépendamment 0, 1, 2, 3, ou 4 ;

T étant une liaison, O, ou NR ;

X étant O, S, NR, SO, ou SO₂ ;

Y étant un groupe de liaisons ;

P_g étant un groupe polymérisable ;

R étant en chaque occurrence indépendamment H, C₁-C₆ alkyle, cycloalkyle, hétérocycloalkyle, aryle, hétéroaryle, ou Y-P_g ;

R¹ et R², s'ils sont présents, étant indépendamment en chaque occurrence C₁-C₆ alkyle, C₁-C₆ alcoxy, C₁-C₆ thioalkyle, C₃-C₇ cycloalkyle, aryle, halogéno, hydroxy, amino, NR³R⁴, ou benzyle, R³ et R⁴ étant indépendamment H ou C₁-C₆ alkyle, ou deux groupes R¹ ou R² adjacents, conjointement avec les atomes de carbone auxquels ils sont fixés, se combinant pour former un cycle cycloalkyle ou aryle ; et

EWG étant un groupe électroattracteur ; et

(b) la polymérisation du mélange réactif pour former le dispositif ophtalmique.

7. Dispositif ophtalmique selon une quelconque revendication précédente, ou procédé selon une quelconque revendication précédente, m et n étant chacun indépendamment 0 ou 1.
8. Dispositif ophtalmique selon une quelconque revendication précédente, ou procédé selon une quelconque revendication précédente, Y en chaque occurrence étant indépendamment alkylène, cycloalkylène, hétérocycloalkylène, arylène, hétéroarylène, oxaalkylène, alkylène-amide-alkylène, alkylène-amine-alkylène, ou des combinaisons correspondantes.
9. Dispositif ophtalmique selon une quelconque revendication précédente, ou procédé selon une quelconque revendication précédente, P_g comprenant styryle, carbonate de vinyle, éther de vinyle, carbamate de vinyle, N-vinylacétamide, N-vinylamide, (méth)acrylate ou (méth)acrylamide.
10. Dispositif ophtalmique selon une quelconque revendication précédente, ou procédé selon une quelconque revendication précédente, X étant :
 - (a) O ; ou
 - (b) S.
11. Dispositif ophtalmique selon une quelconque revendication précédente, ou procédé selon une quelconque revendication précédente, EWG étant cyano, amide, ester, céto ou aldéhyde ; éventuellement, EWG étant cyano.
12. Dispositif ophtalmique selon l'une quelconque des revendications 1 à 5, ou procédé selon la revendication 6, le composé de formule I étant :

méthacrylate de 2-(2-cyano-2-(9H-thioxanthène-9-ylidène)acétamido)éthyle ;

acrylate de 2-(2-cyano-2-(9H-thioxanthène-9-ylidène)acétamido)éthyle ;

N-(2-(2-cyano-2-(9H-thioxanthène-9-ylidène)acétamido)éthyl)méthacrylamide ;

N-(2-(2-cyano-2-(9H-thioxanthène-9-ylidène)acétamido)éthyl)acrylamide ;

méthacrylate de 2-(2-cyano-N-méthyl-2-(9H-thioxanthène-9-ylidène)acétamido)éthyle ;

2-cyano-2-(9H-thioxanthène-9-ylidène)-N-(2-(N-vinylacétamido)éthyl)acétamide ;

méthacrylate de 2-(2-cyano-2-(9H-xanthène-9-ylidène)-acétamido)éthyle ;
 acrylate de 2-(2-cyano-2-(9H-xanthène-9-ylidène)acétamido)éthyle ;
 N-(2-(2-cyano-2-(9H-xanthène-9-ylidène)acétamido)éthyl)méthacrylamide ;
 N-(2-(2-cyano-2-(9H-xanthène-9-ylidène)acétamido)éthyl)acrylamide ;
 5 méthacrylate de 2-(2-cyano-N-méthyl-2-(9H-xanthène-9-ylidène)acétamido)éthyle ;
 2-cyano-N-(2-(N-vinylacétamido)éthyl)-2-(9H-xanthène-9-ylidène)acétamide ;
 acrylate de 2-(2-(acridin-9(10H)-ylidène)-2-cyanoacétamido)éthyle ;
 N-(2-(2-(acridin-9(10H)-ylidène)-2-cyanoacétamido)éthyl)méthacrylamide ;
 N-(2-(2-(acridin-9(10H)-ylidène)-2-cyanoacétamido)éthyl)acrylamide ;
 10 méthacrylate de 2-(2-(acridin-9(10H)-ylidène)-2-cyano-N-méthylacétamido)éthyle ;
 2-(acridin-9(10H)-ylidène)-2-cyano-N-(2-(N-vinylacétamido)éthyl)acétamide ;
 méthacrylate de 2-(2-cyano-2-(9H-thioxanthène-9-ylidène)-acétamido)-2-méthylpropyle ;
 acrylate de 2-(2-cyano-2-(9H-thioxanthène-9-ylidène)-acétoxy)-2-méthylpropyle ;
 méthacrylate de (Z)-2-(2-cyano-2-(3-hydroxyacridine-9(10H)-ylidène)acétamido)éthyle ;
 15 méthacrylate de 2-(2-cyano-2-(10-méthylacridine-9(10H)-ylidène)acétamido)éthyle ;
 méthacrylate de 2-(2-cyano-2-(3,6-dihydroxyacridine-9(10H)-ylidène)acétamido)éthyle ;
 méthacrylate de (E)-2-(2-(7H-benzo[c]xanthène-7-ylidène)-2-cyanoacétamido)éthyle ;
 méthacrylate de (Z)-2-(2-cyano-2-(3-méthoxy-9H-xanthène-9-ylidène)acétamido)éthyle ;
 méthacrylate de 2-(2-cyano-2-(3,6-dihydroxy-9H-xanthène-9-ylidène)acétamido)éthyle ;
 20 méthacrylate de (E)-2-(2-cyano-2-(2-méthyl-9H-xanthène-9-ylidène)acétamido)éthyle ;
 méthacrylate de (E)-2-(2-cyano-2-(1-hydroxy-9H-xanthène-9-ylidène)acétamido)éthyle ;
 méthacrylate de (E)-2-(2-cyano-2-(2,4-dichloro-9H-thioxanthène-9-ylidène)acétamido)éthyle ;
 méthacrylate de (E)-2-(2-(2-chloro-9H-thioxanthène-9-ylidène)-2-cyanoacétamido)éthyle ;
 méthacrylate de (E)-2-(2-cyano-2-(2-isopropyl-9H-thioxanthène-9-ylidène)acétamido)éthyle ;
 25 méthacrylate de (E)-2-(2-cyano-2-(4-isopropyl-9H-thioxanthène-9-ylidène)acétamido)éthyle ; méthacrylate de
 2-(3-oxo-2-(9H-thioxanthène-9-ylidène)propanamido)éthyle ;
 méthacrylate de 2-(3-oxo-2-(9H-thioxanthène-9-ylidène)butanamido)éthyle ;
 méthacrylate de 2-(3-méthoxy-3-oxo-2-(9H-thioxanthène-9-ylidène)propanamido)éthyle ;
 méthacrylate de 2-(3-amino-3-oxo-2-(9H-thioxanthène-9-ylidène)propanamido)éthyle ;
 30 méthacrylate de 2-(2-cyano-2-(10,10-dioxydo-9H-thioxanthène-9-ylidène)acétamido)éthyle ;
 N-(2-(2-cyano-2-(10-méthylacridine-9(10H)ylidène)acétamido)éthyle) méthacrylamide ; ou
 méthacrylate de 2-(2-cyano-2-(9H-thioxanthène-9-ylidène)acétoxy)éthyle.

13. Dispositif ophtalmique selon une quelconque revendication précédente, le dispositif ophtalmique transmettant :

35 45 pour cent ou moins de lumière possédant une longueur d'onde de 280 à 399 nm ;
 de 1 pour cent à 70 pour cent de lumière possédant une longueur d'onde de 400 à 400 nm ; et
 au moins 80 pour cent de lumière possédant une longueur d'onde de 450 à 800 nm ;
 éventuellement, le dispositif ophtalmique transmettant en outre :

40 de 10 pour cent à 95 pour cent de lumière possédant une longueur d'onde de 410 à 424 nm ; et
 au moins 50 pour cent de lumière possédant une longueur d'onde de 425 à 449 nm ;
 éventuellement, le dispositif ophtalmique transmettant :

45 20 pour cent ou moins de lumière possédant une longueur d'onde de 280 à 399 nm ;
 de 3 pour cent à 70 pour cent de lumière possédant une longueur d'onde de 400 à 400 nm ; et
 au moins 85 pour cent de lumière possédant une longueur d'onde de 450 à 800 nm.

14. Dispositif ophtalmique selon la revendication 13, m et n dans le composé de formule I étant chacun en chaque occurrence 0.

15. Dispositif ophtalmique selon la revendication 13, le dispositif ophtalmique étant une lentille de contact d'hydrogel
 de silicone, et la lentille de contact d'hydrogel de silicone possédant un angle de contact d'environ 70° ou moins,
 une teneur en eau d'au moins 25 pour cent, et une perméabilité à l'oxygène d'au moins 268×10^{-16} mol m (m² s
 55 Pa)⁻¹ (80 barrers) .




FIG. 1 – UV-VIS Transmission Spectra of 0.2 mM solutions of Compounds (B), (C), and (E) in methanol




FIG. 2 - UV-VIS Transmission Spectra of 0.2 mM solutions of Compounds (G), (H), and (J) in methanol and of Compound (L) in dichloromethane




FIG. 3 – UV-VIS Transmission Spectrum of Silicone Hydrogel Contact Lenses 9A and 9B




FIG. 4 – UV-VIS Transmission Spectrum of Silicone Hydrogel Contact Lenses 9A and 9C




FIG. 5 – UV-VIS Transmission Spectrum of Silicone Hydrogel Contact Lenses 9A and 9D




FIG. 6 – UV-VIS Transmission Spectrum of Silicone Hydrogel Contact Lenses 10A and 10B




FIG. 7 – UV-VIS Transmission Spectrum of Silicone Hydrogel Contact Lenses 10A and 10C




FIG. 8 – UV-VIS Transmission Spectrum of Silicone Hydrogel Contact Lenses 10A and 10D




FIG. 9 – UV-VIS Transmission Spectra of Silicone Hydrogel Contact Lenses (11A) comprising Compound (B) after exposure to direct sunlight




FIG. 10 – UV-VIS Transmission Spectra of Silicone Hydrogel Contact Lenses (11B) comprising Compound (B) after exposure to indoor lighting

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 2015175732 A1 [0007]
- WO 2007050395 A2 [0008]
- WO 9963366 A1 [0009]
- US 3808178 A [0042]
- US 4120570 A [0042]
- US 4136250 A [0042]
- US 4153641 A [0042]
- US 4740533 A [0042]
- US 5034461 A [0042]
- US 5070215 A [0042] [0140]
- US 5244981 A [0042] [0051]
- US 5314960 A [0042] [0051]
- US 5331067 A [0042] [0051]
- US 5371147 A [0042] [0051]
- US 5760100 A [0042] [0051]
- US 5849811 A [0042] [0051]
- US 5962548 A [0042]
- US 5965631 A [0042] [0051]
- US 5998498 A [0042] [0051]
- US 6367929 B [0042] [0051]
- US 6822016 B [0042] [0051]
- US 6943203 B [0042] [0051]
- US 6951894 B [0042]
- US 7052131 B [0042]
- US 7247692 B [0042] [0051]
- US 7396890 B [0042]
- US 7461937 B [0042]
- US 7468398 B [0042]
- US 7538146 B [0042]
- US 7553880 B [0042] [0051]
- US 7572841 B [0042]
- US 7666921 B [0042] [0051]
- US 7691916 B [0042]
- US 7786185 B [0042] [0051]
- US 7825170 B [0042]
- US 7915323 B [0042]
- US 7994356 B [0042]
- US 8022158 B [0042] [0051]
- US 8163206 B [0042]
- US 8273802 B [0042] [0051]
- US 8399538 B [0042] [0051]
- US 8415404 B [0042]
- US 8420711 B [0042]
- US 8450387 B [0042] [0051]
- US 8487058 B [0042] [0051]
- US 8568626 B [0042]
- US 8937110 B [0042] [0051]
- US 8937111 B [0042] [0051]
- US 8940812 B [0042] [0051]
- US 8980972 B [0042]
- US 9056878 B [0042] [0051]
- US 9125808 B [0042] [0051]
- US 9140825 B [0042] [0051]
- US 9156934 B [0042] [0051]
- US 9170349 B [0042] [0051]
- US 9217813 B [0042]
- US 9244196 B [0042] [0051]
- US 9244197 B [0042] [0051]
- US 9260544 B [0042] [0051]
- US 9297928 B [0042] [0051]
- US 9297929 B [0042] [0051]
- EP 080539 A [0042]
- US 4436887 A [0050]
- US 4495313 A [0050]
- US 4889664 A [0050]
- US 5006622 A [0050]
- US 5039459 A [0050]
- US 5236969 A [0050]
- US 5270418 A [0050]
- US 5298533 A [0050]
- US 5824719 A [0050]
- US 6420453 B [0050]
- US 6423761 B [0050]
- US 6767979 B [0050]
- US 7934830 B [0050]
- US 8138290 B [0050]
- US 8389597 B [0050]
- US 4659782 A [0051]
- US 4659783 A [0051]
- US 6087415 A [0051]
- US 5776999 A [0051]
- US 5789461 A [0051]
- US 6867245 B [0051]
- US 7249848 B [0051]
- US 7956131 B [0051]
- US 8470906 B [0051]
- US 8507577 B [0051]
- US 8637621 B [0051]
- US 8703891 B [0051]
- US 9057821 B [0051]
- WO 0322321 A [0051]
- WO 2008061992 A [0051]
- US 20100048847 A [0051]
- US 4910277 A [0140]
- WO 03022321 A [0220]
- US 6020445 A [0220]
- US 3408429 A [0241]
- US 3660545 A [0241]

EP 3 759 171 B9

- US 4113224 A [0241]
- US 4197266 A [0241]
- US 20180037690 A [0248]
- US 5944853 A [0253]

Non-patent literature cited in the description

- DOUTCH, J.J. ; QUANTOCK, A.J. ; JOYCE, N.C. ; MEEK, K.M. *Biophys. J.*, 2012, vol. 102, 1258-1264 [0002]
- HAM, W.T ; MUELLER, H. A. ; SLINNEY, D. H. *Nature*, 1976, vol. 260 (5547), 153-5 [0003]
- CHEMICAL ABSTRACTS, 148969-96-4 [0208]
- CHEMICAL ABSTRACTS, 79704-35-1 [0208]
- CHEMICAL ABSTRACTS, 80293-60-3 [0208]
- CHEMICAL ABSTRACTS, 163674-35-9 [0208]
- J. V. CRIVELLO ; K. DIETLIKER. Photoinitiators for Free Radical Cationic & Anionic Photopolymerization. John Wiley and Sons, 1998 [0224]
- CHEMICAL ABSTRACTS, 20168-55-2 [0293]