



(11) **EP 3 792 379 A8**

(12) **CORRECTED EUROPEAN PATENT APPLICATION**
published in accordance with Art. 153(4) EPC

(15) Correction information:
Corrected version no 2 (W2 A1)
Corrections, see
Bibliography INID code(s) 84

(51) Int Cl.:
D01F 6/46 ^(2006.01) **D01D 1/02** ^(2006.01)
D01D 5/06 ^(2006.01) **D01D 5/12** ^(2006.01)
A41D 19/015 ^(2006.01) **D02G 3/44** ^(2006.01)
D04B 1/28 ^(2006.01) **D03D 1/00** ^(2006.01)
D03D 15/00 ^(2021.01)

(48) Corrigendum issued on:
25.08.2021 Bulletin 2021/34

(86) International application number:
PCT/CN2019/105436

(43) Date of publication:
17.03.2021 Bulletin 2021/11

(87) International publication number:
WO 2021/007943 (21.01.2021 Gazette 2021/03)

(21) Application number: **19850783.2**

(22) Date of filing: **11.09.2019**

(84) Designated Contracting States:
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR
Designated Extension States:
BA ME
Designated Validation States:
KH MA MD TN

(72) Inventors:
• **ZHOU, Xingyu**
Weifang, Shandong 261512 (CN)
• **ZHOU, Haitao**
Weifang, Shandong 261512 (CN)
• **ZHOU, Hongbo**
Weifang, Shandong 261512 (CN)
• **ZHAO, Yong**
Weifang, Shandong 261512 (CN)

(30) Priority: **18.07.2019 CN 201910651423**

(74) Representative: **Kayahan, Senem**
Yalciner Patent and Consulting Ltd.
Tunus Cad. No: 85/3-4
Kavaklidere Cankaya
06680 Ankara (TR)

(71) Applicant: **Xingyu Safety Protection Technology Co., Ltd.**
Weifang City, Shandong 261512 (CN)

(54) **POLYETHYLENE FIBER HAVING ULTRAHIGH ANTI-CUTTING PERFORMANCE AND ULTRAHIGH MOLECULAR WEIGHT AND PREPARATION METHOD THEREFOR**

(57) The present invention relates to an ultra-high molecular weight polyethylene fiber with ultra-high cut resistance, including: an ultra-high molecular weight polyethylene matrix and carbon fiber powder particles dispersed therein. The content of the carbon fiber powder particles is 0.25-10 wt%. The present invention further relates to a method for preparing the ultra-high molecular weight polyethylene fiber with the ultra-high cut resistance and a cut-resistant glove woven therefrom. The test proves that the glove woven from the ultra-high molecular weight polyethylene fiber with the ultra-high cut resist-

ance is soft and comfortable, and does not have prickling sensation. According to the test of the Standard EN388-2003, the level of the cut-resistant grade ranges from 4 to 5. Compared with the application of other existing inorganic high-hardness reinforcing materials, the production process of the ultra-high molecular weight polyethylene fiber with the ultra-high cut resistance of the present invention has relatively less abrasion on the equipment. Moreover, the knitted cut-resistant gloves have higher durability and the cut-resistant performance is maintained longer than other gloves.