



(11) **EP 4 428 977 A8**

(12) **CORRECTED EUROPEAN PATENT APPLICATION**

(15) Correction information:
Corrected version no 1 (W1 A2)
Corrections, see
Bibliography INID code(s) 62
Remarks

(51) International Patent Classification (IPC):
H01M 10/0525^(2010.01)

(52) Cooperative Patent Classification (CPC):
H01M 4/625; H01M 4/134; H01M 4/386;
H01M 10/0525; H01M 2004/027; Y02E 60/10

(48) Corrigendum issued on:
23.10.2024 Bulletin 2024/43

(43) Date of publication:
11.09.2024 Bulletin 2024/37

(21) Application number: **24191187.4**

(22) Date of filing: **19.06.2020**

(84) Designated Contracting States:
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB
GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO
PL PT RO RS SE SI SK SM TR

(30) Priority: **28.06.2019 KR 20190078182**

(62) Document number(s) of the earlier application(s) in
accordance with Art. 76 EPC:
20830905.4 / 3 940 820

(71) Applicant: **LG Energy Solution, Ltd.**
Seoul 07335 (KR)

(72) Inventors:
• **Kim, Ye Lin**
34122 Daejeon (KR)

• **Yoo, Jung Woo**
34122 Daejeon (KR)
• **Kim, Tae Gon**
34122 Daejeon (KR)
• **Kim, Young Jae**
34122 Daejeon (KR)

(74) Representative: **Hoffmann Eitle**
Patent- und Rechtsanwälte PartmbB
Arabellastraße 30
81925 München (DE)


Remarks:

This application was filed on 26-07-24 as a divisional
application to the application mentioned under INID
code 62.

(54) **NEGATIVE ELECTRODE AND SECONDARY BATTERY COMPRISING THE SAME**

(57) The present invention provides a negative electrode which includes: a negative electrode current collector; and a negative electrode active material layer formed on the negative electrode current collector, wherein the negative electrode active material layer includes a silicon-based negative electrode active material, a binder, a conductive material, and single-walled carbon nanotubes, and the single-walled carbon nanotubes are included at 0.001 wt% to 1 wt% in the negative electrode active material layer.

[FIG. 1]



EP 4 428 977 A8