



(11) **EP 4 451 407 A8**

(12) **CORRECTED EUROPEAN PATENT APPLICATION**  
published in accordance with Art. 153(4) EPC

(15) Correction information:  
**Corrected version no 1 (W1 A1)**  
**Corrections, see**  
**Bibliography INID code(s) 72**

(51) International Patent Classification (IPC):  
**H01M 10/0565** <sup>(2010.01)</sup> **H01M 4/505** <sup>(2010.01)</sup>  
**H01M 4/525** <sup>(2010.01)</sup> **H01M 10/0567** <sup>(2010.01)</sup>  
**H01M 10/0568** <sup>(2010.01)</sup>

(48) Corrigendum issued on:  
**11.12.2024 Bulletin 2024/50**

(52) Cooperative Patent Classification (CPC):  
**H01M 10/0565; H01M 4/131; H01M 4/505;**  
**H01M 4/525; H01M 10/0525; H01M 10/056;**  
**H01M 10/0567; H01M 10/0568; H01M 10/0569;**  
**H01M 10/4235; H01M 50/105; H01M 50/119;**  
**H01M 50/121; H01M 50/124; H01M 2004/028;**

(43) Date of publication:  
**23.10.2024 Bulletin 2024/43**

(21) Application number: **22907314.3**

(Cont.)

(22) Date of filing: **07.12.2022**

(86) International application number:  
**PCT/JP2022/045033**

(87) International publication number:  
**WO 2023/112787 (22.06.2023 Gazette 2023/25)**

(84) Designated Contracting States:  
**AL AT BE BG CH CY CZ DE DK EE ES FI FR GB**  
**GR HR HU IE IS IT LI LT LU LV MC ME MK MT NL**  
**NO PL PT RO RS SE SI SK SM TR**  
Designated Extension States:  
**BA**  
Designated Validation States:  
**KH MA MD TN**

(72) Inventors:  
• **YOSHIOKA, Takuya**  
**Kyoto-shi, Kyoto 600-8873 (JP)**  
• **HOSHIHARA, Yuji**  
**Kyoto-shi, Kyoto 600-8873 (JP)**  
• **MURAKAMI, Satoshi**  
**Kyoto-shi, Kyoto 600-8873 (JP)**  
• **HIGASHIZAKI, Tetsuya**  
**Kyoto-shi, Kyoto 600-8873 (JP)**

(30) Priority: **15.12.2021 JP 2021203701**

(74) Representative: **Kuhnen & Wacker**  
**Patent- und Rechtsanwaltsbüro PartG mbB**  
**Prinz-Ludwig-Straße 40A**  
**85354 Freising (DE)**

(71) Applicant: **DKS Co. Ltd.**  
**Kyoto-shi, Kyoto 600-8873 (JP)**


(54) **NONAQUEOUS ELECTROLYTIC SOLUTION AND LITHIUM-ION SECONDARY BATTERY**

(57) A nonaqueous electrolytic solution used in a lithium ion secondary battery can provide good output characteristics and cycle characteristics and suppresses deterioration in interface resistance.

A nonaqueous electrolytic solution according to an embodiment is a nonaqueous electrolytic solution including a supporting salt, an aprotic solvent, a copolymer represented by general formula (1) and having a weight-average molecular weight of 200,000 or more and 600,000 or less, and vinylene carbonate, but not including 4-fluoro-1,3-dioxolan-2-one. The content of the copolymer is 0.5 to 2.5 mass% relative to the total amount of the supporting salt, the aprotic solvent, and the copolymer. The content of the vinylene carbonate is 0.5 to 2.5 mass% relative to the total amount of the supporting salt, the aprotic solvent, and the copolymer.

EP 4 451 407 A8

[Chem. 1]



(52) Cooperative Patent Classification (CPC): (Cont.)  
Y02E 60/10